

FICHE TECHNIQUE :

USINE 40 CARTON BLANC DOS KRAFT

Property/Unit	Nominal	Testing method
Base board		
Basis weight, g/m ²	240	ISO 536
Caliper, um	385	ISO 534
Stiffness L&W 15° MD, mN	350	ISO 2493
Stiffness L&W 15° CD, mN	140	ISO 2493
Stiffness L&W 15° GM, mN	220	ISO 2493
Surface smoothness, PPS 10, um	2,6	*Stora Enso
Surface smoothness, Bendtsen, ml/min	100	ISO 8791-2
Scott Bond, J/m ²	200	TAPPI 569
ISO Brightness C/2°, %, Top	78	ISO 2470
Moisture, %	7,5	ISO 287