

COATED 2 SIDES MATT

Product Information

Technical specifications

Parameter	Standard	Unit											
Basis weight	ISO 536	g/m ²	90	100	115	130	135	150	170	200	250	300	350
Brightness (illuminant D65/10°)	ISO 2470-2	%	98	98	98	98	98	98	98	98	98	98	98
CIE whiteness (D65/10°)	ISO 11475	%	125	125	125	125	125	125	125	125	125	125	125
Opacity	ISO 2471	%	91,5	93	94,5	95,5	96	97	97,5	98	98,5	99	99
Gloss TAPPI 75°	ISO 8254-1	%	29	29	29	29	29	29	29	29	34	34	34
Roughness PPS	ISO 8791-4	µm	1,6	1,6	1,6	1,6	1,6	1,6	1,6	1,6	1,6	1,6	1,6
Thickness	ISO 534	µm	74	82	95	108	112	125	145	171	220	276	336
Bulk	ISO 534	cm ³ /g	0,82	0,82	0,83	0,83	0,83	0,83	0,85	0,86	0,88	0,92	0,96
Relative humidity (23°C)	TAPPI 502	%	50	50	50	50	50	50	50	50	50	50	50

Print recommendations

Dot area	For dot areas over 320% we recommend Under Colour Removal (UCR).
Processing	Allow paper time to acclimatise to press room conditions before removing outer packaging. Strapping bands (if applied) should be removed shortly after delivery. Outer wrappers should be removed only when ready to print. Ideal press room conditions should be 50% ± 5 % relative humidity at 20°C.
Finishing	Suitable for all standard finishes, foil laminating (>130 gsm), embossing and die cutting. Varnishes include: dispersion, print, UV, spot, relief, iriodin, scented & aqueous.
Converting	Pre-creasing before folding is recommended from 135 µm thickness onwards. Crease channel width should be a minimum of 2x paper thickness plus thickness creasing knife (plus or minus 0,2 mm). Crease channel depth should ± 1.5x paper thickness. Creasing knife 2 point (0,71 mm) (this and that depending on your crease/fold device).
Assisted drying methods	When using infra red drying methods, stack temperature should not exceed 37°C. Suitable for UV cure inks.

Product Certification



PEFC certification on request/subject to availability.



FSC certification on request/subject to availability.



dry and fatty foodstuff.



Meets the purity requirements (heavy metal content) of EN 71-3 'Toy Safety', part 3 'Migration of certain elements' and part 9 'Organic chemical compounds'.



The key environmental parameters of the product are presented at the Paper Profile.



Archivability tested according to the requirements of DIN 6738, Lifespan class - LDK 24-85.



Pulp is bleached without the use of chlorine (ECF).



Dry toner: Suitable for dry toner.

Packaging of product complies with packaging and waste directive 94/62/EC (article 11).
Product is fully recyclable.

Target production values · Regional variations in specifications may apply; please contact your local Sales office for more information. Updated: 22.03.2022.