Invited Paper

Toward cloaking in nanosphere dispersed liquid crystal (NDLC) metamaterial

G. Pawlik[a], W. Salejda[a], K. Tarnowski[a], W. Walasik[a], A.C. Mitus[a], I. C. Khoo[b]

[a]Institute of Physics, Wroclaw University of Technology, Wybrzeze Wyspianskiego 27, Poland
[b]Department of Electrical Engineering, Pennsylvania State University, University Park, PA, 16802 USA

ABSTRACT

We discuss the concept of infrared cloaking using nanosphere dispersed liquid crystal (NDLC) matematerial in cylindrical geometry for TM polarization. The system consists of six layers of NDLC with different values of ordinary refractive index. Finite element calculations (COMSOL Multiphysics) show that scattering from the hidden object is strongly limited in the presence of the cloak.

1. METAMATERIALS, CLOAKING AND TRANSFORMATION OPTICS

The concept of metamaterials was proposed in 1968 by Veselago[1] who has shown that Maxwell equations predict negative values of refractive index. However, this concept was not further explored because materials with such unusual properties can not be found in nature. The interest in the field of metamaterials started to grow steadily since the first experimental realization by Pendry[2] in 1998. The proposed metamaterial composed of thin metal wires and split ring resonator offered no possibility of tuning.

Since the first experimental realization of metamaterial many different approaches to obtain the negative effective refractive index were invented. Basing on them different types of metamaterial–based devices were designed.[3] One of the first applications for metamaterials was a perfect lens proposed by Pendry[4] that allows to image the object without aberrations and with sub–wavelength resolution.

New possibilities of tailoring the light flow became available with the use of transformation optics.[5] This method allows to mold the flow of light in practically arbitrary way using a particular spatial distribution of electromagnetic parameters of the medium. Using the form–invariance of Maxwell equations with respect to the space coordinate transformation one can shape the light trajectory and bend it in a similar way as it happens in the curved space in the general theory of relativity. To achieve this effect the spatial distribution of the permeability and permittivity tensor of the medium has to satisfy the conditions resulting from the coordinate transformation.

One of the applications of transformation optics is a long time dream of human civilization – invisibility. Novel metamaterials where the spatial distribution of optical parameters can be specifically defined allow to design/produce cloaking devices providing invisibility effect. The light flow can follow a desired trajectory so that the hidden object appears to be invisible. The omnidirectional spherical cloak was proposed.[6,7] However, in this case the conditions imposed on permeability and permittivity tensors are very hard to meet. Therefore the first experimental realization used a cylindrical cloak working only for one particular polarization of light. The design was based on the array of split–ring resonators and was operating in the microwaves range. The details of linear coordinate transformation and metamaterials can be found in Ref.[8] Similar devices operating in the visible range were proposed by Cai *et al.*[9] The same linear coordinate transformation was used but the metamaterial consisted of thin metal wires in a dielectric medium. The devices mentioned above were designed just for one polarization and cause a non–zero scattering due to impedance mismatch. To avoid this problem the higher order coordinate transformations can be used[10,11] that, on one hand result in a more complex distributions of the medium parameters but, on the other hand, cause less scattering.

Send correspondence to antoni.mitus@pwr.wroc.pl

Liquid Crystals XV, edited by Iam Choon Khoo, Proc. of SPIE Vol. 8114, 81140G
© 2011 SPIE · CCC code: 0277-786X/11/$18 · doi: 10.1117/12.893900

Downloaded from SPIE Digital Library on 02 Nov 2011 to 89.79.65.70. Terms of Use: http://spiedl.org/terms

A different approach to cloaking is related to the concept of invisibility carpet proposed in paper.[12] It allows to "hide" the bump on the flat reflecting surface. Above the bump the layer of metamaterial with spatial distribution of optical parameters is placed that causes the light to reflect as from the flat surface. Big advantage of this kind of cloaking is that the properties of the material providing cloaking are not resonant. As a result the invisibility effect is achieved for the broad range of frequencies in contrast to the invisibility cloak where the proper values of material parameters occur close to the resonance and the operating range is very narrow.

The first experimental realization of the invisibility carpet was proposed in Ref.[13] The carpet was operating in millimeter wavelength region. More recent designs[14,15] allow for cloaking in near infra–red range and are based on silicon structures and photonic crystals.

The similarities between transformation optics and general relativity were pointed out by Leonhardt.[16] The link between the Fermat principle, stating that light chooses the trajectory with the shortest optical path, and the celestial mechanics in curved time–space was established by Genov.[17] It opens the way to investigate the orbital motion, strange attractors and chaos, in a controlled laboratory environment using the light. The optical–mechanical analogy enables direct studies of critical light/matter behavior around massive celestial bodies and, on the other hand, points toward the design of novel optical cavities and photon traps for application in microscopic devices and lasers systems. Basing on these principles the omnidirectional broadband photon absorber forming an optical black hole equivalent was designed.[18] Also, the light storing device was proposed where light can be accumulated and recovered from when needed.[19]

The effects mentioned above were designed using transformation optics where only the spatial coordinates undergo the transformation. There is also the possibility to involve time in the transformation. This allows us to hide not only the objects but also the events. By appropriate slowing down the light rays and speeding them up one can cause that some events can be undetectable for a distant observer.[20]

Besides those effects transformation optics can play more tricks. Is allows us to create the stereoscopic illusion so that an arbitrary object appears to be an object with completely different shape. Lai *et al.* was the first to numerically demonstrate this unusual optical phenomenon.[21] The principle lies in two distinct pieces of metamaterial: first one annihilates the light coming from the object and the second one recovers the light forming from it the image of another object chosen for illusion.

Liquid crystal based metamaterial[22] offers a possibility of tuning of refractive index because the reorientation of LC molecules causes the change of the permittivity of the host and influences the effective parameters of the metamaterial. The aim of this paper is to propose a specific design of layered NDLC metamaterial which mimics the invisibility effect in a cylindrical cell for TM polarization of light with fixed wavelength.

2. NANOSPHERE DISPERSED LIQUID CRYSTAL METAMATERIAL

The idea of the metamaterial that is used in this paper was started by Wheeler *et al.*[23] The material consisting of coated spheres was proposed as a medium with negative refractive index. The possibility of tuning of refractive index in this material was proposed by Khoo and co–workers.[22] The coated spheres were randomly dispersed in liquid crystal (LC) host. The reorientation of LC molecules allows to control the effective refractive index of nanodispersed liquid crystal (NDLC) metamaterial.

Scattering of the electromagnetic wave on a single coated sphere was analyzed using Mie scattering theory.[24] The scattered field in the dipole approximation was compared to the field produced by radiating dipole. From this comparison the electric and magnetic polarizabilities of a single coated sphere have been calculated. The effective parameters of an ensemble of coated spheres dispersed in NLC matrix were analyzed in the framework of effective medium theory. Using Maxwell Garnet mixing rule[25] that relates the properties of the spherical inclusions in the bulk material to the effective optical parameters the effective permittivity and permeability of NDLC metamaterial were retrieved. The resulting effective parameters are different from the parameters of the components forming the medium.

The proper choice of the parameters is crucial for design of the effective material properties. The resulting effective refractive index of the NDLC media strongly depends on the properties of the building blocs: core and shell of the coated spheres and nematic liquid crystal (NLC) host.

Downloaded from SPIE Digital Library on 02 Nov 2011 to 89.79.65.70. Terms of Use: http://spiedl.org/terms

The procedure described at the beginning of this paragraph yields the following expressions for effective permittivity and permeability:[22]

$$\epsilon_{eff} = \epsilon_3 \left(\frac{k_3^3 + 4\pi i N a_1}{k_3^3 - 2\pi i N a_1} \right), \tag{1}$$

$$\mu_{eff} = \frac{k_3^3 + 4\pi i N b_1}{k_3^3 - 2\pi i N b_1}, \tag{2}$$

where N denotes number density of the spheres, $k_3 = \sqrt{\epsilon_3} k_0$, where ϵ_3 denotes permittivity of the liquid crystal host and $k_0 = 2\pi/\lambda_0$. λ_0 stands for the free space wavelength. According to the Mie theory in the dipolar (electric and magnetic) approximations the amplitudes of scattered electric and magnetic fields are proportional to coefficients a_1 and b_1, respectively. The detailed expressions can be found in Ref.[24] Those coefficients enter the expressions for effective permittivity and permeability of NDLC (1) and (2) and are responsible for the resonances. The formulas given above are valid only for small number density $N = 3f/4\pi r_2^3$ of spheres (f is the filling factor) and in long–wavelength limit $2\pi/k_3 \gg r_2$.

The effective index of refraction was calculated as:

$$n_{eff} = \pm\sqrt{\epsilon_{eff}\ \mu_{eff}}, \tag{3}$$

where the root with a positive imaginary part should be chosen. Khoo et al. have shown[22] that for some values of the parameters of the model there is a range of frequencies ω and angles θ between directions of incident light wave vector and director of NLC for which

$$n'_{eff}(\omega, \theta) \equiv \Re\big(n_{eff}(\omega, \theta)\big) < 0. \tag{4}$$

To ensure the resonance in the effective permeability (2) high values of bulk permittivity of the material of the core have to be obtained.[23] Therefore the core with radius r_1 is made of polaritonic material (such as $LiTaO_3$) with relative bulk permittivity given by:

$$\epsilon_1(\omega) = \epsilon_1(\infty) \left(1 + \frac{\omega_L^2 - \omega_T^2}{\omega_T^2 - \omega^2 - i\omega\gamma_1} \right), \tag{5}$$

where $\epsilon_1(\infty)$ denotes the high–frequency dielectric constant, γ_1 – damping coefficient, ω_T and ω_L – transverse and longitudinal phonon frequencies, respectively. The resonance in effective permittivity μ_{eff} occurs at relative bulk permittivity of the order of magnitude 10^2. Due to high value of bulk permittivity of the core material the resonance in the core is a bulk cavity resonance and is responsible for negative effective permeability of the assembly of spheres at particular electromagnetic wavelengths.

To obtain the resonant behavior of the effective permittivity (1) the shell with outer radius r_2 should have small negative value of the bulk permittivity. To this end we chose the material of the shell to be semiconductor with the relative bulk permittivity described by Drude model:

$$\epsilon_2(\omega) = 1 - \frac{\omega_p^2}{\omega^2 + i\omega\gamma_2}, \tag{6}$$

where ω_p denotes plasma frequency and γ_2 – the damping coefficient. Due to negative value of the permittivity for frequencies lower than the plasma frequency ω_p the resonance in the shell will be surface resonance and will not influence the core properties. The shell resonance is responsible for negative effective permittivity, at the frequency slightly smaller than ω_p. The negative effective refractive index is designed to occur at this frequency. The parameters of the materials creating the coated sphere and the sizes of the core and the shell are precisely chosen in such a way that they provide both negative effective permittivity and permeability in the same interval of frequencies.[23]

Downloaded from SPIE Digital Library on 02 Nov 2011 to 89.79.65.70. Terms of Use: http://spiedl.org/terms

The tunability of effective refractive index is provided by changing the permittivity of the LC host. Permittivity of the liquid crystal host for extraordinary polarized wave depends on angle θ:[26]

$$\epsilon_3(\theta) = \frac{\epsilon_{\parallel}\epsilon_{\perp}}{\epsilon_{\parallel}\cos^2(\theta) + \epsilon_{\perp}\sin^2(\theta)}, \tag{7}$$

where $\epsilon_{\parallel}$ and $\epsilon_{\perp}$ are the permittivities for light polarized parallel and perpendicular to the director (or optical axis), respectively. The reorientation of the LC molecules and the resulting change of the angle θ cause a small change in the resonance conditions for effective permittivity and permeability and therefore influences the values of those parameters. Reorientation of NLC molecules can be induced by external electric or optical field or by anchoring forces.[27–29]

3. CLOAKING IN LAYERED SYSTEM OF NDLC FOR CHOSEN INFRARED WAVELENGTHS

We discuss some aspects of the design of an infrared cylindrical cloak using NDLC metamaterial. Devices based on liquid crystal potentially offer the possibility of real–time control of invisibility.



Figure 1. Cylindrical NLC cell with inner and outer radii a and b, filled with NDLC metamaterial.

Consider a cylindrical NLC cell with inner and outer radii a and b, filled with NDLC metamaterial (Fig. 1). The optical transformation for cylindrical systems and general requirements for tensor components of permittivity and permeability which satisfy cloaking condition for transverse magnetic (TM) polarization of incident light were discussed in Refs.:[3,9]

$$(\mu'_{eff})_z(\varepsilon'_{eff})_r = \left(\frac{b}{b-a}\right)^2\left(\frac{r-a}{r}\right)^2, \tag{8}$$

$$(\mu'_{eff})_z(\varepsilon'_{eff})_\Theta = \left(\frac{b}{b-a}\right)^2. \tag{9}$$

Indices z, r, Θ refer to cylindrical coordinates (Fig. 2).

If the long axes of NLC molecules are in $x-y$ plane then the wave with TM polarization incidents as an extraordinary wave onto the NLC host. Based on local orientation of NLC molecules local tensor of permittivity of the host ϵ_3 is calculated:

$$\varepsilon_3 = \begin{pmatrix} \varepsilon_\perp + \Delta\varepsilon\sin^2\theta & \Delta\varepsilon\sin\theta\cos\theta & 0 \\ \Delta\varepsilon\sin\theta\cos\theta & \varepsilon_\perp + \Delta\varepsilon\cos^2\theta & 0 \\ 0 & 0 & \varepsilon_\perp \end{pmatrix}. \tag{10}$$

In the next step effective parameters ϵ_{eff}, μ_{eff} are calculated from Eqs. (1, 2).

The design consists in finding a set of parameters (size of nanospheres, ordinary and extraordinary refractive indices of NLC host, filling factor, size of cloak a and b, configuration of NLC particles, wavelength) for which

Downloaded from SPIE Digital Library on 02 Nov 2011 to 89.79.65.70. Terms of Use: http://spiedl.org/terms



Figure 2. Cylindrical coordinates.

the cloaking requirements can be met. In this paper the design of a cloak composed of cylindrically layered NDLC is presented.

The effective permittivity and permeability of NDLC were calculated for $r_1 = 123.5$nm, $d = 19.5$nm, $\lambda = \lambda_0 = 2.93\mu$m and $f = 0.06$. In each layer of NDLC an extraordinary index of refraction n_e of the host has the same value $n_e = 1.732$. On the contrary the ordinary index of refraction of the host n_o is different in each layer. In this way a stepwise radial distribution of ordinary index of NLC host is introduced.

In Fig. 3 an example of layered system is presented. Size of hidden object is $a = 10$ μm and size of cloak $b = 30.15$ μm. The cloak consists of 6 separated cylindrical cells with the same thickness. Parameters of liquid crystal and related effective parameters of NDLC are presented in Table 1. To evaluate the performance of this particular cloak design we performed field–mapping simulations using Finite Element package (COMSOL Multiphysics). The object hidden inside the cloak is an ideal metallic cylinder with radius a. Fig. 4 shows the z-component of magnetic field distribution around the metallic cylinder surrounded by the NDLC shell. Without the NDLC shell (Fig. 4 (a)) a shadow is cast behind the cylinder while in the presence of the cloak (Fig. 4 (b)) the wave fronts flow around the cloaked region with remarkably small perturbation. The quantitative measure of the effect, given by the integral of the Poynting vector over a line (plane) behind the cloak confirms the cloaking capability of the design.



Figure 3. Model of the system. The desired distribution of the orientations of LC molecules results from anchoring forces on the cylindrical walls of layers.

Downloaded from SPIE Digital Library on 02 Nov 2011 to 89.79.65.70. Terms of Use: http://spiedl.org/terms

layer	μ_z	$(\varepsilon'_{eff})_\Theta$	$(\varepsilon'_{eff})_r$	n_o	n_e
1	1.158	1.933	0.12	1.432	1.732
2	1.158	1.933	0.31	1.458	1.732
3	1.158	1.933	0.49	1.482	1.732
4	1.158	1.933	0.63	1.502	1.732
5	1.158	1.933	0.76	1.519	1.732
6	1.158	1.933	0.86	1.532	1.732

Table 1. Parameters used in the cloak design. The effective permittivity and permeability of NDLC were calculated for $r_1 = 123.5$nm, $d = 19.5$nm, $\lambda = \lambda_0 = 2.93\mu$m and $f = 0.06$ from Eqs. (1, 2).

4. SUMMARY

We have presented a design of a cylindrical cloak for TM light polarization based on nanosphere dispersed liquid crystal (NDLC) metamaterial. We have shown, using Finite Element simulations (COMSOL Multiphysics) that a cylindrical system consisting of six layers of NDLC realizes the cloaking effect. The design can be easily repeated for different sets of parameters, e.g. for a larger size of hidden object and cloak thickness, which can be of importance for experimental realizations. The maximization of cloaking effects requires numerical optimization procedures;[32,33] design presented in this paper is devoid of any optimization. Those topics will be discussed in detail in forthcoming papers.

Acknowledgements

G.Pawlik thanks Polish National Science Centre for financial support under Grant N N507 322440. K. Tarnowski thanks the Foundation for Polish Science for their support within the "Mistrz" Program. I.C. Khoo acknowledges support from Army Research Office.

REFERENCES

1. Veselago, V. G., "Electrodynamics of substances with simultaneously negative values of ϵ and μ.", Sov. Phys. Usp. 10, 509 (1968).
2. Pendry, J. B., Holden, A. J., Robbins, D. J. and W. J. Stewart, "Low frequency plasmons in thin-wire structures", J. Phys. Condens. Matter 10, 4785 (1998).
3. Cai, W. and Shalaev, V., [Optical Metamaterials Fundamentals and Applications], Springer, New York, 137–191 (2010).
4. Pendry, J. B., "Negative Refraction Makes a Perfect Lens", Phys. Rev. Lett., 85, 3966 (2000).
5. Leonhardt, U. and Philbin, T. G., "Transformation Optics and the Geometry of Light", Prog. Opt. 53, 69 (2009).
6. Pendry, J. B., Schurig, D. and Smith, D.R., "Controlling Electromagnetic Fields", Science 312, 1780 (2006).
7. Schurig, D., Pendry, J. B. and Smith, D. R., "Calculation of material properties and ray tracing in transformation media", Opt. Express 14, 9794 (2006).
8. Schurig, D., Mock, J. J., Justice, B. J., Cummer, S. A., Pendry, J. B., Starr, A. F. and Smith, D. R., "Metamaterial Electromagnetic Cloak at Microwave Frequencies", Science 314, 977 (2006).
9. Cai, W., Chettiar, U. K., Kildishev, A. V. and Shalaev, V. M., "Optical cloaking with metamaterials", Nature Photonics 1, 224 (2007).
10. Cai, W., Chettiar, U. K., Kildishev, A. V., Shalaev, V. M. and Milton, G. W., "Nonmagnetic cloak with minimized scattering", Appl. Phys. Lett., 91, 111105 (2007).
11. Cai, W., Chettiar, U. K., Kildishev, A. V. and Shalaev, V. M., "Designs for optical cloaking with high–order transformations", Opt. Express 16, 5444 (2008).
12. Li, J. S. and Pendry, J. B., "Hiding under the Carpet: A New Strategy for Cloaking", Phys. Rev. Lett. 101, 203901 (2008).
13. Liu, R., Ji, C., Mock, J. J., Chin, J. Y., Cui, T. J. and Smith, D. R., "Broadband Ground-Plane Cloak", Science 323, 366 (2009).

Downloaded from SPIE Digital Library on 02 Nov 2011 to 89.79.65.70. Terms of Use: http://spiedl.org/terms



Figure 4. Finite Element simulations of the magnetic field mapping around the cloaked object with TM illumination: the object is surrounded by vacuum without the cloak (a); the object is inside layered NDLC shell cloak consisting of 6 layers (b). $\lambda_0 = 2.93\mu$m, $a = 10\mu$m, $b = 30.15\mu$m.

Downloaded from SPIE Digital Library on 02 Nov 2011 to 89.79.65.70. Terms of Use: http://spiedl.org/terms

14. Valentine, J., Li, J., Zentgraf, T., Bartal, G. and Zhang, X., "An optical cloak made of dielectrics", Nat. Mater. 8, 568 (2009).
15. Ergin, T., Stenger, N., Brenner, P., Pendry, J. B. and Wegener, M., "Three-Dimensional Invisibility Cloak at Optical Wavelengths", Science 328, 337 (2010).
16. Leonhardt, U. and Philbin, T. G., "General relativity in electrical engineering", New Journal of Phys. 8, 247 (2006).
17. Genov, D. A., Zhang, S. and Zhang, X., "Mimicking celestial mechanics in metamaterials", Nat. Phys. 5, 687 (2009).
18. Narimanov, E. E. and Kildishev, A. V., "Optical black hole: Broadband omnidirectional light absorber", Appl. Phys. Lett. 95, 041106 (2009).
19. Bai, Q., Chen, J., Shen, N. H., Cheng, C. and Wang, H. T., "Controllable optical black hole in left-handed materials", Opt. Expr. 18, 2106 (2010).
20. McCall, M. W., Favaro, A., Kinsler, P. and Boardman, A., "A spacetime cloak, or a history editor", J. Opt. 13, 024003 (2011).
21. Lai, Y., Ng, J., Chen, H. Y., Han, D. Z., Xiao, J. J., Zhang Z. Q. and Chan, C. T. "Illusion Optics: The Optical Transformation of an Object into Another Object", Phys. Rev. Lett. 102, 253902 (2009).
22. Khoo, I. C., Werner, D. H., Liang, X., Diaz, A. and B. Weiner, "Nanosphere dispersed liquid crystals for tunable negativezeropositive index of refraction in the optical and terahertz regimes", Opt. Lett. 31, 2592 (2006).
23. Wheeler, M. S., Aitchison, J. S. and Mojahedi, M., "Coated nonmagnetic spheres with a negative index of refraction at infrared frequencies", Phys. Rev. B 73, 045105 (2006).
24. Bohren, C. F. and Huffman, D. R., [Absorption and Scattering of Light by Small Particles], Wiley, New York, 181–183 (1998).
25. Maxwell Garnett, J. C., "Colors in metal glasses and in metallic films", Philos. Trans. R. Soc. London, Ser. A 203, 385 (1904).
26. Khoo, I.C., [Liquid Crystals, 2nd*ed.*], Wiley, Hoboken, 124-127 (2007).
27. Pawlik, G., Jarema, M., Walasik, W., Mitus, A.C, and Khoo, I.C., "Field-induced inhomogeneous index distribution of a nano-dispersed nematic liquid crystal metamaterial near the Freedericksz transition: Monte Carlo studies", J. Opt. Soc. Am. B 27, 567 (2010).
28. Pawlik, G., Walasik, W., Mitus, A.C., and Khoo, i.C., "Large gradients of refractive index in nanosphere dispersed liquid crystal metamaterial with inhomogeneous anchoring: Monte Carlo study", Opt. Mater. 33, 1459 (2011).
29. Pawlik, G., Walasik, W., Mitus, A.C., Khoo, I.C., "Field-, temperature-, and anchoring-induced inhomogeneous index distribution of a nano-dispersed nematic liquid crystal near the Freedericksz transition: Monte Carlo studies", Proc. SPIE 7775, 77750K (2010).
30. Allen, P., and Tildesley, D., [Computer Simulation of Liquids], Clarendon Press, Oxford, 1987.
31. Landau D., and Binder, K., [A Guide to Monte Carlo Simulations in Statistical Physics], Cambridge University Press, 2000.
32. Ivsic, B., Komljenovic, T., and Sipus, Z., "Optimization of Uniaxial Multilayer Cylinders Used for Invisible Cloak Realization," IEEE Transactions on Antennas and Propagation **58**, 3397–3401 (2010).
33. Xi, S., Chen, H., Zhang, B., Wu, B.–I., and Kong, J.A., "Route to low-scattering cylindrical cloaks with finite permittivity and permeability," Phys. Rev. B **79**, 155122, (2009).

Downloaded from SPIE Digital Library on 02 Nov 2011 to 89.79.65.70. Terms of Use: http://spiedl.org/terms