

Tests Conducted (As Requested By The Applicant)

1 Colorfastness To Crocking (AATCC TM8-2016e(2022)e):			<u>Requirement</u>
Dry - Lengthwise	4		Data Only
Dry - Widthwise	4		Data Only
Wet - Lengthwise	3		Data Only
Wet - Widthwise	3		Data Only
2 Resistance To Pilling (ASTM D4970/D4970M-22(2026), Martindale Tester):			<u>Requirement</u>
After 600 Cycles - Grade	3-4		Data Only
3 Colorfastness To Perspiration (AATCC TM15-2021e):			<u>Requirement</u>
Acid Perspiration - Color Change	4		Data Only
Acid Perspiration - Color Staining	4		Data Only
Alkaline Perspiration - Color Change*	4		Data Only
Alkaline Perspiration - Color Staining*	4		Data Only
4 Colorfastness To Laundering (AATCC TM61-2013e(2020)e2):			<u>Requirement</u>
Color Change	4		Data Only
Color Staining	4-5		Data Only
5 Colorfastness To Water (AATCC TM107-2022e):			<u>Requirement</u>
Color Change	4		Data Only
Color Staining	4-5		Data Only
6 Colorfastness To Saliva (GB/T 18886-2019; No Direct AATCC/ASTM Equivalent):			<u>Requirement</u>
Color Change	4		Data Only
Color Staining	4-5		Data Only
7 Dimensional Change After Home Laundering (AATCC TM135-2025):			<u>Requirement</u>
After Wetting/Relaxation - Length	1.5%		Data Only
After Wetting/Relaxation - Width	2.5%		Data Only
After Line Drying - Length	3.5%		Data Only
After Line Drying - Width	4%		Data Only
8 Skew Change After Home Laundering (AATCC TM179-2025):			<u>Requirement</u>
Skew Change	0.08%		Data Only
9 Colorfastness To Light (AATCC TM16.3-2020, Option 3, Xenon-Arc Lamp):			<u>Requirement</u>
Exposure: Not Stated In Source - Grade	4		Data Only
10 pH Of The Water-Extract From Wet Processed Textiles (AATCC TM81-2022):			<u>Requirement</u>
pH Value	5.6		Data Only

CONVERSION DRAFT - Results are transcribed from the supplied GB/T report images and applicant-provided pilling data; they were not generated by retesting to ASTM/AATCC methods. Method conditions may differ. *AATCC TM15 covers the acid-perspiration condition; alkaline-perspiration values are retained from the source report.