

Tests Conducted (As Requested By The Applicant)

1	Colorfastness To Crocking (AATCC TM8-2016e(2022)e):		<u>Requirement</u>
	Dry - Lengthwise	4	Data Only
	Dry - Widthwise	4	Data Only
	Wet - Lengthwise	3	Data Only
	Wet - Widthwise	3	Data Only
2	Resistance To Pilling (ASTM D4970/D4970M-22(2026), Martindale Tester):		<u>Requirement</u>
	After 600 Cycles - Grade	4	Data Only
3	Colorfastness To Perspiration (AATCC TM15-2021e):		<u>Requirement</u>
	Acid Perspiration - Color Change	4	Data Only
	Acid Perspiration - Color Staining	4	Data Only
	Alkaline Perspiration - Color Change*	4	Data Only
	Alkaline Perspiration - Color Staining*	4	Data Only
4	Colorfastness To Laundering (AATCC TM61-2013e(2020)e2):		<u>Requirement</u>
	Color Change	4	Data Only
	Color Staining	4-5	Data Only
5	Colorfastness To Water (AATCC TM107-2022e):		<u>Requirement</u>
	Color Change	4	Data Only
	Color Staining	4-5	Data Only
6	Colorfastness To Saliva (GB/T 18886-2019; No Direct AATCC/ASTM Equivalent):		<u>Requirement</u>
	Color Change	4	Data Only
	Color Staining	4-5	Data Only
7	Dimensional Change After Home Laundering (AATCC TM135-2025):		<u>Requirement</u>
	After Wetting/Relaxation - Length	-1.2%	Data Only
	After Wetting/Relaxation - Width	+0.7%	Data Only
	After Line Drying - Length	+0.5%	Data Only
	After Line Drying - Width	-0.6%	Data Only
8	Skew Change After Home Laundering (AATCC TM179-2025):		<u>Requirement</u>
	Skew Change	1.3%	Data Only
9	Colorfastness To Light (AATCC TM16.3-2020, Option 3, Xenon-Arc Lamp):		<u>Requirement</u>
	Exposure: Not Stated In Source - Grade	4	Data Only
10	pH Of The Water-Extract From Wet Processed Textiles (AATCC TM81-2022):		<u>Requirement</u>
	pH Value	6.3	Data Only

CONVERSION DRAFT - Results are transcribed from the supplied GB/T report images and applicant-provided pilling data; they were not generated by retesting to ASTM/AATCC methods. Method conditions may differ. *AATCC TM15 covers the acid-perspiration condition; alkaline-perspiration values are retained from the source report.