

# SABIC® PPCOMPOUND G3230A

PP SHORT GLASS FIBER REINFORCED

## DESCRIPTION

SABIC® PPcompound G3230A is a 30% short glass fiber reinforced Polypropylene for under-the-hood and structural applications. The base material is a PP homopolymer and is available in standard black. The glass fibres are chemically coupled to the PP matrix. This material has been designed to combine a good performance profile with fast processing.

SABIC® PPcompound G3230A is a designated automotive grade.

IMDS ID: 109612410

## TYPICAL PROPERTY VALUES

Revision 20210721

| PROPERTIES                                  | TYPICAL VALUES | UNITS  | TEST METHODS |
|---------------------------------------------|----------------|--------|--------------|
| <b>POLYMER PROPERTIES</b>                   |                |        |              |
| <b>Melt Flow Rate (MFR)</b>                 |                |        |              |
| at 230 °C and 2.16 kg                       | 11             | dg/min | ISO 1133     |
| <b>Density</b> <sup>(1)</sup>               | 1130           | kg/m³  | ISO 1183     |
| <b>Filler content</b>                       | 30             | %      | SABIC method |
| <b>Mould shrinkage</b> <sup>(2)</sup>       |                |        |              |
| 24 hours after injection moulding           | 0.6            | %      | SABIC method |
| <b>MECHANICAL PROPERTIES</b> <sup>(1)</sup> |                |        |              |
| <b>Tensile</b>                              |                |        |              |
| stress at break                             | 93             | MPa    | ISO 527/1A   |
| strain at break                             | 3              | %      | ISO 527/1A   |
| <b>Flexural test</b>                        |                |        |              |
| Flexural modulus                            | 6900           | MPa    | ISO 178/1A   |
| <b>Charpy Impact Strength Notched</b>       |                |        |              |
| at 23 °C                                    | 12             | kJ/m²  | ISO 179/1eA  |
| <b>THERMAL PROPERTIES</b> <sup>(1)</sup>    |                |        |              |
| <b>Heat deflection temperature</b>          |                |        |              |
| at 1.80MPa (HDT/A)                          | 150            | °C     | ISO 75/A     |
| <b>Coeff. of linear thermal expansion</b>   |                |        |              |
| -30 °C to 100 °C                            | 40             | µm/mK  | ISO 11359-2  |

(1) Injection molded sample ISO527-1A

(2) Injection molded plaque 65x65x3.2mm

## STORAGE AND HANDLING

Avoid prolonged storage in open sunlight, high temperatures (<50 °C) and/or high humidity as this could well speed up alteration and consequently loss of quality of the material and/or its packaging. Keep material completely dry for good processing.



## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.