

SABIC® PPCOMPOUND H1200

FLAME RETARDANT POLYPROPYLENE

DESCRIPTION

SABIC® PPcompound H1200 is a high impact, halogen free flame retardant, non mineral filled Polypropylene compound. It has a UL94 V0@ 2mm flame rating. This material has been designed to combine a good performance profile with good processing and FR characteristics.

Melt temperature of 240 °C should not be exceeded during processing.

IMDS ID:1062970462

TYPICAL PROPERTY VALUES

Revision 20250428

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate (MFR)			
at 230 °C and 2.16 kg	13	dg/min	ISO 1133
Density ⁽¹⁾	990	kg/m³	ISO 1183
Filler content	0	%	SABIC method
Mould shrinkage ⁽²⁾			
24 hours after injection moulding	1.2	%	SABIC method
MECHANICAL PROPERTIES ^{(1) (3)}			
Tensile			
Tensile modulus	980	MPa	ISO 527/1A
stress at yield	15	MPa	ISO 527/1A
stress at break	11	MPa	ISO 527/1A
strain at break	19	%	ISO 527/1A
Flexural test			
Flexural modulus	1000	MPa	ISO 178/1A
Izod impact notched ^{(1) (3)}			
at 23 °C	13	kJ/m²	ISO 180/1A
at 0 °C	5	kJ/m²	ISO 180/1A
at -20 °C	4	kJ/m²	ISO 180/1A
THERMAL PROPERTIES			
Heat deflection temperature			
at 1.8 MPa (HDT/A) ⁽¹⁾	48	°C	ISO 75
at 0.45 MPa (HDT/B) ⁽¹⁾	85	°C	ISO 75
Coeff. of linear thermal expansion			
-30 °C to 100 °C	130	µm/mK	ISO 11359-2
FLAMMABILITY PROPERTIES			
UL Yellow Card Link	<u>E111275</u>	-	
Comparative Tracking Index	600	V	IEC 60112
UL94			
Lowest thickness for V0	2.0	mm	UL 94
GWFI			
at 0.8 mm	750	°C	IEC 60695-2-12

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
at 1.6 mm	960	°C	IEC 60695-2-12
GWIT			
at 0.8 mm	650	°C	IEC 60695-2-13

- (1) Injection molded sample ISO527-1A
 (2) Injection molded plaque 65x65x3.2mm
 (3) N.B.: No Break

STORAGE AND HANDLING

Avoid prolonged storage in open sunlight, high temperatures (<50 °C) and/or high humidity as this could well speed up alteration and consequently loss of quality of the material and/or its packaging. Keep material completely dry for good processing.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.