

TECHNICAL REPORT

CEN ISO/TR 20172

RAPPORT TECHNIQUE

TECHNISCHER BERICHT

May 2021

ICS 25.160.20

Supersedes CEN ISO/TR 20172:2009

English Version

Welding - Grouping systems for materials - European materials (ISO/TR 20172:2021)

Soudage - Systèmes de groupement des matériaux -
Matériaux européens (ISO/TR 20172:2021)

Schweißen - Werkstoffgruppeneinteilung -
Europäische Werkstoffe (ISO/TR 20172:2021)

This Technical Report was approved by CEN on 20 March 2021. It has been drawn up by the Technical Committee CEN/TC 121.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

European foreword

This document (CEN ISO/TR 20172:2021) has been prepared by Technical Committee ISO/TC 44 "Welding and allied processes" in collaboration with Technical Committee CEN/TC 121 "Welding and allied processes" the secretariat of which is held by DIN.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes CEN ISO/TR 20172:2009.

Endorsement notice

The text of ISO/TR 20172:2021 has been approved by CEN as CEN ISO/TR 20172:2021 without any modification.

Contents

	Page
Foreword	iv
Introduction.....	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 International grouping system for European materials	1
4.1 Types of steel in accordance with the grouping system of ISO/TR 15608:2017, Table 1.....	1
4.2 Types of aluminium and aluminium alloy in accordance with the grouping system of ISO/TR 15608:2017, Table 2.....	22
4.3 Types of copper and copper alloy in accordance with the grouping system of ISO/ TR 15608:2017, Table 3	24
4.4 Types of cast iron in accordance with the grouping system of ISO/TR 15608:2017, Table 7	25
4.5 Types of nickel and nickel alloy in accordance with the grouping system of ISO/ TR 15608:2017, Table 4.....	27
Bibliography	29

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 44, *Welding and allied processes*, Subcommittee SC 10, *Quality management in the field of welding*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 121, *Welding and allied processes*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This third edition cancels and replaces the second edition (ISO 20172:2009), which has been technically revised.

The main changes compared to the previous edition are as follows:

- [Tables 1 to 5](#) have been revised;
- new Table 6 has been added for nickel and nickel alloys.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

This document reflects the situation at the time of publication.

Lists of former designations can be found in the relevant European materials standards.

For the materials not listed in this document, ISO/TR 20173:2018 and ISO/TR 20174:2020 are applicable.

Welding — Grouping systems for materials — European materials

1 Scope

This document establishes a European grouping system for materials for welding purposes, classified in accordance with the grouping system of ISO/TR 15608.

It is also applicable for other purposes such as heat treatment, forming and non-destructive testing.

This document covers grouping systems for the following standardized materials:

- a) steel;
- b) aluminium and its alloys;
- c) copper and its alloys;
- d) cast irons;
- e) nickel and nickel alloys.

For materials that are not assigned to a group in this document, the criteria of ISO/TR 15608 apply.

2 Normative references

There are no normative references in this document.

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

4 International grouping system for European materials

4.1 Types of steel in accordance with the grouping system of ISO/TR 15608:2017, Table 1

See [Table 1](#).

Materials grouped according to this document based on chemical composition and mechanical properties but with specific delivering conditions outside ISO/TR 15608:2017 are qualified separately.

Table 1 — Steel materials, classification according to the grouping of material

Designation		Group	Standard(s)
Name	Number		
10CrMo5-5	1.7338	5.1	EN 10216-2
10CrMo9-10	1.7380	5.2	EN 10028-2, EN 10216-2, EN 10273
11CrMo9-10	1.7383	5.2	EN 10028-2, EN 10216-2, EN 10222-2, EN 10273
11MnNi5-3	1.6212	9.1	EN 10028-4, EN 10216-4
12Ni14	1.5637	9.2	EN 10028-4, EN 10216-4, EN 10222-3
12Ni19	1.5680	9.2	EN 10028-4
13CrMo4-5	1.7335	5.1	EN 10028-2, EN 10216-2, EN 10222-2, EN 10273
13MnNi6-3	1.6217	9.1	EN 10028-4, EN 10216-4, EN 10222-3
14MoV6-3	1.7715	6.1	EN 10216-2, EN 10222-2
15MnCrMoNiV5-3	1.6920	4.1	EN 10222-2
15MnMoV4-5	1.5402	1.2	EN 10222-2
15NiCuMoNb5-6-4	1.6368	4.2	EN 10216-2
15NiMn6	1.6228	9.1	EN 10028-4, EN 10222-3
16Mo3	1.5415	1.2	EN 10222-2, EN 10216-2, EN 10217-2, EN 10217-5, EN 10273, EN 10028-2
18MnMoNi5-5	1.6308	3.1	EN 10222-2
20CrMoV13-5-5	1.7779	6.3	EN 10216-2
20Mn5	1.1133	1.4	EN 10250-2
20MnB5	1.5353	3.2	EN ISO 683-2, EN ISO 683-3
20MnNb6	1.0471	1.2	EN 10216-2
20NiCrMo2-2	1.6523	3.1	EN 10297-1
20NiCrMoS2-2	1.6526	3.1	EN 10297-1
24CrMo13-6	1.8516	5.2	EN 10085
25CrMo4	1.7218	5.1	EN ISO 683-2, EN ISO 683-3, EN 10132-2, EN 10216-2, EN 10297-1
25CrMoS4	1.7213	5.1	EN ISO 683-2, EN ISO 683-3, EN 10277
25Mn4	1.1177	1.3	EN 10132-2
26CrMo4-2	1.7219	5.1	EN 10216-4
27MnCrB5-2	1.7182	11.1	EN ISO 683-2, EN ISO 683-3
28Mn6	1.1170	1.4 ^a	EN 10083-2, EN 10250-2
30CrMo4	1.7216	5.1 ^a	EN 10297-1
30MnB5	1.5531	11.1	EN ISO 683-2, EN ISO 683-3
30NiCrMo16-6	1.6747	9.2 ^a	EN ISO 683-2, EN ISO 683-3
31CrMo12	1.8515	5.2 ^a	EN 10085
31CrMoV9	1.8519	6.2 ^a	EN 10085
32CrAlMo7-10	1.8505	5.1 ^a	EN 10085

^a The classification of materials is for informational purposes only, as the strength values or limits of chemical composition specified in this document can be outside the limits of ISO/TR 15608. But these materials have not exactly the same behaviour during welding as his sub-group material. Welding conditions should be specifically adapted.

Table 1 (continued)

Designation		Group	Standard(s)
Name	Number		
33CrMoV12-9	1.8522	6.2 ^a	EN 10085
34Cr4	1.7033	5.1 ^a	EN ISO 683-2, EN ISO 683-3, EN 10250-3
34CrAlMo5-10	1.8507	5.1 ^a	EN 10085
34CrAlNi7-10	1.8550	5.1 ^a	EN 10085
34CrMo4	1.7220	11.2 ^a	EN ISO 683-2, EN ISO 683-3, EN 10297-1
34CrMoS4	1.7226	11.2 ^a	EN ISO 683-2, EN ISO 683-3
34CrNiMo6	1.6582	5.2 ^a	EN 10277
34CrS4	1.7037	5.1 ^a	EN ISO 683-2, EN ISO 683-3
35NiCr6	1.5815	9.1 ^a	EN ISO 683-2, EN ISO 683-3
36NiCrMo16	1.6773	9.2 ^a	EN ISO 683-2, EN ISO 683-3
37Cr4	1.7034	5.1 ^a	EN ISO 683-2, EN ISO 683-3
37CrS4	1.7038	5.1 ^a	EN ISO 683-2, EN ISO 683-3
38Cr2	1.7003	5.1 ^a	EN ISO 683-2, EN ISO 683-3
38Mn6	1.1127	11.2 ^a	EN 10297-1
39MnCrB6-2	1.7189	5.1 ^a	EN ISO 683-2, EN ISO 683-3
39NiCrMo3	1.6510	9.2 ^a	EN ISO 683-2, EN ISO 683-3
40CrMoV13-9	1.8523	6.2 ^a	EN 10085
41Cr4	1.7035	11.2 ^a	EN ISO 683-2, EN ISO 683-3
41CrAlMo7-10	1.8509	5.1 ^a	EN 10085
41CrS4	1.7039	11.2 ^a	EN ISO 683-2, EN ISO 683-3
42CrMo4	1.7225	5.1 ^a	EN ISO 683-2, EN ISO 683-3, EN 10132-2, EN 10297-1
42CrMoS4	1.7227	5.1 ^a	EN ISO 683-2, EN ISO 683-3, EN 10277
46Cr2	1.7006	11.2 ^a	EN ISO 683-2, EN ISO 683-3
50CrMo4	1.7228	5.1 ^a	EN ISO 683-2, EN ISO 683-3
51CrV4	1.8159	6.1 ^a	EN ISO 683-2, EN ISO 683-3
8MoB5-4	1.5450	1.3	EN 10216-2
C10	1.0301	1.1	EN 10277
C10E	1.1121	1.1	EN 10132-2, EN 10297-1
C15	1.0401	1.1	EN 10277
C15E	1.1141	1.1	EN 10132-2, EN 10297-1
C15R	1.1114	1.1	EN 10297-1
C16	1.0407	1.1	EN 10277
C22	1.0402	1.1	EN 10250-2
C22E	1.1151	1.1	EN 10132-2, EN 10083-2, EN 10297-1
C22R	1.1149	1.1	EN 10083-2
C25	1.0406	1.1	EN 10250-2
C25E	1.1158	1.1	EN 10250-2

^a The classification of materials is for informational purposes only, as the strength values or limits of chemical composition specified in this document can be outside the limits of ISO/TR 15608. But these materials have not exactly the same behaviour during welding as his sub-group material. Welding conditions should be specifically adapted.

Table 1 (continued)

Designation		Group	Standard(s)
Name	Number		
C30	1.0528	11.1	EN 10250-2
C30E	1.1178	11.1	EN 10132-2
C35	1.0501	11.1	EN 10083-2, EN 10250-2, EN 10277
C35E	1.1181	11.1	EN 10083-2, EN 10250-2, EN 10297-1, EN 10132-2, EN 10277
C35R	1.1180	11.1	EN 10277
C35R	1.1180	11.2	EN 10083-2
C40	1.0511	11.2	EN 10083-2, EN 10250-2, EN 10277
C40E	1.1186	11.2	EN 10083-2, EN 10132-2, EN 10277
C40R	1.1189	11.2	EN 10083-2, EN 10277
C45	1.0503	11.2 ^a	EN 10083-2, EN 10250-2, EN 10277
C45E	1.1191	11.2 ^a	EN 10083-2, EN 10250-2, EN 10297-1, EN 10132-2
C45R	1.1201	11.2 ^a	EN 10083-2, EN 10277
C50	1.0540	11.2	EN 10250-2, EN 10277
C50E	1.1206	11.3 ^a	EN 10277, EN 10083-2
C50R	1.1241	11.3	EN 10083-2, EN 10277
C55	1.0535	11.3	EN 10250-2, EN 10083-2
C55E	1.1203	11.3	EN 10083-2, EN 10250-2, EN 10132-2
C55R	1.1209	11.3	EN 10083-2
C60	1.0601	11.3	EN 10083-2, EN 10277, EN 10250-2
C60E	1.1221	11.3	EN 10083-2, EN 10132-2, EN 10250-2, EN 10297-1, EN 10277
C60R	1.1223	11.3	EN 10083-2, EN 10277
E155	1.0033	1.1	EN 10296-1, EN 10305-2, EN 10305-3, EN 10305-6
E190	1.0031	1.1	EN 10296-1, EN 10305-3
E195	1.0034	1.1	EN 10296-1, EN 10305-3, EN 10305-6, EN 10305-2
E215	1.0212	1.1	EN 10305-1, EN 10305-4
E220	1.0215	1.1	EN 10296-1, EN 10305-3, EN 10305-5
E235	1.0308	1.1	EN 10296-1, EN 10297-1, EN 10305-1, EN 10305-2, EN 10305-3, EN 10305-4, EN 10305-6
E260	1.0220	1.1	EN 10296-1, EN 10305-3
E275	1.0225	1.1	EN 10296-1, EN 10297-1, EN 10305-2, EN 10305-3, EN 10305-5, EN 10305-6
E275K2	1.0456	1.1	EN 10296-1, EN 10297-1
E275M	1.8895	1.1	EN 10296-1
E295GC	1.0533	1.2	EN 10277

^a The classification of materials is for informational purposes only, as the strength values or limits of chemical composition specified in this document can be outside the limits of ISO/TR 15608. But these materials have not exactly the same behaviour during welding as his sub-group material. Welding conditions should be specifically adapted.

Table 1 (continued)

Designation		Group	Standard(s)
Name	Number		
E315	1.0236	1.2	EN 10297-1
E320	1.0237	1.2	EN 10296-1, EN 10305-3, EN 10305-5
E335GC	1.0543	1.2	EN 10277
E355	1.0580	1.2 ^a	EN 10296-1, EN 10305-2, EN 10305-3, EN 10305-4, EN 10305-6, EN 10305-1, EN 10297-1
E355K2	1.0599	1.2	EN 10297-1
E355K2	1.0920	1.2	EN 10296-1
E355M	1.8896	1.2	EN 10296-1
E370	1.0261	1.3	EN 10296-1, EN 10305-3, EN 10305-5
E420	1.0575	1.3	EN 10305-3, EN 10305-5
E420J2	1.0920	1.3	EN 10297-1
E420M	1.8897	2.1	EN 10296-1
E460K2	1.8891	1.3	EN 10296-1, EN 10297-1
E460M	1.8898	2.1	EN 10296-1
E470	1.0536	1.3	EN 10297-1
E590K2	1.0644	1.3	EN 10297-1
E730K2	1.8893	1.3	EN 10297-1
G12MoCrV5-2	1.7720	6.1	EN 10213
G17CrMo5-5	1.7357	5.1	EN 10213
G17CrMo9-10	1.7379	5.2	EN 10213
G17CrMoV5-10	1.7706	6.2	EN 10213
G17Mn5	1.1131	1.1	EN 10213
G17NiCrMo13-6	1.6781	9.2	EN 10213
G18Mo5	1.5422	1.2	EN 10213
G20Mn5	1.6220	1.2	EN 10213
G20Mo5	1.5419	1.2	EN 10213
G9Ni10	1.5636	9.1	EN 10213
G9Ni14	1.5638	9.2	EN 10213
GP240GH	1.0619	1.1	EN 10213
GP240GR	1.0621	1.1	EN 10213
GP280GH	1.0625	1.2	EN 10213
GX15CrMo5	1.7365	5.3	EN 10213
GX23CrMoV12-1	1.4931	6.4	EN 10213
GX2CrNi19-11	1.4309	8.1	EN 10213
GX2CrNiMo19-11-2	1.4409	8.1	EN 10213
GX2CrNiMoCuN25-6-3-3	1.4517	10.2	EN 10213
GX2CrNiMoN22-5-3	1.4470	10.1	EN 10213
GX2CrNiMoN26-7-4	1.4469	10.2	EN 10213

^a The classification of materials is for informational purposes only, as the strength values or limits of chemical composition specified in this document can be outside the limits of ISO/TR 15608. But these materials have not exactly the same behaviour during welding as his sub-group material. Welding conditions should be specifically adapted.

Table 1 (continued)

Designation		Group	Standard(s)
Name	Number		
GX2NiCrMo28-20-2	1.4458	8.2	EN 10213
GX3CrNi13-4	1.6982	7.2	EN 10213
GX4CrNi13-4	1.4317	7.2	EN 10213
GX4CrNiMo16-5-1	1.4405	7.2	EN 10132-2
GX5CrNi19-10	1.4308	8.1	EN 10213
GX5CrNiMo19-11-2	1.4408	8.1	EN 10213
GX5CrNiMoNb19-11-2	1.4581	8.1	EN 10213
GX5CrNiNb19-11	1.4552	8.1	EN 10213
GX8CrNi12	1.4107	7.2	EN 10213
HC180B	1.0395	1.1	EN 10268
HC180P	1.0342	1.1	EN 10268
HC180Y	1.0922	1.1	EN 10268
HC220B	1.0396	1.1	EN 10268
HC220I	1.0346	1.1	EN 10268
HC220P	1.0397	1.1	EN 10268
HC220Y	1.0925	1.1	EN 10268
HC260B	1.0400	1.1	EN 10268
HC260I	1.0349	1.1	EN 10268
HC260LA	1.0480	1.1	EN 10268
HC260P	1.0417	1.1	EN 10268
HC260Y	1.0928	1.1	EN 10268
HC300B	1.0444	1.2	EN 10268
HC300I	1.0447	1.2	EN 10268
HC300LA	1.0489	1.2	EN 10268
HC300P	1.0448	1.2	EN 10268
HC340LA	1.0548	1.2	EN 10268
HC380LA	1.0550	1.3	EN 10268
HC420LA	1.0556	1.3	EN 10268
L210GA	1.0319	1.1	EN ISO 3183
L235	1.0252	1.1	EN 10224
L235GA	1.0458	1.1	EN ISO 3183
L245GA	1.0459	1.1	EN ISO 3183
L245MB	1.0418	1.1	EN ISO 3183
L245NB	1.0457	1.1	EN ISO 3183
L275	1.0260	1.1	EN 10224
L290GA	1.0483	1.2	EN ISO 3183
L290MB	1.0429	1.2	EN ISO 3183
L290NB	1.0484	1.2	EN ISO 3183
L355	1.0419	1.2	EN 10224
L360GA	1.0499	1.2	EN ISO 3183

^a The classification of materials is for informational purposes only, as the strength values or limits of chemical composition specified in this document can be outside the limits of ISO/TR 15608. But these materials have not exactly the same behaviour during welding as his sub-group material. Welding conditions should be specifically adapted.

Table 1 (continued)

Designation		Group	Standard(s)
Name	Number		
L360MB	1.0578	1.2	EN ISO 3183
L360NB	1.0582	1.2	EN ISO 3183
L360QB	1.8948	1.2	EN ISO 3183
L415MB	1.8973	2.1	EN ISO 3183
L415NB	1.8972	1.3	EN ISO 3183
L415QB	1.8947	3.1	EN ISO 3183
L450MB	1.8975	2.1	EN ISO 3183
L450QB	1.8952	3.1	EN ISO 3183
L485MB	1.8977	2.2	EN ISO 3183
L485QB	1.8955	3.1	EN ISO 3183
L550QB	1.8957	3.1	EN ISO 3183
L555MB	1.8978	2.2	EN ISO 3183
P195GH	1.0348	1.1	EN 10216-2, EN 10217-2
P195TR1	1.0107	1.1	EN 10216-1, EN 10217-1
P195TR2	1.0108	1.1	EN 10216-1, EN 10217-1
P215NL	1.0451	1.1	EN 10216-4, EN 10217-4, EN 10217-6
P235GH	1.0345	1.1	EN 10216-2, EN 10217-2, EN 10217-5, EN 10273, EN 10028-2
P235S	1.0112	1.1	EN 10207
P235TR1	1.0254	1.1	EN 10216-1, EN 10217-1
P235TR2	1.0255	1.1	EN 10216-1, EN 10217-1
P245GH	1.0352	1.1	EN 10222-2
P245NB	1.0111	1.1	EN 10120
P250GH	1.0460	1.1	EN 10273
P255QL	1.0452	1.1	EN 10216-4
P265GH	1.0425	1.1	EN 10216-2, EN 10217-2, EN 10217-5, EN 10273, EN 10028-2
P265NB	1.0423	1.1	EN 10120, EN 10149-3
P265NL	1.0453	1.1	EN 10216-4, EN 10217-4, EN 10217-6
P265S	1.0130	1.1	EN 10207
P265TR1	1.0258	1.1	EN 10216-1, EN 10217-1
P265TR2	1.0259	1.1	EN 10216-1, EN 10217-1
P275N	1.0486	1.1	EN 10028-3
P275NH	1.0487	1.1	EN 10273, EN 10028-3
P275NL1	1.0488	1.1	EN 10216-3, EN 10217-3, EN 10028-3
P275NL2	1.1104	1.1	EN 10216-3, EN 10217-3, EN 10028-3
P275S	1.1100	1.1	EN 10207

^a The classification of materials is for informational purposes only, as the strength values or limits of chemical composition specified in this document can be outside the limits of ISO/TR 15608. But these materials have not exactly the same behaviour during welding as his sub-group material. Welding conditions should be specifically adapted.

Table 1 (continued)

Designation		Group	Standard(s)
Name	Number		
P280GH	1.0426	1.2	EN 10222-2
P285NH	1.0477	1.2	EN 10222-4
P285QH	1.0478	1.2	EN 10222-4
P295GH	1.0481	1.2	EN 10273, EN 10028-2
P305GH	1.0436	1.2	EN 10222-2
P310NB	1.0437	1.2	EN 10120
P355GH	1.0473	1.2	EN 10273, EN 10028-2
P355M	1.8821	1.2	EN 10028-5
P355ML1	1.8832	1.2	EN 10028-5
P355ML2	1.8833	1.2	EN 10028-5
P355N	1.0562	1.2	EN 10216-3, EN 10217-3, EN 10028-3
P355NB	1.0557	1.2	EN 10120
P355NH	1.0565	1.2	EN 10216-3, EN 10217-3, EN 10273, EN 10028-3, EN 10222-4
P355NL1	1.0566	1.2	EN 10216-3, EN 10217-3, EN 10028-3
P355NL2	1.1106	1.2	EN 10216-3, EN 10217-3, EN 10028-3
P355Q	1.8866	1.2	EN 10028-6
P355QH	1.8867	1.2	EN 10273, EN 10028-6
P355QH1	1.0571	1.2	EN 10222-4
P355QL1	1.8868	1.2	EN 10028-6
P355QL2	1.8869	1.2	EN 10028-6
P420M	1.8824	2.1	EN 10028-5
P420ML1	1.8835	2.1	EN 10028-5
P420ML2	1.8828	2.1	EN 10028-5
P420NH	1.8932	1.3	EN 10222-4
P420QH	1.8936	3.1	EN 10222-4
P460M	1.8826	2.1	EN 10028-5
P460ML1	1.8837	2.1	EN 10028-5
P460ML2	1.8831	2.1	EN 10028-5
P460N	1.8905	1.3	EN 10216-3, EN 10217-3, EN 10028-3
P460NH	1.8935	1.3	EN 10273, EN 10216-3, EN 10217-3
P460NH	1.8935	1.3	EN 10028-3
P460NL1	1.8915	1.3	EN 10216-3, EN 10217-3, EN 10028-3
P460NL2	1.8918	1.3	EN 10216-3, EN 10217-3, EN 10028-3
P460Q	1.8870	3.1	EN 10028-6
P460QH	1.8871	3.1	EN 10273, EN 10028-6

^a The classification of materials is for informational purposes only, as the strength values or limits of chemical composition specified in this document can be outside the limits of ISO/TR 15608. But these materials have not exactly the same behaviour during welding as his sub-group material. Welding conditions should be specifically adapted.

Table 1 (continued)

Designation		Group	Standard(s)
Name	Number		
P460QL1	1.8872	3.1	EN 10028-6
P460QL2	1.8864	3.1	EN 10028-6
P500Q	1.8873	3.1	EN 10028-6
P500QH	1.8874	3.1	EN 10028-6
P500QL1	1.8875	3.1	EN 10028-6
P500QL2	1.8865	3.1	EN 10028-6
P620Q	1.8876	3.1	EN 10216-3
P620QH	1.8877	3.1	EN 10216-2
P620QL	1.8890	3.1	EN 10216-2
P690Q	1.8879	3.1	EN 10216-2, EN 10028-6
P690QH	1.8880	3.1	EN 10216-2, EN 10028-6
P690QL1	1.8881	3.1	EN 10216-2, EN 10028-6
P690QL2	1.8888	3.1	EN 10216-2, EN 10028-6
R200	1.0521	11.3	EN 13674-1
R220	1.0524	11.3	EN 13674-1
R260	1.0623	11.3	EN 13674-1
R260Mn	1.0624	11.3	EN 13674-1
R320Cr	1.0915	11.3	EN 13674-1
R350LHT	1.0632	11.3	EN 13674-1
R50HT	1.0631	11.3	EN 13674-1
S195T	1.0026	1.1	EN 10255
S235J0	1.0114	1.1	EN 10025-2
S235J0W	1.8958	1.4	EN 10025-5
S235J2G3	1.0116	1.1	EN 10250-2, EN 10025-2
S235J2G3C	1.0118	1.1	EN 10025-2
S235J2G4	1.0117	1.1	EN 10025-2
S235J2G4C	1.0119	1.1	EN 10025-2
S235JR	1.0037	1.1	EN 10025-2
S235JRG1	1.0036	1.1	EN 10025-2
S235JRG2	1.0038	1.1	EN 10025-2, EN 10250-2
S235JRG2	1.0122	1.1	EN 10277
S235JRH	1.0039	1.1	EN 10210-1, EN 10219-1
S240GP	1.0021	1.1	EN 10248-1
S260NC	1.0971	1.1	EN 10149-3
S270GP	1.0023	1.1	EN 10248-1
S275J0	1.0143	1.1	EN 10025-2
S275J0H	1.0149	1.1	EN 10210-1, EN 10219-1
S275J2G3	1.0144	1.1	EN 10025-2
S275J2G3C	1.0141	1.1	EN 10025-2
S275J2G4	1.0145	1.1	EN 10025-2

^a The classification of materials is for informational purposes only, as the strength values or limits of chemical composition specified in this document can be outside the limits of ISO/TR 15608. But these materials have not exactly the same behaviour during welding as his sub-group material. Welding conditions should be specifically adapted.

Table 1 (continued)

Designation		Group	Standard(s)
Name	Number		
S275J2G4C	1.0142	1.1	EN 10025-2
S275J2H	1.0138	1.1	EN 10210-1, EN 10219-1
S275J2W	1.8961	1.4	EN 10025-5
S275JR	1.0044	1.1	EN 10025-2
S275M	1.8818	1.1	EN 10025-4
S275MH	1.8843	1.1	EN 10219-1
S275ML	1.8819	1.1	EN 10025-4
S275MLH	1.8844	1.1	EN 10219-1
S275N	1.0490	1.1	EN 10025-3
S275NH	1.0493	1.1	EN 10210-1, EN 10219-1
S275NL	1.0491	1.1	EN 10025-3
S275NLH	1.0497	1.1	EN 10210-1, EN 10219-1
S315MC	1.0972	1.2	EN 10149-2
S315NC	1.0973	1.2	EN 10149-3
S320GP	1.0046	1.2	EN 10248-1
S355 G4+M	1.8803+M	1.2	EN 10225
S355G1	1.8814	1.2	EN 10225
S355G1+N	1.8814+N	1.2	EN 10225
S355G10+M	1.8813+M	1.2	EN 10225
S355G10+N	1.8813+N	1.2	EN 10225
S355G11	1.8806	1.2	EN 10225
S355G11+M	1.8806+M	1.2	EN 10225
S355G11+N	1.8806+N	1.2	EN 10225
S355G12	1.8809	1.2	EN 10225
S355G12+M	1.8809+M	1.2	EN 10225
S355G12+N	1.8809+N	1.2	EN 10225
S355G13+N	1.1182+N	1.2	EN 10225
S355G13+Q	1.1182+Q	1.2	EN 10225
S355G14+N	1.1184+N	1.2	EN 10225
S355G14+Q	1.1184+Q	1.2	EN 10225
S355G15+N	1.1190+N	1.2	EN 10225
S355G15+Q	1.1190+Q	1.2	EN 10225
S355G15+Q	1.8852+Q	1.2	EN 10225
S355G1N	1.8814+N	1.2	EN 10225
S355G2+N	1.8801+N	1.2	EN 10225
S355G3+N	1.8802+N	1.2	EN 10225
S355G4	1.8803	1.2	EN 10225
S355G4+M	1.8803+M	1.2	EN 10225
S355G5+M	1.8804+M	1.2	EN 10225
S355G6+M	1.8805+M	1.2	EN 10225

^a The classification of materials is for informational purposes only, as the strength values or limits of chemical composition specified in this document can be outside the limits of ISO/TR 15608. But these materials have not exactly the same behaviour during welding as his sub-group material. Welding conditions should be specifically adapted.

Table 1 (continued)

Designation		Group	Standard(s)
Name	Number		
S355G7+M	1.8808+M	1.2	EN 10225
S355G7+N	1.8808+N	1.2	EN 10225
S355G8+M	1.8810+M	1.2	EN 10225
S355G8+N	1.8810+N	1.2	EN 10225
S355G9+M	1.8811+M	1.2	EN 10225
S355G9+N	1.8811+N	1.2	EN 10225
S355GP	1.0083	1.2	EN 10248-1
S355J0	1.0553	1.2	EN 10025-2
S355J0C	1.0554	1.2	EN 10025-2
S355J0H	1.0547	1.2	EN 10210-1, EN 10219-1
S355J0W	1.8959	1.4	EN 10025-5
S355J0WP	1.8945	1.4	EN 10025-5
S355J2	1.0577	1.2	EN 10025-2
S355J2C	1.0579	1.2	EN 10025-2
S355J2G3	1.0570	1.2	EN 10250-2
S355J2G3C	1.0569	1.2	-
S355J2H	1.0576	1.2	EN 10210-1, EN 10219-1
S355J2W	1.8965	1.4	EN 10025-5
S355J2WP	1.8946	1.4	EN 10025-5
S355JR	1.0045	1.2	EN 10025-2
S355JRC	1.0551	1.2	EN 10025-2
S355K2	1.0596	1.2	EN 10025-2
S355K2C	1.0594	1.2	EN 10025-2
S355K2G3C	1.0593	1.2	EN 10025-2
S355K2G4C	1.0594	1.2	EN 10025-2
S355K2W	1.8967	1.4	EN 10025-5
S355M	1.8823	1.2	EN 10025-4
S355MC	1.0976	1.2	EN 10149-2
S355MH	1.8845	1.2	EN 10219-1
S355ML	1.8834	1.2	EN 10025-4
S355MLH	1.8846	1.2	EN 10219-1
S355N	1.0545	1.2	EN 10025-3
S355NC	1.0977	1.2	EN 10149-3
S355NH	1.0539	1.2	EN 10210-1, EN 10219-1
S355NL	1.0546	1.2	EN 10025-3
S355NLH	1.549	1.2	EN 10210-1, EN 10219-1
S390GP	1.0522	1.3	EN 10248-1
S420G1+M	1.8830+M	2.1	EN 10225
S420G1+M	1.8830	2.1	EN 10225
S420G1+Q	1.8830+Q	3.1	EN 10225

^a The classification of materials is for informational purposes only, as the strength values or limits of chemical composition specified in this document can be outside the limits of ISO/TR 15608. But these materials have not exactly the same behaviour during welding as his sub-group material. Welding conditions should be specifically adapted.

Table 1 (continued)

Designation		Group	Standard(s)
Name	Number		
S420G1+Q	1.8830	3.1	EN 10225
S420G2+M	1.8857+M	2.1	EN 10225
S420G2+M	1.8857	2.1	EN 10225
S420G2+Q	1.8857+Q	3.1	EN 10225
S420G2+Q	1.8857	3.1	EN 10225
S420G3	1.8851	1.3	EN 10225
S420G3+M	1.8851+M	2.1	EN 10225
S420G4	1.8859	1.3	EN 10225
S420G4+M	1.8859+M	2.1	EN 10225
S420G5+Q	1.8853+Q	3.1	EN 10225
S420G6+Q	1.8852+Q	3.1	EN 10225
S420M	1.8825	2.1	EN 10025-4
S420MC	1.0980	2.1	EN 10149-2
S420MH	1.8847	2.1	EN 10219-1
S420ML	1.8836	2.1	EN 10025-4
S420MLH	1.8848	2.1	EN 10219-1
S420N	1.8902	1.3	EN 10025-3
S420NC	1.0981	1.3	EN 10149-3
S420NL	1.8912	1.3	EN 10025-3
S430GP	1.0523	1.3	EN 10248-1
S450J00	1.0590	1.3	EN 10025-2
S460G1+M	1.8878+M	2.1	EN 10225
S460G1+Q	1.8878+Q	3.1	EN 10225
S460G2+M	1.8887+M	2.1	EN 10225
S460G2+Q	1.8887+Q	3.1	EN 10225
S460G3	1.8883	1.3	EN 10225
S460G3+M	1.8883+M	2.1	EN 10225
S460G4	1.8889	1.3	EN 10225
S460G4+M	1.8889+M	2.1	EN 10225
S460G5+Q	1.8885+Q	3.1	EN 10225
S460G6+Q	1.8884+Q	3.1	EN 10225
S460M	1.8827	2.1	EN 10025-4
S460MC	1.0982	2.1	EN 10149-2
S460MH	1.8849	2.1	EN 10219-1
S460ML	1.8838	2.1	EN 10025-4
S460MLH	1.8850	2.1	EN 10219-1
S460N	1.8901	1.3	EN 10025-3
S460NH	1.8953	1.3	EN 10210-1, EN 10219-1
S460NL	1.8903	1.3	EN 10025-3
S460NLH	1.8956	1.3	EN 10210-1, EN 10219-1

^a The classification of materials is for informational purposes only, as the strength values or limits of chemical composition specified in this document can be outside the limits of ISO/TR 15608. But these materials have not exactly the same behaviour during welding as his sub-group material. Welding conditions should be specifically adapted.

Table 1 (continued)

Designation		Group	Standard(s)
Name	Number		
S460Q	1.8908	3.1	EN 10025-6
S460QL	1.8906	3.1	EN 10025-6
S460QL1	1.8916	3.1	EN 10025-6
S500A	1.8980	3.3	EN 10137-3
S500AL	1.8990	3.3	EN 10137-3
S500Q	1.8924	3.1	EN 10025-6
S500QL	1.8909	3.1	EN 10025-6
S500QL1	1.8984	3.1	EN 10025-6
S550A	1.8991	3.3	EN 10137-3
S550AL	1.8992	3.3	EN 10137-3
S550MC	1.0986	2.2	EN 10149-2
S550Q	1.8904	3.1	EN 10025-6
S550QL	1.8926	3.1	EN 10025-6
S550QL1	1.8986	3.1	EN 10025-6
S600MC	1.8969	2.2	EN 10149-2
S620A	1.8993	3.3	EN 10137-3
S620AL	1.8994	3.3	EN 10137-3
S620Q	1.8914	3.1	EN 10025-6
S620QL	1.8927	3.1	EN 10025-6
S620QL1	1.8987	3.1	EN 10025-6
S650MC	1.8976	2.2	EN 10149-2
S690A	1.8995	3.3	EN 10137-3
S690AL	1.8996	3.3	EN 10137-3
S690Q	1.8931	3.1	EN 10025-6
S690QL	1.8928	3.1	EN 10025-6
S690QL1	1.8988	3.1	EN 10025-6
S700MC	1.8974	2.2	EN 10149-2
S890Q	1.8940	3.2	EN 10025-6
S890QL	1.8983	3.2	EN 10025-6
S890QL1	1.8925	3.2	EN 10025-6
S960Q	1.8941	3.2	EN 10025-6
S960QL	1.8933	3.2	EN 10025-6
X105CrMo17	1.4125	7.2	EN 10088-1
X10CrAlSi7	1.4713	7.1	EN 10088-1
X10CrAlSi13	1.4724	7.1	EN 10088-1
X10CrAlSi18	1.4742	7.1	EN 10088-1
X10CrAlSi25	1.4762	7.1	EN 10088-1
X10CrMoVNb9-1	1.4903	6.4	EN 10216-2, EN 10222-2
X10CrNi18-8	1.4310	8.1	EN 10088-1
X10CrNiMoMnNbVB15-10-1	1.4982	8.1	EN 10216-5

^a The classification of materials is for informational purposes only, as the strength values or limits of chemical composition specified in this document can be outside the limits of ISO/TR 15608. But these materials have not exactly the same behaviour during welding as his sub-group material. Welding conditions should be specifically adapted.

Table 1 (continued)

Designation		Group	Standard(s)
Name	Number		
X10Ni9	1.5682	9.3	EN 10216-4
X11CrMo5+L	1.7362+L	5.3	EN 10216-2
X11CrMo5+NT1	1.7362+NT1	5.3	EN 10216-2
X11CrMo5+NT2	1.7362+NT2	5.3	EN 10216-2
X11CrMo9-1+L	1.7386+L	5.4	EN 10216-2
X11CrMo9-1+NT	1.7386+NT	5.4	EN 10216-2
X11CrNiMnN19-8-6	1.4369	8.3	EN 10088-1
X12Cr13	1.4006	7.2	EN 10088-1, EN 10272
X12CrCoNi21-20	1.4971	8.2	EN 10088-1
X12CrMnNiN17-7-5	1.4372	8.3	EN 10088-1
X12CrMnNiN18-9-5	1.4373	8.3	EN 10088-1
X12CrNi23-13	1.4833	8.2	EN 10088-1
X12CrNiMoV12-3	1.4938	7.2	EN 10088-1
X12CrNiWTiB16-13	1.4962	8.1	EN 10088-1
X12CrS13	1.4005	7.2	EN 10088-1
X12Ni5	1.5680	9.2	EN 10028-4, EN 10216-4, EN 10222-3
X14CrMoS17	1.4104	7.2	EN 10088-1
X15Cr13	1.4024	7.2	EN 10088-1
X15CrNiSi20-12	1.4828	8.2	EN 10088-1
X15CrNiSi25-21	1.4841	8.2	EN 10088-1
X15CrNiSi25-4	1.4821	10.2	EN 10088-1
X16CrMo5-1	1.7366	5.3	EN 10222-2
X17CrNi16-2	1.4057	7.2	EN 10088-1
X18CrN28	1.4749	7.1	EN 10088-1
X19CrMoNbVN11-1	1.4913	6.4	EN 10088-1
X1CrNb15	1.4595	7.1	EN 10088-1
X1CrNi25-21	1.4335	8.2	EN 10088-1, EN 10216-5, EN 10028-7
X1CrNiMoAlTi12-10-2	1.4596	7.3	EN 10088-1
X1CrNiMoAlTi12-9-2	1.4530	7.3	EN 10088-1
X1CrNiMoCu12-5-2	1.4422	7.2	EN 10088-1
X1CrNiMoCu12-7-3	1.4423	7.2	EN 10088-1
X1CrNiMoCuN20-18-7	1.4547	8.2	EN 10272, EN 10216-5, EN 10028-7, EN 10296-2, EN 10217-7
X1CrNiMoCuN20-18-7a	1.4547a	8.2	EN 10088-1
X1CrNiMoCuN25-25-5	1.4537	8.2	EN 10088-1, EN 10028-7
X1CrNiMoCuNW24-22-6	1.4659	8.2	EN 10088-1
X1CrNiMoN25-22-2	1.4466	8.2	EN 10088-1, EN 10216-5, EN 10028-7
X1CrNiSi18-15-4	1.4361	8.1	EN 10088-1

^a The classification of materials is for informational purposes only, as the strength values or limits of chemical composition specified in this document can be outside the limits of ISO/TR 15608. But these materials have not exactly the same behaviour during welding as his sub-group material. Welding conditions should be specifically adapted.

Table 1 (continued)

Designation		Group	Standard(s)
Name	Number		
X1NiCrMoCu25-20-5	1.4539	8.2	EN 10216-5, EN 10028-7, EN 10217-7, EN 10272, EN 10088-1, EN 10296-2
X1NiCrMoCu31-27-4	1.4563	8.2	EN 10216-5, EN 10028-7, EN 10217-7, EN 10272, EN 10088-1
X1NiCrMoCuN25-20-7	1.4529	8.2	EN 10216-5, EN 10028-7, EN 10217-7, EN 10272, EN 10088-1
X20Cr13	1.4021	7.2	EN 10088-1
X20CrMoV11-1	1.4922	6.4	EN 10088-1, EN 10216-2, EN 10222-2
X20CrMoWV12-1	1.4935	7.2	EN 10088-1
X22CrMoV12-1	1.4923	6.4	EN 10088-1
X25CrMnNiN25-9-7	1.4872	8.2	EN 10088-1
X29CrS13	1.4029	7.2	EN 10088-1
X2CrMnNiN17-7-5	1.4371	8.3	EN 10088-1
X2CrMoTi17-1	1.4513	7.1	EN 10088-1
X2CrMoTi18-2	1.4521	7.1	EN 10088-1, EN 10296-2
X2CrMoTi29-4	1.4592	7.1	EN 10088-1
X2CrMoTiS18-2	1.4523	7.1	EN 10088-1
X2CrNbZr17	1.4590	7.1	EN 10088-1
X2CrNi12	1.4003	7.1	EN 10088-1, EN 10296-2
X2CrNi18-9	1.4307	8.1	EN 10028-7, EN 10088-1, EN 10216-5, EN 10217-7, EN 10222-2, EN 10222-5, EN 10272, EN 10296-2
X2CrNi19-11	1.4306	8.1	EN 10216-5, EN 10217-7, EN 10028-7, EN 10088-1, EN 10272, EN 10296-2
X2CrNiCu19-10	1.4650	8.1	EN 10088-1, EN 10222-5
X2CrNiCuN23-4	1.4655	10.1	EN 10088-1
X2CrNiMnMoN25-18-6-5	1.4565	8.3	EN 10088-1
X2CrNiMo17-12-2	1.4404	8.1	EN 10216-5, EN 10217-7, EN 10028-7, EN 10088-1, EN 10222-5, EN 10272, EN 10296-2
X2CrNiMo17-12-3	1.4432	8.1	EN 10217-7, EN 10028-7, EN 10088-1, EN 10222-5, EN 10272, EN 10296-2
X2CrNiMo18-12-3	1.4449	8.1	EN 10088-1
X2CrNiMo18-14-3	1.4435	8.1	EN 10216-5, EN 10217-7, EN 10028-7, EN 10088-1, EN 10222-5, EN 10272, EN 10296-2
X2CrNiMo18-15-4	1.4438	8.1	EN 10217-7, EN 10028-7, EN 10088-1

^a The classification of materials is for informational purposes only, as the strength values or limits of chemical composition specified in this document can be outside the limits of ISO/TR 15608. But these materials have not exactly the same behaviour during welding as his sub-group material. Welding conditions should be specifically adapted.

Table 1 (continued)

Designation		Group	Standard(s)
Name	Number		
X2CrNiMoCuN25-6-3	1.4507	10.2	EN 10088-1, EN 10028-7, EN 10216-5, EN 10272
X2CrNiMoCuS17-10-2	1.4598	8.1	EN 10088-1
X2CrNiMoCuWN25-7-4	1.4501	10.2	EN 10088-1, EN 10028-7, EN 10216-5, EN 10272, EN 10217-7,
X2CrNiMoN17-11-2	1.4406	8.1	EN 10028-7, EN 10088-1, EN 10222-5, EN 10272
X2CrNiMoN17-13-3	1.4429	8.1	EN 10216-5, EN 10217-7, EN 10028-7, EN 10088-1, EN 10222-5, EN 10272, EN 10296-2
X2CrNiMoN17-13-5	1.4439	8.1	EN 10216-5, EN 10217-7, EN 10028-7, EN 10088-1, EN 10272, EN 10296-2
X2CrNiMoN18-12-4	1.4434	8.1	EN 10028-7, EN 10088-1
X2CrNiMoN22-5-3	1.4462	10.1	EN 10028-7, EN 10217-7, EN 10222-5, EN 10088-1, EN 102962, EN 10216-5, EN 10272
X2CrNiMoN25-7-4	1.4410	10.2	EN 10222-5, EN 10028-7, EN 10216-5, EN 10272, EN 10217-7, EN 10296-2
X2CrNiMoN25-7-4	1.4410	10.2	EN 10088-1
X2CrNiMoN29-7-2	1.4477	10.2	EN 10088-1
X2CrNiMoSi18-5-3	1.4424	10.1	EN 10216-5, EN 10088-1
X2CrNiMoV13-5-2	1.4415	7.2	EN 10088-1
X2CrNiN18-10	1.4311	8.1	EN 10216-5, EN 10217-7, EN 10222-5, EN 10028-7, EN 10088-1, EN 10296-2, EN 10272
X2CrNiN18-7	1.4318	8.1	EN 10028-7, EN 10088-1, EN 10296-2
X2CrNiN23-4	1.4362	10.3	EN 10028-7, EN 10216-5, EN 10217-7, EN 10272, EN 10296-2
X2CrTi12	1.4512	7.1	EN 10088-1, EN 10296-2
X2CrTi17	1.4520	7.1	EN 10088-1
X2CrTiNb18	1.4509	7.1	EN 10088-1, EN 10296-2
X2NiCrAlTi32-20	1.4558	8.2	EN 10216-5
X30Cr13	1.4028	7.2	EN 10088-1
X38CrMo14	1.4419	7.2 ^a	EN 10088-1
X39Cr13	1.4031	7.2 ^a	EN 10088-1
X39CrMo17-1	1.4122	7.2 ^a	EN 10088-1
X3CrAlTi18-2	1.4736	7.1	EN 10088-1
X3CrNb17	1.4511	7.1	EN 10088-1

^a The classification of materials is for informational purposes only, as the strength values or limits of chemical composition specified in this document can be outside the limits of ISO/TR 15608. But these materials have not exactly the same behaviour during welding as his sub-group material. Welding conditions should be specifically adapted.

Table 1 (continued)

Designation		Group	Standard(s)
Name	Number		
X3CrNiCu18-9-4	1.4567	8.1	EN 10088-1
X3CrNiCu19-9-2	1.4560	8.1	EN 10088-1
X3CrNiCuMo17-11-3-2	1.4578	8.1	EN 10088-1
X3CrNiMo13-4	1.4313	7.2	EN 10028-7, EN 10088-1, EN 10222-5
X3CrNiMo17-13-3	1.4436	8.1	EN 10088-1, EN 10222-5, EN 10272, EN 10216-5, EN 10217-7, EN 10296-2
X3CrNiMo18-12-3	1.4449	8.1	EN 10222-5
X3CrNiMoBN17-13-3	1.4910	8.1	EN 10088-1, EN 10216-5, EN 10028-7
X3CrNiMoN17-13-3	1.4910	8.1	EN 10028-7, EN 10222-5
X3CrNiMoN27-5-2	1.4460	10.2	EN 10088-1
X3CrNiN18-11	1.4949	8.1	EN 10216-5, EN 10028-7
X3CrTi17	1.4510	7.1	EN 10088-1, EN 10296-2
X40CrMoVN16-2	1.4123	7.2 ^a	EN 10088-1
X46Cr13	1.4034	7.2 ^a	EN 10088-1
X46CrS13	1.4035	7.2 ^a	EN 10088-1
X4CrNi18-12	1.4303	8.1	EN 10088-1
X4CrNiMo16-5-1	1.4418	7.2	EN 10088-1
X50CrMoV15	1.4116	7.2 ^a	EN 10088-1
X55CrMo14	1.4110	7.2 ^a	EN 10088-1
X5CrNi17-7	1.4319	8.1	EN 10088-1
X5CrNi18-10	1.4301	8.1	EN 10216-5, EN 10217-7, EN 10222-2, EN 10028-7, EN 10088-1, EN 10222-5, EN 10272, EN 10296-2
X5CrNiCuNb16-4	1.4542	7.3	EN 10088-1
X5CrNiMo17-12-2	1.4401	8.1	EN 10216-5, EN 10217-7, EN 10222-5, EN 10028-7, EN 10088-1, EN 10296-2, EN 10272
X5CrNiMoCuNb14-5	1.4594	7.3	EN 10088-1
X5CrNiMoTi15-2	1.4589	7.1	EN 10088-1
X5CrNiN19-9	1.4315	8.1	EN 10028-7, EN 10088-1
X5NiCrAlTi31-20	1.4958	8.2	EN 10216-5, EN 10028-7, EN 10088-1
X5NiCrAlTi31-20+RA	1.4958+RA	8.2	EN 10028-7
X5NiCrTiMoVB25-15-2	1.4606	7.3	EN 10088-1
X6Cr13	1.4000	7.1	EN 10088-1
X6Cr17	1.4016	7.1	EN 10088-1, EN 10296-2
X6CrAl13	1.4002	7.1	EN 10088-1
X6CrMo17-1	1.4113	7.1	EN 10088-1

^a The classification of materials is for informational purposes only, as the strength values or limits of chemical composition specified in this document can be outside the limits of ISO/TR 15608. But these materials have not exactly the same behaviour during welding as his sub-group material. Welding conditions should be specifically adapted.

Table 1 (continued)

Designation		Group	Standard(s)
Name	Number		
X6CrMoNb17-1	1.4526	7.1	EN 10088-1, EN 10296-2
X6CrMoS17	1.4105	7.1	EN 10088-1
X6CrNi17-1	1.4017	7.1	EN 10088-1
X6CrNi18-10	1.4948	8.1	EN 10088-1, EN 10216-5, EN 10028-7, EN 10222-5
X6CrNi23-13	1.4950	8.2	EN 10088-1, EN 10028-7
X6CrNi25-20	1.4951	8.2	EN 10088-1, EN 10028-7
X6CrNiCuS18-9-2	1.4570	8.1	EN 10088-1
X6CrNiMo17-13-2	1.4918	8.1	EN 10088-1
X6CrNiMoB17-12-2	1.4919	8.1	EN 10088-1
X6CrNiMoNb17-12-2	1.4580	8.1	EN 10216-5, EN 10028-7, EN 10088-1, EN 10272
X6CrNiMoTi17-12-2	1.4571	8.1	EN 10216-5, EN 10217-7, EN 10222-5, EN 10028-7, EN 10088-1, EN 10296-2, EN 10272
X6CrNiMoTiB17-13	1.4983	8.1	EN 10088-1
X6CrNiNb18-10	1.4550	8.1	EN 10216-5, EN 10217-7, EN 10222-5, EN 10028-7, EN 10088-1, EN 10296-2, EN 10272
X6CrNiSiNc19-10	1.4818	8.1	EN 10088-1
X6CrNiTi12	1.4516	7.1	EN 10088-1
X6CrNiTi18-10	1.4541	8.1	EN 10216-5, EN 10217-7, EN 10222-5, EN 10028-7, EN 10088-1, EN 10296-2, EN 10272
X6CrNiTiB18-10	1.4941	8.1	EN 10088-1, EN 10222-5, EN 10028-7
X6CrNiWbNb16-16	1.4945	8.1	EN 10088-1
X6NiCrTiMoVB25-15-2	1.4980	8.1	EN 10088-1
X70CrMo15	1.4109	7.2 ^a	EN 10088-1
X7CrNiAl17-7	1.4568	7.3	EN 10088-1
X7CrNiMoBNb16-16	1.4986	8.1	EN 10088-1
X7CrNiNb18-10	1.4912	8.1	EN 10088-1, EN 10216-5, EN 10222-5
X7CrNiTi18-10	1.4940	8.1	EN 10088-1, EN 10216-5, EN 10222-5
X7Ni9	1.5663	9.3	EN 10028-4
X8CrMnCuNb17-8-3	1.4597	8.3	EN 10088-1
X8CrMnNi18-9-5	1.4374	8.3	EN 10088-1
X8CrNi25-21	1.4845	8.2	EN 10088-1
X8CrNiMoNb16-16	1.4981	8.1	EN 10088-1, EN 10216-5
X8CrNiMoVNb16-13	1.4988	8.1	EN 10088-1, EN 10216-5

^a The classification of materials is for informational purposes only, as the strength values or limits of chemical composition specified in this document can be outside the limits of ISO/TR 15608. But these materials have not exactly the same behaviour during welding as his sub-group material. Welding conditions should be specifically adapted.

Table 1 (continued)

Designation		Group	Standard(s)
Name	Number		
X8CrNiNb16-13	1.4961	8.1	EN 10088-1, EN 10216-5, EN 10028-7
X8CrNiS18-9	1.4305	8.1	EN 10088-1
X8CrTi18-10	1.4878	8.1	EN 10088-1
X8Ni9	1.5662	9.3	EN 10028-4, EN 10222-3
X8NiCrAlTi32-21	1.4959	8.2	EN 10216-5, EN 10028-7, EN 10088-1
X90CrMoV18	1.4112	7.2 ^a	EN 10088-1
X9CrNi18-9	1.4325	8.1	EN 10088-1
X9CrNiSiNc21-11-2	1.4835	8.2	EN 10088-1
X1CrNiMoCuN24-22-8	1.4652	8.2	EN 10088-1, EN 10088-2, EN 10088-3
X10CrWMoVNb9-2	1.4901	6.4	EN 10216-2
7CrMoVTiB10-10	1.7378	6.2	EN 10216-2
7CrWVMoNb9-6	1.8201	6.2	EN 10216-2
X11CrMoWVNb9-1-1	1.4905	6.4	EN 10216-2, EN 10088-1, EN 10302
X10CrNiCuNb18-9-3	1.4907	8.1	EN 10216-5
DC01	1.0330	1.1	EN 10130, EN 10139, EN 10152, EN 10271
DC04	1.0338	1.1	EN 10130, EN 10139, EN 10152, EN 10271
DC05	1.0312	1.1	EN 10130, EN 10139, EN 10152, EN 10271
DC06	1.0873	1.1	EN 10130, EN 10139, EN 10152, EN 10271
DC07	1.0898	1.1	EN 10130
DD11	1.0332	1.1	EN 10111
DD12	1.0398	1.1	EN 10111
DD13	1.0335	1.1	EN 10111
DD14	1.0389	1.1	EN 10111
E255	1.0408	1.1	EN 10305-1
G10MnMoV6-3	1.5410	1.2	EN 10293, EN 10340
G15CrMoV6-9	1.7710	6.2	EN 10293
G18NiMoCr3-6	1.6759	5.1	EN 10340
G20NiMoCr8-5-4	1.6570	9.1	EN 10293
G24Mn6	1.1118	1.1	EN 10293, EN 10340
G26CrMo4	1.7221	5.1	EN 10293
G28Mn6	1.1165	11.1	EN 10293
G30CrMoV6-4	1.7725	6.1	EN 10293
G34CrMo4	1.7230	5.1 ^a	EN 10293
G35CrNiMo6-6	1.6579	9.1 ^a	EN 10293

^a The classification of materials is for informational purposes only, as the strength values or limits of chemical composition specified in this document can be outside the limits of ISO/TR 15608. But these materials have not exactly the same behaviour during welding as his sub-group material. Welding conditions should be specifically adapted.

Table 1 (continued)

Designation		Group	Standard(s)
Name	Number		
GE200	1.0420	1.1	EN 10293
GE240	1.0446	1.1	EN 10293
GE300	1.0558	1.2	EN 10293
GS200	1.0449	1.1	EN 10293, EN 10340
GS240	1.0455	1.1	EN 10293, EN 10340
E410	1.0509	1.3	EN 10305-1
S355K2H	1.0512	1.2	EN 10210-1
S420NH	1.8750	1.3	EN 10210-1
S420NLH	1.8751	1.3	EN 10210-1
S500MC	1.0984	2.2	EN 10149-2
R260Cr	1.0911	11.3	EN 13674-2
12CrMoV12-10	1.7767	6.2	EN 10028-2
13CrMoSi5-5	1.7336	5.1	EN 10028-2
13CrMoV9-10	1.7703	6.2	EN 10028-2
17NiCrMoS6-4	1.6569	9.1	EN ISO 683-3
18MnMo4-5	1.5414	1.2	EN 10028-2
19MnB4	1.5523	3.1	EN 10269
19MnVS6	1.1301	3.1	EN 10267
20MnMoNi4-5	1.6311	4.1	EN 10028-2, EN 10250-3
20CrMoVTiB4-10	1.7729	6.2	EN 10269
26Mn5	1.1161	11.1	EN 10305-1
28Cr4	1.7030	5.1	EN ISO 683-3
28CrS4	1.7036	5.1	EN ISO 683-3
28Mn6	1.1170	11.1	EN 10250-2
28NiCrMoV8-5	1.6932	9.1	EN 10250-3
30CrMoV9	1.7707	5.2 ^a	EN 10250-3
30CrNiMo8	1.6580	9.2 ^a	EN ISO 683-2, EN ISO 683-3, EN 10250-3, EN 10269
32CrMo12	1.7361	5.2 ^a	EN 10250-3
33NiCrMoV14-5	1.6956	9.2 ^a	EN 10250-3
34CrMoS4	1.7226	5.1 ^a	EN ISO 683-2, EN ISO 683-3
38MnB5	1.5532	11.2 ^a	EN ISO 683-2, EN ISO 683-3
GX2NiCrMoN25-20-5	1.4416	8.2	EN 10283
GX2CrNiMoN17-13-4	1.4446	8.1	EN 10283
GX2CrNiMoN25-6-3	1.4468	10.2	EN 10340
GX2CrNiMoN25-7-3	1.4417	10.2	EN 10283
GX2CrNiMoCuN20-18-6	1.4557	8.2	EN 10283
GX4NiCrCuMo30-20-4	1.4527	8.2	EN 10283
GX4CrNiMo16-5-2	1.4411	7.2	EN 10283
GX5CrNiMo19-11-3	1.4412	8.1	EN 10283
GX6CrNiN26-7	1.4347	10.2	EN 10283

^a The classification of materials is for informational purposes only, as the strength values or limits of chemical composition specified in this document can be outside the limits of ISO/TR 15608. But these materials have not exactly the same behaviour during welding as his sub-group material. Welding conditions should be specifically adapted.

Table 1 (continued)

Designation		Group	Standard(s)
Name	Number		
GX7CrNiMo12-1	1.4008	7.2	EN 10283
GX9Ni15	1.5681	9.2	EN 10293
GX10NiCrSiNb32-20	1.4859	8.2	EN 10295
GX12Cr12	1.4011	7.2	EN 10283
GX25CrNiSi18-9	1.4825	8.1	EN 10295
GX25CrNiSi20-14	1.4837	8.2	EN 10295
GX35NiCrSi25-21	1.4805	8.2	EN 10295
GX40NiCrNb45-35	1.4889	8.2 ^a	EN 10295
GX40CrNiSi22-10	1.4826	8.2 ^a	EN 10295
GX40CrNiSi25-20	1.4848	8.2 ^a	EN 10295
GX40CrNiSiNb24-24	1.4855	8.2 ^a	EN 10295
GX40NiCrSi35-17	1.4806	8.1 ^a	EN 10295
GX40NiCrSi35-26	1.4857	8.2 ^a	EN 10295
GX40NiCrSi38-19	1.4865	8.2 ^a	EN 10295
GX40NiCrSiNb35-18	1.4807	8.1 ^a	EN 10295
GX40NiCrSiNb35-26	1.4852	8.2 ^a	EN 10295
GX40NiCrSiNb38-19	1.4849	8.2 ^a	EN 10295
GX50NiCrCo20-20-20	1.4874	8.2	EN 10295
GX50NiCrCoW35-25-15-5	1.4869	8.2	EN 10295
X2CrMnNiN21-5-1	1.4162	10.1	EN 10088-4, EN 10088-5
X6NiCrNbCe32-27	1.4877	8.2	EN 10088-1, EN 10095
X6NiCrSiN25-25	1.4854	8.2	EN 10088-1, EN 10095, EN 10296-2, EN 10297-2
X10CrNiCuNb18-9-3	1.4907	8.1	EN 10216-5
X10CrMoVNb9-1	1.4903	6.4	EN 10028-2, EN 10088-1
X10NiCrSi35-19	1.4886	8.2	EN 10088-1, EN 10095
X10NiCrSiNb35-22	1.4887	8.2	EN 10088-1, EN 10095
X10NiCrAlTi32-21	1.4876	8.2	EN 10088-1, EN 10095, EN 10297-2
X12NiCrSi35-16	1.4864	8.2	EN 10088-1, EN 10095,
X20CrMoWV12-1	1.4935	6.4	EN 10088-1, EN 10302
X22CrMoV12-1	1.4923	6.4	EN 10088-1, EN 10269, EN 10302
X33CrNiMnN23-8	1.4866	8.2	EN 10090
X50CrMnNiNbN21-9	1.4882	8.2	EN 10090
X53CrMnNiNbN21-9	1.4870	8.2	EN 10090
X53CrMnNiN21-9	1.4871	8.2	EN 10090
X55CrMnNiN20-8	1.4875	8.2	EN 10090

^a The classification of materials is for informational purposes only, as the strength values or limits of chemical composition specified in this document can be outside the limits of ISO/TR 15608. But these materials have not exactly the same behaviour during welding as his sub-group material. Welding conditions should be specifically adapted.

4.2 Types of aluminium and aluminium alloy in accordance with the grouping system of ISO/TR 15608:2017, Table 2

See Table 2.

Table 2 — Aluminium and aluminium alloys

Designation		Group	Standard(s)
Name	Number		
EN AC-Al Cu4MgTi	EN AC-21000	26	EN 573
EN AC-Al Cu4Ti	EN AC-21100	26	EN 573, EN 1706
EN AC-Al Mg	EN AC-51100	22.3	EN 573
EN AC-Al Mg3	EN AC-51100	22.3	EN 1706
EN AC-Al Mg5	EN AC-51300	22.4	EN 573, EN 1706
EN AC-Al Mg5(Si)	EN AC-51400	22.4	EN 573, EN 1706
EN AC-Al Mg9	EN AC-51200	22.4	EN 573, EN 1706
EN AC-Al Si10Mg	EN AC-43000	24.2	EN 573, EN 1706
	EN AC-43100		
EN AC-Al Si10Mg(Cu)	EN AC-43200	24.2	EN 573, EN 1706
EN AC-Al Si10Mg(Fe)	EN AC-43400	24.2	EN 573, EN 1706
EN AC-Al Si11	EN AC-44000	24.1	EN 573, EN 1706
EN AC-Al Si11Cu2(Fe)	EN AC-46100	25	EN 573, EN 1706
EN AC-Al Si12	EN AC-44100	24.1	EN 573, EN 1706
EN AC-Al Si12(Cu)	EN AC-47000	24.1	EN 573, EN 1706
EN AC-Al Si12(Fe)	EN AC-44300	24.1	EN 573, EN 1706
EN AC-Al Si12Cu1(Fe)	EN AC-47100	25	EN 573, EN 1706
EN AC-Al Si12CuNiMg	EN AC-48000	25	EN 573
EN AC-Al Si2Mg	EN AC-41000	23.1	EN 1706
EN AC-Al Si5Cu1Mg	EN AC-45300	25	EN 573, EN 1706
EN AC-Al Si5Cu3	EN AC-45400	25	EN 573, EN 1706
EN AC-Al Si5Cu3Mg	EN AC-45100	25	EN 573, EN 1706
EN AC-Al Si5Cu3Mn	EN AC-45200	25	EN 573, EN 1706
EN AC-Al Si6Cu4	EN AC-45000	25	EN 573, EN 1706
EN AC-Al Si7Cu2	EN AC-46600	25	EN 573, EN 1706
EN AC-Al Si7Cu3Mg	EN AC-46300	25	EN 573, EN 1706
EN AC-Al Si7Mg	EN AC-42000	23.1	EN 1706
EN AC-Al Si7Mg	EN AC-42000	24.2	EN 573, EN 1706
EN AC-Al Si7Mg0,3	EN AC-42100	24.2	EN 573, EN 1706
EN AC-Al Si7Mg0,6	EN AC-42200	24.2	EN 573, EN 1706
EN AC-Al Si8Cu3	EN AC-46200	25	EN 573, EN 1706
EN AC-Al Si9	EN AC-44400	24.1	EN 573, EN 1706
EN AC-Al Si9Cu1Mg	EN AC-46400	25	EN 573, EN 1706
EN AC-Al Si9Cu3(Fe)	EN AC-46000	25	EN 573, EN 1706
EN AC-Al Si9Cu3(Fe)(Zn)	EN AC-46500	25	EN 573, EN 1706
EN AC-Al Si9Mg	EN AC-43300	23.1	EN 1706
EN AC-Al Si9Mg	EN AC-43300	24.2	EN 573, EN 1706
EN AC-Al Zn5Mg	EN AC-71000	23	EN 1706
EN AW-Al 99,0	EN AW-1200	21	EN 573

Table 2 (continued)

Designation		Group	Standard(s)
Name	Number		
EN AW-Al 99,0Cu	EN AW-1100	21	EN 573
EN AW-Al 99,5	EN AW-1050A	21	EN 573
EN AW-Al 99,5Ti	EN AW-1450	21	EN 573
EN AW-Al 99,6	EN AW-1060	21	EN 573
EN AW-Al 99,7	EN AW-1070A	21	EN 573
EN AW-Al 99,8	EN AW-1080A	21	EN 573
EN AW-Al 99,85	EN AW-1085	21	EN 573
EN AW-Al 99,90	EN AW-1090	21	EN 573
EN AW-Al 99,98	EN AW-1098	21	EN 573
EN AW-Al 99,98A	EN AW-1198A	21	EN 573
EN AW-Al Ag1Si0,8Cu	EN AW-6013	23.1	EN 573
EN AW-Al Mg0,7Si	EN AW-6063	23.1	EN 573
EN AW-Al Mg1	EN AW-5005	22.2	EN 573
EN AW-Al Mg1,5(C)	EN AW-5050	22.2	EN 573
EN AW-Al Mg1SiCu	EN AW-6061	23.1	EN 573
EN AW-Al Mg2	EN AW-5251	22.3	EN 573
EN AW-Al Mg2,5	EN AW-5052	22.3	EN 573
EN AW-Al Mg2Mn0,8	EN AW-5149	22.3	EN 573
EN AW-Al Mg2Mn0,8Zr	EN AW-5249	22.3	EN 573
EN AW-Al Mg3	EN AW-5754	22.3	EN 573
EN AW-Al Mg3,5	EN AW-5154 A	22.3	EN 573
EN AW-Al Mg3,5Mn0,3	EN AW-5154 B	22.3	EN 573
EN AW-Al Mg3Mn	EN AW-5454	22.3	EN 573
EN AW-Al Mg4	EN AW-5086	22.4	EN 573
EN AW-Al Mg4,5Mn0,7	EN AW-5083	22.4	EN 573
EN AW-Al Mg4,5Mn0,9	EN AW-5383	22.4	EN 573
EN AW-Al Mg4Mn0,4	EN AW-5186	22.4	EN 573
EN AW-Al Mg5	EN AW-5056A	22.4	EN 573
EN AW-Al Mg5Mn1	EN AW-5456A	22.4	EN 573
EN AW-Al MgSi	EN AW-6060	23.1	EN 573
EN AW-Al MgSiMn	EN AW-6106	23.1	EN 573
EN AW-Al Mn0,5Mg0,5	EN AW-3105	22.1	EN 573
EN AW-Al Mn1	EN AW-3103	22.1	EN 573
EN AW-Al Mn1Cu	EN AW-3003	22.1	EN 573
EN AW-Al Mn1Mg0,5	EN AW-3005	22.1	EN 573
EN AW-Al Mn1Mg1	EN AW-3004	22.1	EN 573
EN AW-Al Si0,9MgMn	EN AW-6081	23.1	EN 573
EN AW-Al Si1MgMn	EN AW-6082	23.1	EN 573
EN AW-Al SiMg	EN AW-6005 A	23.1	EN 573
EN AW-Al Zn4,5Mg1	EN AW-7020	23.2	EN 573
EN AW-Al Zn6Mg0,8Zr	EN AW-7003	23.2	EN 573

4.3 Types of copper and copper alloy in accordance with the grouping system of ISO/TR 15608:2017, Table 3

See Table 3.

Table 3 — Copper and copper alloys

Designation		Group	Standard(s)
Name	Number		
CW004A	Cu-ETP	31	EN 1652
CW006A	Cu-FRTP	31	EN 1652
CW008A	Cu-OF	31	EN 1652
CW023A	Cu-DLP	31	EN 1652, EN 1653
CW024A	Cu-DHP	31	EN 1652, EN 1653
CW100C	CuBe1,7	37	EN 1654
CW101C	CuBe2	37	EN 1652, EN 1654
CW104C	CuCo2Be	37	EN 1652, EN 1654
CW107C	CuFe2P	37	EN 1654
CW110C	CuNi2Be	37	EN 1652, EN 1654
CW111C	CuNi2Si	37	EN 1652, EN 1654
CW119C	CuZn0,5	37	EN 1652
CW303G	CuAl8Fe3	35	EN 1652, EN 1653
CW304G	CuAl9Ni3Fe2	35	EN 1653
CW307G	CuAl10Ni5Fe4	35	EN 1653
CW350H	CuNi25	34	EN 1652
CW351H	CuNi9Sn2	34	EN 1652, EN 1654
CW352H	CuNi10Fe1Mn	34	EN 1652, EN 1653
CW354H	CuNi30Mn1Fe	34	EN 1652, EN 1653
CW401J	CuNi10Zn27	36	EN 1652
CW403J	CuNi12Zn24	36	EN 1652, EN 1654
CW404J	CuNi12Zn25Pb1	36	EN 1652
CW405J	CuNi12Zn29	36	EN 1654
CW409J	CuNi18Zn20	36	EN 1652, EN 1654
CW410J	CuNi18Zn27	36	EN 1652, EN 1654
CW450K	CuSn4	33	EN 1652, EN 1654
CW451K	CuSn5	33	EN 1652, EN 1654
CW452K	CuSn6	33	EN 1652, EN 1654
CW453K	CuSn8	33	EN 1652, EN 1654
CW454K	CuSn3Zn9	33	EN 1652, EN 1654
CW500L	CuZn5	32.1	EN 1652
CW501L	CuZn10	32.1	EN 1652
CW502L	CuZn15	32.1	EN 1652, EN 1654
CW503L	CuZn20	32.1	EN 1652
CW505L	CuZn30	32.1	EN 1652, EN 1654
CW506L	CuZn33	32.1	EN 1652
CW507L	CuZn36	32.1	EN 1652, EN 1654
CW508L	CuZn37	32.1	EN 1652
CW509L	CuZn40	32.1	EN 1652

Table 3 (continued)

Designation		Group	Standard(s)
Name	Number		
CW702R	CuZn20Al2As	32.2	EN 1652, EN 1653
CW703R	CuZn23Al2Co	32.2	EN 1653, EN 1654
CW715R	CuZn38AlFeNiPbSn	32.2	EN 1653
CW717R	CuZn38Sn1As	32.2	EN 1653
CW719R	CuZn39Sn1	32.2	EN 1653

4.4 Types of cast iron in accordance with the grouping system of ISO/TR 15608:2017, Table 7

See [Table 4](#).

Table 4 — Cast iron materials

Designation		Group	Standard(s)
Name	Number		
EN-JL1010	EN-GJL-100	71	EN 1561
EN-JL1020	EN-GJL-150	71	EN 1561
EN-JL1030	EN-GJL-200	71	EN 1561
EN-JL1040	EN-GJL-250	71	EN 1561
EN-JL1050	EN-GJL-300	71	EN 1561
EN-JL1060	EN-GJL-350	71	EN 1561
EN-JL2010	EN-GJL-HB155	71	EN 1561
EN-JL2020	EN-GJL-HB175	71	EN 1561
EN-JL2030	EN-GJL-HB195	71	EN 1561
EN-JL2040	EN-GJL-HB215	71	EN 1561
EN-JL2050	EN-GJL-HB235	71	EN 1561
EN-JL2060	EN-GJL-HB255	71	EN 1561
EN-JM1010	EN-GJMW-350-4	73.2	EN 1562
EN-JM1020	EN-GJMW-360-12	73.1	EN 1562
EN-JM1030	EN-GJMW-400-5	73.2	EN 1562
EN-JM1040	EN-GJMW-450-7	73.2	EN 1562
EN-JM1050	EN-GJMW-500-4	73.2	EN 1562
EN-JM1110	EN-GJMB-300-6	73.3	EN 1562
EN-JM1130	EN-GJMB-350-10	73.3	EN 1562
EN-JM1140	EN-GJMB-450-6	73.3	EN 1562
EN-JM1150	EN-GJMB-500-5	73.3	EN 1562
EN-JM1160	EN-GJMB-550-4	73.3	EN 1562
EN-JM1170	EN-GJMB-600-3	73.3	EN 1562
EN-JM1180	EN-GJMB-650-2	73.3	EN 1562
EN-JM1190	EN-GJMB-700-2	73.3	EN 1562
EN-JM1200	EN-GJMB-800-1	73.3	EN 1562
EN-JN2010	EN-GJN-HV350	76.1	EN 12513
EN-JN2020	EN-GJN-HV520	76.1	EN 12513
EN-JN2030	EN-GJN-HV550	76.1	EN 12513

Table 4 (continued)

Designation		Group	Standard(s)
Name	Number		
EN-JN2040	EN-GJN-HV600	76.1	EN 12513
EN-JN2050	EN-GJN-HV600 (XCr11)	76.1	EN 12513
EN-JN2060	EN-GJN-HV600 (XCr14)	76.1	EN 12513
EN-JN2070	EN-GJN-HV600 (XCr18)	76.1	EN 12513
EN-JN2080	EN-GJN-HV600 (XCr23)	76.1	EN 12513
EN-JS1010	EN-GJS-350-22	72.1	EN 1563
EN-JS1014	EN-GJS-350-22-RT	72.2	EN 1563
EN-JS1015	EN-GJS-350-22-LT	72.2	EN 1563
EN-JS1019	EN-GJS-350-22U-LT	72.2	EN 1563
EN-JS1020	EN-GJS-400-18	72.1	EN 1563
EN-JS1024	EN-GJS-400-18-RT	72.2	EN 1563
EN-JS1025	EN-GJS-400-18-LT	72.2	EN 1563
EN-JS1029	EN-GJS-350-22U-RT	72.2	EN 1563
EN-JS1030	EN-GJS-400-15	72.1	EN 1563
EN-JS1032	EN-GJS-350-22U	72.1	EN 1563
EN-JS1040	EN-GJS-450-10	72.1	EN 1563
EN-JS1049	EN-GJS-400-18U-LT	72.2	EN 1563
EN-JS1050	EN-GJS-500-7	72.1	EN 1563
EN-JS1059	EN-GJS-400-18U-RT	72.2	EN 1563
EN-JS1060	EN-GJS-600-3	72.1	EN 1563
EN-JS1062	EN-GJS-400-18U	72.1	EN 1563
EN-JS1070	EN-GJS-700-2	72.1	EN 1563
EN-JS1072	EN-GJS-400-15U	72.1	EN 1563
EN-JS1080	EN-GJS-800-2	72.1	EN 1563
EN-JS1082	EN-GJS-500-7U	72.1	EN 1563
EN-JS1090	EN-GJS-900-2	72.1	EN 1563
EN-JS1092	EN-GJS-600-3U	72.1	EN 1563
EN-JS1100	EN-GJS-800-8	74	EN 1564
EN-JS1102	EN-GJS-700-2U	72.1	EN 1563
EN-JS1104	EN-GJS-800-8-RT	74	EN 1564
EN-JS1109	EN-GJS-800-8-S-RT	74	EN 1564
EN-JS1110	EN-GJS-1000-5	74	EN 1564
EN-JS1112	EN-GJS-800-2U	72.1	EN 1563
EN-JS1120	EN-GJS-1200-2	74	EN 1564
EN-JS1122	EN-GJS-900-2U	72.1	EN 1563
EN-JS1130	EN-GJS-1400-1	74	EN 1564
EN-JS1132	EN-GJS-450-10U	72.1	EN 1563
EN-JS2010	EN-GJS-HB130	72.1	EN 1563
EN-JS2020	EN-GJS-HB150	72.1	EN 1563
EN-JS2030	EN-GJS-HB155	72.1	EN 1563
EN-JS2040	EN-GJS-HB185	72.1	EN 1563
EN-JS2050	EN-GJS-HB200	72.1	EN 1563
EN-JS2060	EN-GJS-HB230	72.1	EN 1563

Table 4 (continued)

Designation		Group	Standard(s)
Name	Number		
EN-JS2070	EN-GJS-HB265	72.1	EN 1563
EN-JS2080	EN-GJS-HB300	72.1	EN 1563
EN-JS2090	EN-GJS-HB330	72.1	EN 1563

4.5 Types of nickel and nickel alloy in accordance with the grouping system of ISO/TR 15608:2017, Table 4

See Table 5.

Table 5 — Nickel and nickel alloys

Designation		Group	Standard(s)
Name	Number		
Ni99,7Mg	2.4052	41	DIN 17740
Ni99,6	2.4060	41	DIN 17740
LC-Ni99,6	2.4061	41	DIN 17740
Ni99,4Fe	2.4062	41	DIN 17741
Ni99,2	2.4066	41	DIN 17740
LC-Ni99	2.4068	41	DIN 17740
NiMn1	2.4106	41	DIN 17741
NiMn1C	2.4108	41	DIN 17741
NiMn2	2.4110	41	DIN 17741
NiMn5	2.4116	41	DIN 17741
NiMn3Al	2.4122	41	DIN 17741
G-Ni95	2.4170	41	DIN 17730
G-Ni93C	2.4175	41	DIN 17730
G-Ni90Si	2.4180	41	DIN 17730
NiCu30Fe	2.4360	42	DIN 17743
LC-NiCu30Fe	2.4361	42	DIN 17743
NiCu30FeS	2.4363	42	DIN 17743
G-NiCu30Nb	2.4365	42	DIN 17730
G-NiCu30Si3	2.4367	42	DIN 17730
G-NiCu30Si4	2.4368	42	DIN 17730
NiCu30Al	2.4375	42	DIN 17743
NiMo29Cr	2.4600	44	DIN 17744
NiCr21Mo14W	2.4602	43	DIN 17744
NiCr23Mo16Al	2.4605	43	DIN 17744
NiCr21Mo16W	2.4606	43	DIN 17744
NiCr26MoW	2.4608	43	EN 10302
NiMo16Cr16Ti	2.4610	43	DIN 17744
NiMo28	2.4617	44	DIN 17744
NiCr22Mo7Cu	2.4619	43	DIN 17744
NiCr20Co18Ti	2.4632	46	EN 10302
NiCr25FeAlY	2.4633	45	EN 10302

Table 5 (continued)

Designation		Group	Standard(s)
Name	Number		
NiCr29Fe	2.4642	45	EN 10302
NiCr25FeAlYC	2.4647	45	DIN 17742
NiCo20Cr20MoTi	2.4650	46	EN 10302
NiCr20Co13Mo4Ti3Al	2.4654	46	EN 10302
NiCr7030	2.4658	45	DIN 17742
NiCr20CuMo	2.4660	48	DIN 17744
NiCr23Co12Mo	2.4663	46	EN 10302
NiCr22Fe18Mo	2.4665	45	EN 10302
NiCr19Fe19Nb5Mo3	2.4668	45	EN 10302
NiCr15Fe7TiAl	2.4669	45	EN 10269, EN 10302
NiCr23Mo16Cu	2.4675	47	DIN 17744
G-NiCr50Nb	2.4680	43	EN 10295
NiMo23Cr8Fe	2.4710	43	DIN 17744
NiCr22W14Mo	2.4733	43	DIN 17744
G-NiCr15	2.4815	43	EN 10295
NiCr15Fe	2.4816	43	EN 10095
LC-NiCr15Fe	2.4817	43	DIN 17742
NiMo16Cr15W	2.4819	43	DIN 17744
NiCr23Fe	2.4851	43	EN 10095
NiCr22Mo9Nb	2.4856	43	EN 10095
NiCr21Mo	2.4858	43	DIN 17744
NiCr6015	2.4867	45	DIN 17470, DIN 17742
NiCr8020	2.4869	45	DIN 17470, DIN 17742
NiCr20AlSi	2.4872	45	DIN 17742
NiCr25Co20TiMo	2.4878	46	EN 10302
G-NiCr28W	2.4879	45	EN 10295
NiCr28FeSiCe	2.4889	45	EN 10095
NiCr20Ti	2.4951	45	EN 10095
NiCr20TiAl	2.4952	45	EN 10269, EN 10302

Bibliography

- [1] DIN 17470, *Heating conductor alloys — Technical delivery conditions for round and flat wire*
- [2] DIN 17730, *Nickel and nickel-copper alloys — Castings*
- [3] DIN 17740, *Wrought nickel — Chemical composition*
- [4] DIN 17741, *Wrought nickel alloys, low alloyed — Chemical composition*
- [5] DIN 17742, *Wrought nickel alloys with chromium — Chemical composition*
- [6] DIN 17743, *Wrought nickel alloys with copper — Chemical composition*
- [7] DIN 17744, *Wrought nickel alloys with molybdenum and chromium — Chemical composition*
- [8] EN 573, *Aluminium and aluminium alloys — Chemical composition and form of wrought products — Part 1: Numerical designation system*
- [9] EN 1561, *Founding — Grey cast irons*
- [10] EN 1562, *Founding — Malleable cast irons*
- [11] EN 1563, *Founding — Spheroidal graphite cast irons*
- [12] EN 1564, *Founding — Ausferritic spheroidal graphite cast irons*
- [13] EN 1652, *Copper and copper alloys — Plate, sheet, strip and circles for general purposes*
- [14] EN 1653, *Copper and copper alloys — Plate, sheet and circles for boilers, pressure vessels and hot water storage units*
- [15] EN 1654, *Copper and copper alloys — Strip for springs and connectors*
- [16] EN 1706, *Aluminium and aluminium alloys — Castings — Chemical composition and mechanical properties*
- [17] EN 10025-2, *Hot rolled products of structural steels — Part 2: Technical delivery conditions for non-alloy structural steels*
- [18] EN 10025-3, *Hot rolled products of structural steels — Part 3: Technical delivery conditions for normalized/normalized rolled weldable fine grain structural steels*
- [19] EN 10025-4, *Hot rolled products of structural steels — Part 4: Technical delivery conditions for thermomechanical rolled weldable fine grain structural steels*
- [20] EN 10025-5, *Hot rolled products of structural steels — Part 5: Technical delivery conditions for structural steels with improved atmospheric corrosion resistance*
- [21] EN 10025-6, *Hot rolled products of structural steels — Part 6: Technical delivery conditions for flat products of high yield strength structural steels in the quenched and tempered condition*
- [22] EN 10028-2, *Flat products made of steels for pressure purposes — Part 2: Non-alloy and alloy steels with specified elevated temperature properties*
- [23] EN 10028-3, *Flat products made of steels for pressure purposes — Part 3: Weldable fine grain steels, normalized*
- [24] EN 10028-4, *Flat products made of steels for pressure purposes — Part 4: Nickel alloy steels with specified low temperature properties*

- [25] EN 10028-5, *Flat products made of steels for pressure purposes — Part 5: Weldable fine grain steels, thermomechanically rolled*
- [26] EN 10028-6, *Flat products made of steels for pressure purposes — Part 6: Weldable fine grain steels, quenched and tempered*
- [27] EN 10028-7, *Flat products made of steels for pressure purposes — Part 7: Stainless steels*
- [28] EN 10083-2, *Quenched and tempered steels — Part 2: Technical delivery conditions for unalloyed quality steels*
- [29] EN 10085, *Nitriding steels — Technical delivery conditions*
- [30] EN 10088-1, *Stainless steels — Part 1: List of stainless steels*
- [31] EN 10088-2, *Stainless steels — Part 2: Technical delivery conditions for sheet/plate and strip of corrosion resisting steels for general purposes*
- [32] EN 10088-3, *Stainless steels — Part 3: Technical delivery conditions for semi-finished products, bars, rods, wire, sections and bright products of corrosion resisting steels for general purposes*
- [33] EN 10088-4, *Stainless steels — Part 4: Technical delivery conditions for sheet/plate and strip of corrosion resisting steels for construction purposes*
- [34] EN 10088-5, *Stainless steels — Part 5: Technical delivery conditions for bars, rods, wire, sections and bright products of corrosion resisting steels for construction purposes*
- [35] EN 10090, *Valve steels and alloys for internal combustion engines*
- [36] EN 10095, *Heat resisting steels and nickel alloys*
- [37] EN 10111, *Continuously hot rolled low carbon steel sheet and strip for cold forming — Technical delivery conditions*
- [38] EN 10120, *Steel sheet and strip for welded gas cylinders*
- [39] EN 10130, *Cold rolled low carbon steel flat products for cold forming — Technical delivery conditions*
- [40] EN 10132-2, *Cold rolled narrow steel strip for heat treatment — Technical delivery conditions — Part 2: Case hardening steels*
- [41] EN 10137-3,¹⁾ *Plates and wide flats made of high yield strength structural steels in the quenched and tempered or precipitation hardened conditions — Part 3: Delivery conditions for precipitation hardened steels*
- [42] EN 10139, *Cold rolled uncoated low carbon steel narrow strip for cold forming — Technical delivery conditions*
- [43] EN 10149-2, *Hot rolled flat products made of high yield strength steels for cold forming — Part 2: Technical delivery conditions for thermomechanically rolled steels*
- [44] EN 10149-3, *Hot rolled flat products made of high yield strength steels for cold forming — Part 3: Technical delivery conditions for normalized or normalized rolled steels*
- [45] EN 10152, *Electrolytically zinc coated cold rolled steel flat products for cold forming - Technical delivery conditions*
- [46] EN 10207, *Steels for simple pressure vessels — Technical delivery requirements for plates, strips and bars*

1) Withdrawn.

- [47] EN 10210-1, *Hot finished structural hollow sections of non-alloy and fine grain steels — Part 1: Technical delivery conditions*
- [48] EN 10213, *Steel castings for pressure purposes*
- [49] EN 10216-1, *Seamless steel tubes for pressure purposes — Technical delivery conditions — Part 1: Non-alloy steel tubes with specified room temperature properties*
- [50] EN 10216-2, *Seamless steel tubes for pressure purposes — Technical delivery conditions — Part 2: Non-alloy and alloy steel tubes with specified elevated temperature properties*
- [51] EN 10216-3, *Seamless steel tubes for pressure purposes — Technical delivery conditions — Part 3: Alloy fine grain steel tubes*
- [52] EN 10216-4, *Seamless steel tubes for pressure purposes — Technical delivery conditions — Part 4: Non-alloy and alloy steel tubes with specified low temperature properties*
- [53] EN 10216-5, *Seamless steel tubes for pressure purposes — Technical delivery conditions — Part 5: Stainless steel tubes*
- [54] EN 10217-1, *Welded steel tubes for pressure purposes — Technical delivery conditions — Part 1: Electric welded and submerged arc welded non-alloy steel tubes with specified room temperature properties*
- [55] EN 10217-2, *Welded steel tubes for pressure purposes — Technical delivery conditions — Part 2: Electric welded non-alloy and alloy steel tubes with specified elevated temperature properties*
- [56] EN 10217-3, *Welded steel tubes for pressure purposes — Technical delivery conditions — Part 3: Electric welded and submerged arc welded alloy fine grain steel tubes with specified room, elevated and low temperature properties*
- [57] EN 10217-4, *Welded steel tubes for pressure purposes — Technical delivery conditions — Part 4: Electric welded non-alloy steel tubes with specified low temperature properties*
- [58] EN 10217-5, *Welded steel tubes for pressure purposes — Technical delivery conditions — Part 5: Submerged arc welded non-alloy and alloy steel tubes with specified elevated temperature properties*
- [59] EN 10217-6, *Welded steel tubes for pressure purposes — Technical delivery conditions — Part 6: Submerged arc welded non-alloy steel tubes with specified low temperature properties*
- [60] EN 10217-7, *Welded steel tubes for pressure purposes — Technical delivery conditions — Part 7: Stainless steel tubes*
- [61] EN 10219-1, *Cold formed welded structural hollow sections of non-alloy and fine grain steels — Part 1: Technical delivery conditions*
- [62] EN 10222-2, *Steel forgings for pressure purposes — Part 2: Ferritic and martensitic steels with specified elevated temperatures properties*
- [63] EN 10222-3, *Steel forgings for pressure purposes — Part 3: Nickel steels with specified low temperature properties*
- [64] EN 10222-4, *Steel forgings for pressure purposes — Part 4: Weldable fine grain steels with high proof strength*
- [65] EN 10222-5, *Steel forgings for pressure purposes — Part 5: Martensitic, austenitic and austenitic-ferritic stainless steels*
- [66] EN 10224, *Non-alloy steel tubes and fittings for the conveyance of aqueous liquids including water for human consumption — Technical delivery conditions*
- [67] EN 10225, *Weldable structural steels for fixed offshore structures — Technical delivery conditions*

- [68] EN 10248-1, *Hot rolled sheet piling of non alloy steels — Part 1: Technical delivery conditions*
- [69] EN 10250-2, *Open die steel forgings for general engineering purposes — Part 2: Non-alloy quality and special steels*
- [70] EN 10250-3, *Open die steel forgings for general engineering purposes — Part 3: Alloy special steels*
- [71] EN 10255, *Non-Alloy steel tubes suitable for welding and threading — Technical delivery conditions*
- [72] EN 10267, *Ferritic-pearlitic steels for precipitation hardening from hot-working temperatures*
- [73] EN 10268, *Cold rolled steel flat products with high yield strength for cold forming — Technical delivery conditions*
- [74] EN 10269, *Steels and nickel alloys for fasteners with specified elevated and/or low temperature properties*
- [75] EN 10271, *Electrolytically zinc-nickel (ZN) coated steel flat products — Technical delivery conditions*
- [76] EN 10273, *Hot rolled weldable steel bars for pressure purposes with specified elevated temperature properties*
- [77] EN 10277, *Bright steel products — Technical delivery conditions*
- [78] EN 10283, *Corrosion resistant steel castings*
- [79] EN 10293, *Steel castings — Steel castings for general engineering uses*
- [80] EN 10295, *Heat resistant steel castings*
- [81] EN 10296-1, *Welded circular steel tubes for mechanical and general engineering purposes — Technical delivery conditions — Part 1: Non-alloy and alloy steel tubes*
- [82] EN 10296-2, *Welded circular steel tubes for mechanical and general engineering purposes — Technical delivery conditions — Part 2: Stainless steel*
- [83] EN 10297-1, *Seamless circular steel tubes for mechanical and general engineering purposes — Technical delivery conditions — Part 1: Non-alloy and alloy steel tubes*
- [84] EN 10297-2, *Seamless circular steel tubes for mechanical and general engineering purposes — Technical delivery conditions — Part 2: Stainless steel*
- [85] EN 10302, *Creep resisting steels, nickel and cobalt alloys*
- [86] EN 10305-1, *Steel tubes for precision applications — Technical delivery conditions — Part 1: Seamless cold drawn tubes*
- [87] EN 10305-2, *Steel tubes for precision applications — Technical delivery conditions — Part 2: Welded cold drawn tubes*
- [88] EN 10305-3, *Steel tubes for precision applications — Technical delivery conditions — Part 3: Welded cold sized tubes*
- [89] EN 10305-4, *Steel tubes for precision applications — Technical delivery conditions — Part 4: Seamless cold drawn tubes for hydraulic and pneumatic power systems*
- [90] EN 10305-5, *Steel tubes for precision applications — Technical delivery conditions — Part 5: Welded cold sized square and rectangular tubes*
- [91] EN 10340, *Steel castings for structural uses*
- [92] EN 12513, *Founding — Abrasion resistant cast irons*
- [93] EN 13674-1, *Railway applications — Track - Rail — Part 1: Vignole railway rails 46 kg/m and above*

- [94] EN 13674-2, *Railway applications — Track - Rail — Part 2: Switch and crossing rails used in conjunction with Vignole railway rails 46 kg/m and above*
- [95] EN ISO 683-2, *Heat-treatable steels, alloy steels and free-cutting steels — Part 2: Alloy steels for quenching and tempering*
- [96] EN ISO 683-3, *Heat-treatable steels, alloy steels and free-cutting steels — Part 3: Case-hardening steels*
- [97] EN ISO 3183, *Petroleum and natural gas industries — Steel pipe for pipeline transportation systems*
- [98] ISO/TR 15608:2017, *Welding — Guidelines for a metallic materials grouping system*
- [99] ISO/TR 20173:2018, *Welding — Grouping systems for materials — American materials*
- [100] ISO/TR 20174:2020, *Welding — Grouping systems for materials — Japanese materials*