

Laromer[®] LR 9019

General	Modified aromatic epoxide acrylate for the formulation of radiation curable coatings and printing inks for wood, wood-based products, paper and plastics.
Key features & benefits	<div>free of reactive diluents</div> <div>high reactivity</div> <div>good scratch resistance</div>
Chemical nature	modified, aromatic epoxide acrylate resin, free of reactive diluents

Properties

Appearance	viscous liquid	
Typical characteristics <i>(should not be interpreted as specifications)</i>	viscosity at 23°C	12~20 Pa·s
	acid number	≤ 5 mg KOH/g solids
	iodine color number	≤ 2.5
	density at 20°C	1.16 g/mL
	flash point	> 100 °C

Application

Laromer[®] LR 9019 can be used for the formulation of highly reactive coatings. It leads to films with good chemical resistance and high scratch resistance. Due to the balanced mechanical properties Laromer[®] LR 9019 can be used as base product for many applications such as primers, sealers and topcoats for wood and wood-based materials.

The resin can be diluted for processing with low volatile monomers such as monofunctional, difunctional and trifunctional acrylates or with low viscous polyether acrylates such as Laromer[®] LR 8863, Laromer[®] PO 33 F, Laromer[®] PO 43 F or Laromer[®] PO 8967. Co-polymerizable reactive diluents will influence the coating properties depending on their chemical nature and concentration in the formulation.

Inert, volatile solvents such as ketones or esters can be used to reduce the viscosity of the formulation based on Laromer[®] LR 9019. In this case, the solvent must be flashed off sufficiently prior to UV / EB curing.

A suitable photoinitiator must be used to photocure Laromer[®] LR 9019. The photoinitiator types include, for example, α -hydroxy ketone, benzophenone, acyl phosphine oxide, and blends thereof, for typical coating applications. The amount of photoinitiator varies between 2%~5% based on Laromer[®] LR 9019 as delivered. Acyl phosphine oxide types (MAPO, MAPO-Liquid and BAPO) of photoinitiators are recommended for film thicknesses of 50 g/cm² and more to ensure through curing.

Storage

Product ought to be kept within sealed unopened containers. Containers should be stored below 35 °C and away from sunlight.

For further detailed application information please contact our Technical Support Department.

Safety

When handling this product, please comply with the advice and information given in the safety data sheet and observe protective and workplace hygiene measures adequate for handling chemicals.

Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. The agreed contractual quality of the product results exclusively from the statements made in the product specification. It is the responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed.

® = registered trademark, ™ = trademark of the BASF Group, unless otherwise noted

BASF East Asia Regional Headquarters Ltd.

45th Floor, Jardine House, No. 1 Connaught Place, Central, Hong Kong