

Hydropalat® WE 3485

general

wetting agent

- excellent wetting agent for aqueous formulations
- strong reduction of surface tension
- highly dynamic substrate wetting
- contains no flammable co-solvent

chemical nature

anionic compound

Properties

physical form

viscous liquid

storage

Hydropalat® WE 3485 should be stored in a cool dry place.

typical properties (no supply specification)

solids	~ 85%
pH value (1 %)	~ 6
sodium sulfate	~ 0.5%
2-ethylhexanol	< 0.5%

Application

Hydropalat® WE 3485 is a highly dynamic wetting agent for aqueous coatings, printing inks, over print varnishes and related systems. Due to its excellent wetting properties it is particularly suitable for difficult-to-wet substrates such as plastics and metal surfaces, cellulose film, aluminum and plastic foils, silicone treated papers or glass.

Hydropalat® WE 3485 can be used to optimize the compatibility (color acceptance) of aqueous pigment concentrates in different coatings. It can be incorporated either into the pigment concentrate or directly into the base paint. It can also be used as "post additive".

recommended concentrations

0.1 - 1.0% active substance on finished coatings
1.0 – 5.0% in over print varnishes (OPV)
1.0 – 5.0% in pigment concentrates

The exact dosage should be determined by appropriate tests. Hydropalat® WE 3485 may be incorporated at any stage of the manufacturing process. To ensure optimal incorporation it is advisable to add it after grinding by stirring vigorously.

Contacts worldwide

Asia

BASF East Asia Regional Headquarters Ltd
45/F, Jardine House
No. 1 Connaught Place
Central Hong Kong
China
formulation-additives-asia@basf.com

North America

BASF Corporation
11501 Steele Creek Road
Charlotte, NC 28273
USA
formulation-additives-nafta@basf.com

Europe

BASF SE
Formulation Additives
67056 Ludwigshafen
Germany
formulation-additives-europe@basf.com

South America

BASF S.A
Rochaverá - Crystal Tower
Av. das Nações Unidas, 14.171
Morumbi - São Paulo-SP
Brazil
formulation-additives-south-america@basf.com

Validity

This Technical Data Sheet is valid for all versions of the Hydropalat WE 3485.

Safety

When handling these products, please comply with the advice and information given in the safety data sheet and observe protective and workplace hygiene measures adequate for handling chemicals.

Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. The agreed contractual quality of the product results exclusively from the statements made in the product specification. It is the responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed.

® = registered trademark, ™ = trademark of BASF Group, unless otherwise noted

www.basf.com/formulation-additives