

Sovermol® 760

General

Sovermol® 760 is a polyol used in the manufacturing of UV-stable polyurethanes.

Key features & benefits

- Hydrolysis stable
- Hydrophobic
- Extremely high Tg-polyol
- High Shore D hardness (D~90)
- High renewable raw material content
- High saponification stable
- Excellent chemical resistance

Chemical nature

Branched polyether/polyester

Properties

Appearance

Medium viscous, yellow, liquid

Typical characteristics

(should not be interpreted as specifications)

Water content	DGF C-III 13 A	< 0.2 %
Acid number	DGF C-V 2	< 2.0
Hydroxyl number	DIN 53240-98	370 – 410 mgKOH/g
Viscosity, dynamic, 25 °C	DIN 53015	1.500 – 3.000 mPa.s
Density, 20 °C	DGF C-IV 2B (52)	1.0 – 1.04 g/cm³

Application

In combination with Polymer MDI Sovermol® 760 can be used for the production of 2 pack coating and casting materials. In combination with an aliphatic, HDI-based polyisocyanate, Sovermol® 760 is suitable for the production of UV-stable and weathering resistant coatings.

In addition, Sovermol® 760 is strongly water repellent, which results in less sensitivity to moisture while curing.

Mixing formulation (without filler)

100 g Sovermol® 760
5 g Zeolith Paste
94 g Polymer MDI*

*e.g. Lupranate M 20 S – BASF Polyurethanes

Storage

Sovermol® 760 shouldn't be stored at temperatures below 15 °C because it may crystallize partially. This effect is reversible by warming up to approx. 50 °C.

For further detailed application information please contact our Technical Support Department.

Safety

When handling this product, please comply with the advice and information given in the safety data sheet and observe protective and workplace hygiene measures adequate for handling chemicals.

Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. The agreed contractual quality of the product results exclusively from the statements made in the product specification. It is the responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed.

® = registered trademark, ™ = trademark of the BASF Group, unless otherwise noted

BASF Advanced Chemical Co., Ltd.
No. 300 Jiang Xin Sha Rd, Pudong, Shanghai, China