

# Efka® PU 4015

general

high-molecular-weight dispersing agent

Efka<sup>®</sup> PU 4015 is a polymeric dispersant for stabilizing inorganic and organic pigments with strong viscosity depressing properties. This results in:

- improved gloss
- · reduced flooding
- · higher color strength
- lower viscosity
- higher pigment loads

Due to its particularly good combination of price and performance, Efka<sup>®</sup> PU 4015 is a very attractive substitute for conventional wetting and dispersing agents.

chemical nature

modified polyurethane

# **Properties**

physical form clear, slightly yellowish liquid

storage Efka® PU 4015 may solidify when stored below 10 °C (50 °F). Heat to

35-40 °C (95-104 °F) to reliquify.

typical properties (no supply specification)

solvent	butyl acetate / methoxypropyl acetate / alkylbenzene
density at 20 °C (68 °F)	~ 1.00 g/cm <sup>3</sup>
solids content (1 h at 120 °C)	~ 49 %
flash point	24 °C (75°F)
amine value	~ 10 mg KOH/g
color	≤ 7

# **Application**

Efka® PU 4015 is recommended for universal solvent-based pigment concentrates, particularly where cost-effective performance is vital. It can also be used as a general dispersing agent for all solvent-based paints from high-performance industrial coatings to normal decorative paints.

Efka® PU 4015 page 2 of 2 March 2017

# recommended concentrations

Calculation method for the required amount of active ingredient on pigment:

titanium dioxide	6–8 %
inorganic pigments	5–10 %
organic pigments	20–40 %
carbon blacks	30–60 %

Efka® PU 4015 should be incorporated in the mill base before adding the pigments.

## Contacts worldwide

Asia BASF East Asia Regional Headquarters Ltd

45/F, Jardine House No. 1 Connaught Place Central Hong Kong

China

formulation-additives-asia@basf.com

Europe BASF SE

Formulation Additives 67056 Ludwigshafen

Germany

formulation-additives-europe@basf.com

North America **BASF** Corporation 11501 Steele Creek Road Charlotte, NC 28273

formulation-additives-nafta@basf.com

South America BASF S.A

Rochaverá - Crystal Tower Av. das Naçoes Unidas, 14.171 Morumbi - São Paulo-SP

Brazil

formulation-additives-south-america@basf.com

Validity
This Technical Data Sheet is valid for all versions of the Efka® PU 4015.

When handling these products, please comply with the advice and information given in the safety data sheet and observe protective and workplace hygiene measures adequate for handling chemicals.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. The agreed contractual quality of the product results exclusively from the statements made in the product specification. It is the responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed.

<sup>® =</sup> registered trademark, ™ = trademark of BASF Group, unless otherwise noted