

Dispex[®] Ultra PX 4575

general

Dispex[®] Ultra PX 4575 is a high-molecular-weight dispersing agent based on controlled free radical polymerization technology (CFRP).

- especially suited for the dispersion of pigments in water-borne coatings and colorants
- high efficiency and wide compatibility
- excellent performance with inorganic pigments

chemical nature

acrylic block copolymer formulation in water

Properties

physical form

clear, slightly yellowish liquid

shelf life

Dispex[®] Ultra PX 4575 may partially solidify when stored below 10 °C (50 °F). Heat to 35–40 °C (95–104 °F) to reliquify.

typical properties (no supply specification)

solvent	water
VOC	no VOC*
active ingredients	~ 40 %
amine value	~ 32 mg KOH/g
color	≤ 9

* VOC typically < 0.1% according to ISO 11890-2 and typically < 0.4% according to EPA-24

Application

Dispex® Ultra PX 4575 offers high efficiency in stabilizing pigments and demonstrates wide compatibility with many water-based resin systems.

The new Dispex® Ultra PX 4575 is a universal dispersing agent with particular good performance in inorganic pigments which complements Dispex® Ultra PX 4585 which has an excellent performance for organic pigments. This makes Dispex® Ultra PX 4575 ideally suited for the use of the concept of resin-free pigment concentrates.

Dispex® Ultra PX 4575 is very broad in its compatibility with different water-based resins and pigments.

- decorative coatings based on acrylics, alkyds
- industrial coatings based on acrylics, 2-pack PUR
- automotive OEM coatings based on urethane modified polyester
- melamine, thermosetting acrylic dispersion
- refinish based on: 2-pack PUR
- for high performance water based paints

Dispex® Ultra PX 4575 can be used

- for organic and inorganic pigments
- in resin-free pigment concentrates
- in resin containing pigment concentrates
- for water-based architectural in-plant tinters
- for high performance water based paints

recommended concentrations

Calculation method to estimate the minimum required amount of actives/solids ingredients on pigment:

inorganic pigments	10–20 % on oil absorption value
organic pigments	25–50 % on BET value
carbon blacks (LCF)	15–20 % on DBP value
carbon blacks (HCC)	50–80 % on DBP value

The correct dosage of dispersing agent should be determined in a ladder study where the starting point can be calculated using above calculation method.

Dispex® Ultra PX 4575 should be incorporated into the mill base before adding the pigments.

Contacts worldwide

Asia

BASF East Asia Regional Headquarters Ltd
45/F, Jardine House
No. 1 Connaught Place
Central Hong Kong
China
formulation-additives-asia@basf.com

North America

BASF Corporation
11501 Steele Creek Road
Charlotte, NC 28273
USA
formulation-additives-nafta@basf.com

Europe

BASF SE
Formulation Additives
67056 Ludwigshafen
Germany
formulation-additives-europe@basf.com

South America

BASF S.A
Rochaverá - Crystal Tower
Av. das Nações Unidas, 14.171
Morumbi - São Paulo-SP
Brazil
formulation-additives-south-america@basf.com

Validity

This Technical Data Sheet is valid for all versions of the Dispex Ultra PX 4575.

Safety

When handling these products, please comply with the advice and information given in the safety data sheet and observe protective and workplace hygiene measures adequate for handling chemicals.

Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. The agreed contractual quality of the product results exclusively from the statements made in the product specification. It is the responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed.

® = registered trademark, ™ = trademark of BASF Group, unless otherwise noted

www.basf.com/formulation-additives