

Dispex[®] Ultra PA 4560

general

Dispex[®] Ultra PA 4560 is a high-molecular-weight dispersing agent. It stabilizes the pigment dispersion of inorganic and organic pigments and improves the following properties:

- gloss
- color strength
- flocculation stability
- anti-flooding behavior

chemical nature

modified polyacrylate

Properties

physical form

clear, slightly yellowish liquid

storage

Dispex[®] Ultra PA 4560 may partially solidify when stored below 10 °C (50 °F). Heat to 35–40 °C (95–104 °F) to reliquify.

typical properties (no supply specification)

| | |
|--------------------------|--------------------------|
| solvent | water |
| density at 20 °C (68 °F) | ~ 1.04 g/cm ³ |
| active ingredients | ~ 40 % |
| amine value | ~ 25 mg KOH/g |
| color | ≤ 6 |

Application

Dispex[®] Ultra PA 4560 is, in combination with Dispex[®] Ultra PA 4503, suitable to formulate VOC-free tinting concentrates for both water- and solvent-based decorative paints. These concentrates have excellent compatibility and can therefore be incorporated by the use of low shear forces (shaking machines).

recommended concentrations

Calculation method for the required amount of active ingredient on pigment:

| | |
|--------------------|------------------------------|
| inorganic pigments | 10 % of oil absorption value |
| organic pigments | 25–50 % of BET value |
| carbon blacks | 20 % of DBP absorption value |

Dispex[®] Ultra PA 4560 should be incorporated in the mill base before adding the pigments.

Contacts worldwide

Asia

BASF East Asia Regional Headquarters Ltd
45/F, Jardine House
No. 1 Connaught Place
Central Hong Kong
China
formulation-additives-asia@basf.com

North America

BASF Corporation
11501 Steele Creek Road
Charlotte, NC 28273
USA
formulation-additives-nafta@basf.com

Europe

BASF SE
Formulation Additives
67056 Ludwigshafen
Germany
formulation-additives-europe@basf.com

South America

BASF S.A
Rochaverá - Crystal Tower
Av. das Nações Unidas, 14.171
Morumbi - São Paulo-SP
Brazil
formulation-additives-south-america@basf.com

Validity

This Technical Data Sheet is valid for all versions of the Dispex Ultra PA 4560.

Safety

When handling these products, please comply with the advice and information given in the safety data sheet and observe protective and workplace hygiene measures adequate for handling chemicals.

Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. The agreed contractual quality of the product results exclusively from the statements made in the product specification. It is the responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed.

® = registered trademark, ™ = trademark of BASF Group, unless otherwise noted

www.basf.com/formulation-additives