

# Rheovis® AS 1956

## general

rheology modifier

- efficient acrylic thickener (ASE) in powder form with pronounced pseudoplastic (low-shear) flow behavior

## chemical nature

anionic polyacrylate

---

## Properties

### physical form

powder

### storage

Rheovis® AS 1956 should be stored in a cool dry place.

### typical properties (no supply specification)

solid content	> 85%
pH value (ISO 1148)	~ 6
bulk density	~ 700 kg/m <sup>3</sup>

---

## Application

Rheovis® AS 1956 is an efficient acrylic thickener (ASE) in powder form with pronounced pseudoplastic (low-shear) flow behavior for many aqueous paint and coating systems. It is especially suited for textured finishes and marble stone finishes. Rheovis® AS 1956 offers performance highlights such as:

- outstanding thickening efficiency
- pronounced pseudoplastic (low-shear) flow behaviour
- increased KU-viscosity
- prolonged open time
- can substitute (partially) cellulose
- reduced sagging
- excellent resistant against water whitening

**recommended concentrations**

1 to 3.5 percent on total formulation

We recommend to determine the optimum dosage level for Rheovis® AS 1956 by laboratory trials to achieve the desired performance.

## Contacts worldwide

## Asia

BASF East Asia Regional Headquarters Ltd  
45/F, Jardine House  
No. 1 Connaught Place  
Central Hong Kong  
China  
[formulation-additives-asia@basf.com](mailto:formulation-additives-asia@basf.com)

## North America

BASF Corporation  
11501 Steele Creek Road  
Charlotte, NC 28273  
USA  
[formulation-additives-nafta@basf.com](mailto:formulation-additives-nafta@basf.com)

## Europe

BASF SE  
Formulation Additives  
67056 Ludwigshafen  
Germany  
[formulation-additives-europe@basf.com](mailto:formulation-additives-europe@basf.com)

## South America

BASF S.A  
Rochaverá - Crystal Tower  
Av. das Nações Unidas, 14.171  
Morumbi - São Paulo-SP  
Brazil  
[formulation-additives-south-america@basf.com](mailto:formulation-additives-south-america@basf.com)

**Validity**

This Technical Data Sheet is valid for all versions of the Rheovis AS 1956.

**Safety**

When handling these products, please comply with the advice and information given in the safety data sheet and observe protective and workplace hygiene measures adequate for handling chemicals.

**Note**

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. The agreed contractual quality of the product results exclusively from the statements made in the product specification. It is the responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed.

® = registered trademark, ™ = trademark of BASF Group, unless otherwise noted

[www.basf.com/formulation-additives](http://www.basf.com/formulation-additives)