

Rheovis® HS 1162

general rheology modifier

outstanding extreme low-shear to thixotropic rheology modifier for aqueous coatings

chemical nature hydrophobic modified acrylic swellable copolymer emulsion (HASE) in

water

Properties

physical form white liquid (dispersion)

storage Rheovis® HS 1162 should be stored in a cool dry place.

typical properties (no supply specification)

solid content ~ 35%
density at 20°C ~ 1.067 g/cm³
Brookfield viscosity at 25°C,20 rpm ~ 5 mPa·s
pH ~ 3.5

Application

Rheovis® HS 1162 is an outstanding rheology modifier for water based coatings with an extreme low–shear to thixotropic flow behavior.

The polymer provides the rheology–control effect through extensive swelling of the high-molecular-weight polymer in combination with a hydrophobic component. This leads to an excellent balance between sag-resistance and leveling which is ideal for airless spray applications or non-dripping paints and stains.

Rheovis® HS 1162 is most effective between pH 8 to 10. It offers the following benefits:

- thixotropic low-shear thickener
- excellent balance between sag and leveling
- outstanding efficiency
- for paints and stains

December 2016 page 2 of 2 Rheovis® HS 1162

recommended concentrations and incorporation

0.3 to 1.5 % on total formulation

We recommend to determine the optimum dosage of Rheovis® HS 1162 by laboratory trials to achieve optimum performance.

Rheovis® HS 1162 can be added at any stage of the production process. Afterwards the pH should be checked again and adjusted to 8-10.

Rheovis® HS 1162 can also be mixed into polymer dispersions in the form of an alkaline solution. The solid content of the solution should not exceed 1% to allow easy handling. It is recommended to dilute the thickener with water and add alkaline whilst stirring. Check and adjust pH afterwards.

Depending on the application, it can be advisable to use Rheovis[®] HS 1162 in combination with other Rheovis[®] thickeners or cellulose derivatives in order to obtain desired rheological effects.

Contacts worldwide

Asia

BASF East Asia Regional Headquarters Ltd

45/F, Jardine House No. 1 Connaught Place Central Hong Kong

China

formulation-additives-asia@basf.com

Europe BASF SE

Formulation Additives 67056 Ludwigshafen

Germany

formulation-additives-europe@basf.com

North America BASF Corporation 11501 Steele Creek Road Charlotte, NC 28273

USA

formulation-additives-nafta@basf.com

South America BASF S.A

Rochaverá - Crystal Tower
Av. das Naçoes Unidas, 14.171
Morumbi - São Paulo-SP

Brazil

formulation-additives-south-america@basf.com

Validity

This Technical Data Sheet is valid for all versions of the Rheovis HS 1162.

Safety

When handling these products, please comply with the advice and information given in the safety data sheet and observe protective and workplace hygiene measures adequate for handling chemicals.

Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. The agreed contractual quality of the product results exclusively from the statements made in the product specification. It is the responsibility of the recipient of our product to ensure that any proprietary rights and existing laws and legislation are observed.

 $^{^{\}text{®}}$ = registered trademark, $^{\text{TM}}$ = trademark of BASF Group, unless otherwise noted