



Investigation Report

Determination of ITF Court Pace Rate

Report-No.:	903 2376 000/1E/Kd
Client:	Systembau Horst Babinsky GmbH Fabrikstraße 14 83371 Stein
Order-No. (Client):	-
Order-No. (MPA):	903 2376 000 /Kd
Test Item:	Glass floor "ASB MultisportsFloor"
Specification Applied:	[1] "ITF Tennis Court Pace Rate", 2010-07 ITF CS 01/02; Instructions for testing samples for Court Pace
Date of Receipt of Test Item	Testing in situ at production facility of Systembau Babinsky GmbH in 83371 Stein
Date of Test:	2016-08-23
Date of Report:	2016-09-13
Page 1 of	3 text pages
Enclosures :	-
Supplements:	-
Total Number of Pages:	3
Number of Reports:	1

The test results relate only to the items tested.

Publication of this report in full or partly is only allowed with written authorization by MPA University of Stuttgart.

1 Purpose of Investigation

You commissioned us with pre- testing of the Court Pace on the glass floor "ASB MultisportsFloor" according to „ITF CS 01/02“ [1]. The test was performed at the production facility of Systembau Horst Babinsky GmbH in 83371 Stein.

2 Tests and Analyses Performed

The tests were carried out according to test method „ITF CS 01/02“.

The Materials Testing Institute University Stuttgart is an ITF accredited test laboratory for this test method.

3 Results of Investigation

The following test results were obtained.

Table 1: Test results of CPR for the glass floor "ASB MultisportsFloor"


	Shot 1	Shot 2	Shot 3	Shot 4	Shot 5	Shot 6	Shot 7	Shot 8	Shot 9
CPR (Ball 1)	55,6	56,4	53,8	56,8	54,3	53,5	56,4	55,9	58,5
CPR (Ball 2)	57,1	58,9	58,9	57,5	58,3	56,2	56,9	56,0	56,8
CPR (Ball 3)	55,8	55,7	57,3	55,6	57,6	59,3	56,2	57,3	57,1
Mean value CPR: 56,7									

According to ITF there are the following categories:

categorie	CPR
Slow	≤ 29
Medium-slow	29 – 34
Medium	35 - 39
Medium-fast	40 – 44
Fast	≥ 45

Based on the mean value for CPR of 57, the tested glass floor “ASB MultisportsFloor“ is categorized as “Fast”.


Prepared by



Oliver Konrad
Testing Engineer



Approved and released by



Dr.-Ing. Michael Stegmaier
Section leader