XG sciences
THE MATERIAL DIFFERENCE

XG-SiG™ TECHNICAL DATA SHEET

XG-SiG™ Energy Storage Materials

Silicon-Graphene Li-ion battery anode

High Energy Anode - XG Sciences' *AN-S* delivers high specific capacity in an **xGnP®** graphene-stabilized silicon anode material for enhanced run-time portable electronics. Our proprietary manufacturing process coats silicon particles with highly conductive, flexible graphene platelets establishing a network that provides silicon with robust mechanical support and high rate capacity.

General characteristics:

- ***Composition*** - Silicon graphene
- ***Morphology*** - Porous aggregates
- ***High reversible capacity***
- ***Efficient Li+ storage***
- ***Enhanced life cycle***

AN-S Si-graphene anode properties

Reversible Capacity	600-2000 mAh/g
1st cycle efficiency	85-90%
Charge/discharge rate	C/2
Discharge temperature	30°C
Recommended binders	Carboxy methyl cellulose (CMC) Polyacrylic acid (PAA)



xGnP® Graphene

Conductive additive

xGnP® graphene nanoplatelets are short stacks of graphene sheets in a platelet shape. Typical platelet electrical conductivity parallel to the surface is 10^7 S/m.

xGnP® Graphene bulk properties

Appearance	Black granules
Bulk density	0.1 g/cc
Carbon content	>99.5%
Oxygen content	<1%

XG Sciences believes the information in this technical data sheet to be accurate at publication. XG Sciences does not assume any obligation or liability for the information in this technical data sheet. No warranties are given. All implied warranties of fitness for a particular purpose are expressly excluded. No freedom from infringement of any patent owned by XG Sciences or other is to be inferred. XG Sciences encourages its customers to review their manufacturing processes and applications for xGnP Graphene Nanoplatelets from the standpoint of human health and environmental quality to ensure that this material is not utilized in ways that it is not intended or tested. Product literature and safety data sheets should be consulted prior to use. Please contact XG Sciences or visit www.xgsciences.com for the most current technical information.

© 2013 XG Sciences, Inc. All rights reserved.