

## MOTIP Effect Frigo White

## Technical Information



Alkyd lacquer with good adhesion to repair small damages to kitchen equipment. The lacquer has excellent coverage and filling properties, a lasting colour and a lasting gloss. Deco Effect Frigo White is rust preventive, is scratch free and shock proof and is resistant to chemicals.

**Ord.-no:** 303202

### Quality & properties

Excellent coverage  
Fast drying  
Lasting gloss

### Physical & chemical data

Base: Alkyd resin  
Colourname: white  
Efficiency: 400 ML – 0.8 - 1.2 m<sup>2</sup>  
Dust dry: 30 min  
Completely dry: 24 h  
Overcoatable: 2 min  
Surfaces: Kitchen equipment  
Flash point: n.a.  
Content: 400 ML

### How to use

The surface should be clean, dry and free of grease. Slightly sand the surface (grain 600). The aerosol should have room temperature. Best processing temperature 10 to 25°C. Before use, shake the aerosol for 2 minutes and spray a sample. Distance to the surface to be treated approximately 25 to 30 centimetre. Apply the lacquer in several thin layers. Before applying the next layer, again shake the aerosol. After use, clean the valve (turn aerosol upside down and press the nozzle for approximately 5 seconds). The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.

### Environmentally sound

European Aerosols is committed to apply formulations without restricted or critical ingredients and to achieve best possible performance. The caps and packagings are made of recyclable material.

### Disposal

Only the completely emptied cans should be put into the recycling skip or appropriate container for reclaimable refuse. Cans which are not empty should be disposed off as "special refuse".

### Marking/Labelling

All products made by European Aerosols comply with the actual labelling regulations according to Preparation Guideline 1999/45/EG. All aerosols correspond to TRGS 200 and TRG 300 as well as to aerosol guideline 75/324/EWG in the actually valid version.

**As of August 4, 2025** – This release replaces all eventually earlier issued versions.