Supporting Information

Thermally Reversible and Microscopically Tunable Gelation in Recombinant Polypeptides

Doga Ozgulbas[1], Miaoqi Chu[2], Alex Lavens[2], Nicholas Marks[1], Ming Du[2], Xiaobing Zuo[2], Michael Irvin[1], Heng Ma[1], Soenke Seifert[2], Byeongdu Lee[2], Rafael Vescovi[1], Ian Foster[1], Victor Mateevitsi[3], Don Jensen Jr.[2], Chase Akins[4], Arvind Ramanathan[1,*], Gyorgy Babnigg[4,*], and Qingteng Zhang[2,*]

[1]Data Science and Learning Division, Argonne National Laboratory, Lemont, Illinois 60439, United States
[2]X-ray Science Division, Argonne National Laboratory, Lemont, Illinois 60439, United States
[3]Argonne Leadership Computing Facility, Argonne National Laboratory, Lemont, Illinois 60439, United States
[4]Biosciences Division, Argonne National Laboratory, Lemont, Illinois 60439, United States

[*]ramanathana@anl.gov; gbabnigg@anl.gov; qzhang234@anl.gov

Contents

1 Recombinant Synthesis and Purification **2**
1.1 Materials . . . 2
1.2 Gene construction . . . 2
1.3 Protein expression and purification . . . 2

2 Sample Cells and Robotic Assembly **3**

3 SA-XPCS Measurements and Reduction **3**
3.1 Protocol . . . 3
3.2 Averaging and outlier rejection . . . 4
3.3 Absolute scattering cross section . . . 4

4 Structure and Dynamics on Heating and Cooling **5**

5 Reversibility and the Dispersed State **5**

6 Molecular Dynamics of a $(VPAVG)_{30}$ Array **6**

7 Radiation-Damage Mitigation and Controls **6**

8 Code, Data and AI-Assisted Development **6**

1 Recombinant Synthesis and Purification

1.1 Materials

Shrimp alkaline phosphatase, PfuUltra II Fusion HS DNA polymerase, GoTaq Green Master Mix and T4 DNA ligase with PEG4000 additive were purchased from Thermo Fisher Scientific. T4 DNA ligase and exonuclease I were purchased from New England Biolabs, CircLigase ssDNA ligase from Lucigen, and KOD Hot Start DNA polymerase from Sigma-Aldrich. PCR products and plasmids were purified with Monarch PCR & DNA Cleanup kits and Monarch Plasmid Miniprep columns (New England Biolabs), and DNA was recovered from agarose gels with the Monarch DNA Gel Extraction kit. SYBR Green I and SYBR Gold nucleic acid gel stains, for double- and single-stranded DNA, were purchased from Thermo Fisher Scientific. Granulated Terrific Broth was purchased from VWR and isopropyl-β-D-thiogalactopyranoside (IPTG) from Fisher Scientific. *E. coli* BL21(DE3)-Gold cells were obtained from Stratagene. The oligonucleotides for PCR and the 5′-phosphorylated synthetic template for rolling-circle amplification were synthesized by Integrated DNA Technologies.

1.2 Gene construction

The repetitive ELP genes were prepared by overlap-extension rolling-circle amplification (OERCA).[1] A single-stranded DNA template encoding five VPAVG repeats was circularized in a 20 µL reaction containing 10 pmol template, 2 µL of 10× CircLigase buffer, 1 µL of 1 mM ATP, 1 µL of 50 mM $MnCl_2$ and 100 U CircLigase. The reaction was incubated for 1 h at 60 °C, heat-inactivated for 10 min at 80 °C, purified and eluted in 50 µL of 1× nuclease buffer, and treated with exonuclease I for 1 h at 37 °C to remove unreacted linear template.

OERCA was performed with 300 ng of circular template, 1.5 µL each of 50 µM primers A1 and A2 (Figure S9), 2 µL of 70% GC dNTP mix, 2 µL of 25 mM $MgSO_4$, 10 µL of 10× PfuUltra II buffer, 5 µL DMSO and 2 µL PfuUltra II polymerase in 100 µL. Cycling consisted of 2 min at 95 °C, then 30 cycles of 20 s at 95 °C, 20 s at 54 °C and 90 s at 72 °C, and a final 10 min at 72 °C. Products above about 1.2 kb were excised from a 0.8% agarose gel stained with SYBR Green I and purified.

Ligation-independent cloning adapters were introduced by PCR with KOD Hot Start polymerase and primers B1 and B2 (Figure S9),[2] and the products were cloned into the pMCSG53 expression vector[3] as described previously.[4] Constructs were transformed into *E. coli* BL21(DE3)-Gold and screened for expression and solubility: 24 colonies were grown in 1 mL of Luria broth at 37 °C, induced with 0.2 mM IPTG for 4 h, lysed by sonication, and clarified at 10,000 × g, and the supernatants were bound to IMAC Sepharose High Performance resin (Cytiva). Lysates and eluted proteins were analyzed by SDS-PAGE, and clones with good expression, solubility and a range of molecular weights (10–30 kDa) were sequenced by the Sanger method. Clones with 10, 20 and 30 repeats of the VPAVG pentapeptide were chosen for this study.

1.3 Protein expression and purification

For every purification, fresh transformants were grown in Terrific Broth containing 10 mM $MgSO_4$ and 300 µg mL^{-1} ampicillin at 37 °C to an optical density of 0.6–0.8 at 600 nm. Cultures were cooled to 18 °C, induced with 0.2 mM IPTG and grown overnight. Cells were harvested at 5000 × g and resuspended in 30 mL of ice-cold lysis buffer (500 mM NaCl, 5% glycerol by volume, 50 mM HEPES at pH 8.0, 20 mM

imidazole and 10 mM 2-mercaptoethanol) with one tablet of protease inhibitor cocktail (cOmplete Ultra, EDTA-free; Sigma) per liter of culture, treated with 1 mg mL^{-1} lysozyme for 10 min, sonicated and clarified at 29,000 × g.[5] The supernatant was applied to 5 mL of IMAC Sepharose High Performance resin, washed with lysis buffer using a vacuum-assisted purification system, and the His_6-tagged protein was eluted with lysis buffer containing 500 mM imidazole. The purified protein was exchanged into 20 mM HEPES at pH 8.0, 250 mM NaCl and 2 mM DTT, concentrated to about 100 mg mL^{-1} with an Amicon Ultra-15 centrifugal concentrator (10 kDa cutoff), and stored at 4 °C. Fresh purifications were performed before the X-ray measurements.

2 Sample Cells and Robotic Assembly

The SA-XPCS measurements used aluminum liquid cells with a cylindrical sample reservoir 3 mm in diameter and 2 mm thick along the beam (Figure S1a). Assembly requires punching circular windows from Kapton or polycarbonate sheet, inserting O-rings into the grooves of the metallic caps, and bolting the cell on both sides with 16 screws. The solutions were held at 6 °C in a multi-zone temperature-controlled stage (Quantum Northwest) until measured.

Because manual handling can warm the sample and thereby affect the reversibility being measured, a robotic workflow was developed for preparing, assembling and exchanging liquid cells (Video S2). It uses a simplified cell whose body is machined from a single piece of metal and is closed by two CNC-machined, vapor-polished polycarbonate caps, each with a flat window (Figure S1b),[6] which removes the variation in exterior contour that uneven O-ring compression produces. Two six-axis robotic arms (UR3e and UR5e, Universal Robots) work on a 600 × 1200 mm optical breadboard. The UR3e carries a finger gripper (Robotiq Hand-e) and an electronic pipette (TriContinent Air-Z), exchanged through a mechanical tool changer (Wingman, TripleA Robotics) whose electrical connection runs through the wrist, so that the arm can rotate without limit for screw driving and vial opening. A locking ring at the tip of the hex bit holds a cap during transfer and releases it once installed. The robots are controlled through a Python package that handles initialization through the UR dashboard, motion through URx, the gripper through Modbus TCP/IP and the pipette through RS485,[7] and the workflow is orchestrated by the Workflow Execution Interface (WEI).[8] Sample alignment uses an on-axis optical microscope, in which a 45° mirror with a 1 mm central hole passes the X-ray beam; a computer-vision routine based on Otsu thresholding, morphological closing and connected-component analysis identifies the bubble-free region of the window available for measurement.[9, 10] The measurements reported here used the bolted cell of Figure S1a.

3 SA-XPCS Measurements and Reduction

3.1 Protocol

The three heating and cooling ramps were measured at 8-ID-I, $(VPAVG)_{10}$ (runs B039 and B040) and $(VPAVG)_{20}$ (T214 and T215) in July 2021 and $(VPAVG)_{30}$ (E0110 and E0111) in March 2022, with the same cell, stage and protocol. The ramp rate recorded by the stage RTD is 0.10 °C min^{-1} on heating and on cooling for all three. Consecutive acquisitions started every 5 s in 2021 and every 6 s in 2022, which sets the time axes of Figures S2–S4. The correlation functions were computed with the multi-tau algorithm.[11]

3.2 Averaging and outlier rejection

Each heating and each cooling ramp was cut into consecutive sections of equal acquisition count: ten sections of 278 acquisitions for $(\mathrm{VPAVG})_{10}$, twenty of 119 or 120 for $(\mathrm{VPAVG})_{20}$, and ten of 119 or 120 for $(\mathrm{VPAVG})_{30}$. On a constant-rate ramp these are equal temperature steps, of 2.5, 1.1 and 1.3 °C, respectively. Within a section, the g_2, the uncertainty of g_2 and $\log I(Q)$ of every acquisition were compared with those of every other through their cosine similarity, and an acquisition whose summed similarity fell in the lowest 5% for any of the three was excluded. The rest were averaged; between 85% and 91% of the acquisitions of a section survive. The comparison of the two-step decay (Figure 4) uses a finer cut of the same ramps: twenty sections of the $(\mathrm{VPAVG})_{10}$ heating ramp after its first 70 acquisitions, the twenty sections of $(\mathrm{VPAVG})_{20}$, and twenty of $(\mathrm{VPAVG})_{30}$.

In Figures S2–S4, a g_2 curve is not drawn when five or more of its 61 points fall outside 1.00–1.25. This omits the seven coldest heating sections and the two coldest cooling sections of $(\mathrm{VPAVG})_{30}$, whose coherent intensity at the lowest Q is too weak for a correlation function to be resolved. It also omits one cooling section of $(\mathrm{VPAVG})_{10}$, at 26.3 °C. In that section, 48 consecutive acquisitions carry a nearly constant g_2 of 1.7–1.8 in the lowest Q bin alone, which raises the average to 1.29 there; the cross-correlation cut compares the shapes of the curves rather than their levels and keeps them.

The seven-cycle measurement of Figure S6 was reduced separately, from the October 2026 reprocessing of the 2022 data, in groups defined by acquisition number: each 6 °C hold, and two windows of ten acquisitions near the top of each ramp. After the same cross-correlation cut, a second cut removes any acquisition whose mean intensity over 0.004–0.008 $\mathrm{Å}^{-1}$ lies more than three robust standard deviations above the median of its group, the scale being 1.4826 times the median absolute deviation and both statistics being recomputed from the survivors until the selection stops changing. A large scatterer drifting through the beam during an acquisition raises only its lowest-Q intensity, which leaves the shape of the curve close to that of the group and passes the cross-correlation cut; the second cut removes such acquisitions. It takes 4, 2, 1, 11, 4, 1 and 1 acquisitions from the seven 6 °C groups, 9 from the buffer, and none from the fourteen high-temperature windows.

3.3 Absolute scattering cross section

The SAXS intensity is reported as a differential scattering cross section,

$$I(Q) = A_s I_s(Q) - A_b I_b(Q), \qquad A_j = \frac{N}{F_j T_j t_{\mathrm{exp}}\, L\, \Delta\Omega}, \tag{S1}$$

where I_s and I_b are the azimuthally averaged intensities of the sample and of the buffer in photons per pixel per frame, N is the number of frames, F_j the incident flux, T_j the transmission, t_{exp} the exposure time, $L = 2\,\mathrm{mm}$ the thickness of the cell and $\Delta\Omega = (d_{\mathrm{pix}}/D)^2$ the solid angle of one pixel, with d_{pix} the pixel size and D the sample-to-detector distance.[12] With lengths in millimeters, $I(Q)$ is in mm^{-1}. The upstream ion-chamber reading was converted to incident flux by a linear calibration against a PIN diode across an attenuation series (Figure S10a), and the transmission is the ratio of the downstream to the upstream ion-chamber readings divided by the transmission of the air path between them, 0.8679 ± 0.0009 (Figure S10b). Every averaged section is scaled by the mean ion-chamber readings of the acquisitions averaged into it.

The 2021 beamtime recorded the upstream ion chamber but not the downstream one. For $(\mathrm{VPAVG})_{10}$ and $(\mathrm{VPAVG})_{20}$ the transmission is therefore taken from $(\mathrm{VPAVG})_{30}$ in the same cell in 2022, 0.369, the

mean of two loadings that differ by 11%. It is common to every 2021 curve, so it scales them together and moves no exponent or ratio within a profile. The buffer of the 2022 measurement (D0138) and a water blank of the 2021 one (D029) were subtracted with their own coefficients; the blank carries the same borrowed transmission as the samples.

4 Structure and Dynamics on Heating and Cooling

Figures S2–S4 show the complete heating and cooling ramps of the three chain lengths. In all three, the low-Q intensity rises on heating, by factors of 15, 37 and 190 for $(\mathrm{VPAVG})_{10}$, $(\mathrm{VPAVG})_{20}$ and $(\mathrm{VPAVG})_{30}$ between the first and the last section, and g_2 evolves from a full decay to a plateau. On cooling, $I(Q)$ and g_2 of $(\mathrm{VPAVG})_{10}$ and $(\mathrm{VPAVG})_{20}$ remain at their high-temperature values. Those of $(\mathrm{VPAVG})_{30}$ return most of the way: the low-Q intensity at the end of cooling is 5 times its value at the start of heating, and below about 24 °C g_2 decays again within the 2 s window.

5 Reversibility and the Dispersed State

Video S1 shows the reversible transition in $(\mathrm{VPAVG})_{30}$ directly. Brief warming of a capillary of $(\mathrm{VPAVG})_{30}$ by touch turns the solution turbid within about 5 s, and it returns to transparency about 60 s after the heat source is removed.

Two aliquots of the same $(\mathrm{VPAVG})_{30}$ stock were sealed in 2 mm quartz capillaries for measurement at 12-ID-B. The aliquot labeled Measurement had been through more than ten heating and cooling cycles, and the Reference aliquot had remained at 4 °C. Both were measured at 10 and 30 °C by simultaneous SAXS and WAXS, and the two detectors' profiles were merged by scaling the WAXS intensity onto the SAXS intensity over their common Q interval.[13–15] The two aliquots overlap at both temperatures (Figure S5a). At 30 °C both follow a low-Q power law, $I \propto Q^{-3.17}$ for the Reference and $Q^{-3.15}$ for the Measurement over $0.012 < Q < 0.040\ \text{Å}^{-1}$, and both develop two broad wide-angle peaks that are absent at 10 °C. Each peak was fitted independently with a Gaussian on a linear background, over 0.48–1.00 and 1.18–1.70 Å^{-1}. The peaks lie at 0.717 and 1.383 Å^{-1} in the Reference and at 0.743 and 1.356 Å^{-1} in the Measurement (Figure S5a, inset). The corresponding spacings, 8.8 and 4.5 Å, are compatible with the sheet-to-sheet and strand-to-strand distances of cross-β-like packing, whose reflections are reported between 8 and 11 Å across the fibril direction and at about 4.8 Å along it.[16, 17] Both peaks are broad, with full widths at half maximum of 0.34 and 0.25 Å^{-1} in the Reference, so the ordering extends over correlation lengths $2\pi/\Delta Q$ of only about 19 and 25 Å, a few repeat spacings rather than extended cross-β crystallites. A Guinier fit of the Reference profile at 10 °C, weighted by the propagated uncertainties over $0.020 \le Q \le 0.055\ \text{Å}^{-1}$ ($Q_{\max} R_g = 1.25$), gives an apparent radius of gyration $R_g = 22.65 \pm 0.50$ Å (Figure S5b). Because the protein concentration is high, it is reported as an apparent R_g.

A separate loading of $(\mathrm{VPAVG})_{30}$ (March 2022) was taken through seven consecutive heating and cooling cycles at 8-ID-I (Figure S6). In each cycle the sample was held at 6 °C for one group of 50 acquisitions, heated from 6.1 to 34.0 °C at 1.01 °C min^{-1} over 270 acquisitions, and cooled at 10 °C min^{-1} back to 6 °C; the whole sequence took 5.8 h. The 6 °C measurement of each cycle began 7 to 41 min after the end of the preceding ramp. Averaged over 0.004–0.008 Å^{-1}, the 6 °C intensity of the seven cycles has a relative standard deviation of 8.6%. The first five agree within 3.4%, and the sixth and seventh lie 11% and 21% above their mean, against a 140-fold rise at the top of every ramp. At 33.8 °C the cycles agree to 4.8%, and to 1.4% once the small differences in the temperature at which each cycle crossed the

window are regressed out. At 31.9 °C the spread is 33%, but the windows fall between 31.62 and 32.48 °C, on the steep part of the transition, where $\ln I$ tracks the window temperature with $\mathrm{d}\ln I/\mathrm{d}T = 0.95\,^{\circ}\mathrm{C}^{-1}$ ($r = 0.974$); with that trend removed the spread is 7%. In every cycle, g_2 at 33.8 °C shows no resolvable decay within the 2 s window and runs just below the correlation level of a static reference measured in the same beamtime, whereas at 31.9 °C it decays within the window. The sample therefore arrested on every heating and returned to nearly the same dispersed state on every cooling.

$(\mathrm{VPAVG})_{10}$ behaves differently. A cell loaded with $(\mathrm{VPAVG})_{10}$ and taken through the heating ramp of Figure S2 remained opaque after more than 48 h at 4 °C (Figure S7).

6 Molecular Dynamics of a $(\mathrm{VPAVG})_{30}$ Array

Figure S8 shows a molecular dynamics simulation of a $3 \times 3 \times 3$ cuboidal array of $(\mathrm{VPAVG})_{30}$ chains. The contact timeline records which pairs of chains are in contact as the simulation proceeds. Over the 25 ns shown, contacts form, break and re-form, so a simulation of this size samples the association and dissociation of the chains directly.

7 Radiation-Damage Mitigation and Controls

A Cartesian grid of 100×100 positions, spaced by at least one beam diameter in both directions, was defined on each sample, and every 2 s acquisition was taken at a previously unexposed position. Three controls test for radiation damage within an exposure and with flux.

First, the twelve consecutive subsets of 8,333 frames of a single acquisition give the same $I(Q)$ at the beginning and at the end of the $(\mathrm{VPAVG})_{10}$ heating ramp (Figure S11). Their spread below 0.01 $\mathrm{Å}^{-1}$, 7% at 20.0 °C and 2% at 45.2 °C, matches the photon-counting statistics of a subset. At 20.0 °C the intensity below 0.006 $\mathrm{Å}^{-1}$ rises by about 5% from the first subset to the last, small against the 15-fold rise that gelation produces in the same range.


Second, g_2 correlated from the first 50,000 frames of each acquisition, from the last 50,000 and from all 100,000 agree throughout the $(\mathrm{VPAVG})_{10}$ heating ramp (Figure S12). Beyond 1 ms, the half-exposure correlation functions differ from the full one by 0.001 in the median, about one standard deviation, so the dynamics stay the same throughout an exposure. The comparison follows a previous study.[11]

Third, a 20 mg mL^{-1} $(\mathrm{VPAVG})_{30}$ sample was measured after the APS Upgrade at four attenuator settings, which gave incident fluxes of 2.7 to 4.9×10^{11} photons/s, more than ten times the flux of the main experiment (Figure S13). $I(Q)$ keeps its shape and g_2 overlaps within uncertainty across the series, so the dynamics measured in the main experiment are intrinsic to the sample.


8 Code, Data and AI-Assisted Development

The reduced data and the code that turns them into every data-derived figure of the main text and of this document are at `https://github.com/qzhang234/PubCode-2021-IDPP-Reversibility`; the original analysis is also public.[18] The reduction reads the per-acquisition correlation results of the 8-ID-I measurements, and every figure is regenerated from the committed reduced data alone. The authors used Anthropic's Claude models, accessed through Argo, Argonne National Laboratory's internal

generative AI interface, to assist with manuscript preparation and with the development of the analysis and figure-generation code. The authors take full responsibility for all content and results.



Video S1: Reversible phase transition in $(VPAVG)_{30}$, stills from the video. (a) A thin quartz capillary containing $(VPAVG)_{30}$ is held in a fixture. (b) The capillary is warmed for about 5 s between thumb and index finger through nitrile gloves. (c) The solution becomes visibly cloudy as sub-micrometer structures form. (d) About 60 s after the heat source is removed, the sample is transparent again. Full video: `https://anl.box.com/s/lsukldjnr45nhfrkobijsar1tqhba7jw`.



Video S2: Automated liquid-cell assembly with a six-axis robot and exchangeable end effectors, stills from the video. (a) The UR3e robot with a finger gripper drives the first cap into the cell. The screwdriver handle and the gripper fingers are 3D-printed to match each other's contour, and a locking ring at the tip of the hex bit keeps the polycarbonate cap from falling during transfer. (b) The robot opens a 3 mL glass vial with a twist cap; the grooves of the gripper and of the vial holder are padded with Silastic tubing for friction. (c) The robot exchanges the finger gripper for the electronic pipette through a tool changer that locks mechanically, with no compressed air. (d) The robot transfers the liquid sample into the reservoir formed by the 3 mm through-hole and the first cap; closing the top with the second cap completes the cell. Full video: `https://anl.box.com/s/lsukldjnr45nhfrkobijsar1tqhba7jw`.




Figure S1: Assembly of the liquid cells. (a) The cell used for the temperature-induced gelation studies. Assembly requires punching circular windows from Kapton or polycarbonate sheet, inserting O-rings into the grooves of the metallic caps, and bolting the cell on both sides with 16 screws. (b) The cell used for robotic assembly. Its body is machined from a single piece of metal, which removes the variation in exterior contour that uneven O-ring compression produces, and it is closed by torquing CNC-machined, vapor-polished polycarbonate caps into both ends.




Figure S2: Evolution of structure and dynamics of $(VPAVG)_{10}$ during heating (left) and the cooling that followed (right). (a, b) Temperature of every acquisition against elapsed time. (c, d) Buffer-subtracted SAXS intensity $I(Q)$ on the absolute scale, one curve per section of 278 acquisitions. (e, f) Intensity autocorrelation function g_2 at $Q = 0.0038\,\text{Å}^{-1}$ for the same sections. Color is the mean temperature of the section, on one scale for both columns. The curve of the cooling section at 26.3 °C is not drawn in (f) (see text).




Figure S3: Evolution of structure and dynamics of $(VPAVG)_{20}$ during heating (left) and cooling (right), as in Figure S2, with twenty sections of 119 or 120 acquisitions per ramp.




Figure S4: Evolution of structure and dynamics of $(VPAVG)_{30}$ during heating (left) and cooling (right), as in Figure S2, with ten sections of 119 or 120 acquisitions per ramp. The g_2 curves of the seven coldest heating sections and the two coldest cooling sections are not drawn: the coherent intensity at this Q is too weak there for a correlation function to be resolved. The heating profiles in (c) are those of Figure 2a.




Figure S5: Reversibility and cross-β-like ordering of $(VPAVG)_{30}$, from SAXS and WAXS at APS 12-ID-B. (a) Merged SAXS and WAXS profiles of two aliquots of the same stock in 2 mm quartz capillaries, at 10 and 30 °C. The Measurement aliquot (markers) had been through more than ten heating and cooling cycles; the Reference aliquot (lines) had remained at 4 °C. The dashed line is the power law fitted to the Reference at 30 °C over $0.012 < Q < 0.040$ Å^{-1}. Inset: the wide-angle region of the same profile (open circles), with independent fits of a Gaussian on a linear background over 0.48–1.00 and 1.18–1.70 Å^{-1} (red curves); the dashed lines and labels mark the fitted peak centers, which correspond to spacings of 8.8 and 4.5 Å. (b) Guinier plot of the Reference aliquot at 10 °C with the weighted fit over $0.020 \leq Q \leq 0.055$ Å^{-1}. The fitted radius of gyration is the characteristic length of the dispersed state used for $\xi(T)$ in Figure 2b.




Figure S6: Thermal-cycling repeatability of $(\mathrm{VPAVG})_{30}$: one loading through seven consecutive cycles. (a) Sample temperature over the 5.8 h sequence. Solid curves are measured, the stage RTD being read once per 2 s acquisition. No acquisitions were taken during the last five cool-downs, so no temperature was recorded there; the dashed curves over those intervals are the profile of the control protocol, 10 °C min^{-1} cooling to 6 °C followed by a hold. Open symbols mark every acquisition group plotted in (b) and (c), at the time and temperature at which it was taken. (b) Buffer-subtracted SAXS on the absolute scale at 6 °C (circles, 32–41 surviving acquisitions averaged), 31.9 °C (squares, acquisitions 241–250 of the ramp) and 33.8 °C (triangles, acquisitions 261–270). Each group is scaled by the mean ion-chamber readings of the acquisitions it contains, and the averaged buffer (69 surviving of 89 acquisitions) is subtracted with no empirical scale factor. (c) Correlation functions at the lowest Q bin for the two high-temperature states. The dashed line is the correlation level of a static reference measured in the same beamtime at the same Q bin, the instrumental contrast. The 33.8 °C curves run flat just below it across four decades of delay; the 31.9 °C curves decay away from it. Error bars are the measured pointwise uncertainties, and the y axis is capped so that a few short-delay error bars clip. The key gives the seven cycles in its columns, on one color scale, and the three temperature states in its rows, distinguished by marker shape.




Figure S7: Irreversibility of thermally induced gelation in $(VPAVG)_{10}$. (a) The metallic liquid cell containing $(VPAVG)_{10}$ before the temperature ramp of Figure S2. (b) The same cell after the ramp and more than 48 h in a refrigerator at 4 °C. The sample remains opaque.




Figure S8: Molecular dynamics simulation of a $3 \times 3 \times 3$ cuboidal array of $(\text{VPAVG})_{30}$. (a) Contact timeline between pairs of chains: a bright line marks contact, with simulation time along x and the index of the chain pair along y. (b) Snapshot of two chains in contact.

A1 (forward) 5′-GTTCCAGCTGTTGGTG

A2 (reverse) 5′-ACCTACTGCTGGTACG

B1 (forward) 5′-TACTTCCAATCCAATGCCGTTCCAGCTGTTGGTGTGCCG

B2 (reverse) 5′-TTATCCACTTCCAATGTTAACCTACTGCTGGTACGCCGAC

VPAVG OERCA single-stranded template

/5Phos/GTTCCAGCTGTTGGTGTGCCGGCCGTGGGCGTGCCTGC
GGTGGGCGTCCCGGCGGTCGGCGTACCAGCAGTAGGT

Figure S9: Oligonucleotide primers and the 5′-phosphorylated single-stranded OERCA template used to construct the ELP genes.




Figure S10: Conversion of the SAXS intensity to an absolute scattering cross section with the upstream and downstream ion chambers. (a) Photon count measured by a PIN diode against the upstream ion-chamber reading across the attenuation series, with the linear fit used to convert the ion-chamber signal to incident flux. The unattenuated point lies off the line defined by the others and is not shown or fitted. (b) Transmission of the air path between the upstream and downstream ion chambers across the same seven measurements, and its mean.




Figure S11: SAXS of single acquisitions shows no radiation-induced structural change. $I(Q)$ of the twelve consecutive subsets of 8,333 frames of one 100 000-frame acquisition of $(\mathrm{VPAVG})_{10}$, (a) the first acquisition of the heating ramp, at 20.0 °C, and (b) the last, at 45.2 °C. Each subset is restored to its own mean intensity and the twelve are placed on the photons-per-pixel-per-frame scale of the whole acquisition.




Figure S12: XPCS dynamics remain stable throughout an acquisition. g_2 at $Q = 0.0038\,\text{Å}^{-1}$ for the ten heating sections of $(\text{VPAVG})_{10}$ (Figure 3), correlated from all 100,000 frames of each acquisition (circles), from the first 50,000 (squares) and from the last 50,000 (triangles). The y axis is capped at 0.98, so a few short-delay points of the coldest sections fall below it.




Figure S13: Varying the X-ray flux does not alter the measured structure or dynamics. (a) SAXS intensity and (b) intensity autocorrelation function of a $20\,\text{mg}\,\text{mL}^{-1}$ $(\text{VPAVG})_{30}$ sample at four incident fluxes, recovered for each measurement from its upstream ion-chamber reading and keyed in the legend.

References

[1] Amiram, M.; Quiroz, F. G.; Callahan, D. J.; Chilkoti, A. A highly parallel method for synthesizing DNA repeats enables the discovery of 'smart' protein polymers. *Nat. Mater.* **2011**, *10*, 141–148.

[2] Aslanidis, C.; de Jong, P. J. Ligation-independent cloning of PCR products (LIC-PCR). *Nucleic Acids Res.* **1990**, *18*, 6069–6074.

[3] Eschenfeldt, W. H.; Lucy, S.; Millard, C. S.; Joachimiak, A.; Mark, I. D. A family of LIC vectors for high-throughput cloning and purification of proteins. *Methods Mol. Biol.* **2009**, *498*, 105–115.

[4] Kim, Y.; Babnigg, G.; Jedrzejczak, R.; Eschenfeldt, W. H.; Li, H.; Maltseva, N.; Hatzos-Skintges, C.; Gu, M.; Makowska-Grzyska, M.; Wu, R.; An, H.; Chhor, G.; Joachimiak, A. High-throughput protein purification and quality assessment for crystallization. *Methods* **2011**, *55*, 12–28.

[5] Makowska-Grzyska, M.; Kim, Y.; Maltseva, N.; Li, H.; Zhou, M.; Joachimiak, G.; Babnigg, G.; Joachimiak, A. Protein production for structural genomics using E. coli expression. *Methods Mol. Biol.* **2014**, *1140*, 89–105.

[6] Ozgulbas, D. Y.; Jensen, D.; Butler, R.; Vescovi, R.; Foster, I. T.; Irvin, M.; Nakaye, Y.; Chu, M.; Dufresne, E. M.; Seifert, S.; Babnigg, G.; Ramanathan, A.; Zhang, Q. Robotic pendant drop: containerless liquid for μs-resolved, AI-executable XPCS. *Light: Science & Applications* **2023**, *12*, 196.

[7] Ozgulbas, D. github.com/AD-SDL/ur_module. 2024; `https://github.com/AD-SDL/ur_module`.

[8] Vescovi, R. et al. Towards a modular architecture for science factories. *Digit. Discov.* **2023**, *2*, 1980–1998.

[9] Otsu, N. A Threshold Selection Method from Gray-Level Histograms. *IEEE Transactions on Systems, Man, and Cybernetics* **1979**, *9*, 62–66.

[10] Du, M. github.com/AdvancedPhotonSource/auto_beamline_ops. 2024; `https://github.com/AdvancedPhotonSource/auto_beamline_ops`.

[11] Switalski, K.; Fan, J.; Li, L.; Chu, M.; Sarnello, E.; Jemian, P.; Li, T.; Wang, Q.; Zhang, Q. Direct measurement of Stokes-Einstein diffusion of Cowpea mosaic virus with 19 µs-resolved XPCS. *Journal of Synchrotron Radiation* **2022**, *29*, 1429–1435.

[12] Sheyfer, D.; Zhang, Q.; Lal, J.; Loeffler, T.; Dufresne, E. M.; Sandy, A. R.; Narayanan, S.; Sankaranarayanan, S. K. R. S.; Szczygiel, R.; Maj, P.; Soderholm, L.; Antonio, M. R.; Stephenson, G. B. Nanoscale Critical Phenomena in a Complex Fluid Studied by X-Ray Photon Correlation Spectroscopy. *Phys. Rev. Lett.* **2020**, *125*, 125504.

[13] Advanced Photon Source 12-ID-B Home Page and Detector Configuration. Advanced Photon Source, Argonne National Laboratory, 2026; `https://www.aps.anl.gov/Sector-12/12-ID-B`, Accessed July 22, 2026.

[14] Xu, L.; Wang, Z.; Chen, J.; Chen, S.; Yang, W.; Ren, Y.; Zuo, X.; Zeng, J.; Wu, Q.; Sheng, H. Folded Network and Structural Transition in Molten Tin. *Nature Communications* **2022**, *13*, 126.

[15] Zheng, C. Y.; Yao, Y.; Deng, J.; Seifert, S.; Wong, A. M.; Lee, B.; Mirkin, C. A. Confined Growth of DNA-Assembled Superlattice Films. *ACS Nano* **2022**, *16*, 4813–4822.

[16] Sunde, M.; Serpell, L. C.; Bartlam, M.; Fraser, P. E.; Pepys, M. B.; Blake, C. C. F. Common Core Structure of Amyloid Fibrils by Synchrotron X-Ray Diffraction. *Journal of Molecular Biology* **1997**, *273*, 729–739.

[17] Sawaya, M. R.; Sambashivan, S.; Nelson, R.; Ivanova, M. I.; Sievers, S. A.; Apostol, M. I.; Thompson, M. J.; Balbirnie, M.; Wiltzius, J. J. W.; McFarlane, H. T.; Madsen, A. Ø.; Riekel, C.; Eisenberg, D. Atomic Structures of Amyloid Cross-β Spines Reveal Varied Steric Zippers. *Nature* **2007**, *447*, 453–457.

[18] Chu, M. github.com/AZjk/llps-saxpcs. 2022; `https://github.com/AZjk/llps-saxpcs`, GitHub Repository hosting the python code used for SA-XPCS data reduction and figure rendering.