

1	5	0	7	PHYSICAL PROPERTIES				23°C
HARDNESS, ASTM D2240, IRHD				55.000	45.000	50.000	PTS	OK
TENSILE STRENGTH, ASTM D412, MIN					7.000	12.000	MPA	OK
ULTIMATE ELONGATION, ASTM D412, MIN					225.000	345.000	%	OK
SPECIFIC GRAVITY, ASTM D297				1.230	1.170	1.200	—	OK

2	A	2	6	HEAT RESISTANCE, ASTM D865, 70H				150°C
CHANGE IN HARDNESS				10.000		2.000	PTS	OK
CHANGE IN TENSILE STRENGTH					-25.000	1.000	%	OK
CHANGE IN ULTIMATE ELONGATION					-30.000	-3.000	%	OK

3	B	1	6	COMPRESSION SET, ASTM D395, 22H, METHOD B, SOLID				150°C
COMPRESSION SET				50.000		11.000	%	OK

4	EO	1	6	OIL RESISTANCE, ASTM D471, ASTM OIL IRM 901, 70H				150°C
CHANGE IN HARDNESS				15.000	-8.000	4.000	PTS	OK
CHANGE IN TENSILE STRENGTH					-20.000	2.000	%	OK
CHANGE IN ULTIMATE ELONGATION					-30.000	6.000	%	OK
CHANGE IN VOLUME				10.000	-5.000	-1.000	%	OK

5	EO	3	6	OIL RESISTANCE, ASTM D471, ASTM OIL IRM 903, 70H				150°C
CHANGE IN HARDNESS					-30.000	-9.000	PTS	OK
CHANGE IN TENSILE STRENGTH					-60.000	-32.000	%	OK
CHANGE IN ULTIMATE ELONGATION					-40.000	-30.000	%	OK
CHANGE IN VOLUME				50.000		45.000	%	OK