

8	EO	3	4	OIL RESISTANCE, ASTM D471, ASTM OIL IRM 903, 70H					100°C
CHANGE IN HARDNESS				5.000	-10.000	-0.300	PTS	OK	
CHANGE IN TENSILE STRENGTH					-45.000	-8.000	%	OK	
CHANGE IN ULTIMATE ELONGATION					-45.000	-13.000	%	OK	
CHANGE IN VOLUME				25.000	0.000	3.200	%	OK	