

1	9	1	0	PHYSICAL PROPERTIES				23°C
	HARDNESS, ASTM D2240, SHORE A			90.000	80.000	82.000	PTS	OK
	TENSILE STRENGTH, ASTM D412, MIN				10.000	10.800	MPA	OK
	ULTIMATE ELONGATION, AS 測試內容 2[tc_vbb14]				100.000	120.000	%	OK
	SPECIFIC GRAVITY, ASTM D297			1.870	1.810	1.840	—	OK

2	A	1	11	HEAT RESISTANCE, ASTM D573, 70H				275°C
	CHANGE IN HARDNESS			10.000	-5.000	-1.000	PTS	OK
	CHANGE IN TENSILE STRENGTH				-40.000	21.000	%	OK
	CHANGE IN ULTIMATE ELONGATION				-20.000	-17.000	%	OK

3	B	3	8	COMPRESSION SET, ASTM D395, 22H, METHOD B, PLIED				200°C
	COMPRESSION SET			15.000		8.000	%	OK

4	EF	3	1	FLUID RESISTANCE, ASTM D471, REFERENCE FUEL C, 70H				23°C
	CHANGE IN HARDNESS			5.000	-5.000	-5.000	PTS	OK
	CHANGE IN TENSILE STRENGTH				-25.000	-15.000	%	OK
	CHANGE IN ULTIMATE ELONGATION				-20.000	-20.000	%	OK
	CHANGE IN VOLUME			10.000	0.000	3.700	%	OK

5	EO	7	8	OIL RESISTANCE, ASTM D471, SERVICE LIQUID NO.101, 70H				200°C
	CHANGE IN HARDNESS			20.000	-20.000	-8.000	PTS	OK
	CHANGE IN TENSILE STRENGTH			20.000	-20.000	-9.600	%	OK
	CHANGE IN ULTIMATE ELONGATION			40.000	-40.000	-22.700	%	OK
	CHANGE IN VOLUME			40.000	-40.000	22.100	%	OK

6	EO	1	6	OIL RESISTANCE, ASTM D471, ASTM OIL IRM 901, 70H				150°C
	CHANGE IN HARDNESS			10.000	-10.000	-2.000	PTS	OK
	CHANGE IN TENSILE STRENGTH			20.000	-20.000	7.000	%	OK
	CHANGE IN ULTIMATE ELONGATION			20.000	-20.000	-6.000	%	OK
	CHANGE IN VOLUME			10.000	-10.000	0.830	%	OK

7	EO	3	6	OIL RESISTANCE, ASTM D471, ASTM OIL IRM 903, 70H				150°C
	CHANGE IN HARDNESS			10.000	-10.000	-2.000	PTS	OK
	CHANGE IN TENSILE STRENGTH			20.000	-20.000	-7.000	%	OK
	CHANGE IN ULTIMATE ELONGATION			20.000	-20.000	-10.000	%	OK
	CHANGE IN VOLUME			10.000	-10.000	1.720	%	OK