

1	8	1	4	PHYSICAL PROPERTIES					23°C
HARDNESS, ASTM D2240, SHORE A				85.000	75.000	80.800	PTS	OK	
TENSILE STRENGTH, ASTM D412, MIN					14.000	14.110	MPA	OK	
ULTIMATE ELONGATION, ASTM D412, MIN					125.000	193.000	%	OK	
SPECIFIC GRAVITY, ASTM D297						1.290	—	OK	
2	A	1	4	HEAT RESISTANCE, ASTM D573, 70H					100°C
CHANGE IN HARDNESS				15.000	-15.000	4.400	PTS	OK	
CHANGE IN TENSILE STRENGTH				30.000	-30.000	8.000	%	OK	
CHANGE IN ULTIMATE ELONGATION					-50.000	-15.000	%	OK	
CHANGE IN VOLUME						-3.200	%	OK	
3	B	1	4	COMPRESSION SET, ASTM D395, 22H, METHOD B, SOLID					100°C
COMPRESSION SET				25.000		8.000	%	OK	
4	E0	1	4	OIL RESISTANCE, ASTM D471, ASTM OIL IRM 901, 70H					100°C
CHANGE IN HARDNESS				10.000	-5.000	8.800	PTS	OK	
CHANGE IN TENSILE STRENGTH					-25.000	6.000	%	OK	
CHANGE IN ULTIMATE ELONGATION					-45.000	-20.000	%	OK	
CHANGE IN VOLUME				5.000	-10.000	-7.600	%	OK	
5	E0	3	4	OIL RESISTANCE, ASTM D471, ASTM OIL IRM 903, 70H					100°C
CHANGE IN HARDNESS				5.000	-10.000	-0.800	PTS	OK	
CHANGE IN TENSILE STRENGTH					-45.000	6.000	%	OK	
CHANGE IN ULTIMATE ELONGATION					-45.000	-21.000	%	OK	
CHANGE IN VOLUME				25.000	0.000	5.300	%	OK	
6	F	1	7	LOW-TEMP. RESISTANCE, ASTM D2137, METHOD A, 3 MIN					-40°C
NONBRITTLE AFTER 3 MIN							PASS	OK	