

項次	SUFFIX LETTER	FIRST LETTER No	SECOND LETTER No	測 標準上限	試 標準下限	項 目 容測值	單位	測試溫度 結果	
1	Z	1		PHYSICAL PROPERTIES				23℃	
				HARDNESS, ASTM D2240, SHORE A	75.000	65.000	70.000	PTS	OK
				TENSILE STRENGTH, ASTM D412, MIN		7.000	15.100	MPA	OK
				ULTIMATE ELONGATION, ASTM D412, MIN	550.000	250.000	299.300	%	OK
				SPECIFIC GRAVITY, ASTM D297	1.240	1.180	1.210	—	OK
				MODULUS AT 100%, ASTM D412, MIN			3.800	MPA	OK
2	Z	2		HEAT RESISTANCE, ASTM D573, 70H				100℃	
				CHANGE IN HARDNESS	3.000		0.000	PTS	OK
				CHANGE IN TENSILE STRENGTH		7.000	14.070	MPA	OK
				CHANGE IN ULTIMATE ELONGATION	550.000	200.000	306.240	%	OK

3	Z	3		FLUID RESISTANCE (WATER:METHANOL=1:1), 96 H					50°C
					5.000	-4.000	-4.000	PTS	OK
						6.000	13.120	MPA	OK
					550.000	200.000	335.560	%	OK
					5.000	-4.000	1.500	%	OK
					10.000		6.000	%	OK