

1	B	0	6	PHYSICAL PROPERTIES				23°C
HARDNESS, ASTM D2240, SHORE A				80.000	70.000	70.800	PTS	OK
TENSILE STRENGTH, ASTM D412, MIN					6.000	11.100	MPA	OK
ULTIMATE ELONGATION, ASTM D412, MIN					100.000	293.300	%	OK
SPECIFIC GRAVITY, ASTM D297						1.380		OK
2	A	2	6	HEAT RESISTANCE, ASTM D665, 70H				150°C
CHANGE IN HARDNESS				10.000		1.000	PTS	OK
CHANGE IN TENSILE STRENGTH					-25.000	1.900	%	OK
CHANGE IN ULTIMATE ELONGATION					-30.000	-19.500	%	OK
CHANGE IN VOLUME						-2.500	%	OK

3	B	1	6	COMPRESSION SET, ASTM D395, 22H, METHOD B, SOLID				150°C
COMPRESSION SET				60.000		16.000	%	OK

4	E0	1	6	OIL RESISTANCE, ASTM D471, ASTM OIL IRM 901, 70H				150°C
CHANGE IN HARDNESS				10.000	-5.000	4.000	PTS	OK
CHANGE IN TENSILE STRENGTH					-20.000	-1.200	%	OK
CHANGE IN ULTIMATE ELONGATION					-40.000	-7.200	%	OK
CHANGE IN VOLUME				5.000	-5.000	-1.500	%	OK

5	E0	3	6	OIL RESISTANCE, ASTM D471, ASTM OIL IRM 903, 70H				150°C
CHANGE IN HARDNESS					-15.000	-10.000	PTS	OK
CHANGE IN TENSILE STRENGTH					-40.000	-22.500	%	OK
CHANGE IN ULTIMATE ELONGATION					-40.000	-31.000	%	OK
CHANGE IN VOLUME				25.000		11.500	%	OK