

惠州麥豐全面物性檢測報告

料号		NN5025MA		检测日期	24/11/14	
ASTM D2000		ASTM D2000 M2BG 510 A14 B14 B34 EA14 EF11 EF21 E014 E034 F17				
序號	檢測項目		檢測條件/要求	標準	检测数据	判定
1	硬度		Shore A	50±5	51.9	OK
2	抗張強度/ MPA		N/A	≥10	10.9	OK
3	伸長率/%		N/A	≥300	690	OK
4	壓縮歪%		100℃/ 22 H	≤25	23.6	OK
5	A14	硬度變化	100℃/ 70H	-	3.6	OK
		抗張強度變化率%		-	9.2	OK
		伸長率變化率%		-	-14.3	OK
6	E014	硬度變化	100℃/ 70H	-5~10	9.5	OK
		抗張強度變化率%		≥-25	17.8	OK
		伸長率變化率%		≥-45	-13.2	OK
		体积变化率%		-10~5	-9.2	OK
7	E034	硬度變化	100℃/ 70H	5~-10	-5.2	OK
		抗張強度變化率%		≥-45	-2.8	OK
		伸長率變化率%		≥-45	-13.6	OK
		体积变化率%		0~25	3.5	OK
8	EF11	硬度變化	23℃/ 70H	-10~10	-4.7	OK
		抗張強度變化率%		≥-25	-10.6	OK
		伸長率變化率%		≥-25	-4.2	OK
		体积变化率%		-5~10	1.5	OK
9	EF21	硬度變化	23℃/ 70H	-30~0	-17.1	OK
		抗張強度變化率%		≥-60	-59.4	OK
		伸長率變化率%		≥-60	-44.4	OK
		体积变化率%		0~40	22.3	OK
10	EA14	硬度變化	100℃/ 70H	-10~10	-6.3	OK
		抗張強度變化率%		-	-7.5	OK
		伸長率變化率%		-	-12.5	OK
		体积变化率%		-15~15	7.5	OK
9	F17	耐低温	-40℃/ 3MIN	未做		

核准: 張記輝

品保審核: 廖國新
原料審核: 廖國明

檢測: 王少

表單編號: FM02026 版次: 1.1