


惠州麥豐全面物性檢測報告

料号		NN9076MA		检测日期	24/11/06	
ASTM D2000		M7BG 910 A14 B14 EA14 EF11 EF21 E014 E034				
序號	檢測項目		檢測條件/要求	標準	检测数据	判定
1	硬度		Shore A	90±5	90.7	OK
2	抗張強度/ MPA		N/A	≧10	17.8	OK
3	伸長率/%		N/A	≧100	171	OK
4	比重		N/A	1.25~1.31	1.3	OK
5	壓縮歪%		100℃/ 22 H	≦25	21	OK
6	A14	硬度變化	100℃/ 70H	-15~15	1.5	OK
		抗張強度變化率%		-30~30	7.1	OK
		伸長率變化率%		≧-50	-17.4	OK
7	E014	硬度變化	100℃/ 70H	-5~5	3.5	OK
		抗張強度變化率%		≧-25	11.6	OK
		伸長率變化率%		≧-45	-15.4	OK
		体积变化率%		-10~5	-3.7	OK
8	E034	硬度變化	100℃/ 70H	5~-10	-5.5	OK
		抗張強度變化率%		≧-45	-12	OK
		伸長率變化率%		≧-45	-13.7	OK
		体积变化率%		0~25	7.01	OK
9	EF11	硬度變化	23℃/ 70H	-10~10	-2	OK
		抗張強度變化率%		≧-25	-3.7	OK
		伸長率變化率%		≧-25	2.2	OK
		体积变化率%		-5~10	1.2	OK
10	EF21	硬度變化	23℃/ 70H	-30~0	-15	OK
		抗張強度變化率%		≧-60	-37.5	OK
		伸長率變化率%		≧-60	-40.7	OK
		体积变化率%		0~40	23.2	OK
11	EA14	硬度變化	100℃/ 70H	-10~10	-14.5	OK
		体积变化率%		-15~15	7.5	OK

核准:



品保審核:
原料審核:



檢測:



表單編號: FM02026 版次: 1.1