

**Phase-field Approach to Studying Shape Memory Effects and  
Thermomechanical Properties of Low Dimensional Nanostructures**

**Melnik. R., Wang, L.X.**

**Advanced Research in Physics and Engineering (in book series:  
Mathematics and Computers in Science and Engineering),  
Eds. Martin, O. et al,  
Proceedings of the 2nd International Conference on Nanotechnology  
(University of Cambridge, UK, February 20-22, 2010),  
pp. 125--130, 2010.**





**Editors:**

Prof. Olga Martin, University "Politehnica" of Bucharest, ROMANIA

Prof. Alain Walcarius, CNRS - Nancy Universite, FRANCE

Prof. Mohamed Henini, University of Nottingham, UK

Prof. Anthony P. F. Turner, Cranfield University, UK

Prof. Mohsen Adeli, Sharif University, IRAN

Prof. Donald Lynden-Bell, University of Cambridge, UK

# ADVANCED RESEARCH IN PHYSICS AND ENGINEERING

Proceedings of the 2<sup>nd</sup> WSEAS International Conference on  
Nanotechnology (NANOTECHNOLOGY '10)

Proceedings of the 5<sup>th</sup> WSEAS International Conference on  
Optics - Astrophysics - Astronomy (ICOAA '10)

Proceedings of the 1<sup>st</sup> WSEAS International Conference on  
Plasma- Fusion - Nuclear Physics (IPLAFUN '10)

University of Cambridge, UK  
February 20-22, 2010

Mathematics and Computers in Science and Engineering  
A Series of Reference Books and Textbooks

ISBN: 978-960-474-163-2  
ISSN: 1790-5117

Published by WSEAS Press  
[www.wseas.org](http://www.wseas.org)



ADVANCED RESEARCH IN PHYSICS AND ENGINEERING





# **ADVANCED RESEARCH in PHYSICS and ENGINEERING**

**Proceedings of the 2nd WSEAS International Conference on  
NANOTECHNOLOGY (NANOTECHNOLOGY '10)  
Proceedings of the 5th WSEAS International Conference on OPTICS  
- ASTROPHYSICS - ASTRONOMY (ICOAA '10)  
Proceedings of the 1st WSEAS International Conference on  
PLASMA- FUSION - NUCLEAR PHYSICS (IPLAFUN '10)**

**University of Cambridge, UK  
February 20-22, 2010**

Mathematics and Computers in Science and Engineering  
A Series of Reference Books and Textbooks

Published by WSEAS Press  
[www.wseas.org](http://www.wseas.org)

ISSN: 1790-5117  
ISBN: 978-960-474-163-2

# **ADVANCED RESEARCH in PHYSICS and ENGINEERING**

**Proceedings of the 2nd WSEAS International Conference on  
NANOTECHNOLOGY (NANOTECHNOLOGY '10)**

**Proceedings of the 5th WSEAS International Conference on OPTICS  
- ASTROPHYSICS - ASTRONOMY (ICOAA '10)**

**Proceedings of the 1st WSEAS International Conference on  
PLASMA- FUSION - NUCLEAR PHYSICS (IPLAFUN '10)**

**University of Cambridge, UK  
February 20-22, 2010**

Mathematics and Computers in Science and Engineering  
A Series of Reference Books and Textbooks

Published by WSEAS Press  
[www.wseas.org](http://www.wseas.org)

**Copyright © 2010, by WSEAS Press**

All the copyright of the present book belongs to the World Scientific and Engineering Academy and Society Press. All rights reserved. No part of this publication may be reproduced, stored in a retrieval system, or transmitted in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of the Editor of World Scientific and Engineering Academy and Society Press.

All papers of the present volume were peer reviewed by two independent reviewers. Acceptance was granted when both reviewers' recommendations were positive.  
See also: <http://www.worldses.org/review/index.html>

ISSN: 1790-5117  
ISBN: 978-960-474-163-2



World Scientific and Engineering Academy and Society

# Phase-field Approach to Studying Shape Memory Effects and Thermomechanical Properties of Low Dimensional Nanostructures

RODERICK MELNIK

Wilfrid Laurier University

M2NeT Laboratory, Department of Mathematics

75 University Ave W., Waterloo, ON N2L 3C5

CANADA

rmelnik@wlu.ca

LINXIANG WANG

Hangzhou Dianzi University

Faculty of Mechanical Engineering

Xiasha, Hangzhou, 310018

P.R. CHINA

**Abstract:** We focus on the development of mesoscopic models for the description of strongly nonlinear coupled thermomechanical effects, such as shape memory effects, in low dimensional nanostructures. The main model is a result of the phase-field approach which we extend to the present problems from our previous works on ferroelectrics. The resulting coupled system of partial differential equations is solved based on a combination of the Chebyshev collocation method and the extended proper orthogonal decomposition. The developed model and its numerical implementation allow us to study properties of nanostructures and we present macrostructure computations for nanowires and nanoplates.

**Key-Words:** Nanostructures, Shape Memory Effect, Nonlinear Thermomechanics, Mesoscopic Models, Size-dependent Effects, Dynamics, Phase Transformations, Galerkin projection, Coupled Problems.

## 1 Introduction

Low dimensional semiconductor nanostructures have many applications in nanotechnology, but they provide serious theoretical and computational challenges when it comes to the prediction of their properties [4]. This especially true when we need to account for finite size effects as it is the case, for example, for finite length nanowires [14]. Coupled effects in nanostructures are also their intrinsic feature that must be accounted for better [12]. One such effect, namely piezoelectric, has been studied for a long time and is known to have important consequences on bandstructure calculations of low dimensional nanostructures. More recently, the importance of thermal effects has been demonstrated in the context of their coupling to electromechanical fields [15, 16]. While many such effects are linear, the importance of nonlinear effects have recently been also emphasized in [13]. It was shown that the applicability of linear models is limited for low dimensional nanostructures, in particular quantum dots, and both coupled and nonlinear effects need to be accounted for in the analysis of more realistic structures. In this contribution, we continue research along this direction and analyze the nonlinear coupling between mechanical and thermal fields in SMA-based nanowires. We use some generalizations of ideas originally developed for ferroelectric materials to arrive to a model based on a system of coupled partial differential equations [24, 25]. The

resulting system can be solved efficiently by several different methodologies such as finite volume [20] or finite element methods [5]. In this paper, we apply the Chebyshev collocation method for the solution of the resulting problem, followed by the application of an extended proper orthogonal decomposition as was proposed in [18, 19].

To get started, we recall that it has been known for some time that in gold (Au) nanowires, the energy as a function of lattice spacing exhibits two distinct minima that correspond to fcc and bcc phases. The fact that these nanowires exhibit shape memory effects has also been confirmed computationally with such methodologies as tight-binding and density functional theory. A similar situation holds for many other nanowires that show substantial potential for many applications in nano- and bio-nanotechnologies, including Cu, Ni, ZnO, FePd, Al, Ag, etc.

While many results up to date have been obtained for infinitely long nanowires (as well as for infinitely large nanoplates), including those obtained with *ab initio* calculations, the question has remained on whether phase transformations is a generic effect for the same material-type nanowires of finite length. Recently, there has been mounting evidence towards a positive answer to this question. However, comprehensive studies of finite nanowires and nanoplates are limited due to the fact that the methodologies applied for their studies are computationally expensive.

In this contribution, we present a relatively simple and computationally inexpensive model to study phase transformations in finite nanostructures with our major focus given here to finite nanowires and nanoplates. Based on our previous results, the models describing shape memory effects at the mesoscopic level for the case of square-to-rectangle transformations can be reduced to a two-dimensional case.

Before moving to the model construction, we shall note that martensitic transformations at the nanoscale have received substantial attention from experimentalists. A number of alloys that undergo these transformations have recently been studied in [17] where the results of transmission electron microscopy studies were reported.

## 2 Mathematical Model

To account for the first order phase transformations in ferroelastic materials such as shape memory alloys, time-dependent models of coupled dynamic thermoelasticity must account for a nonconvex highly nonlinear character of the associated free energy function. We start with the following 1D mathematical model [10, 7]:

$$\begin{aligned} \rho \frac{\partial^2 u}{\partial t^2} &= \frac{\partial}{\partial x} \left( k_1 (\theta - \theta_1) \frac{\partial u}{\partial x} - k_2 \left( \frac{\partial u}{\partial x} \right)^3 + k_3 \left( \frac{\partial u}{\partial x} \right)^5 \right) + \nu \frac{\partial}{\partial t} \frac{\partial^2 u}{\partial x^2} - \delta \frac{\partial^4 u}{\partial x^4} + F, \\ c_v \frac{\partial \theta}{\partial t} &= k \frac{\partial^2 \theta}{\partial x^2} + k_1 \theta \frac{\partial u}{\partial x} \frac{\partial v}{\partial x} + G, \end{aligned} \quad (1)$$

where  $u$  is displacement,  $\theta$  temperature,  $\rho$  density,  $k_1, k_2, k_3, c_v, \nu, \delta$  and  $k$  are normalized material-specific constants,  $\theta_1$  is the reference temperature for 1D martensitic transformations, and  $F$  and  $G$  are distributed mechanical and thermal loadings. The interested reader can find efficient numerical procedures for reducing systematically the general 3D model to models such as (1) in [10].

Although this is only a 1D model for the nonlinear dynamics of ferroelastic materials, it presents a number of challenges in its analysis and numerical implementation due to the coupling between thermal and elastic fields and strong nonlinearities. Furthermore, the inclusion of thermal and mechanical hystereses and the first order martensitic transformations into the model gives additional difficulties. First, we re-write the above system for numerical convenience

as follows [7]:

$$\begin{aligned} c_v \frac{\partial \theta}{\partial t} &= k \frac{\partial^2 \theta}{\partial x^2} + k_1 \theta \epsilon \frac{\partial v}{\partial x} + G, \quad \frac{\partial \epsilon}{\partial t} = \frac{\partial v}{\partial x} \\ \rho \frac{\partial v}{\partial t} &= \frac{\partial}{\partial x} (k_1 (\theta - \theta_1) \epsilon - k_2 \epsilon^3 + k_3 \epsilon^5) + \\ \nu \frac{\partial}{\partial t} \frac{\partial^2 u}{\partial x^2} &- \delta \frac{\partial^3 \epsilon}{\partial x^3} + F, \end{aligned} \quad (2)$$

where  $\epsilon = \partial u / \partial x$  is the strain, and  $v = \partial u / \partial t$  is the velocity. Note that this representation is convenient for a reduction of the original PDE-based model to a system of differential-algebraic equations the approach that was initiated in [8].

More generally, our consideration in this paper is based on the nonlocal model developed in [10] based on the equation of motion

$$\rho \frac{\partial^2 \mathbf{u}}{\partial t^2} = \nabla_{\mathbf{x}} \cdot \mathbf{s} + \mathbf{F} \quad \text{with} \quad \mathbf{F} = \rho(\mathbf{f} + \hat{\mathbf{f}}) - \hat{\rho} \mathbf{v}, \quad (3)$$

and the energy balance equation

$$\rho \frac{\partial e}{\partial t} - \mathbf{s}^T : (\nabla \mathbf{v}) + \nabla \cdot \mathbf{q} = g, \quad (4)$$

where  $\mathbf{u}$  is the displacement vector,  $\rho$  is the density of the material,  $e$  is the internal energy (per unit mass),  $\mathbf{q}$  is the heat flux,  $\mathbf{f}$  is a given body force per unit mass,  $\hat{\rho}$  and  $\hat{\mathbf{f}}$  are nonlocal mass and force residuals respectively (similarly,  $g$  accounts for both local and non-local contributions),  $\mathbf{v} = \partial \mathbf{u} / \partial t$  is the velocity

vector,  $\mathbf{s}$  is the stress tensor,  $\mathbf{a}^T : \mathbf{b} = \sum_{i,j=1}^3 a_{ij} b_{ij}$  is

the standard notation for the rank 2 tensors  $\mathbf{a}$  and  $\mathbf{b}$  (further details can be found in [10]). The constitutive relationships that couple stresses, deformation gradients, temperature and heat fluxes have the following general form:

$$\Phi_1(\mathbf{s}, \epsilon) = 0, \quad \Phi_2(\mathbf{q}, \theta) = 0, \quad (5)$$

where it is implicitly assumed that these relations may involve spatial and temporal derivatives of the functions. Particular forms for  $\Phi_1$  and  $\Phi_2$  are problem specific. In dealing with phase transformations, the approach adopted in this paper is based on the Landau criterion stating that any isothermal equilibrium configuration of the lattice corresponds to a minimum (global or local) of the free energy function.

In order to characterize both, austenite at high temperature and martensite at low temperature, having in mind the analysis of finite length nanowires and other low dimensional nanostructures, by using a generic expression, the potential energy is constructed

on the basis of the modified Ginzburg-Landau free energy function. We follow [23] to get the evolution equations for our case as follows:

$$\frac{\partial^2 u_1}{\partial t^2} = \frac{\partial \sigma_{11}}{\partial x} + \frac{\sigma_{12}}{\partial y} + f_1, \quad (6)$$

$$\frac{\partial^2 u_2}{\partial t^2} = \frac{\partial \sigma_{12}}{\partial x} + \frac{\sigma_{22}}{\partial y} + f_2, \quad (7)$$

$$c_v \frac{\partial T}{\partial t} = k \left( \frac{\partial^2 T}{\partial x^2} + \frac{\partial^2 T}{\partial y^2} \right) + \quad (8)$$

$$a_2 T e_2 \frac{\partial e_2}{\partial t} + g \quad (9)$$

with

$$\sigma_{11} = \frac{\sqrt{2}}{2} \rho (a_1 e_1 + a_2 (T - T_0) e_2 - a_4 e_2^3) \quad (10)$$

$$a_6 e_2^5) + \frac{d_2}{2} \nabla_x^2 e_2, \quad \sigma_{12} = \frac{1}{2} \rho a_3 e_3 = \sigma_{21}, \quad (11)$$

$$\sigma_{22} = \frac{\sqrt{2}}{2} \rho (a_1 e_1 - a_2 (T - T_0) e_2 + a_4 e_2^3) \quad (12)$$

$$a_6 e_2^5) + \frac{d_2}{2} \nabla_y^2 e_2, \quad (13)$$

where all the notation here are identical to those of [23].

### 3 Numerical approximations

A similar model has been recently applied in [1]. As we have already mentioned, under appropriate boundary and initial conditions, the models like this can be efficiently solved with several recently developed numerical methodologies, including the Chebyshev collocation procedure [21], the proper orthogonal decomposition [19], the genetic algorithm based optimization procedure [22], and the finite volume methodology [20], as well as finite element techniques [6].

For the sake of convenience, the governing equations are re-written in the form of evolution operator equation:

$$\frac{d\mathcal{U}}{dt} = \mathcal{M}(\mathcal{U}), \quad (14)$$

where  $\mathcal{U}$  is the solution and  $\mathcal{M}(\mathcal{U})$  is an operator which contains all the spatial derivatives of  $\mathcal{U}$ . In general, the approximation given by our model will not satisfy Eq.(14), i.e., the residual

$$\mathcal{R} = \frac{d\mathcal{U}^N}{dt} - \mathcal{M}(\mathcal{U}^N) \quad (15)$$

will not vanish everywhere. To determine all the expansion coefficients, the Galerkin method requires the

following condition to be satisfied:

$$\int_0^L \left( \frac{d\mathcal{U}^N}{dt} - \mathcal{M}(\mathcal{U}^N) \right) \psi_i(x) dx = 0, \quad (16)$$

where  $\psi_i(x)$  are the test functions.

In the Chebyshev collocation methods the trial functions are chosen to satisfy the following conditions:

$$\phi_i(x_j) = \begin{cases} 1, & i=j, \\ 0, & i \neq j. \end{cases} \quad (17)$$

and the test functions are chosen as:

$$\psi_i(x) = \delta(x_i) = \begin{cases} 1, & x=x_i, \\ 0, & x \neq x_i, \end{cases} \quad (18)$$

where  $\{x_i\}$  is a set of chosen discretization points in the computational domain. For the Chebyshev approximation, it is chosen as follows:

$$x_i = L \left( 1 - \cos\left(\frac{\pi i}{N}\right) \right) / 2, \quad i = 0, 1, \dots, N, \quad (19)$$

where  $L$  is the length of the considered ferroelastic rod.

Following the standard procedure, our equation can be written in a matrix form as:

$$\mathbf{U}_x = \mathbf{D}\mathbf{U}. \quad (20)$$

By substituting corresponding approximations of the spatial derivatives, the PDE-based model is converted into a set of Differential-Algebraic Equations (DAEs). The idea of a reduction of the original PDE model to a system of DAEs was first proposed in [8], followed by a subsequent development of low dimensional models based on the center manifold technique [10]. The application of an efficient time integrator can finally solve the problem in a way similar discussed earlier [7, 19]. The described methodology allows us to determine the temperature, stress, strain and displacement of the material at any point of the computational domain at any time. Then, the resultant data can be used for the POD analysis. It is carried out in a way similar to that described in [18, 19].

Having obtained optimal basis functions for the dynamical system, its lower dimensional approximation can be obtained by projecting the full system orthogonally onto the subspace spanned by the chosen basis functions (by the Galerkin projection). The model reduction can be achieved due to the fact that much smaller number of basis functions is needed for the approximation of the full system provided the chosen basis functions are optimal in a sense specified above.

### 3.1 Extended POD with Galerkin Projection

From the above described procedure, we obtain a collection of system states, so that the eigenmode series for the approximation to the system dynamics can be constructed using the extended POD method. First we obtain optimal basis functions for our dynamical system, and then its lower dimensional approximation can be obtained by projecting the full system orthogonally onto the subspace spanned by the chosen basis functions. For the current problem, the phase transformation can take place at different temperatures, by either mechanical or thermal stimulations. There may be no phase transformation if the temperature is sufficiently high. In order to model the dynamics of the ferroelastic material correctly, the empirical eigenfunctions have to take into account the temperature influence. Following [26], we choose a few (three) representative temperature values to demonstrate the analysis, in particular those for which the system has only martensite phase (low temperature  $\theta_1$ ), metastable austenite and martensite phases (medium temperature  $\theta_2$ ), or only austenite phase (high temperature  $\theta_3$ ), respectively. We denote the collection of snapshots with initial temperatures  $\theta_i$  as  $U_i$ ,  $i = 1, 2, 3$ . If one employs the POD method directly to all the overall snapshots  $U = [U_1, U_2, U_3]$  by putting all snapshots together, the characteristics of different blocks will be mixed and dispersed with each other, and that is why we are using the extended POD method to construct the eigenmodes using the snapshots collected in all the blocks. Taking all the blocks of snapshots simultaneously into account, the extended POD analysis can be formally represented in the following matrix form:

$$U = \phi C, \quad (21)$$

where

$$U = [U_1 \ U_2 \ U_3], \quad \phi = [\phi_1 \ \phi_2 \ \phi_3] \quad (22)$$

is a collection of snapshots and eigenmodes from each block, while the coefficient matrix is given as follows [3]:

$$C = \begin{bmatrix} C_1 & \phi_1^T U_2 & \phi_1^T U_3 \\ 0 & C_2 & \phi_2^T U_3 \\ 0 & 0 & C_3 \end{bmatrix}, \quad (23)$$

where all the entries in the matrix can be obtained once the blocks of snapshots are provided. For those situations where more snapshot blocks are available, the extended POD can be carried out in a similar manner.

## 4 RESULTS

A number of examples for nanostructures of different geometry and materials have been analyzed with the above model, and in what follows we present only a few representative calculations carried out for iron-based (FePd) nanostructures. Values of parameters for FePd can be found in [1]. In Fig. 1 we observe the formation of microstructures in two nanowires with increasing diameter-to-length ratio (same length, increasing diameter). With decreasing length of the nanowire, the microstructure acquires a more regular pattern as seen in Fig. 2 (left). In all these three cases  $K_g = 1 \times 10^{-4}$ . The analysis of the evolution of the microstructure for a square nanoplate is given in Fig. 2 (right) and Fig. 3. In this case,  $K_g = 5 \times 10^{-5}$ . All the results here have been obtained for  $\theta_0 = 265K$  and presented for  $\theta = 250K$ . A typical number of degree of freedom in these finite element calculations is on the order of 100,000. Results on critical diameters of finite length nanowires will be presented elsewhere. Finally, we note that some initial three-dimensional modelling results with mesoscopic models were presented in [5].




Figure 1: Size dependency of nanowires with increasing diameter-length ratio.






Figure 2: Microstructures in the nanowire of smaller length (left) and in the square nanoplate.

## 5 Conclusions

In this contribution, we focused on the development of mesoscopic phase-field-type models for the description of strongly nonlinear coupled thermomechanical effects. Our main attention was on shape memory effects and phase transformations in low dimensional nanostructures. The resulting model was successfully implemented and solved based on a combination of the Chebyshev collocation method and the extended proper orthogonal decomposition. We reported several representative examples presenting results on the analysis of microstructure evolution in finite nanostructures with the developed models for finite nanowires and nanoplates.

### References:

- [1] M. Bouville and R. Ahluwalia, Microstructure and mechanical properties of constrained shape-memory alloy nanograins and nanowires, *Acta Materialia*, 56, 2008, pp. 3558-3567.
- [2] N. Bubner, Landau-Ginzburg model for a deformation-driven experiment on shape memory alloys, *Continuum Mech. Thermodyn.* 8, 1996, pp. 293-308.
- [3] B.H. Jorgensen, J.N. Sorensen and M. Brons, Low-dimensional modelling of a driven cavity flow




Figure 3: Evolution of microstructure in the square nanoplate.

with two free parameters. *Theor. Comput. Fluid Dynamics* 16, 2003, pp. 299-317.

- [4] B. Lassen, R.V.N. Melnik, RVN, M. Willatzen, Spurious Solutions in the Multiband Effective Mass Theory Applied to Low Dimensional Nanostructures, *Communications in Computational Physics*, 6 (4), 2009, pp. 699-729.
- [5] D.R. Mahapatra and R.V.N. Melnik, Finite element approach to modelling evolution of 3D shape memory materials, *Mathematics and Computers in Simulation*, 76 (1-3), 2007, pp. 141-148.
- [6] D.R. Mahapatra and R.V.N. Melnik. Finite element modelling and simulation of phase transformations in shape memory alloy thin films. *International Journal for Multiscale Computational Engineering*, 5 (1), 2007, pp. 65-71.
- [7] P. Matus, R. Melnik, L. Wang and I. Rybak, Application of fully conservative schemes in nonlinear thermoelasticity: Modelling shape memory materials, *Mathematics and Computers in Simulation* 65(4-5), 2004, pp. 489-509.
- [8] R.V.N. Melnik, A.J. Roberts and K.A. Thomas, Computing dynamics of copper-based SMA via centre manifold reduction of 3D models *Computational Materials Science* 18(3-4), 2000, pp. 255-268.
- [9] R.V.N. Melnik, A.J. Roberts and K.A. Thomas, Coupled Thermomechanical dynamics of phase

- transitions in shape memory alloys and related hysteresis phenomena, *Mechanics Research Communications* 28(6), 2001, pp. 637-651.
- [10] R.V.N. Melnik and A.J. Roberts and K.A. Thomas, Phase transitions in shape memory alloys with hyperbolic heat conduction and differential algebraic models, *Computational Mechanics* 29(1), 2002, pp. 16-26.
- [11] R.V.N. Melnik and A.J. Robert, Modelling nonlinear dynamics of shape memory alloys with approximate models of coupled thermoelasticity, *Zeitschrift für Angewandte Mathematik und Mechanik* 83(2), 2003, pp. 93-104.
- [12] R.V.N. Melnik and A. Povitsky, A special issue on modelling coupled and transport phenomena in nanotechnology, *Journal of Computational and Theoretical Nanoscience*, 3 (4), 2006.
- [13] R. Melnik and R. Mahapatra, Coupled effects in quantum dot nanostructures with nonlinear strain and bridging modelling scales, *Computers & Structures*, 85 (11-14), 2007, pp. 698-711.
- [14] S.R. Patil and R.V.N. Melnik, Coupled electromechanical effects in II-VI group finite length semiconductor nanowires, *Journal of Physics D - Applied Physics*, 42 (14), 2009, Art. No. 145113.
- [15] S.R. Patil and R.V.N. Melnik, Thermopiezoelectric effects on optoelectronic properties of CdTe/ZnTe quantum wires, *Physica Status Solidi A - Applications and Materials Science*, 206 (5), 2009, pp. 960-964.
- [16] S.R. Patil and R.V.N. Melnik, Thermoelectromechanical effects in quantum dots, *Nanotechnology*, 20 (12), 2009, Art. No. 125402.
- [17] D. Schryvers, P. Boullay, P. Potapov and C. Satto, Martensitic transformations studied on nano- and microscopic length scales, *Advances in Solid State Physics*, 40, 2007, pp. 375-387.
- [18] L.X. Wang and R.V.N. Melnik, Mechanically induced phase combination in shape memory alloys by Chebyshev collocation methods, *Materials Science and Engineering A - Structural Materials Properties Microstructure and Processing*, 438, SI, 2006, pp. 427-430.
- [19] L.X. Wang and R.V.N. Melnik, Model reduction applied to square to rectangular martensitic transformations using proper orthogonal decomposition, *Applied Numerical Mathematics*, 57 (5-7), 2007, pp. 510-520.
- [20] L.X. Wang and R.V.N. Melnik, Finite volume analysis of nonlinear thermo-mechanical dynamics of shape memory alloys, *Heat and Mass Transfer*, 43 (6), 2007, pp. 535-546.
- [21] L. Wang and R.V.N. Melnik. Thermo-mechanical wave propagation in shape memory alloy rod with phase transformations. *Mechanics of Advanced Materials and Structures*, 14 (8), 2007, pp. 665-676.
- [22] L. Wang and R.V.N. Melnik. Simulation of phase combinations in shape memory alloys patches by hybrid optimization methods. *Applied Numerical Mathematics*, 58 (4), 2008, pp. 511-524.
- [23] L. Wang and R.V.N. Melnik. Modifying macroscale variant combinations in 2D structure using mechanical loadings during thermally induced transformation. *Materials Science and Engineering: A*, 481-482, 2008, pp. 190-193.
- [24] L.X. Wang and R.V.N. Melnik, Control of coupled hysteretic dynamics of ferroelectric materials with a Landau-type differential model and feedback linearization, *Smart Materials & Structures*, 18 (7), 2009, Art. No. 074011.
- [25] L.X. Wang, R. Liu, and R.V.N. Melnik, Modeling large reversible electric-field-induced strain in ferroelectric materials using 90 degrees orientation switching, *Science in China Series E - Technological Sciences*, 52 (1), 2009, pp. 141-147.
- [26] L.X. Wang and R.V.N. Melnik, Low Dimensional Approximations to Ferroelastic Dynamics and Hysteretic Behaviour Due to Phase Transformations, *ASME Journal of Applied Mechanics*, 2010, to appear.

<b><u>Photocatalytic Performance of Pyrochlore-Type Structure Compounds, Bi<sub>2</sub>MTaO<sub>7</sub> (M = Al, Ga, Fe or In), On Alizarin Red S Degradation</u></b>	73
<i>Leticia M. Torres-Martinez, Isaias Juarez-Ramirez, Juan S. Ramos-Garza, Francisco Vazquez-Acosta, Soo Wahn Lee</i>	
<b><u>Imaginary Relativity</u></b>	79
<i>Mehran Rezaei</i>	
<b><u>Combined Spectral and Finite Difference Methods for a Stationary Neutron Transport Equation</u></b>	91
<i>Nikos Mastorakis, Olga Martin</i>	
<b><u>An Ultrasensitive Vibrating Channel Mass Sensor based on Tunnelling Current Detection</u></b>	97
<i>Maurizio Migliore, Zakaria Moktadir, Hiroshi Mizuta</i>	
<b><u>Instability of Ion-Acoustic Oscillations and Anomalous Thermal Conductivity in the Transition Region of Stellar Atmosphere</u></b>	103
<i>P. A. Bespalov, O. N. Savina</i>	
<b><u>A Perpetual Evolution of Electrochemically Deposited Nano-Structured Cu Thin Films Driven by Acoustic Cavitation</u></b>	108
<i>A. Mallik, B. C. Ray</i>	
<b><u>Effect of Organoclay and SEBS-g-MA Contents on Constituting Balance between Stiffness vs. Toughness in PP/SEBS-g-MA/Organoclay Nanocomposites</u></b>	113
<i>M. Ranjbar, A. Arefazar, Gh. Bakhshandeh</i>	
<b><u>Numerical Analysis of the Heating Effects of an Atmospheric Air Barrier Dielectric Discharge</u></b>	119
<i>Antonis P. Papadakis, Andrew C. Metaxas</i>	
<b><u>Phase-field Approach to Studying Shape Memory Effects and Thermomechanical Properties of Low Dimensional Nanostructures</u></b>	125
<i>Roderick Melnik, Linxiang Wang</i>	
<b><u>Modelisation of Accumulation Barrier of Nanostructure AlGaAs/GaAs</u></b>	131
<i>I. Bouneb, M. Marir-Benabbas</i>	
<b><u>Continuous-Microflow Synthesis of Multiscale Materials based on Polymer Microparticles / Inorganic Nanoparticles Composites</u></b>	135
<i>Z. Chang, S. Li, M. Bouquey, I. Kraus, C. A. Serra, J. M. Kohler</i>	
<b><u>Stabilization and Enhancement of Microcirculatory Video Sequences</u></b>	140
<i>Maher I. Rajab, Stephen P. Morgan, Ian M. Stockford, John A. Crowe</i>	
<b><u>Investigation of Olive Oil as a New Photonic Liquid Crystal for Optical Communication Systems</u></b>	144
<i>Anwaar A. Al-Dergazly, Aqeel Fadhel</i>	
<b><u>Results of UV Photoelectric Observations of the Early-Type Eclipsing Binary System XZ Cep</u></b>	150
<i>M. I. Kumsiashvili, K. B. Chargeishvili, E. B. Janiashvili</i>	
<b><u>Analysis of MWIR Infrared Pyroelectric Detectors Parameters</u></b>	161
<i>Genc Hyseni, Nebi Caka, Kujtim Hyseni</i>	