PT. JASA MUTU MINERAL INDONESIA
Coal Laboratory & Superintending
Jl. Rapak Indah No.189 Samarinda Kalimantan Timur - Indonesia
Telp : (0541) 6276886 Fax : (0541) 6276887
Email : pt.jammin@yahoo.co.id

REPORT OF ANALYSIS

Job Number : 640/SS/LAB/X/2018
Date Of Received Sample : Oct 19, 2018
Amount Of Sample : 4 Sample
Date Issued : Oct 21, 2018
Attention : -
Email : groupjakindo@gmail,com

Principle : PT. Jayakhisma Globe Indonesia
Reference : STM/SPL-OKT/13/200

CODE SAMPLE	Test Method	OC - 1 - JGI - (1.00 M)			
		SS -1172			
Basis		Air Dried	Dry	Dry Ash Free	As Received
Mass as Received (kg)		9.15			
Total Moisture	ASTM D3302/D3302M– 12	-	-	-	29.60
Moisture in the Analysis Sample	ASTM D 3173 - 11	12.32	-	-	-
Ash Content	ASTM D 3174 - 12	0.69	0.79	-	0.55
Volatile Matter	ASTM D 3175 - 11	45.90	52.35	52.76	36.85
Fixed Carbon	ASTM D 3172 - 07a	41.09	46.86	47.24	32.99
Total Sulphur	ASTM D 4239 – 12	1.03	1.17	1.18	0.83
Gross Calorific Value	ASTM D5865 – 12	5914	6745	6798	4748

CODE SAMPLE	Test Method	OC - 2 - JGI - (0.80 M)			
		SS - 1173			
Basis		Air Dried	Dry	Dry Ash Free	As Received
Mass as Received (kg)		10.25			
Total Moisture	ASTM D3302/D3302M– 12	-	-	-	31.35
Moisture in the Analysis Sample	ASTM D 3173 - 11	15.27	-	-	-
Ash Content	ASTM D 3174 - 12	3.44	4.06	-	2.79
Volatile Matter	ASTM D 3175 - 11	41.49	48.97	51.04	33.62
Fixed Carbon	ASTM D 3172 - 07a	39.80	46.97	48.96	32.25
Total Sulphur	ASTM D 4239 – 12	1.02	1.20	1.25	0.83
Gross Calorific Value	ASTM D5865 – 12	5564	6567	6845	4508

CODE SAMPLE	Test Method	OC - 3 - JGI - (1.10 M)			
		SS - 1174			
Basis		Air Dried	Dry	Dry Ash Free	As Received
Mass as Received (kg)		8.60			
Total Moisture	ASTM D3302/D3302M– 12	-	-	-	32.11
Moisture in the Analysis Sample	ASTM D 3173 - 11	15.69	-	-	-
Ash Content	ASTM D 3174 - 12	1.67	1.98	-	1.34
Volatile Matter	ASTM D 3175 - 11	43.98	52.16	53.22	35.41
Fixed Carbon	ASTM D 3172 - 07a	38.66	45.85	46.78	31.13
Total Sulphur	ASTM D 4239 – 12	0.88	1.04	1.06	0.71
Gross Calorific Value	ASTM D5865 – 12	5842	6929	7069	4704

CODE SAMPLE	Test Method	OC - 5 - JGI - UPPER - (1.00 M)			
		SS - 1176			
Basis		Air Dried	Dry	Dry Ash Free	As Received
Mass as Received (kg)		11.45			
Total Moisture	ASTM D3302/D3302M– 12	-	-	-	29.34
Moisture in the Analysis Sample	ASTM D 3173 - 11	13.20	-	-	-
Ash Content	ASTM D 3174 - 12	2.97	3.42	-	2.42
Volatile Matter	ASTM D 3175 - 11	44.92	51.75	53.58	36.57
Fixed Carbon	ASTM D 3172 - 07a	38.91	44.83	46.42	31.67
Total Sulphur	ASTM D 4239 – 12	1.03	1.19	1.23	0.84
Gross Calorific Value	ASTM D5865 – 12	5993	6904	7149	4879

Analysis according to : ASTM Method

Regards,

Ahmad Latif, S.Si
Laboratory Manager

JAMMIN-508