

SHREE GANESH CORRUGATORS – QUALITY LAB

Test Report No. SGC/QC/TR/2609-14 Date of test: 24/09/2026

Sample: 5 Ply RSC box 400x300x300, Paper 180/120/150/120/180, BF 20, BC flute, Lot 2609-B

Parameter	Method	Specification	Result	Status
Bursting strength (kg/cm ²)	IS 1060 Pt II	min 12.0	13.4	OK
Box compression (BCT, kgf)	TAPPI T804	min 450	492	OK
Edge crush (ECT, kN/m)	TAPPI T839	min 7.0	7.6	OK
Grammage (g/m ²)	IS 1060 Pt I	900 +/- 5%	912	OK
Moisture (%)	IS 1060	max 9.0	7.8	OK

Tested by: S. Pawar (QC Chemist)

Approved by: M. Deshpande (QC Head)