

Thermal Evaporation Method Thickness Results

Distance between source and substrate: 17.5 cm

Element: Au

Mass: 0.05 g


Area: 0.3 cm²

Pressure: 0.0000001 mbar

Particle distribution: Isotropic

Time needed to evaporate the source: 565 s

Thickness distribution on substrate



Uncertainty of Thickness distribution on substrate

