
A Held−out QC CV
Batch
Both
Run order
Held−out QC CV (%)
40
30
20
10
0
50
100
Alignment strength (%)
Raw
WiNN