














Work Size		Pieces/Box (nos.)	Coverage/Box (sq.mtr.)	Weight/Box (kgs.)
Dimensions (in mm)	Thickness (in mm)			
300x300 (Paving Tiles)	10	8	0.72	15.2

	Properties	I.S.-4457 : 2007	Our Value
	Deviation in Length & Width (from work size)	±0.6%	±0.1%
	Deviation in Thickness	±5%	±4%
	Straightness of Sides (Facial)	±0.2%	±0.2%
	Rectangularity	±0.2%	±0.2%
	Surface Flatness (%)	±0.3%	±0.3%
	Surface Quality	±95%	±95%
	Water Absorption by weight	Average <0.5% individual 0.6 Max.	Average <0.5% individual 0.6 Max.
	Breaking Strength (N)	1300 Min.	1500 Min.
	Modulus of Rupture (N/mm ²)	Average - 35, indiv. 32, Min.	Average - 35, indiv. 32, Min.
	Deep Abrasion Resistance (mm ³)	175 Max.	175 Max.
	Chemical Resistance • Resistance to chemicals • Resistance to concentrated HNO ₃ and H ₂ SO ₄	Required as agreed between Manufacturer and Purchaser Loss in Mass - 1.5% max.	Required as agreed between Manufacturer and Purchaser Loss in Mass - 1.5% max.