QUICK CARD · METROLOGY LAB (MÅLETEKNISK LAB)

Modix BIG-60 – 3D printer

Version 3 · 2 × Titan Aero · Duet 2 WiFi · PanelDue i7 · § = section in the guide

Full guide: **scan the QR code** or go to **ravo10.github.io/USN-kongsberg-lab-mech**.

DO NOT PRINT PETG! PETG can bond permanently to the PEI sheet and damage it.

SAFETY

- Nozzle and plate get **very hot**
- **IPA**: cold plate only, wear gloves
- **Do not leave** during PID tuning
- "Allow unhomed moves": **crash risk**

A. Before printing §2, §3.4

1. Print from the **SD card** (slot under the screen).
2. PEI sheet clean? If prints do not stick: **IPA** on a **cold** plate.
3. Filament loaded. Using one head only: disable extruder 2 in Cura.
4. Start the print from the screen or Duet Web Control.

B. Cura 5.3+ (Machine Settings) §3.1

5. **Z (Height): 630 mm**.
6. Start G-code: **G28** / **M566 E3600** / **M572 D0 S0.02**.
7. End G-code: only **M0 ;** (delete the rest).
8. **2** extruders; Right Extruder: **Cooling Fan Number 1**.
9. Nozzle: **1.2 mm Nozzle**.

E. After printing §3.6

☐ Turn off the plate heating so the print comes loose
☐ Remove leftover plastic from the plate
☐ Clean up after yourself

C. Print settings (Ø1.2 mm) §3.2–3.3

Layer height	1.0 mm (0.4–1.0)
Width	100 %
Speed	90 mm/s
Max. flow	110 mm³/s
PLA	225–250 °C, default 230 °C
Max. temperature	285 °C (stock parts)
Support Z distance	2–4 mm
Fan	from layer 2
Z hop	do not use unless needed

D. Wi-Fi and Duet Web Control §2, §5

Network	**USN BIG-60**
Password	ask Rasmus or Richard
Address	**http://192.168.0.1**

Troubleshooting §3, §5, §7

Print does not stick	Clean the PEI with IPA (cold plate)
Plastic curls / clogs	Change the nozzle (every 3–6 months)
No Wi-Fi	"WiFi reset" macro on the screen
"DuetTest" on the screen	Wrong configuration files (§7)