

Reinaldo Arturo Zapata Peña presents

Novel Optical Effects in Functionalized Graphene: Formalism and Simulations

to earn the degree of Doctor of Science (Optics)




CENTRO DE INVESTIGACIONES
EN ÓPTICA, A.C.

December 11, 2017

General properties of graphene

- Good heat conductor ¹
- Extremely strong ²
- Flexible ³



Transmission electron microscopy of
graphene. ⁴

¹A.K. Geim and K.S. Novoselov. Nature Materials, 6(3):183-191, 2007.

²C. Lee, et al. Science, 321(5887):385-388, 2008.

³Briggs, B. D. et. al. App. Phys. Lett. 97: 223102. 2010.

⁴E. Stolyarova, et al. PNAS, 104(22):9209, 2007.

Synthesis of graphene

- Exfoliation¹
- Micromechanical cleavage ²
- Reduction of graphite oxide in dimethylformamide ³
- Chemical Vapor Deposition ⁴



Graphite, a graphene transistor, and a tape dispenser donated to the Nobel Museum.⁵


¹ A.K. Geim and K.S. Novoselov. Nature Materials, 6(3):183-191, 2007.

² R.R. Nair, et al. Science, 320(5881):1308-1308, 2008.


³ S. Park, J. et al. Nano letters, 9(4):1593-1597, 2009.

⁴ E. Rollings, et al. JPCS, 67(9-10):2172-2177, 2006.


⁵ By Gabriel Hildebrand - Nobelmuseet, Public Domain.



Carbon nanotube



Fullerene




Graphite

Structures obtained from graphene

Electronic properties of graphene

- Quantum Hall effect at room temperature¹
- Excellent electrical current conduction ¹
- Transparent to visible light ²
- Tunable bandgap ³



Photograph of graphene in transmitted light.⁴

¹A.K. Geim and K.S. Novoselov. Nature Materials, 6(3):183-191, 2007.


²R.R. Nair, et al. Science, 320(5881):1308-1308, 2008.

³M.Y. Han, et. al. Physical Review Letters, 98(20):206805, 2007

⁴By Rahul Nair - Manchester group.

■ Tunable bandgap by:

- changing sheet size ¹
- changing number of sheets and stacking ¹
- applying an electric field ²
- doping ³
- hydrogenation ⁴







Variation of the energy gap with the size of graphene sheet model.¹

¹C. Feng et al. 2009. Jour. of Chem. Phys. 131:194702, 2009.

²Y. Zhang et al. Nature, 459(7248):820-823, 2009.

³T. Ohta et al. Science, 313(5789):951-954, 2006.


⁴D.C. Elias et al. Science, 323(5914):610-613, 2009.







Functionalization by hydrogenation





Centrosymmetric Materials

A centrosymmetric system presents inversion of symmetry, such that a point $p(a, b, c)$ corresponds a point $p'(-a, -b, -c)$.






Alt structure: 50% hydrogenation; hydrogen at bot sides.



Up structure: 50% hydrogenation; hydrogen on the upper side.

Optical spin injection and degree of spin polarization (DSP)

- Spintronics is based in the injection, detection and transport of spin polarized electrons in nonmagnetic materials.¹
- Spin polarized electrons in a given a direction can be injected through circularly polarized light.²



¹A. Fert et. al. Rev. Mod. Phys., 80(4):1517, 2008.

²N. Arzate et al. Phys. Rev. B, 90(20):205310, 2014.

- The Spin generation rate and the carrier generation rate can be written as

$$\dot{S}^a(\omega) = \zeta^{abc}(\omega)E^b(-\omega)E^c(\omega),$$
$$\dot{n}(\omega) = \xi^{ab}(\omega)E^a(-\omega)E^b(\omega),$$

where $\zeta^{abc}(\omega)$ is the spin injection rate tensor and $\xi^{ab}(\omega)$ is the carrier generation rate tensor.

- The degree of spin polarization (DSP) quantifies the fraction of injected electrons in the conduction bands that are spin polarized along direction a and is given by


$$\mathcal{D}^a(\omega) = \frac{\dot{S}^a(\omega)}{(\hbar/2)\dot{n}(\omega)} \quad (1)$$

- DSP is a second order optical effect; it is possible to generate spin polarized electrons along three Cartesian directions with an incident circularly polarized beam.

Pure spin current and spin velocity injection (SVI)

Pure spin current injection

- The spin current moves along direction \hat{a} with the spin polarized along direction \hat{b} .¹
- There is no net motion of charge but a spin current is produced.¹



¹A. Najmaie et. al. Phys. Rev. B, 68(16):165348, 2003.

- Is a second-order optical nonlinear effect.
- A pure spin current can be produced by a single linearly polarized beam in noncentrosymmetric materials¹ and is given by²


$$\dot{K}^{ab}(\omega) = \mu^{abcd}(\omega) E^c(\omega) E^{d*}(\omega), \quad (2)$$

where $\mu^{abcd}(\omega)$ is the pseudotensor that describes the rate of change of the PSC.

¹A. Najmaie et. al. Phys. Rev. B, 68(16):165348, 2003.

²Reinaldo Zapata-Peña et. al. Phys. Rev. B 96, 195415. 2017

Spin velocity injection



- The spin velocity injection is defined as¹


$$\mathcal{V}^{ab}(\omega) \equiv \frac{\dot{K}^{ab}(\omega)}{(\hbar/2)\dot{n}(\omega)}, \quad (3)$$

which gives the velocity, along direction \hat{a} , at which the spin moves in a polarized state along direction \hat{b} .

¹Reinaldo Zapata-Peña et. al. Phys. Rev. B 96, 195415. 2017


- With 2D structures we can use the direction of the polarized electric field to control $\mathcal{V}^{ab}(\omega)$.
- Writing $\mathbf{E}(\omega) = E_0(\omega)(\cos \alpha \hat{\mathbf{x}} + \sin \alpha \hat{\mathbf{y}})$, where α is the polarization angle, we obtain that

$$\mathcal{V}^{ab}(\omega, \alpha) = \frac{2}{\hbar \xi(\omega)} (\mu^{abxx}(\omega) \cos^2 \alpha + \mu^{abyy}(\omega) \sin^2 \alpha + \mu^{abxy}(\omega) \sin 2\alpha). \quad (4)$$



Fixing the spin polarization¹

Spin fixed along z direction



- Magnitude of the velocity when the spin is fixed in the b direction

$$\begin{aligned} \mathcal{V}_{\sigma^b}(\omega, \alpha) \equiv \\ \sqrt{(\mathcal{V}_{xb}(\omega, \alpha))^2 + (\mathcal{V}_{yb}(\omega, \alpha))^2} \end{aligned} \quad (5)$$

- Angle of the velocity when the spin is fixed in the b


$$\gamma_{\sigma^b}(\omega, \alpha) = \tan^{-1} \left(\frac{\mathcal{V}_{yb}(\omega, \alpha)}{\mathcal{V}_{xb}(\omega, \alpha)} \right) \quad (6)$$

¹Reinaldo Zapata-Peña et. al. Phys. Rev. B 96, 195415. 2017

We have two special cases


- When the velocity vector is parallel to the electric incident field

$$\gamma_{\sigma^b}^{\parallel}(\omega, \alpha) = \alpha, \quad (7)$$




- When the velocity vector is perpendicular to the electric incident field

$$\gamma_{\sigma^b}^{\perp}(\omega, \alpha) = \alpha \pm 90^\circ, \quad (8)$$



Fixing the spin velocity¹

Velocity fixed along y direction



- Magnitude of the velocity when it is fixed along \hat{a} direction

$$\mathcal{V}_a(\omega, \alpha) \equiv \left[(\mathcal{V}^{ax}(\omega, \alpha))^2 + (\mathcal{V}^{ay}(\omega, \alpha))^2 + (\mathcal{V}^{az}(\omega, \alpha))^2 \right]. \quad (9)$$

- Angles of the spin

Polar angle


$$\theta_a(\omega, \alpha) = \cos^{-1} \left(\frac{\mathcal{V}^{az}(\omega, \alpha)}{\mathcal{V}_a(\omega, \alpha)} \right). \quad (10)$$

Azimuthal angle

$$\varphi_a(\omega, \alpha) = \tan^{-1} \left(\frac{\mathcal{V}^{ay}(\omega, \alpha)}{\mathcal{V}^{ax}(\omega, \alpha)} \right). \quad (11)$$

¹Reinaldo Zapata-Peña et. al. Phys. Rev. B 96, 195415. 2017

Optical current injection



- It is possible to control a photocurrent in a bulk structure¹ or in the surface of a 2D system.^{2, 3}
- Is a second-order optical nonlinear effect that can be produced with a single optical circularly-polarized beam.²

¹A. Hacheét. al. Phys. Rev. Lett., 78:306-309, Jan 1997.

²N. Arzate et al. Phys. Rev. B, 90(20):205310, 2014.

³R. Zapata-Peña et. al. Phys. Stat. Sol. (b), 253 (2):226-233, 2016.

- A photocurrent can be injected into noncentrosymmetric materials or at the surface of bulk centrosymmetric materials and is given by ¹

$$\mathbf{j}_{\text{inj}}^a(\omega) = \eta^{abc}(\omega) E_b(\omega) E_c(\omega),$$


where $\eta^{abc}(\omega)$ is the current injection tensor which quantifies the current injection along the a direction a .

- The response was calculated layer by layer.

¹N. Arzate et al. Phys. Rev. B, 90(20):205310, 2014.

Second harmonic generation (SHG)

- Is a second-order optical nonlinear effect and a particular case of sum frequency generation.
- The nonlinear polarization in the media acts as a source for the electromagnetic waves of frequency 2ω .
- SHG spectroscopy offer a non-invasive technique to study material properties.



- The second-order nonlinear polarization is given by ¹




$$\mathcal{P}(2\omega) = \chi^{abc}(-2\omega; \omega, \omega) E^b(\omega) E^c(\omega),$$

where $\chi^{abc}(-2\omega; \omega, \omega)$ is the nonlinear susceptibility tensor responsible for the SHG.

- The formalism includes ¹
 - the scissors correction,
 - the contribution of the nonlocal part of the pseudopotentials
 - the cut function used to select the individual contribution for a given layer.

¹S. M. Anderson et al. Phys. Rev. B, 91(7):075302, 2015.

Degree of spin polarization




Response in the Near Infrared
 $0.717 \text{ eV} = 1.72 \mu\text{m} = 173 \text{ THz}$




Response in the Mid Infrared
 $0.084 \text{ eV} = 14.7 \mu\text{m} = 20.3 \text{ THz}$

Spin velocity injection




Components with maximum values of the \mathcal{V}^{ab} for the alt, up, CdSe and GaAs structures.



└ Results


└ Spin velocity injection

Fixing the spin along z for up



When the spin is polarized along z the spin velocity V_{σ^z} :


- Is maximized for $\hbar\omega = 0.084$ eV
- The absolute maxima is 739.7 Km/s for $\alpha = 35^\circ$
- The velocity is directed almost at a constant angle $\gamma_{\sigma^z} = 64.5^\circ$




└ Results

└ Spin velocity injection


- A local maxima is found for $\hbar\omega = 1.954 \text{ eV}$ (634 nm, visible red)
- The maxima is 193.5 Km/s for $\alpha = 35^\circ$
- The velocity angle γ_{σ^z} has values between 75.5° and 77.8°



Fixing the spin along z for up




Fixing the spin along z for *alt*



When the spin is polarized along z the spin velocity V_{σ^z} :



- Is maximized for $\hbar\omega = 0.720$ eV (near infrared, $1.72\ \mu\text{m}$)
- The absolute maxima is 644.9 Km/s for $\alpha = 150^\circ$
- The velocity angle γ_{σ^z} has values from 108° to 110°



└ Results

└ Spin velocity injection

Fixing the velocity on x and y directions for up





- The responses are maximized for $\alpha = 35^\circ$ and $\hbar\omega = 0.084$ eV
- The absolute x maxima is $V_x = 431.7$ Km/s at $\theta_x = 42.5^\circ$ and $\varphi_x = 208.3^\circ$
- The absolute y maxima is $V_y = 687.9$ Km/s at $\theta_y = 13.9^\circ$ and $\varphi_y = 82.1^\circ$

└ Results

└ Spin velocity injection


- The responses has a local maxima for $\alpha = 35^\circ$ and $\hbar\omega = 0.084 \text{ eV}$
- The local x maxima is $v_x = 61.2 \text{ Km/s}$ at $\theta_x = 48.3^\circ$ and $\varphi_x = 54.3^\circ$
- The local y maxima is $v_y = 293.2 \text{ Km/s}$ at $\theta_y = 49.8^\circ$ and $\varphi_y = 51.9^\circ$




└ Results

└ Spin velocity injection



Fixing the velocity on x and y directions for α





- The responses has a local maxima for $\alpha = 150^\circ$ and $\hbar\omega = 0.720$ eV
- The local x maxima is $V_x = 301.7$ Km/s at $\theta_x = 44.5^\circ$ and $\varphi_x = 51.2^\circ$
- The absolute y maxima is $V_y = 905.6$ Km/s at $\theta_y = 119.7^\circ$ and $\varphi_y = 163.4^\circ$



Optical current injection






Intense response in the Near Infrared
 $0.95 \text{ eV} = 230 \mu\text{m}$



Response in the Mid Infrared
 $0.084 \text{ eV} = 14.7 \mu\text{m} = 20.3 \text{ THz}$

Optical current injection



Intense response in the Near Infrared
 $0.95 \text{ eV} = 230 \mu\text{m}$



Response in the Mid Infrared
 $0.084 \text{ eV} = 14.7 \mu\text{m} = 20.3 \text{ THz}$


Conclusions

- Due to the fact that both structures are high non-centrosymmetric materials, then it is possible to induced high intensity nonlinear responses in them.
- Both structures are excellent candidates for spintronics applications:
 - * We found that the *up* is more spin-polarizable than the *alt* but both reaches more than 50% of DSP.
 - * It is possible to generate pure-spin currents in our structures; also it is possible to control the spin orientation or the current direction making variations in the angle of the polarization of the incoming beam.
 - * The spin velocities reached in the structures are usable for spintronics devices.
- The *up* structure can achieve a large injection current being the response bigger than most of other structures.¹
- Both structures are excellent candidates to generate second harmonic, particularly the *up* one.

¹R. Zapata-Peña, et. al. Phys. Rev. B 96, 195415, 2017.

Articles

- R. Zapata-Peña, et. al. Pure spin current injection in hydrogenated graphene structures. Phys. Rev. B 96, 195415, 2017.
- Anatoli I. Shkrebtii, R. Zapata-Peña, et. al. Graphene-Boron Nitride 2D Heterosystems Functionalized with Hydrogen. Advances in Science and Technology 98:117-124, 2017.
- R. Zapata-Peña, et. al. Nonlinear optical responses in hydrogenated graphene structures. Phys. Stat. Sol. (b), 253(2):226-233, 2016.



Conferences


- OSI-11 2015 (Poster)
- IX Riao-Opticas 2016 (Poster)

Specialized courses


- Control de versiones usando Git y GitHub (2013)
- Cómputo en paralelo mediante FORTRAN/C++ con MPI y OpenMP (2013)
- Cálculo de propiedades ópticas de la materia con el uso de teoría de muchos cuerpos (2013)

Perspectives

Continue the study of this phenomenon in other structures and make new publication:



Functionalized
boron-nitride-graphene with
hydrogen



Boron-nitride nanotubes

Acknowledgments

- Dr. Bernardo Mendoza
- Dr. Ramón Carriles Jaimes
- Dr. Gabriel Merino Hernández
- My friend Dr. Sean M. Anderson
- My wife, Patricia, and my kids
- My mother, Eloisa
- My sisters
- All my friends who shared time with me
- The CIO
- The CONACYT

Delete

End

Page
Down