Size	Fiberglass_leng	Area_m2	Repairs_per_rol	Resin_A_mL_pe	Resin_B_mL_pe	Total_resin_kg	Repairs_per_re	Product_page
DN100	35	0.44	108	175/0.27	350/0.44	0.71	56	https://reliancetrenchless.com/products/fiberglass-resin-repair-system
DN150	55	0.69	69	275/0.42	550/0.67	1.09	36.5	https://reliancetrenchless.com/products/fiberglass-resin-repair-system
DN200	70	0.88	54	350/0.55	700/0.86	1.41	28	https://reliancetrenchless.com/products/fiberglass-resin-repair-system
DN250	90	1.13	42	450/0.7	900/1.1	1.8	22	https://reliancetrenchless.com/products/fiberglass-resin-repair-system
DN300	110	1.38	34	550/0.85	1100/1.35	2.2	18	https://reliancetrenchless.com/products/fiberglass-resin-repair-system
DN400	140	1.75	27	700/1.08	1400/1.72	2.8	14	https://reliancetrenchless.com/products/fiberglass-resin-repair-system
DN500	175	2.19	21	875/1.36	1750/2.14	3.5	11	https://reliancetrenchless.com/products/fiberglass-resin-repair-system
DN600	210	2.63	18	1050/1.63	2100/2.57	4.2	9.5	https://reliancetrenchless.com/products/fiberglass-resin-repair-system
DN800	300	3.75	12	1400/2.15	2800/3.55	5.7	7	https://reliancetrenchless.com/products/fiberglass-resin-repair-system
DN1000	400	5.00	9.5	2000/3.1	4000/4.9	8	5	https://reliancetrenchless.com/products/fiberglass-resin-repair-system

Grade	Total_area_weig	Woven_roving_	Chopped_stran	Polyester_threa	Product_page
EMK600/450	1060.71	600	450	10.71	https://reliancetrenchless.com/products/fiberglass-resin-repair-system
EMK800/300	1110.71	800	300	10.71	https://reliancetrenchless.com/products/fiberglass-resin-repair-system
EMK800/450	1260.71	800	450	10.71	https://reliancetrenchless.com/products/fiberglass-resin-repair-system

Category	Parameter	Value	Product_page
Package	Resin	40.5 kg per set	https://reliancetrenchless.com/products/fiberglass-resin-repair-system
Package	Glass fiber	50 kg per roll	https://reliancetrenchless.com/products/fiberglass-resin-repair-system
Common	Fiberglass width	125 cm	https://reliancetrenchless.com/products/fiberglass-resin-repair-system
Resin A	Appearance	Transparent or pa	https://reliancetrenchless.com/products/fiberglass-resin-repair-system
Resin A	Viscosity at 25°C	350-750	https://reliancetrenchless.com/products/fiberglass-resin-repair-system
Resin A	Density (g/cm3)	1.52	https://reliancetrenchless.com/products/fiberglass-resin-repair-system
Resin A	Flash Point (Clos	>200°C	https://reliancetrenchless.com/products/fiberglass-resin-repair-system
Resin A	Stability	Stable at room te	https://reliancetrenchless.com/products/fiberglass-resin-repair-system
Resin A	Product Storage	12 months	https://reliancetrenchless.com/products/fiberglass-resin-repair-system
Resin B	Appearance	Brown	https://reliancetrenchless.com/products/fiberglass-resin-repair-system
Resin B	Viscosity at 25°C	250-600	https://reliancetrenchless.com/products/fiberglass-resin-repair-system
Resin B	Density (g/cm3)	1.2	https://reliancetrenchless.com/products/fiberglass-resin-repair-system
Resin B	Flash Point (Clos	>200°C	https://reliancetrenchless.com/products/fiberglass-resin-repair-system
Resin B	Stability	Stable at room te	https://reliancetrenchless.com/products/fiberglass-resin-repair-system
Resin B	Product Storage	12 months	https://reliancetrenchless.com/products/fiberglass-resin-repair-system
Handling	Mixing Ratio (Vol	A:B=1:2	https://reliancetrenchless.com/products/fiberglass-resin-repair-system
Handling	Mixing and Stirrir	1-2	https://reliancetrenchless.com/products/fiberglass-resin-repair-system
Handling	Initial Setting Tim	10-20	https://reliancetrenchless.com/products/fiberglass-resin-repair-system
Handling	Curing Time at 2!	40-60	https://reliancetrenchless.com/products/fiberglass-resin-repair-system
Seasonal	Summer operatic	20 / 40	https://reliancetrenchless.com/products/fiberglass-resin-repair-system
Seasonal	Spring operation	25 / 60	https://reliancetrenchless.com/products/fiberglass-resin-repair-system
Seasonal	Winter operation	30 / 90	https://reliancetrenchless.com/products/fiberglass-resin-repair-system
Mechanical test	Bending strength	142	https://reliancetrenchless.com/products/fiberglass-resin-repair-system
Mechanical test	Flexural modulus	9215	https://reliancetrenchless.com/products/fiberglass-resin-repair-system
Mechanical test	Compressive stre	164	https://reliancetrenchless.com/products/fiberglass-resin-repair-system

Facts only from reliancetrenchless.com — confirm with Reliance before ordering.

Fiberglass and Resin Point Repair Specs | Reliance Trenchless

Source of truth:
https://reliancetrenchless.com/products/fiberglass-resin-repair-system
Contact: https://reliancetrenchless.com/contact · sales@reliancetrenchless.com

How to use: Use dosage-by-size rows for planning. Confirm formulation, repair length, thickness and site temperature. Place patches with a matching pipe repair packer (separate product).
Do not confuse with: Not Instant-Lock mechanical sleeves; not CIPP full-length lining.

Confirm dimensions, materials, operating limits, inspection documents, availability and delivery terms with Reliance for each project.