Twenty Frontiers: A Deep Research Review of the Unresolved Questions in Quantum Materials

Expert Persona

The author of this report is a distinguished PhD researcher in condensed matter physics, specializing in the theory and phenomenology of quantum materials. With an extensive publication record in leading journals such as *Physical Review Letters*, *Nature Physics*, and *Reviews of Modern Physics*, this expert is recognized for their ability to synthesize complex experimental and theoretical results into coherent, insightful narratives. Their work is characterized by a deep understanding of both the foundational principles and the cutting-edge techniques that drive the field, making them an ideal authority to produce this exhaustive review of the twenty most significant open problems in quantum materials.

Twenty Frontiers: A Deep Research Review of the Unresolved Questions in Quantum Materials

Abstract

The field of quantum materials, a cornerstone of modern condensed matter physics, is defined by emergent phenomena where quantum mechanical effects manifest on a macroscopic scale. From the enduring mystery of high-temperature superconductivity to the exotic physics of topological states and frustrated magnetism, this field presents a landscape of profound scientific questions and promises transformative technological applications. This review provides an exhaustive, expert-level analysis of twenty of the most significant open problems that currently define the frontiers of quantum materials research. These challenges are organized into four thematic areas: the grand, long-standing challenges such as the mechanism of high-T_c superconductivity and the realization of a fault-tolerant quantum computer; the frontiers of topology and geometry, including novel topological phases and moiré materials; the world of magnetic frustration and spin liquids; and overarching challenges in materials synthesis, characterization, and theoretical methodology. For each problem, this report provides a crisp statement of the challenge, a detailed review of the current state of research with extensive citations, an analysis of

promising future directions, and a discussion of the potential scientific and technological impact of its resolution. Furthermore, it summarizes the synergistic roles of theory, computation, and experiment, and provides a justified, ranked analysis of the U.S. National Laboratories best positioned to lead the research efforts, based on their unique facilities and expertise. This comprehensive review serves as a roadmap to the critical questions shaping the future of physics, materials science, and quantum technology.

Introduction

The Landscape of Quantum Materials: From Emergent Phenomena to Transformative Technologies

The study of quantum materials represents a paradigm shift in our understanding of matter. It moves beyond the successful single-particle picture that describes conventional metals and semiconductors to a realm where collective quantum phenomena—such as strong electron-electron interactions, quantum entanglement, and geometric or topological constraints—govern the macroscopic electronic, magnetic, and optical properties of a solid. This field was born from a series of landmark discoveries that defied classical and semi-classical explanations. The discovery of high-temperature superconductivity in ceramic copper oxides (cuprates) by Bednorz and Müller in 1986 shattered the perceived limits of the Bardeen-Cooper-Schrieffer (BCS) theory and opened a new, still-unfolding chapter in condensed matter physics.[1] Similarly, the isolation of graphene and the subsequent explosion of research into two-dimensional (2D) materials revealed a new platform for realizing novel electronic phenomena [3], while the prediction and discovery of topological insulators demonstrated that the topology of electronic wavefunctions could give rise to robust, protected surface states with properties unlike any bulk material.[4]

These discoveries underscore a central theme: in quantum materials, the whole is profoundly different from the sum of its parts. The intricate dance of electrons, spins, orbitals, and lattice vibrations gives rise to a rich tapestry of emergent phases, from the zero-resistance flow of electricity in superconductors to the fractionalized excitations of quantum spin liquids. Understanding and controlling these emergent phenomena is not merely an academic pursuit; it is the foundation for a new generation of technologies. A room-temperature superconductor could revolutionize the global energy grid.[5] A fault-tolerant topological qubit could unlock the full power of quantum computation.[8] And new 2D materials could enable unprecedented advances in electronics, sensing, and catalysis.[9]

The Twenty Grand Challenges: A Roadmap to the Frontiers of Condensed Matter Physics

This report outlines twenty of the most significant open problems in quantum materials. These challenges have been selected for their fundamental scientific importance and their potential for transformative impact. They represent the major roadblocks and the most exciting opportunities that are currently driving research worldwide. The problems are organized into four thematic parts to provide a coherent narrative structure:

- **Part I: The Grand Challenges.** These are the overarching, long-standing problems that have defined the field for decades, such as the mechanism of high-temperature superconductivity and the development of a general theory for strongly correlated systems.
- **Part II: Topological and Geometrical Frontiers.** This section explores the rapidly evolving landscape of topological matter, from the search for new topological phases to the engineering of novel properties in twisted 2D materials.
- **Part III: The World of Frustration and Spin Liquids.** Here, the focus is on exotic magnetic states that arise when competing interactions prevent conventional ordering, leading to highly entangled ground states like quantum spin liquids and spin ices.
- **Part IV: Novel Materials, Phenomena, and Methodologies.** This part addresses the cross-cutting challenges related to the discovery, synthesis, and characterization of new materials, as well as the theoretical and computational tools needed to advance the entire field.

The resolution of these twenty problems requires a deeply integrated approach, combining advances in theoretical modeling, large-scale computation, materials synthesis, and sophisticated experimental characterization. The following table provides a high-level overview of this research landscape, serving as a guide to the detailed review that follows.

Table 1: Overview of the Twenty Frontiers in Quantum Materials

Problem #	Problem Title	Core Concept(s)	Key Material Systems	Primary Experimental Probes	Primary Theoretical/ Computational Tools
1	Mechanism	Cooper	Cuprates	Neutron	Hubbard

	of High-Temperature Superconductivity	pairing, electron correlation, magnetism	(YBCO, LSCO), Iron Pnictides, Nickelates	Scattering, ARPES, STM, Transport	Model, Spin-Fluctuation Theory, DMFT
2	Nature of the Pseudogap Phase	Competing order, quantum criticality, precursor pairing	Cuprates (YBCO, Nd-LSCO)	ARPES, STM, Nernst Effect, RIXS	Hubbard Model, Spin-Fermion Models
3	Room-Temperature Superconductivity	BCS theory, phonon/non-phonon mechanisms, metastability	High-pressure hydrides (H_3S, LaH_{10}), LK-99	Diamond Anvil Cell, Resistivity, Magnetization	DFT, High-Throughput Screening, BCS/Eliashberg
4	Theory of Strongly Correlated Systems	Electron correlation, Mott physics, emergent phenomena	Transition-metal oxides, Heavy Fermions	ARPES, Neutron Scattering, Optical Spectroscopy	DMFT, QMC, Tensor Network States
5	Fault-Tolerant Topological Qubit	Non-Abelian anyons, Majorana zero modes, braiding	Semiconductor/Superconductor nanowires, QAH/SC hybrids	Tunneling Spectroscopy, Interferometry	Kitaev Model, Topological Field Theory
6	Classification of Novel Topological Phases	Band topology, symmetry protection, Berry curvature	Axion insulators ($MnBi_2Te_4$), Topological Crystalline Insulators	ARPES, STM, Transport Measurements	Topological Quantum Chemistry, k·p theory, DFT
7	Quantum Anomalous Hall Effect at Higher T	Chern number, intrinsic magnetism, topological gap	Magnetically doped TIs, $MnBi_2Te_4$, Moiré systems	Transport (Hall effect), MOKE, ARPES	DFT, Wannier functions, Model Hamiltonians

8	Understanding and Engineering Moiré Materials	Twistronics, flat bands, strong correlation	Twisted bilayer graphene (TBG), TMD heterostructures	STM, ARPES, Transport Measurements	Continuum Models, DFT, DMFT
9	Intrinsic Magnetic Topological Insulators	Time-reversal symmetry breaking, band inversion	$MnBi_2Te_4$, $EuIn_2As_2$	ARPES, Neutron Scattering, Magnetotransport	DFT+U, Model Hamiltonians
10	Definitive Signature of a Quantum Spin Liquid	Fractionalization, long-range entanglement, no order	Herbertsmithite, α-$RuCl_3$, Kagome/triangular lattices	Neutron Scattering, Thermal Transport, NMR	Kitaev Model, RVB Theory, DMRG
11	Role of Geometric Frustration	Degenerate ground states, competing interactions	Spin ice ($Dy_2Ti_2O_7$), Spin glasses, Kagome lattices	Neutron Scattering, Magnetization, Specific Heat	Ising/Heisenberg Models, Monte Carlo Simulations
12	Controlling Skyrmions for Spintronics	Topological spin textures, Dzyaloshinskii-Moriya interaction	B20 compounds (MnSi), Magnetic multilayers	MFM, LTEM, Topological Hall Effect	Micromagnetic Simulations, Thiele Equation
13	2D Materials Beyond Graphene	Monolayer properties, bandgap engineering	TMDs (MoS_2), Phosphorene, MXenes, 2D magnets	ARPES, STM, Optical Spectroscopy	DFT, High-Throughput Screening
14	Mastering Van der Waals Heterostructures	Interfacial engineering, proximity effects, twist angle	Graphene/hBN, TMD/TMD stacks	Optical Spectroscopy, Transport, STM/AFM	DFT, Effective Models
15	Understanding Metal-Insulat	Mott transition, Peierls	Vanadium oxides (VO_2), Nickelates,	Resistivity, ARPES, X-ray Diffraction	Hubbard Model, Peierls

	or Transitions	transition, electron correlation	Organic salts		Model, DMFT
16	Non-Equilibrium Quantum Phenomena	Ultrafast dynamics, Floquet engineering, photo-induced phases	All quantum materials	Pump-Probe Spectroscopy, tr-ARPES, UED	Keldysh Formalism, Floquet Theory, TD-DFT
17	Predictive Materials Discovery via AI/ML	High-throughput screening, inverse design	All material classes	N/A (Methodological)	Machine Learning, Generative Models, NLP
18	Advanced Characterization Techniques	High resolution (space, time, energy), multi-modal probes	All quantum materials	Synchrotron/ XFEL, Neutron sources, NV-centers	N/A (Methodological)
19	Bridging Theory and Experiment	Model fidelity, parameter extraction, collaborative frameworks	All quantum materials	N/A (Methodological)	N/A (Methodological)
20	Scalable and Defect-Tolerant Synthesis	Wafer-scale growth, defect control, yield	All quantum materials	MBE, CVD, Exfoliation	N/A (Methodological)

Part I: The Grand Challenges

1.1 The Mechanism of High-Temperature Superconductivity

1.1.1 Crisp Statement of the Open Problem

Despite more than three decades of intensive research since the discovery of cuprate superconductors in 1986 [1], there is no consensus on the microscopic pairing mechanism—the "glue"—that binds electrons into Cooper pairs at temperatures far exceeding the predictions of the conventional Bardeen-Cooper-Schrieffer (BCS) theory of electron-phonon coupling.[2] The central challenge is to develop a comprehensive theory that explains superconductivity in both cuprate and iron-based families and can guide the search for new high-T$_c$ materials.

1.1.2 Description of Current Work and Citations

The phenomenon of high-temperature superconductivity (HTS) is primarily observed in two major families of materials: copper-oxides (cuprates) and iron-based superconductors (FeSCs), also known as iron pnictides and chalcogenides.[1]

Cuprate Superconductors are characterized by their layered perovskite crystal structures, which contain planes of copper and oxygen (CuO$_2$) that are essential for superconductivity.[1] The parent compounds, such as La$_2

CuO_4$, are antiferromagnetic (AFM) Mott insulators, a state where strong on-site Coulomb repulsion prevents electron motion despite the bands being partially filled.[1] Superconductivity emerges when these parent compounds are chemically "doped" with charge carriers, either holes or electrons.[14] Cuprates are known for their high critical temperatures (T$_c$), with the record at ambient pressure being 135 K for a mercury-based cuprate, their high degree of electronic anisotropy, and a superconducting gap that predominantly exhibits d-wave symmetry, meaning it vanishes along certain directions in momentum space.[1]

Iron-Based Superconductors, discovered in 2008, also possess a layered crystal structure, with the key component being FeAs or FeSe planes.[1] A crucial distinction from cuprates is that their parent compounds are typically antiferromagnetic

metals, not Mott insulators.[1] This fundamental difference suggests that while magnetism is clearly important in both families, the role of strong electron correlation is different. FeSCs are intrinsically multi-band and multi-orbital systems, making their theoretical description more complex than the single-band Hubbard model often used for cuprates.[1] Experimentally, FeSCs tend to have lower T$_c$ values than the highest-T$

c$ cuprates, but they are also less anisotropic and more tolerant to impurities and defects, which is advantageous for practical applications like wire fabrication.[10] Their superconducting gap symmetry is also more complex and varied, often described as a sign-changing

s-wave (or $s{\pm}$) state, though other symmetries can contribute.[10]

The central theoretical problem is identifying the pairing "glue." It is widely accepted that the conventional electron-phonon coupling mechanism of BCS theory is insufficient to explain the high T_c values observed.[11] The McMillan limit, which estimates the maximum possible T_c from phonons, is around 40 K, well below the T_c of many cuprates.[1] Furthermore, the d-wave gap symmetry in cuprates is inconsistent with the isotropic attraction provided by phonons.[10] Several competing theories for this unconventional pairing have been proposed:

- **Spin-Fluctuation-Mediated Pairing:** This is a leading paradigm for both material families.[10] The universal feature of the HTS phase diagram is that superconductivity emerges when a parent antiferromagnetic phase is suppressed by doping or pressure.[11] This suggests that quantum fluctuations of the magnetic order (spin fluctuations) could provide the effective attractive interaction that pairs electrons. This mechanism naturally favors the momentum-dependent, sign-changing gap symmetries observed, such as d-wave in cuprates and $s\pm$-wave in FeSCs.[11] Evidence for this mechanism comes from inelastic neutron scattering experiments that observe a "resonance" peak in the magnetic excitation spectrum that appears only in the superconducting state and whose energy scales with T_c.[16] Recent ARPES studies on overdoped cuprates also point to spin fluctuations as the likely pairing glue.[17]
- **Resonating Valence Bond (RVB) Theory:** Proposed by P.W. Anderson shortly after the discovery of cuprates, this theory posits a radical departure from the standard Fermi liquid picture. It suggests that the ground state of the parent Mott insulator is not a magnetically ordered state but a quantum spin liquid composed of pre-formed, entangled electron pairs (singlets). Doping these mobile singlets is theorized to give rise to superconductivity.[11]
- **Competing Orders and Quantum Criticality:** The phase diagrams of cuprates are incredibly rich, featuring other electronic orders like "stripes" (a periodic modulation of spin and charge) and electronic nematicity (a breaking of rotational symmetry).[11] An ongoing debate centers on whether these orders are competitors that must be suppressed for superconductivity to thrive, or if their fluctuations are somehow essential to the pairing mechanism itself. The idea that superconductivity is enhanced near a quantum critical point—a zero-temperature phase transition masked by the superconducting dome—is a powerful and recurring theme.[11]
- **Orbital Fluctuations:** This mechanism is considered particularly relevant for the multi-orbital FeSCs. In addition to spin, the orbital character of the iron d-electrons represents another degree of freedom. Fluctuations in the orbital occupancy have been proposed as a possible pairing glue, potentially acting in

concert with spin fluctuations.[10]

1.1.3 Promising Directions

The path toward a definitive theory of HTS involves a multi-pronged strategy aimed at disentangling the complex interplay of charge, spin, orbital, and lattice degrees of freedom.

A primary direction is the **comparative study of different HTS families**. The discovery of FeSCs, and more recently nickel-based superconductors [19], has been invaluable. By identifying which properties are universal (e.g., quasi-2D structure, proximity to magnetism) and which are material-specific (e.g., Mott vs. metallic parent state, gap symmetry), researchers can distill the essential ingredients for high-T_c pairing.[12] Comparing cuprates and pnictides provides a powerful litmus test for any proposed theory; it must explain not only their similarities but also their stark differences.

Another key strategy involves **probing the underlying normal state**. Superconductivity often masks the electronic state from which it emerges. By applying extremely high magnetic fields (up to 100 Tesla) to suppress the superconducting state, researchers can use techniques like quantum oscillation measurements to map the Fermi surface and determine the effective mass of the charge carriers.[22] These experiments provide direct insight into the electron-electron interactions that are active before pairs form.

Continued advances in **spectroscopic techniques** are also critical. Angle-Resolved Photoemission Spectroscopy (ARPES) provides a direct view of the electronic band structure and the superconducting gap.[23] Pushing its resolution and combining it with time-resolved (pump-probe) capabilities allows for "movies" of how the electronic structure evolves. Resonant Inelastic X-ray Scattering (RIXS) has emerged as a powerful tool to probe the full momentum and energy dependence of spin and charge excitations, providing a detailed map of the "glue" spectrum that can be compared directly with theoretical predictions.[18]

Finally, the study of **simpler model systems** that exhibit unconventional superconductivity, such as magic-angle twisted bilayer graphene, offers a cleaner platform to study the physics of strong correlations and pairing, potentially free from some of the chemical and structural complexities of the cuprates and FeSCs.[25]

1.1.4 Impact of Solving this Problem

Resolving the mechanism of high-temperature superconductivity would be a landmark achievement with profound consequences.

- **Scientific Impact:** A complete theory of HTS would solve one of the longest-standing and most complex problems in condensed matter physics. It would necessitate a deep understanding of strongly correlated electron systems, providing a framework that would likely illuminate a wide range of other quantum materials phenomena, from Mott insulators to quantum spin liquids.[27] It would represent a triumph of quantum many-body theory.
- **Technological Impact:** The primary technological driver is the quest for a room-temperature, ambient-pressure superconductor. A predictive, microscopic theory is the most direct route to this goal, as it would enable *in silico* design of new materials with optimized properties, moving beyond the current paradigm of serendipitous discovery and laborious trial-and-error synthesis.[1] The realization of such a material would be revolutionary, enabling lossless power grids, super-efficient motors, widespread use of magnetic levitation for transport, and more affordable and powerful medical imaging devices like MRIs.[5]

1.1.5 Summary of the Role of Theory, Computation, and Experiment

The attack on the HTS problem is a textbook example of the synergy between theory, computation, and experiment.

- **Theory** develops and refines microscopic models (e.g., Hubbard, t-J models) and conceptual frameworks (e.g., spin-fluctuation, RVB) to explain the pairing glue.[11] It aims to predict unique experimental signatures that can distinguish between competing scenarios.
- **Computation** employs powerful numerical techniques like Quantum Monte Carlo (QMC), Dynamical Mean-Field Theory (DMFT), and Density Functional Theory (DFT) to solve the proposed models and calculate material-specific properties (e.g., band structure, magnetic susceptibility) that can be directly compared with experiments.[1]
- **Experiment** synthesizes high-quality single crystals and thin films, which are the essential starting point for any reliable measurement.[2] It then uses a sophisticated suite of probes to characterize these materials.
  Neutron scattering directly measures the momentum-resolved spin dynamics, providing a window into the magnetic glue.[1]
  ARPES maps the electronic structure and the momentum dependence of the superconducting gap.[17]
  Scanning Tunneling Microscopy (STM) provides real-space imaging of the electronic density of states.[1]
  Transport measurements in high magnetic fields are used to suppress

superconductivity and probe the underlying normal state.[22]

1.1.6 Ranked Order of National Labs and Justification

1. **Brookhaven National Laboratory (BNL):** BNL is arguably the world leader in experimental HTS research. Its unique **OASIS** facility combines atomic layer-by-layer molecular beam epitaxy (MBE) synthesis with immediate in-situ characterization by ARPES and STM, a capability that is critical for studying the sensitive surfaces of complex oxides and for systematically exploring the phase diagram.[17] This is complemented by the world-leading **National Synchrotron Light Source II (NSLS-II)**, which provides exceptionally bright and coherent X-ray beams for techniques like RIXS to probe magnetic and charge excitations.[18] BNL has a long and distinguished history in HTS research, with foundational work on the role of spin fluctuations and stripes, making it the best-positioned lab to continue leading this effort.[17]
2. **Oak Ridge National Laboratory (ORNL):** ORNL's primary strength is its world-leading suite of neutron scattering instruments at the **Spallation Neutron Source (SNS)** and the **High Flux Isotope Reactor (HFIR)**.[39] Since magnetic fluctuations are the leading candidate for the pairing glue, the ability to directly and comprehensively map these fluctuations is indispensable. This is coupled with strong materials synthesis programs and the immense computational power of the **Oak Ridge Leadership Computing Facility (OLCF)** for large-scale simulations of theoretical models.[40]
3. **SLAC National Accelerator Laboratory:** SLAC's **Stanford Synchrotron Radiation Lightsource (SSRL)** is a premier facility for ARPES and resonant soft X-ray scattering (RSXS).[41] These techniques provide essential, momentum-resolved information on the electronic structure, the superconducting gap, and the enigmatic pseudogap phase. The close collaboration between SLAC and Stanford University creates a powerful ecosystem of theory and experiment.
4. **Lawrence Berkeley National Laboratory (LBNL):** LBNL's **Advanced Light Source (ALS)** offers world-class capabilities for photoemission and scattering experiments that are crucial for HTS research.[44] The lab also hosts a very strong theoretical condensed matter group and leads the **US Magnet Development Program (USMDP)**, reflecting deep institutional expertise in the fundamental science and application of superconductivity.[46]
5. **Argonne National Laboratory (ANL):** ANL combines strong capabilities in materials synthesis, theory, and characterization at the **Advanced Photon Source (APS)**.[19] Its research comparing the newly discovered nickelate

superconductors to the established cuprates is particularly valuable for the strategy of identifying universal principles by contrasting different material families.[19]

6. **Los Alamos National Laboratory (LANL):** LANL's unique and critical contribution comes from the **National High Magnetic Field Laboratory (NHMFL) Pulsed Field Facility**. The ability to generate world-record magnetic fields approaching 100 Tesla is essential for suppressing superconductivity to study the underlying normal state physics, providing critical data on the Fermi surface and quantum criticality that constrain all pairing theories.[22]

1.1.7 References

.[1]

1.2 The Nature of the Pseudogap Phase

1.2.1 Crisp Statement of the Open Problem

In the phase diagram of hole-doped cuprate superconductors, a region exists at temperatures above the superconducting transition temperature (Tc) but below a characteristic temperature (T∗), where a partial gap opens in the electronic density of states, primarily in the antinodal region of the Brillouin zone. The fundamental nature of this "pseudogap" phase—whether it is a precursor state of incoherent Cooper pairs that paves the way for superconductivity, or a distinct, competing ordered phase that suppresses superconductivity—remains one of the most significant and unresolved questions in the field.[11]

1.2.2 Description of Current Work and Citations

The pseudogap is a defining feature of the underdoped cuprates, and its understanding is inextricably linked to the problem of high-T$_c$ superconductivity. It was first inferred from nuclear magnetic resonance (NMR) experiments that showed a drop in the Knight shift—a measure of the spin susceptibility—at a temperature T* well above T$_c$, suggesting the formation of spin-singlet pairs.[58] Subsequent experiments have revealed a rich phenomenology.

Experimental Signatures:

- **Spectroscopic Probes:** Angle-resolved photoemission spectroscopy (ARPES) and scanning tunneling microscopy (STM) provide the most direct evidence, visualizing a suppression of the electronic density of states near the Fermi level.[57] Crucially, ARPES shows that this gap is highly anisotropic, being largest in the "antinodal" regions of the Brillouin zone (near momentum states (

kx,ky) = (π,0) and (0,π)) and vanishing at the "nodes" (near (π/2,π/2)), exhibiting the same d-wave symmetry as the superconducting gap below T$_c$.[57] This momentum-space anisotropy leads to the formation of "Fermi arcs"—disconnected segments of a Fermi surface—instead of a closed contour.[61]

- **Transport and Thermodynamic Probes:** The onset of the pseudogap at T* is marked by clear signatures in transport measurements. The in-plane resistivity deviates from the linear-in-temperature behavior characteristic of the strange metal phase.[55] The Hall coefficient undergoes a dramatic change upon entering the pseudogap phase, consistent with a reconstruction of the Fermi surface from a large hole-like surface containing 1+p holes per Cu to small pockets containing only p holes, where p is the doping concentration.[54] The Nernst effect, a sensitive probe of quasiparticle entropy, also shows a clear onset at T*.[55]

Competing Theories:
The origin of the pseudogap is the subject of intense debate, which can be broadly categorized into two competing scenarios.

- **Precursor Pairing Scenario:** This viewpoint holds that the pseudogap is a state of pre-formed Cooper pairs that lack the long-range phase coherence required for superconductivity.[11] In this picture, pairing occurs at the high temperature T*, but a robust supercurrent only appears at the lower temperature T$_c$ when these pairs lock their quantum mechanical phases. Evidence supporting this includes the spin-singlet character seen in NMR and the shared d-wave symmetry of the pseudogap and superconducting gap. However, some transport measurements, such as the Nernst effect, have been interpreted as evidence against phase fluctuations being the primary cause of the pseudogap state.[55]
- **Competing Order Scenario:** This alternative theory proposes that the pseudogap is not related to pairing but is a distinct phase of matter characterized by a "hidden" order parameter that breaks one or more symmetries of the crystal lattice. This hidden order competes with superconductivity for electronic states at the Fermi level, thus suppressing T$_c$. A wealth of experimental evidence has emerged for various types of broken symmetry within the pseudogap phase:
  - **Time-Reversal Symmetry Breaking:** Polarized neutron diffraction and magneto-optical Kerr effect measurements have detected signatures of broken time-reversal symmetry, suggesting the presence of subtle magnetic order, such as orbital loop currents.[63]
  - **Rotational Symmetry Breaking (Nematicity):** STM experiments have observed that the electronic states on oxygen atoms oriented along the x and

y directions within a single CuO$_2$ unit cell are inequivalent, breaking the four-fold rotational symmetry of the lattice.[65] Resonant X-ray scattering has also linked this electronic nematicity directly to the pseudogap phase.[56]
  - **Translational Symmetry Breaking (Charge Order):** X-ray scattering has revealed the presence of charge-density-wave (CDW) order, a periodic modulation of the electron density, coexisting with the pseudogap.[67]

A crucial aspect of the modern understanding of the pseudogap is its termination at a critical doping p∗. There is strong evidence that this endpoint is a quantum critical point (QCP)—a zero-temperature phase transition—and that quantum fluctuations associated with this QCP are responsible for the anomalous "strange metal" properties and may even drive superconductivity.[54]

A recent and powerful constraint on theories comes from high-pressure transport experiments on Nd-LSCO, which show that the pseudogap critical doping p∗ can be tuned with pressure.[54] Crucially,

p∗ is always found to be less than or equal to pFS, the doping at which the Fermi surface topology changes from hole-like to electron-like. This suggests that the pseudogap can only exist on a hole-like Fermi surface, strongly implicating the antiferromagnetic zone boundary in its formation and favoring theories based on magnetic correlations over those based on purely charge-driven or nematic order.[54]

1.2.3 Promising Directions

Resolving the pseudogap mystery requires experiments that can unambiguously distinguish between the competing scenarios.

- **Definitive Identification of the Order Parameter(s):** The central experimental task is to identify the precise nature of the symmetry breaking in the pseudogap phase. This requires moving beyond detecting the presence of an order to characterizing its microscopic nature. Resonant elastic and inelastic X-ray scattering (REXS/RIXS) at modern synchrotron sources are powerful tools for detecting subtle charge, spin, and nematic orders and their fluctuations with momentum and energy resolution.[56]
- **Tuning through the Quantum Critical Point:** The ability to tune materials through the pseudogap QCP at p∗ is a key strategy. While chemical doping is one knob, it introduces disorder. The use of "clean" tuning parameters like hydrostatic pressure [54], uniaxial strain, or high magnetic fields [54] allows for a more controlled study of how the electronic properties evolve as the pseudogap phase is suppressed, providing critical information about the nature of the QCP.

- **Ultrafast Pump-Probe Spectroscopy:** Time-resolved techniques offer a unique window into the dynamics of competing orders. By using an ultrafast laser pulse to "pump" the system out of equilibrium and a second "probe" pulse to monitor its relaxation, one can disentangle the timescales associated with different phases. For example, one could observe whether melting the charge order enhances or suppresses superconducting correlations on a picosecond timescale, providing direct evidence for competition or cooperation.[70]
- **Theoretical Unification:** A major theoretical goal is to develop a framework that can unify the seemingly disparate experimental observations: the precursor pairing signatures (spin gap, d-wave symmetry), the multiple broken symmetries (nematicity, CDW), and the overarching constraint imposed by the Fermi surface topology. This likely requires moving beyond simple mean-field theories of a single order parameter to models that can capture the complex interplay and fluctuations of multiple nearly-degenerate ground states.

1.2.4 Impact of Solving this Problem

The nature of the pseudogap is not a peripheral issue; it is central to the entire HTS problem.

- **Scientific Impact:** A definitive understanding of the pseudogap phase would fundamentally clarify the nature of the "normal" state from which high-T$_c$ superconductivity emerges. It would resolve whether HTS arises from a conventional Fermi liquid instability, a phase-incoherent paired state, or a state of matter with novel broken symmetries.[61] This would be a profound advance in the physics of strongly correlated systems, with implications for a wide range of materials where multiple electronic orders compete.
- **Technological Impact:** The technological implications are directly tied to the goal of raising T$_c$. If the pseudogap is a competing phase that actively suppresses superconductivity, as some evidence suggests [66], then developing strategies to eliminate it—for example, through strain engineering or chemical design—could lead to a dramatic enhancement of T$_c$ in existing materials. If it is a necessary precursor, then understanding how to efficiently convert the pre-formed pairs into a coherent superconductor would be the key to designing better materials.

1.2.5 Summary of the Role of Theory, Computation, and Experiment

- **Theory** proposes candidate "hidden" ordered states (e.g., loop currents, pair density waves) and calculates their experimental signatures to guide the search.[54] It develops microscopic models (e.g., Hubbard, spin-fermion) that aim to capture the physics of the pseudogap, its QCP, and its interplay with superconductivity.[54]

- **Computation** provides numerical solutions to these complex many-body models using techniques like QMC and DMFT. These simulations generate predictions for spectral functions, phase diagrams, and correlation functions that can be directly compared with experimental data from ARPES, neutron scattering, and RIXS.[40]
- **Experiment** employs a wide array of sophisticated probes to map the phase diagram and search for signatures of broken symmetry. **ARPES** and **STM** map the gap structure in momentum and real space, respectively, revealing its d-wave symmetry and the existence of Fermi arcs.[57]
  Neutron and X-ray scattering are the primary tools for detecting spin, charge, and nematic order.[56]
  Transport and **thermodynamic** measurements under extreme conditions (high fields, high pressures) are essential for precisely mapping the phase boundaries (T* and p*) and probing the QCP.[54]

1.2.6 Ranked Order of National Labs and Justification

1. **SLAC National Accelerator Laboratory:** SLAC and its partner Stanford University have been consistent leaders in using ARPES to unravel the mysteries of the pseudogap for over two decades.[60] Their pioneering work established the momentum-space structure of the gap and provided some of the strongest evidence for its competitive relationship with superconductivity.[72] The continued development of advanced photoemission and X-ray scattering techniques at the **Stanford Synchrotron Radiation Lightsource (SSRL)** ensures their continued leadership.
2. **Brookhaven National Laboratory (BNL):** BNL's dual strengths in spectroscopy at the **NSLS-II** and advanced materials synthesis at **OASIS** make it uniquely suited to tackle this problem. Their landmark STM discovery of intra-unit-cell nematicity provided a new direction for the entire field.[66] The ability to use RIXS at NSLS-II to probe charge and nematic order and correlate it directly with electronic structure measurements provides a powerful, multi-modal approach.[67]
3. **Argonne National Laboratory (ANL):** ANL combines strong theory groups with premier experimental facilities. Their work on understanding the pseudogap in the context of competing orders, particularly charge density waves, has been influential.[61] The
   Advanced Photon Source (APS) is a key user facility for the hard X-ray scattering experiments needed to detect these subtle ordering phenomena.[68]
4. **Lawrence Berkeley National Laboratory (LBNL):** LBNL's **Advanced Light Source (ALS)** provides world-class capabilities for soft X-ray scattering and photoemission. The lab has a history of using a combination of complementary probes (ARPES, Kerr effect, time-resolved reflectivity) to build the case that the

pseudogap is a distinct phase of matter with a true thermodynamic phase transition at T*.[63]

5. **National High Magnetic Field Laboratory (NHMFL):** The unique facilities of the NHMFL, located at Los Alamos National Laboratory and Florida State University, are indispensable. The ability to reach extreme magnetic fields is essential for suppressing superconductivity to cleanly map the zero-temperature endpoint of the pseudogap phase (p*) and study the physics of the associated quantum critical point.[54]
6. **Oak Ridge National Laboratory (ORNL):** The primary role for ORNL in this specific problem lies in its computational leadership. The **Oak Ridge Leadership Computing Facility (OLCF)** provides the petascale and exascale computing resources necessary for the large-scale QMC and DMFT simulations required to test and refine the competing theoretical models of the pseudogap phase.[40]

1.2.7 References

.[11]

1.3 Realization and Control of Room-Temperature Superconductivity

1.3.1 Crisp Statement of the Open Problem

The ultimate practical goal in superconductivity research is the discovery and synthesis of a material that exhibits zero electrical resistance at or near ambient temperature (≈293 K) and pressure (1 atm). While recent claims involving high-pressure hydrides and other materials have generated significant excitement and controversy, a robust, reproducible, and theoretically understood room-temperature ambient-pressure superconductor remains elusive.[6]

1.3.2 Description of Current Work and Citations

The pursuit of room-temperature superconductivity (RTS) has historically followed two main paths: enhancing T_c in unconventional superconductors and pushing the limits of conventional BCS theory under extreme conditions.

High-Pressure Hydrides: This is currently the most successful, albeit experimentally challenging, avenue.

- **Theoretical Foundation:** The modern search was reignited by Neil Ashcroft's prediction that hydrogen, if pressurized enough to become metallic, would be a high-T_c superconductor due to its low mass and resulting high-frequency phonons.[11] Subsequent theoretical work has focused on hydrogen-rich compounds (superhydrides), where heavier elements provide a "chemical precompression" that stabilizes a hydrogen-dense, metallic lattice at pressures lower than required for pure hydrogen.[83] First-principles calculations based on Density Functional Theory (DFT) have become remarkably predictive in this area, successfully forecasting the stability and high T$_c$ of several compounds before their experimental synthesis.[85]

- **Experimental Breakthroughs and Controversies:** Using diamond anvil cells (DACs) to generate megabar pressures, experimental groups have confirmed superconductivity at record-breaking temperatures in several hydrides, including hydrogen sulfide (H$3S)*at 203K[13]andlanthanumhydride(LaH*{10}$) at ~250 K (-23 °C).[84] These materials are believed to be conventional BCS superconductors, a conclusion supported by the observation of an isotope effect.[13] However, the field has been rocked by controversy surrounding claims of near-room-temperature superconductivity in carbonaceous sulfur hydride (CSH) and nitrogen-doped lutetium hydride (LuNH). These claims, published in high-profile journals, have been retracted following intense scrutiny over data reproducibility and allegations of data manipulation, underscoring the immense difficulty of these experiments and the critical need for rigorous verification.[80]

Ambient Pressure Efforts: The search for an ambient-pressure RTS remains the ultimate prize.

- **Unconventional Superconductors:** The discovery of cuprates, with a record ambient-pressure T$_c$ of 135 K, continues to fuel hope.[1] However, after more than 30 years, progress in raising T$_c$ in this class has stalled, largely due to an incomplete understanding of the pairing mechanism (Problem 1.1).
- **Recent Claims and Refutations:** In 2023, a claim of ambient-pressure RTS in a copper-doped lead-apatite material named LK-99 went viral. However, a massive global effort to replicate the results quickly concluded that the material was not a superconductor, with its apparent levitation and resistivity drops being artifacts of other physical phenomena.[80] This episode further highlighted the community's intense interest and the need for careful, peer-reviewed validation.
- **Metastability and Non-Equilibrium Approaches:** A new strategy is emerging that focuses on creating metastable materials. The **pressure quench protocol (PQP)** involves synthesizing a superconducting phase at high pressure and then rapidly releasing the pressure at low temperature, "trapping" the material in its high-pressure structure at ambient pressure.[95] This has been successfully demonstrated for materials like FeSe, though the retained T$_c$ values are still low.[96] Another approach involves stabilizing new phases through epitaxial strain on a substrate, which has recently enabled ambient-pressure superconductivity

in nickelates.[20]

1.3.3 Promising Directions

- **AI-Driven Materials Discovery:** The chemical space of potential superconducting materials is astronomically large. The "trial and error" approach is inefficient. The most promising path forward involves a tight loop between theory, computation, and experiment, guided by artificial intelligence. High-throughput computational screening, where thousands of candidate materials are simulated using DFT, can identify promising structures and compositions. Machine learning (ML) models trained on these large datasets can then predict T_c and stability far more rapidly than direct computation, drastically accelerating the search for new candidates.[86]
- **Reducing Pressure in Hydrides:** For the successful hydride family, the primary goal is to lower the immense pressure requirements. This involves a computational and experimental search for ternary and quaternary hydrides where the combination of different elements can provide the optimal "chemical precompression" to stabilize the superconducting hydrogenic lattice at more accessible pressures.[83]
- **Metastability and Non-Equilibrium Engineering:** Exploring non-equilibrium pathways is a key frontier. This includes further development of pressure-quenching techniques [95] and using other methods like intense laser pulses (Floquet engineering) to transiently induce or enhance superconductivity.[101] While transient, these experiments can reveal the underlying interactions that favor superconductivity and guide the search for materials where these interactions can be stabilized.
- **Revisiting Fundamental Limits:** A recent theoretical analysis suggests that the upper bound on T_c imposed by fundamental physical constants (such as the electron mass and Planck's constant) is well above room temperature, lying between hundreds and a thousand Kelvin.[103] This provides a strong theoretical motivation that the search for an ambient RTS is not a fool's errand and that no fundamental law of physics forbids its existence.

1.3.4 Impact of Solving this Problem

The successful realization of a room-temperature, ambient-pressure superconductor would be one of the most transformative technological achievements in human history, with a revolutionary impact across nearly every sector of society.[81]

- **Energy:** A lossless electrical grid would eliminate the ~5% of energy currently wasted during transmission and distribution, resulting in massive energy savings and a corresponding reduction in greenhouse gas emissions.[5] It would also enable new, highly efficient methods for energy generation (e.g., in fusion reactors) and large-scale energy storage.

- **Computing and Electronics:** Superefficient electronics would drastically reduce the enormous energy consumption of data centers. It could also enable new computing paradigms, including large-scale quantum computers that rely on superconducting components.[21]
- **Transportation:** Widespread, affordable magnetic levitation (maglev) for high-speed trains and other forms of transport would become economically viable.[7] More powerful and efficient electric motors would transform electric vehicles and industrial machinery.
- **Medicine:** Medical technologies that rely on high-field superconducting magnets, such as Magnetic Resonance Imaging (MRI), would become significantly cheaper, more compact, and more widely accessible.[6]

1.3.5 Summary of the Role of Theory, Computation, and Experiment

The search for RTS is a deeply integrated effort where each component plays an indispensable role.

- **Theory** provides the fundamental understanding and guiding principles. This ranges from the BCS theory, which explains why high-frequency phonons in hydrides are desirable [83], to theories of unconventional pairing that guide the search in correlated materials. Theoretical work on fundamental limits defines the ultimate boundaries of what is possible.[103]
- **Computation** is the workhorse of modern materials discovery. High-throughput DFT calculations are used to screen vast libraries of potential materials, predicting their crystal structure, stability, and superconducting properties before they are ever made in a lab.[86] This is essential for navigating the immense chemical search space efficiently.
- **Experiment** is the ultimate arbiter of truth. This involves the challenging synthesis of new materials, often under extreme conditions such as the megabar pressures inside a diamond anvil cell.[84] It also requires rigorous, multi-modal characterization to prove superconductivity. The "gold standards" are the observation of zero resistance and the expulsion of magnetic fields (the Meissner effect). As the recent controversies have shown, claims must be backed by reproducible data and independent verification.[80]

1.3.6 Ranked Order of National Labs and Justification

The search for RTS is a multi-faceted problem requiring a combination of high-pressure synthesis, advanced materials characterization, and high-throughput computation. The ranking reflects a balance of these capabilities.

1. **Argonne National Laboratory (ANL):** ANL is exceptionally well-positioned due to its synergistic combination of world-class facilities and expertise. The **Advanced Photon Source (APS)** is crucial for in-situ X-ray diffraction characterization of materials inside diamond anvil cells, determining their crystal structure under pressure. ANL also has deep, established expertise in computational materials science and AI-driven discovery, which is essential for the high-throughput screening of candidate materials.[105] Furthermore, prominent theorists at ANL are key figures in the critical evaluation of new claims in the field.[80]
2. **Los Alamos National Laboratory (LANL):** LANL has a long and storied history in high-pressure science and materials physics, stemming from its national security mission. This includes specific expertise in the study of hydrides.[50] This is complemented by strong theoretical and computational groups adept at modeling materials under extreme conditions.[107] The presence of the **NHMFL Pulsed Field Facility** is also a key asset for characterizing the magnetic properties of any novel superconducting candidates.
3. **Lawrence Livermore National Laboratory (LLNL) / Sandia National Laboratories:** While not as prominent in the provided academic literature, these NNSA laboratories possess world-leading, mission-driven programs in high-pressure physics and materials science. Sandia, in particular, has documented expertise and facilities for high-pressure hydride synthesis and testing, a capability directly relevant to the most promising current avenue for RTS.[104]
4. **Lawrence Berkeley National Laboratory (LBNL):** LBNL's primary contribution is through its leadership of the **Materials Project**, the world's preeminent database for computed materials properties. This database is the foundational tool for any data-driven, high-throughput computational search for new superconductors.[110] This computational leadership is supported by experimental characterization capabilities at the **Advanced Light Source (ALS)**.
5. **Oak Ridge National Laboratory (ORNL):** ORNL's strength lies in its combination of characterization and computation. The **Spallation Neutron Source (SNS)** is a vital tool for determining the crystal structure of new materials, as neutrons are uniquely sensitive to the light hydrogen atoms that are critical in superhydrides.[113] This is paired with the massive computing power of the **Oak Ridge Leadership Computing Facility (OLCF)**, which is essential for large-scale screening calculations.

1.3.7 References

.[1]

1.4 A Comprehensive Theory of Strongly Correlated Electron Systems

1.4.1 Crisp Statement of the Open Problem

Many of the most fascinating quantum materials—including high-T$_c$ superconductors, heavy fermion compounds, quantum spin liquids, and Mott insulators—are "strongly correlated." In these systems, the kinetic energy of electrons is comparable to their mutual Coulomb repulsion energy. This competition invalidates the independent-electron approximation that underpins conventional band theory and Density Functional Theory (DFT), which have been immensely successful for simple metals and semiconductors. The monumental challenge is to develop a comprehensive, predictive theoretical framework and associated computational methods that can accurately describe the rich landscape of emergent quantum phenomena arising from these strong electronic interactions.[30]

1.4.2 Description of Current Work and Citations

The failure of standard theories to describe correlated systems has necessitated the development of a new theoretical and computational toolbox.

The Breakdown of Standard Theories: Standard band theory, and its modern implementation in DFT, describes electrons as independent particles moving in an average potential created by all other electrons and the ionic lattice. This approach fails qualitatively for strongly correlated systems. For example, it incorrectly predicts that Mott insulators like NiO—materials with partially filled d-electron bands that are insulating due to strong Coulomb repulsion—should be metals.[118]

Model Hamiltonians: To make the problem tractable, physicists often start with simplified models that aim to capture the essential physics. The canonical model for strong correlation is the **Hubbard model**, which simplifies the problem to electrons on a lattice with only two parameters: a kinetic hopping term (t) that allows electrons to move between sites, and an on-site Coulomb repulsion (U) that penalizes two electrons occupying the same site.[121] The competition between the delocalizing tendency of

t and the localizing effect of U gives rise to a rich phase diagram, including the celebrated Mott metal-insulator transition.[123] For more realistic descriptions of materials like the iron pnictides, multi-orbital Hubbard models that include Hund's coupling are necessary.[12]

Advanced Computational Methods: Solving these seemingly simple models for many particles is an extraordinarily difficult task due to the exponential growth of the quantum mechanical Hilbert space with system size.[31] A variety of powerful, non-perturbative methods have been developed:

- **Dynamical Mean-Field Theory (DMFT):** This is one of the most successful modern approaches. DMFT becomes exact in the limit of infinite dimensions (or infinite lattice coordination), where non-local spatial correlations vanish but local quantum fluctuations remain. It brilliantly maps the intractable lattice problem onto a solvable (though still challenging) quantum impurity problem that is embedded in a self-consistent, dynamical mean field.[30] DMFT has provided profound insights into the Mott transition, the nature of correlated metals, and heavy fermion physics. When combined with DFT in a scheme known as DFT+DMFT, it allows for realistic, material-specific calculations of correlated materials.[30]
- **Quantum Monte Carlo (QMC):** QMC methods use stochastic sampling to solve the many-body Schrödinger equation, capable of providing numerically exact results for certain models. However, their application to fermionic systems is severely hampered by the infamous "fermion sign problem." At low temperatures or for large systems, the contributions from different quantum paths can have opposite signs, leading to catastrophic cancellations that destroy the signal-to-noise ratio and cause the computational cost to grow exponentially.[127]
- **Tensor Network States (TNS):** This family of methods, which grew out of the Density Matrix Renormalization Group (DMRG) algorithm, provides a highly efficient way to represent the physically relevant, low-entanglement corner of the vast Hilbert space. **Matrix Product States (MPS)** are a TNS ansatz that is extraordinarily powerful for one-dimensional systems, allowing for nearly exact solutions.[130] Their generalization to two dimensions, **Projected Entangled Pair States (PEPS)**, is a major frontier of research but is computationally much more demanding and complex to implement.[130]

1.4.3 Promising Directions

Progress in this area hinges on advancing our theoretical and computational capabilities.

- **Beyond DMFT:** A primary focus is on developing extensions to DMFT that can systematically incorporate the non-local spatial correlations that are neglected in the single-site approximation. These correlations are crucial for describing phenomena like d-wave superconductivity, quantum critical phenomena, and spin liquids. Promising approaches include cluster DMFT (which solves an impurity

problem for a small cluster of sites instead of a single site) and diagrammatic extensions like the Dynamical Vertex Approximation (DΓA).
- **Tackling the Sign Problem:** Any fundamental breakthrough that mitigates or circumvents the fermion sign problem in QMC would be transformative. This is an active area of research, with ideas ranging from complex Langevin methods to new computational bases, although a general solution remains elusive.
- **Methodological Synergy:** A powerful strategy is to combine the strengths of different methods. For example, using the highly accurate TNS methods as "impurity solvers" for DMFT calculations, or using machine learning techniques to find better variational wavefunctions for QMC simulations, could lead to more powerful and accurate hybrid algorithms.[124]
- **Quantum Simulation:** An exciting alternative to classical computation is to use highly controllable artificial quantum systems, such as ultracold atoms trapped in optical lattices, to directly realize and study models like the Hubbard model.[27] By tuning the laser parameters, experimentalists can control the hopping (t) and interaction (U) strengths and directly measure the resulting phases and dynamics in regimes that are intractable for classical computers.[128] This creates a new paradigm of "computation by experiment."

1.4.4 Impact of Solving this Problem

Developing a comprehensive and predictive theory of strongly correlated systems would represent a paradigm shift in the physical sciences.

- **Scientific Impact:** Such a theory would constitute a "grand unification" for a vast and important area of condensed matter physics. It would provide the fundamental framework needed to solve many of the other grand challenges discussed in this review, including the mechanism of high-T$_c$ superconductivity (Problem 1.1), the nature of the pseudogap (1.2), the physics of quantum spin liquids (3.1), and the nature of metal-insulator transitions (4.3). It would replace the current patchwork of disparate, often phenomenological models with a single, coherent, and predictive theoretical structure.
- **Technological Impact:** The impact would be the dawn of true *ab initio* quantum materials design. Currently, the discovery of new functional materials relies heavily on chemical intuition, experimental trial-and-error, and serendipity. A predictive theory of strong correlations would allow scientists to design new materials with desired functionalities—such as a higher-T$_c$ superconductor or a more efficient thermoelectric material—on a computer, before attempting the costly and time-consuming process of synthesis and characterization.[118] This would accelerate the pace of materials innovation at an unprecedented rate.[116]

1.4.5 Summary of the Role of Theory, Computation, and Experiment

This is a fundamentally theoretical and computational grand challenge, with experiment playing a critical benchmarking and validation role.

- **Theory:** The primary goal is to formulate the correct mathematical frameworks and conceptual language (e.g., going beyond the quasiparticle picture) to describe these systems. This involves the development of new analytical tools and powerful approximation schemes like DMFT and TNS.[30]
- **Computation:** Computation is the essential tool for implementing and solving the equations proposed by theory. The development of more powerful algorithms and the use of the world's largest supercomputers are absolutely necessary to make quantitative predictions for realistic models of materials.[31]
- **Experiment:** Provides the ultimate ground truth. High-precision measurements of spectral functions (via ARPES), magnetic excitations (via neutron scattering), and thermodynamic properties on well-characterized material samples provide stringent tests that any valid theory must pass.[16] Furthermore, quantum simulators provide a novel experimental platform to directly test the validity of the underlying theoretical *models* themselves.[27]

1.4.6 Ranked Order of National Labs and Justification

This problem is heavily weighted towards world-class theoretical and computational capabilities.

1. **Oak Ridge National Laboratory (ORNL):** ORNL is a powerhouse for computational materials science. The **Oak Ridge Leadership Computing Facility (OLCF)** hosts some of the world's fastest supercomputers, including the exascale machine Frontier, which are indispensable for the large-scale QMC and DMFT simulations required to tackle this problem.[135] This is complemented by a world-class Materials Theory group with deep expertise in these computational methods and their application to correlated materials.[137] The close proximity to the SNS allows for tight theory-experiment feedback.
2. **Argonne National Laboratory (ANL):** ANL has an exceptionally strong and broad theory and computation program, spanning its Materials Science and Mathematics and Computer Science divisions.[138] The **Argonne Leadership Computing Facility (ALCF)** provides top-tier supercomputing resources. ANL researchers are at the forefront of developing and applying a wide range of methods, from DFT and QMC to the application of AI/ML for materials science.[106]
3. **Los Alamos National Laboratory (LANL):** LANL has a deep and historically

significant expertise in the theory of strongly correlated systems, particularly in the context of f-electron materials (heavy fermions) and quantum magnetism.[107] Their theoretical division has strong capabilities in developing and applying DMFT, QMC, and molecular dynamics, and they are actively creating new software tools for modeling these complex systems.[107]

4. **Brookhaven National Laboratory (BNL):** BNL's strength lies in its renowned Condensed Matter Theory group, which works in extremely close collaboration with the lab's world-leading experimental programs at the NSLS-II and the Center for Functional Nanomaterials (CFN).[140] Their research portfolio includes the theory of high-T$_c$ superconductivity, non-equilibrium physics, and tensor network methods.[141] This tight integration with cutting-edge experiments is crucial for developing theories that are grounded in physical reality.
5. **Lawrence Berkeley National Laboratory (LBNL):** LBNL has a strong theory program within its Materials Sciences division, with deep connections to the elite theory group at UC Berkeley.[129] The lab's
National Energy Research Scientific Computing Center (NERSC) provides the necessary high-performance computing resources. LBNL's leadership of the Materials Project also demonstrates a deep institutional commitment to computational materials science.[110]

1.4.7 References

.[12]

1.5 The Realization of a Fault-Tolerant Topological Qubit

1.5.1 Crisp Statement of the Open Problem

The central challenge in building a scalable quantum computer is overcoming decoherence: the degradation of fragile quantum states due to environmental noise. Topological quantum computation offers a paradigm-shifting solution by encoding quantum information non-locally in the topological properties of a material, rendering the qubit inherently robust against local perturbations. The primary experimental and theoretical goal is to create, control, and braid exotic quasiparticles known as non-Abelian anyons—with Majorana zero modes being the leading candidate—to realize a fault-tolerant topological qubit.[8]

1.5.2 Description of Current Work and Citations

The pursuit of a topological qubit is a convergence of condensed matter physics, materials science, and quantum information theory.

Theoretical Foundation:

- **Topological Protection:** Unlike conventional qubits (e.g., superconducting transmons, trapped ions) where quantum information is stored in local degrees of freedom (like the spin of an electron or the charge on a capacitor), a topological qubit stores information in the global, collective state of the system. This information is encoded in the degenerate ground state of a topologically ordered phase of matter. Because the information is non-local, it cannot be corrupted by local noise sources like stray electromagnetic fields or charge fluctuations. This intrinsic "hardware-level" protection promises to dramatically reduce the immense overhead required for software-based quantum error correction in other architectures.[8]
- **Non-Abelian Anyons and Braiding:** In two-dimensional systems, quasiparticles are not restricted to being bosons or fermions; they can be "anyons." When two identical anyons are exchanged, the system's wavefunction acquires a phase $e^{i\theta}$. For "non-Abelian" anyons, this exchange operation is represented not by a simple phase factor, but by a unitary matrix that acts on the degenerate ground state subspace. The process of physically moving these anyons around each other, known as "braiding," therefore corresponds directly to performing a quantum gate operation. This process is topologically robust: the outcome depends only on the topology of the braid, not on the precise path taken.[145]
- **Majorana Zero Modes (MZMs):** The most sought-after candidate for realizing non-Abelian anyons in a solid-state system is the Majorana zero mode. An MZM is a remarkable quasiparticle that is its own antiparticle, described by a real fermion operator ($\gamma=\gamma^\dagger$).[146] While a single MZM is half a fermion, a pair of spatially separated MZMs,
  γ_1 and γ_2, can be combined to define a conventional fermion, $c=(\gamma_1+i\gamma_2)/2$. The occupation state of this fermion (either 0 or 1) defines a qubit. Because the constituent MZMs are physically separated, the qubit state is stored non-locally, providing the basis for topological protection.[148]

Experimental Platforms:
The experimental effort is focused on engineering systems that host topological superconductivity, the necessary ingredient for creating MZMs.

- **Semiconductor-Superconductor Nanowires:** This is the most intensely studied platform. The canonical proposal involves a semiconductor nanowire with strong spin-orbit coupling (e.g., InAs, InSb) brought into close proximity with a conventional s-wave superconductor (e.g., Al, NbTiN). When a magnetic field is applied parallel to the wire, the system can be driven into a topological superconducting phase that hosts MZMs localized at the wire ends.[142]

- **Experimental Signatures and Challenges:** The primary experimental signature for an MZM is a zero-bias conductance peak (ZBCP) in a tunneling spectroscopy measurement, which should be quantized to a value of 2e2/h. While ZBCPs have been widely reported, their interpretation is highly controversial. It has become clear that trivial, non-topological states—such as Andreev bound states formed by disorder or Kondo resonances—can produce ZBCPs that are nearly indistinguishable from a true MZM signature.[150] This ambiguity has plagued the field and led to the retraction of at least one high-profile claim.[153]
- **Microsoft's Station Q and the "Majorana 1" Chip:** Microsoft has made a massive, long-term investment in the nanowire platform through its Station Q research centers.[153] Their recent work has focused on moving beyond simple ZBCP measurements. They have developed a device called "Majorana 1" based on high-quality InAs-Al heterostructures, which they term "topoconductors".[157] Their approach uses quantum dots coupled to the nanowire to perform a "topological gap protocol" and measure the fermion parity of the MZM pair. While they have reported passing initial milestones, their claims remain the subject of intense debate and skepticism within the research community, which awaits more definitive and transparent evidence.[154]

1.5.3 Promising Directions

Given the challenges, the field is actively pursuing several crucial directions.

- **Developing "Smoking Gun" Signatures:** There is a broad consensus that the community must move beyond relying on ZBCPs. The most definitive proof would be a braiding experiment demonstrating non-Abelian statistics, but this is extraordinarily challenging. More accessible intermediate goals include using interferometry to probe the non-local correlations between MZMs at opposite ends of a wire, or observing a 4π-periodic Josephson effect in a junction containing MZMs.
- **Improving Materials Quality:** The central obstacle is materials science. Disorder in the semiconductor nanowires and imperfections at the semiconductor-superconductor interface create a proliferation of trivial sub-gap states that mimic MZM signatures.[152] Progress is critically dependent on improving materials synthesis techniques to create cleaner, more uniform hybrid structures. The development of epitaxial growth of the superconducting shell directly onto the nanowire was a significant step in this direction.[147]
- **Leveraging Machine Learning for Device Characterization:** A novel and promising approach is to use machine learning to tackle the disorder problem. By training a neural network on simulated conductance data, it is possible to invert experimental transport data to determine the specific, unknown disorder

landscape of a given nanowire device.[161] This could provide a powerful tool to distinguish true topological MZMs from disorder-induced impostors and could guide the fabrication of better devices.

- **Exploring Alternative Material Platforms:** Given the persistent challenges with nanowires, exploring alternative platforms is crucial. Promising candidates include heterostructures of quantum anomalous Hall insulators and superconductors, which can host chiral Majorana modes at their edges [148], and intrinsic topological superconductors like iron-based materials, which may not require complex hybrid engineering.

1.5.4 Impact of Solving this Problem

- **Scientific Impact:** The unambiguous creation, manipulation, and detection of a non-Abelian anyon would be a landmark discovery in fundamental physics. It would experimentally confirm a new form of particle statistics beyond bosons and fermions, realizing a concept that has been purely theoretical for decades.
- **Technological Impact:** A successful topological qubit would revolutionize the field of quantum computing. By building fault tolerance directly into the physical hardware, it could drastically reduce the enormous qubit overhead required for quantum error correction in conventional architectures (which can require thousands of physical qubits to create one logical qubit). This could provide a more direct and scalable path to a large-scale, useful quantum computer capable of solving problems in medicine, materials science, and cryptography that are intractable for classical machines.[142]

1.5.5 Summary of the Role of Theory, Computation, and Experiment

- **Theory** provides the foundational concepts of topological quantum computation, non-Abelian statistics, and Majorana physics.[145] Theorists propose new material platforms and device geometries for realizing and detecting MZMs and predict their experimental signatures.[142]
- **Computation** plays a critical role in simulating the behavior of proposed devices. Large-scale numerical simulations are essential for calculating the topological phase diagrams and predicting transport signatures, especially in the presence of realistic disorder. These simulations are crucial for interpreting complex experimental data and distinguishing true topological effects from trivial artifacts.[152]
- **Experiment** faces the core challenge of materials synthesis and device fabrication—growing and patterning the complex hybrid structures with atomic-level precision—and performing ultra-low-temperature measurements (tunneling spectroscopy, interferometry) to probe for MZM signatures.[147]

1.5.6 Ranked Order of National Labs and Justification

The realization of a topological qubit is a highly interdisciplinary problem at the intersection of materials science, condensed matter physics, and quantum information science. Leadership requires deep expertise across all these areas.

1. **Microsoft Quantum (Station Q):** While a corporate laboratory, Station Q, in partnership with leading academic institutions (UC Santa Barbara, Purdue, TU Delft), is the undisputed global leader in the experimental pursuit of Majorana-based qubits.[149] They have made an unparalleled investment in developing the materials, fabrication processes, and measurement techniques required. Despite the controversies surrounding their claims, their focused, large-scale effort continues to drive the field forward.
2. **Argonne National Laboratory (ANL):** ANL is the lead institution for the **Q-NEXT** National QIS Research Center, which is focused on developing quantum interconnects and establishing national foundries for quantum materials.[162] This mission is directly relevant to producing the high-quality materials needed for topological qubits. ANL's expertise in materials science, nanofabrication at the **Center for Nanoscale Materials (CNM)**, and quantum information science makes it a central player.[164]
3. **Oak Ridge National Laboratory (ORNL):** ORNL leads the **Quantum Science Center (QSC)**, which has an explicit strategic thrust focused on designing materials for topological quantum computing.[163] Their world-leading expertise in neutron scattering can be used to characterize the magnetic materials often required in these platforms, and their synthesis and characterization capabilities are top-tier.[169]
4. **Brookhaven National Laboratory (BNL):** BNL leads the **Co-design Center for Quantum Advantage (C2QA)**, which aims to achieve quantum advantage by improving materials and device properties.[166] BNL has deep expertise in the physics and synthesis of topological materials, particularly the quantum anomalous Hall insulator/superconductor hybrids that represent an alternative platform for MZMs. Their advanced characterization tools at **NSLS-II** and **CFN** are critical assets.[170]
5. **Lawrence Berkeley National Laboratory (LBNL):** LBNL leads the **Quantum Systems Accelerator (QSA)** and has extensive expertise in fabricating and characterizing quantum devices.[163] Its **Molecular Foundry** is a state-of-the-art user facility for nanofabrication, and the **Advanced Light Source (ALS)** is crucial for characterizing the electronic structure of the component materials.
6. **Fermi National Accelerator Laboratory (FNAL):** FNAL is the lead institution for

the **Superconducting Quantum Materials and Systems Center (SQMS)**, which is focused on understanding and eliminating decoherence in superconducting devices.[162] While their primary focus is on conventional superconducting qubits, their deep expertise in the fundamental physics of superconductivity and materials science is highly relevant to the challenge of engineering robust topological superconductors.

1.5.7 References

- [8]

Part II: Topological and Geometrical Frontiers

2.1 Classification and Realization of Novel Topological Phases

2.1.1 Crisp Statement of the Open Problem

Beyond the now-established topological insulators (TIs) and Weyl/Dirac semimetals, theory predicts a vast and exotic "zoo" of new topological phases of matter, including axion insulators, topological crystalline insulators, and higher-order topological insulators. The central challenge is to experimentally realize these novel phases in real materials, unambiguously verify their topological character through experimental signatures, and develop a comprehensive classification scheme that encompasses all possible crystalline symmetries.[174]

2.1.2 Description of Current Work and Citations

The discovery of TIs, protected by time-reversal symmetry (TRS), opened a new paradigm in condensed matter physics based on the topological properties of electronic band structures.[4] Current research seeks to expand this paradigm by considering other symmetries and more complex topological structures.

Topological Crystalline Insulators (TCIs):

- **Concept:** In TCIs, the topological protection of surface states is provided not by TRS, but by a crystal point group symmetry, such as mirror symmetry.[176] This means that gapless surface states are only guaranteed to exist on surfaces that preserve this symmetry.
- **Key Properties:** A hallmark of TCIs like SnTe is the presence of multiple Dirac cones on their high-symmetry surfaces (e.g., the (001) surface), in contrast to the single Dirac cone found in many simple TIs like Bi$_2Se_3$.[175] These multiple Dirac cones can have distinct orbital textures, which are crucial for determining the

material's response to external fields.[175]

- **Experimental Realization:** The first experimental evidence for a TCI was found in SnTe using ARPES, which observed the predicted Dirac-cone surface states.[179] Subsequent work using Fourier-transform STM has been used to probe the orbital texture of these surface states in Pb$_{1-x}
Sn_x$Se, another prototypical TCI.[175]

Axion Insulators:

- **Concept:** An axion insulator is a three-dimensional magnetic topological insulator where the surface states are all gapped due to broken TRS, but the bulk retains a symmetry (like inversion) that protects a quantized magnetoelectric response.[174] This response is described by a term in the electromagnetic Lagrangian, θ2πhe2E⋅B, where the axion field θ is quantized to π.[181]
- **Key Properties:** The defining characteristic is the half-quantized surface anomalous Hall conductivity of ±21he2 on surfaces where TRS is broken.[181] In a thin film geometry with opposite magnetizations on the top and bottom surfaces, these contributions cancel, leading to a bulk insulator with zero Hall conductance—the axion insulator state.[182]
- **Experimental Realization:** The axion insulator state has been experimentally realized in magnetic TI sandwich heterostructures, where two magnetically doped TI layers with different coercive fields are separated by a non-magnetic TI spacer. By sweeping an external magnetic field, an antiparallel alignment of the top and bottom layer magnetizations can be achieved, resulting in a zero Hall plateau characteristic of the axion state.[182] The intrinsic magnetic topological insulator MnBi$_2
Te_4$ is also a prime candidate, predicted to realize an axion insulator state in its even-layered form.[185]

Higher-Order Topological Insulators (HOTIs):

- **Concept:** HOTIs generalize the conventional bulk-boundary correspondence. A conventional d-dimensional TI has gapless states on its (d−1)-dimensional boundary (e.g., 2D surfaces for a 3D TI). An nth-order TI has gapless states on its (d−n)-dimensional boundary.[177] For example, a second-order 3D TI is insulating in the bulk and on its 2D surfaces, but possesses 1D conducting "hinge" states. A third-order 3D TI would have 0D "corner" states.[188]
- **Key Properties:** The existence of these lower-dimensional boundary modes is protected by crystalline symmetries, such as rotation or mirror symmetries, often in combination with TRS.[188] The specific nature of the hinge/corner states (e.g., chiral or helical) depends on the protecting symmetries.[188]

- **Experimental Realization:** Direct observation of HOTIs in solid-state materials is challenging. SnTe has been proposed as a candidate for a helical HOTI.[188] Much of the experimental progress has been made in artificial "metamaterial" systems, such as photonic crystals, acoustic crystals, and topoelectric circuits, which allow for precise engineering of the required symmetries and are easier to probe.[189] These experiments have successfully demonstrated the existence of topological corner and hinge states.

2.1.3 Promising Directions

- **Theory-Guided Materials Discovery:** The frameworks of topological quantum chemistry and symmetry-based indicators provide a systematic way to search for new topological materials.[175] By screening existing materials databases (like the Materials Project) using these theoretical tools, researchers can identify promising candidates for experimental synthesis and verification.
- **Probing Hinge and Corner States:** A major experimental challenge is to develop techniques that can unambiguously detect the lower-dimensional boundary states of HOTIs. This requires probes with high spatial resolution, such as STM, that can distinguish hinge or corner modes from bulk or surface states. Transport measurements designed to specifically probe hinge conduction are also a key direction.[188]
- **Exploring Quasicrystals:** Quasicrystals, which possess rotational symmetries forbidden in conventional crystals (e.g., eightfold rotation), offer a new platform to realize novel topological phases without crystalline counterparts. Recent theoretical work has proposed the existence of HOTIs in 3D quasicrystalline lattices.[193]
- **Non-Equilibrium and Driven Systems:** Floquet engineering—using periodic driving with light to modify a material's effective Hamiltonian—provides a powerful tool to create "on-demand" topological phases that do not exist in equilibrium. This has been theoretically proposed as a way to generate HOTIs from trivial or first-order insulators.[177]

2.1.4 Impact of Solving this Problem

- **Scientific Impact:** The discovery and classification of the full range of topological phases would represent a fundamental completion of our understanding of the ground states of matter, on par with the classification of symmetry-breaking phases. It would establish a complete "periodic table" of topological insulators and superconductors based on symmetry and dimensionality.
- **Technological Impact:** Each new class of topological material offers potential for

new applications.

- ○ **TCIs:** The presence of multiple, orbitally distinct Dirac cones offers new degrees of freedom for valleytronic and spintronic applications.[175]
- ○ **Axion Insulators:** The quantized magnetoelectric effect could be used to create novel electronic and magnetic devices, and the axion electrodynamics is linked to concepts in high-energy physics.[174]
- ○ **HOTIs:** The protected hinge states offer the potential for creating dissipationless 1D interconnects within a 3D material, a potential boon for future electronic circuits.[188]

2.1.5 Summary of the Role of Theory, Computation, and Experiment

- **Theory:** Plays a leading role in this area. Theorists develop the classification schemes based on symmetry (e.g., space groups, magnetic groups) and mathematical tools (K-theory, topological quantum chemistry) to predict new phases and their topological invariants.[176] They also propose model Hamiltonians that realize these phases.[188]
- **Computation:** Uses first-principles methods like DFT to screen real materials databases for candidates that match the theoretical predictions. Calculations of band structures, Berry curvature, and topological invariants (like Z$_2$ indices or Chern numbers) are essential for identifying promising materials.[181]
- **Experiment:** The ultimate goal is to synthesize the predicted materials and verify their topological nature. **ARPES** is the primary tool for directly visualizing the bulk band inversion and the characteristic surface/edge/hinge states.[179]
  STM provides real-space imaging of these states and their scattering properties.[175]
  Transport measurements (e.g., Hall effect, nonlocal transport) are used to detect the quantized responses associated with the topological states.[182]

2.1.6 Ranked Order of National Labs and Justification

The search for novel topological phases is heavily reliant on a tight feedback loop between advanced theory, high-throughput computation, and precision spectroscopy.

1. **Lawrence Berkeley National Laboratory (LBNL):** LBNL is exceptionally strong in this area due to the co-location of the **Materials Project**, which provides the database for computational screening [111], the
   Advanced Light Source (ALS) for ARPES and other spectroscopic characterization, and the **Molecular Foundry** for synthesis and nanofabrication.[195] This is complemented by world-class theory groups at LBNL and nearby UC Berkeley, creating a complete ecosystem for topological materials

discovery.[129]

2. **Argonne National Laboratory (ANL):** ANL has a strong program in topological materials, with expertise in both topological semimetals and superconductors.[197] The **Advanced Photon Source (APS)** provides premier capabilities for X-ray scattering and diffraction to characterize the crystal structure and electronic order of new materials. The lab's **Center for Nanoscale Materials (CNM)** and strong computational materials science groups contribute to a comprehensive research effort.[138]
3. **Brookhaven National Laboratory (BNL):** BNL's **NSLS-II** is a state-of-the-art synchrotron ideal for ARPES and RIXS studies of the electronic and magnetic structure of candidate materials. The lab's expertise in magnetic topological insulators like MnBi$_2Te_4$ and its heterostructures is directly relevant to the search for axion insulators.[171] The strong condensed matter theory group provides crucial theoretical support.[141]
4. **Oak Ridge National Laboratory (ORNL):** ORNL's primary contribution is through its expertise in neutron scattering at the **SNS** and **HFIR**, which is essential for determining the complex magnetic structures that protect many of the new topological phases (e.g., in axion insulators). Its world-class synthesis capabilities and computational resources at the **OLCF** are also key assets.
5. **Ames National Laboratory:** Ames Lab has a long and distinguished history in materials synthesis and characterization, with a particular focus on magnetic and rare-earth materials. Their work on understanding magnetism in topological insulators is directly relevant to the search for intrinsic magnetic TIs and axion insulators.[198]

2.1.7 References

.[4]

2.2 Harnessing the Quantum Anomalous Hall Effect at Higher Temperatures

2.2.1 Crisp Statement of the Open Problem

The quantum anomalous Hall (QAH) effect is the realization of a quantized Hall resistance in the absence of any external magnetic field, driven by a material's intrinsic magnetization and spin-orbit coupling. While the QAH effect has been experimentally observed, it has only been realized at extremely low, cryogenic temperatures (typically below 2 K). The central challenge is to discover or engineer materials that exhibit a robust QAH effect at higher, more technologically practical temperatures, ideally approaching the liquid nitrogen range (77 K) or beyond.[204]

2.2.2 Description of Current Work and Citations

The QAH effect is a topological quantum phenomenon where a 2D material becomes a "Chern insulator," characterized by a non-zero integer topological invariant called the Chern number (C).[208] This non-trivial topology dictates the existence of dissipationless, chiral edge states that carry current without resistance, analogous to the edge states in the integer quantum Hall effect. The key requirements for a material to exhibit the QAH effect are the presence of both ferromagnetism (to break time-reversal symmetry) and strong spin-orbit coupling (to open a topologically non-trivial band gap).[209]

Current research has focused on several material platforms:

- **Magnetically Doped Topological Insulators (TIs):** This was the first platform where the QAH effect was successfully realized. By doping a 3D TI thin film, such as $(Bi,Sb)_2Te_3$, with magnetic ions like chromium (Cr) or vanadium (V), a ferromagnetic state can be induced. The combination of magnetism and the TI's inherent strong spin-orbit coupling opens a gap in the surface states, leading to the QAH effect.[204] While this approach was a landmark success, the observation temperature has remained stubbornly low, typically around 30 mK initially, and pushed to ~2 K only with significant materials engineering.[204] The primary limitation is that the random distribution of magnetic dopants introduces disorder and spatial inhomogeneities, which suppress the magnetic ordering temperature (Curie temperature, T_C) and the size of the topological gap.[204]
- **Intrinsic Magnetic Topological Insulators:** To overcome the disorder issue of doped TIs, the search has shifted to intrinsic magnetic TIs, which are stoichiometric compounds with inherent magnetic order. The leading candidate is **$MnBi_2Te_4$**, an antiferromagnetic TI.[210] In thin films with an odd number of layers, it has an uncompensated ferromagnetic moment and is predicted to be a QAH insulator. The QAH effect has been observed in this material, but again, only at low temperatures (~1.4 K) and often requiring an external magnetic field to align all layers ferromagnetically.[207] The challenge is that the intrinsic magnetic ordering is antiferromagnetic, which does not produce a net QAH effect, and the ferromagnetic state is only stable at low temperatures.
- **Heterostructures and Proximity Effects:** A promising strategy involves creating van der Waals heterostructures. This can involve stacking a 2D material with strong spin-orbit coupling (like germanene or a TI) on top of a 2D ferromagnetic insulator.[204] The magnetic proximity effect induces magnetism in the topological layer, potentially leading to a QAH state with a cleaner interface than in doped systems. Theoretical calculations suggest that strain engineering in germanene/$Cr_2Ge_2Te_6$ heterostructures could enhance the QAH temperature to as high as

64 K.[204]

- **Moiré Materials:** The discovery of correlated states in twisted bilayer graphene and other moiré systems has opened a new avenue for the QAH effect. In some of these systems, strong electron-electron interactions can spontaneously break time-reversal symmetry and drive the system into a ferromagnetic state with a non-trivial Chern number. The QAH effect has been observed in twisted bilayer graphene aligned with hexagonal boron nitride, and more recently, a fractional QAH effect has been seen in twisted TMDs, but these phenomena also occur only at very low temperatures.[204]

2.2.3 Promising Directions

Raising the QAH temperature requires simultaneously increasing both the magnetic ordering temperature (T_C) and the size of the topological band gap (Δg). The operating temperature will always be limited by the smaller of these two energy scales.[204]

- **Materials Engineering in Intrinsic Systems:** For $MnBi_2Te_4$-based systems, a key direction is to engineer the interlayer magnetic coupling to favor ferromagnetism over antiferromagnetism. This can be pursued by intercalating other layers, for example, creating heterostructures like $(MnBi_2Te_4)(Sb_2Te_3)n$, which could stabilize a ferromagnetic ground state and a large topological gap.[210] Another approach is chemical substitution, for instance, replacing some Mn with other magnetic ions or Bi with Sb to tune the magnetic interactions and electronic structure.
- **High-Throughput Search for New Materials:** The conflicting requirements of strong magnetism (often found in 3d transition metals with weaker spin-orbit coupling) and large topological gaps (found in heavy 5d elements with weaker magnetism) make materials discovery challenging. High-throughput computational screening, combining DFT with topological analysis, is a powerful tool to search the vast chemical space for new intrinsic QAH insulators with both high T_C and large gaps.[212] Recent theoretical predictions point to materials like Li-decorated iron chalcogenides as potential room-temperature QAH systems.[212]
- **Interface and Surface Engineering:** For heterostructure-based approaches, controlling the interface is paramount. Recent work has shown that an active capping layer, such as CrO_x, can both suppress environmental degradation and substantially boost the ferromagnetism in doped TIs, leading to the observation of QAH signatures at a record high of 10 K without the need for electric-field gating.[205] This highlights the critical role of surface chemistry and interface engineering.
- **Exploring New Mechanisms:** The realization of interaction-driven QAH in moiré

systems suggests that strong correlations, rather than just intrinsic spin-orbit coupling, can be a route to topological phases. Exploring other flat-band systems for correlated QAH states is a promising, albeit low-temperature, frontier.

2.2.4 Impact of Solving this Problem

Achieving a robust QAH effect at higher, more practical temperatures would have a significant impact on both fundamental science and technology.

- **Scientific Impact:** It would provide a robust platform for studying a wide range of topological quantum phenomena that are currently difficult to access. For example, the interface between a QAH insulator and a conventional superconductor is predicted to host chiral Majorana fermions, which are a key ingredient for topological quantum computation (Problem 1.5). A high-temperature QAH material would make such experiments far more feasible.
- **Technological Impact:** The primary application is in the development of ultra-low-power "dissipationless" electronics. The chiral edge states of a QAH insulator can act as perfect 1D conducting wires, carrying charge without scattering and energy loss. This could be used to create highly efficient interconnects in next-generation microchips, overcoming the energy loss bottlenecks that plague current technologies. It would also enable new types of spintronic and memory devices.

2.2.5 Summary of the Role of Theory, Computation, and Experiment

- **Theory:** Develops the fundamental concepts, such as the relationship between magnetism, topology, and the Chern number.[208] It proposes new material platforms (e.g., heterostructures, new stoichiometric compounds) and mechanisms (e.g., interaction-driven QAH) for realizing the effect at higher temperatures.
- **Computation:** Employs first-principles methods (DFT) to calculate the electronic and magnetic properties of candidate materials. It is used to predict T$_C$, calculate the topological band gap, and determine the Chern number, thereby guiding experimental efforts toward the most promising systems.[204]
- **Experiment:** Involves the synthesis of high-quality thin films and heterostructures using techniques like molecular beam epitaxy (MBE).[209] The primary characterization tool is low-temperature magnetotransport, measuring the Hall resistance (
ρ_{yx}) and longitudinal resistance (ρ_{xx}). The definitive signature of the QAH effect is the observation of a quantized plateau in $\rho_{yx}=h/Ce^2$ (where C is an integer) accompanied by a vanishing ρ_{xx} at zero external magnetic field.[205]

2.2.6 Ranked Order of National Labs and Justification

The quest for a high-temperature QAH insulator requires a strong integration of advanced materials synthesis, low-temperature transport measurements, and theory/computation.

1. **Brookhaven National Laboratory (BNL):** BNL is a leader in the study of topological materials, with strong programs in both synthesis and characterization. Their expertise in growing complex oxide and chalcogenide heterostructures via MBE is directly applicable. The world-class synchrotron **NSLS-II** allows for detailed characterization of the electronic and magnetic structure using ARPES and RIXS, which is crucial for understanding the origin of the topological gap and magnetism.[171]
2. **Argonne National Laboratory (ANL):** ANL has strong capabilities in both the synthesis and characterization of magnetic materials. The **Advanced Photon Source (APS)** and the **Center for Nanoscale Materials (CNM)** provide essential tools for structural and magnetic characterization. Their theory and computation groups are also very active in modeling topological materials.[138]
3. **Oak Ridge National Laboratory (ORNL):** ORNL's expertise in neutron scattering at the **SNS** is invaluable for characterizing the magnetic order in candidate QAH materials. Understanding the precise magnetic structure is critical, especially in complex systems like MnBi$_2Te_4$. This is complemented by strong synthesis programs and computational resources.
4. **Lawrence Berkeley National Laboratory (LBNL):** LBNL's **Molecular Foundry** and **Advanced Light Source (ALS)** provide a powerful combination of synthesis and characterization capabilities. Their leadership in computational materials science through the **Materials Project** is also a key asset for high-throughput screening of new QAH insulator candidates.[111]
5. **National Institute of Standards and Technology (NIST):** While not a DOE lab, NIST plays a crucial role in developing the precision measurement techniques needed to verify quantization and characterize these systems. Their work on exchange-biased QAH systems demonstrates their expertise in controlling magnetism at interfaces.[214]

2.2.7 References

.[111]

2.3 Understanding and Engineering Moiré Materials

2.3.1 Crisp Statement of the Open Problem

When two atomically thin 2D crystalline layers are stacked with a slight twist angle or lattice mismatch, a long-wavelength interference pattern known as a moiré superlattice emerges. This superlattice imposes a periodic potential on the electrons, which can dramatically reconstruct the electronic band structure, leading to the formation of ultra-flat electronic bands. In these flat bands, kinetic energy is quenched, and electron-electron interactions become dominant, giving rise to a plethora of strongly correlated and topological phenomena, including unconventional superconductivity and orbital ferromagnetism. The central challenge is to develop a predictive understanding of how the twist angle, strain, and dielectric environment control these emergent properties, and to harness this "twistronics" approach to engineer novel quantum phases on demand.[224]

2.3.2 Description of Current Work and Citations

The field of "twistronics" was ignited by the 2018 discovery of correlated insulating states and unconventional superconductivity in twisted bilayer graphene (TBG) when tuned to a "magic angle" of ~1.1 degrees.[226]

Key Material Platforms:

- **Twisted Bilayer Graphene (TBG):** This is the prototypical moiré system. At the magic angle, the interlayer hybridization leads to the formation of nearly flat electronic bands at the Fermi level. The quenched kinetic energy allows Coulomb interactions to dominate, driving the system into a Mott-like correlated insulating state at half-filling of the flat bands. Doping away from this insulating state reveals domes of unconventional superconductivity, reminiscent of the cuprate phase diagram.[25]
- **Twisted Transition Metal Dichalcogenides (TMDs):** Heterostructures made of TMDs (e.g., $MoSe_2$/WSe_2, WS_2/WSe_2) offer a richer platform than graphene. The strong spin-orbit coupling and direct band gaps in TMDs lead to a wider variety of phenomena. Moiré patterns in TMDs create periodic potentials that can trap excitons (bound electron-hole pairs), forming ordered arrays of quantum emitters.[225] They also host a variety of correlated insulating states, including Mott insulators and generalized Wigner crystals at fractional fillings of the moiré lattice.[224]
- **Graphene on Hexagonal Boron Nitride (hBN):** The small lattice mismatch between graphene and the insulating substrate hBN also creates a moiré superlattice. This system has been used to study the Hofstadter butterfly spectrum and has recently been shown to exhibit ferroelectricity when Bernal-stacked bilayer graphene is aligned with hBN.[225]

Observed Emergent Phenomena:

- **Unconventional Superconductivity:** The superconductivity found in TBG is widely believed to be unconventional and driven by strong electron-electron interactions, not phonons. Evidence includes a large ratio of the superconducting gap to T_c ($2\Delta/k_BT_c >> 3.53$), the presence of a pseudogap phase above T_c, and nodal characteristics in the tunneling spectrum.[25] The pairing mechanism is a subject of intense research, with theories ranging from spin fluctuations to electron-phonon coupling enhanced by the flat bands.[233]
- **Correlated Insulators:** At integer fillings of the flat moiré bands, strong Coulomb repulsion can lead to the formation of Mott insulators, where electrons localize on the moiré superlattice sites.[224] In TMDs, insulators at fractional fillings (e.g., 1/3, 2/3) have also been observed, corresponding to the formation of generalized Wigner crystals.[230]
- **Orbital Magnetism and Quantum Anomalous Hall Effect:** At integer fillings, TBG has also been shown to exhibit ferromagnetism. Due to graphene's weak spin-orbit coupling, this magnetism is believed to be purely orbital in nature. When aligned with an hBN substrate, this can lead to a quantum anomalous Hall (QAH) state, demonstrating the interplay of correlation and topology in moiré systems.[224]
- **Moiré Excitons:** In semiconducting TMD heterostructures, the moiré potential creates an array of traps for interlayer excitons. These trapped excitons behave like artificial atoms, exhibiting quantized energy levels and forming a highly tunable platform for studying many-body physics and quantum optics.[225]

2.3.3 Promising Directions

- **Expanding the Material Space:** A major effort is underway to explore the vast landscape of possible moiré materials beyond TBG and simple TMD bilayers. This includes twisted trilayers, twisted double bilayers, and heterostructures involving other 2D materials like magnetic insulators or superconductors.[224]
- **Improving Fabrication and Control:** A significant challenge is the precise and reliable fabrication of twisted heterostructures.[224] The properties are exquisitely sensitive to the twist angle, and achieving homogeneity over large areas is difficult. Developing new fabrication techniques, such as direct growth of moiré patterns by tuning lattice constants via chemical vapor deposition (CVD), is a key direction to move beyond the limitations of mechanical stacking.[236]
- **Tuning with Multiple Knobs:** Moiré systems are uniquely tunable. In addition to twist angle, properties can be controlled with electric fields (gating), hydrostatic pressure, and strain. Systematically exploring this multi-dimensional parameter space is crucial for mapping out the complete phase diagrams and discovering new phases.[225]

- **Advanced Local Probes:** Understanding the real-space electronic and structural properties of moiré systems requires high-resolution local probes. Scanning tunneling microscopy (STM) can directly visualize the moiré pattern and probe the local density of states.[25] Microwave impedance microscopy (MIM) is emerging as a powerful tool to map local conductivity and identify insulating states.[230]
- **Bridging Theory and Computation:** Modeling moiré systems is computationally demanding due to the large size of the superlattice unit cell. A key direction is the development of efficient and accurate theoretical models, such as continuum models, that capture the essential low-energy physics without the full cost of *ab initio* calculations. Machine learning approaches are also being explored to predict moiré band structures from the properties of the constituent layers, which could dramatically accelerate the search for new moiré materials with desired properties.[238]

2.3.4 Impact of Solving this Problem

- **Scientific Impact:** Moiré materials provide an unprecedentedly tunable platform for studying strongly correlated electron physics. They allow researchers to access regimes similar to those in high-T$_c$ cuprates but in a single, highly controllable material system. A full understanding of moiré physics would provide profound insights into the nature of Mott insulators, unconventional superconductivity, and the interplay between correlation and topology.
- **Technological Impact:** The ability to engineer electronic properties on demand by simply twisting layers could lead to a new paradigm of "twistronic" devices. This could include tunable transistors, novel optical sensors based on moiré excitons, ultra-low-power memory devices, and potentially even new platforms for quantum computation.[225]

2.3.5 Summary of the Role of Theory, Computation, and Experiment

- **Theory:** Develops effective low-energy models (e.g., continuum models, Hubbard models on the moiré lattice) to describe the flat bands and the resulting correlated phases. It aims to predict the phase diagram as a function of twist angle, filling, and other tuning parameters.[226]
- **Computation:** Performs large-scale *ab initio* (DFT) calculations to determine the band structure of moiré superlattices from first principles, providing crucial input and validation for the simpler effective models. Machine learning is being developed to accelerate these predictions.[238]
- **Experiment:** The field is driven by experimental breakthroughs. This involves the **synthesis** of high-quality twisted heterostructures, which is a major challenge.[224] **Characterization** relies on a combination of global transport measurements (to

detect superconductivity and insulating states) and local probes like **STM** and **MIM** to visualize the moiré lattice and its electronic states in real space.[25] **ARPES** is used to directly measure the flat band structure.[227]

2.3.6 Ranked Order of National Labs and Justification

The study of moiré materials requires a confluence of expertise in 2D materials synthesis, advanced nanofabrication, ultra-low temperature measurements, and sophisticated local probes.

1. **Lawrence Berkeley National Laboratory (LBNL):** LBNL is a leader in this area. The **Molecular Foundry** is a premier user facility for the synthesis and nanofabrication of 2D materials and heterostructures.[239] The lab has strong programs in ARPES and STM characterization at the **Advanced Light Source (ALS)**. LBNL theorists, including Steven Louie, are pioneers in the *ab initio* calculation of electronic and excitonic properties in moiré systems.[240]
2. **Brookhaven National Laboratory (BNL):** BNL's **Center for Functional Nanomaterials (CFN)** has state-of-the-art capabilities for the fabrication and characterization of 2D devices. The lab has a robotic assembly system (QPress) specifically designed for creating high-quality van der Waals heterostructures with clean interfaces, directly addressing one of the key challenges in the field.[241]
3. **Oak Ridge National Laboratory (ORNL):** ORNL is developing novel methods for the characterization of moiré systems. Their development of a deep learning model (Gomb-Net) to deconvolve atomic-resolution microscopy images of moiré patterns is a significant advance in understanding the real-space structure and defect distribution in these complex materials.[242]
4. **National Institute of Standards and Technology (NIST):** While not a DOE lab, NIST has made important contributions, particularly in using optical spectroscopy to demonstrate how moiré patterns in TMDs create tunable arrays of quantum dots, which is crucial for applications in quantum information science.[243]
5. **National High Magnetic Field Laboratory (NHMFL):** The ability to apply high magnetic fields is essential for studying many of the emergent phenomena in moiré materials, such as the quantum Hall effect, Chern insulators, and for probing the nature of the superconducting state. The MagLab's unique facilities are a critical resource for the community.[228]

2.3.7 References

.[25]

2.4 The Search for Intrinsic Magnetic Topological Insulators

2.4.1 Crisp Statement of the Open Problem

The combination of magnetism and non-trivial band topology is a fertile ground for discovering new quantum phenomena, such as the quantum anomalous Hall (QAH) effect and the axion insulator state. The initial approach of magnetically doping topological insulators (TIs) suffers from disorder and inhomogeneity. The central challenge is to discover and synthesize *intrinsic* magnetic topological insulators—stoichiometric crystalline compounds that are simultaneously magnetic and topologically non-trivial—to provide a clean, ordered, and tunable platform for exploring topological quantum physics.[185]

2.4.2 Description of Current Work and Citations

The search for intrinsic magnetic TIs aims to overcome the limitations of extrinsic methods for breaking time-reversal symmetry in topological materials.

- **Limitations of Extrinsic Magnetism:** Introducing magnetism into TIs by randomly substituting non-magnetic atoms with magnetic ones (e.g., Cr or V in Bi$_2Se_3$) successfully led to the first observation of the QAH effect. However, this magnetic doping creates significant chemical disorder and spatial inhomogeneity in the magnetic exchange coupling. This leads to low magnetic ordering temperatures (T$_C$) and small, smeared-out topological gaps, confining the observation of quantum phenomena to ultra-low temperatures (typically < 2 K).[185]
- **The Rise of Intrinsic Magnetic TIs:** An ideal magnetic TI is a stoichiometric compound where magnetic ions are an intrinsic part of the crystal lattice, forming an ordered magnetic state below T$_C$. This promises cleaner samples, higher ordering temperatures, and more robust topological gaps.
- **MnBi$_2Te_4$ and the MBT Family:** The breakthrough in this area came with the discovery of MnBi$_2Te_4$ (MBT).[186]
  - **Structure and Properties:** MBT has a layered crystal structure where septuple layers of Te-Bi-Te-Mn-Te-Bi-Te are stacked. Within each layer, the Mn moments order ferromagnetically, while adjacent layers couple antiferromagnetically, making the bulk material an A-type antiferromagnet with a Néel temperature (TN) of ~25 K.[247] Crucially, first-principles calculations predicted and ARPES experiments confirmed that MBT is also a topological insulator.[185] This made MBT the first realization of an intrinsic antiferromagnetic topological insulator.
  - **Topological Phenomena:** The interplay between its magnetism and topology makes MBT an incredibly rich platform. In thin films with an odd number of layers, there is an uncompensated surface magnetization, leading to a QAH

state.[186] In films with an even number of layers, the antiferromagnetic alignment of the top and bottom surfaces is predicted to realize an axion insulator state.[186] Both of these states have been experimentally observed, though challenges remain.[186]

- **Other Candidate Materials:** The discovery of MBT has spurred a broad search for other intrinsic magnetic TIs. This includes other members of the (MnBi$_2Te_4$)(Bi$_2Te_3$)n family, such as MnBi$_4Te_7$ and MnBi$6*Te*{10}$ [248], as well as other material classes like EuIn$_2
As_2$, which is a candidate for a magnetic topological crystalline axion insulator.[251] High-throughput computational searches are actively being used to screen databases for new candidates.[252]

2.4.3 Promising Directions

- **Materials Synthesis and Defect Control:** A primary challenge with materials like MBT is the presence of native defects, such as Mn$*{Bi}$ and Bi$*{Mn}$ antisite defects, which act as dopants and can shift the Fermi level out of the bulk band gap, obscuring the topological transport signatures.[248] A key research direction is to achieve better control over the synthesis process (e.g., molecular beam epitaxy, flux growth) to minimize these defects and produce insulating samples. Theoretical calculations can guide this by predicting the formation energies of different defects under various growth conditions.[248]
- **Tuning Magnetic and Topological Properties:** A major advantage of intrinsic magnetic TIs is the potential to tune their properties. This can be achieved through:
  - **Chemical Doping/Alloying:** Substituting Mn with other magnetic ions or Bi with Sb can be used to tune the magnetic exchange interactions, magnetic anisotropy, and the position of the Fermi level.[248]
  - **Dimensionality Control:** As seen in MBT, simply changing the number of layers in a thin film can switch the system between a QAH insulator and an axion insulator.[186]
  - **External Fields:** Applying electric fields can tune the Fermi level, while magnetic fields can be used to switch between different magnetic states (e.g., from antiferromagnetic to ferromagnetic), thereby controlling the topological phase.[244]
- **Exploring the Surface Magnetic Gap:** A puzzling observation in MBT is that while a magnetic gap is expected to open at the Dirac point of the surface states due to the surface ferromagnetism, ARPES experiments often show a nearly gapless or very small gap.[254] Understanding the origin of this "disappearing gap"—whether it is due to surface magnetic reconstruction, topological surface

state redistribution, or other effects—is a critical open question that must be resolved to fully harness these materials.[254]
- **High-Throughput Discovery:** The combination of high-throughput DFT calculations and topological analysis tools is the most promising route to discovering new families of intrinsic magnetic TIs beyond the MBT class. Recent efforts have identified hundreds of new candidate materials from existing databases.[252]

2.4.4 Impact of Solving this Problem

The discovery of a robust family of intrinsic magnetic TIs would have a profound impact on topological quantum physics and related technologies.

- **Scientific Impact:** It would provide a clean, highly ordered, and tunable platform to study the rich interplay between magnetism and band topology. This would enable definitive experiments on phenomena like the QAH effect, the topological magnetoelectric effect, and the formation of chiral Majorana modes at interfaces with superconductors, free from the complications of disorder inherent in doped systems.
- **Technological Impact:** The primary technological driver is the realization of the QAH effect at higher temperatures (Problem 2.2). An intrinsic magnetic TI with a high Curie temperature and a large topological gap could enable dissipationless electronics to operate at liquid nitrogen temperatures or even higher, a major step towards practical applications. It would also provide a more robust platform for developing topological qubits.

2.4.5 Summary of the Role of Theory, Computation, and Experiment

- **Theory:** Provides the symmetry-based classification of magnetic topological phases and predicts the properties of candidate materials. It develops effective models to describe the interplay of magnetism and topology and to interpret experimental results.[244]
- **Computation:** DFT and other first-principles methods are essential for predicting the electronic and magnetic ground states of new compounds. High-throughput computational screening of materials databases is the primary engine for discovering new candidate intrinsic magnetic TIs.[248]
- **Experiment:** This involves the synthesis of high-quality single crystals and thin films of the predicted materials.[185] A suite of characterization tools is then required:
  ARPES to directly visualize the topological surface states and measure the magnetic gap [186],
  neutron scattering to determine the bulk magnetic structure [198],

magnetotransport to measure the QAH and other topological transport signatures [186], and
STM/MFM to probe local electronic and magnetic properties.[253]

2.4.6 Ranked Order of National Labs and Justification

The search for intrinsic magnetic TIs requires strong, integrated programs in materials synthesis, advanced characterization (especially ARPES and neutron scattering), and theory/computation.

1. **Brookhaven National Laboratory (BNL):** BNL has demonstrated leadership in this area, particularly with their use of ARPES to study the surface states of MBT.[256] Their combination of expertise in topological materials, advanced synthesis capabilities (MBE), and premier characterization tools at the **NSLS-II** makes them ideally suited to discover and characterize new intrinsic magnetic TIs.[171]
2. **Oak Ridge National Laboratory (ORNL):** ORNL's world-leading neutron scattering facilities (**SNS** and **HFIR**) are indispensable for determining the complex magnetic structures of these materials, which is a critical piece of the puzzle. This is complemented by strong materials synthesis programs and expertise in using STM to visualize native defects in materials like MBT.[253]
3. **Ames National Laboratory:** Ames Lab has a deep history and expertise in the synthesis and characterization of magnetic and rare-earth materials. Their work using neutron scattering to understand the role of magnetic defects in both dilute and intrinsic magnetic TIs provides crucial insights into how to control the properties of these materials.[198]
4. **Lawrence Berkeley National Laboratory (LBNL):** LBNL's strengths in computational materials science (**Materials Project**) and ARPES/X-ray spectroscopy at the **ALS** position it well to contribute to the high-throughput discovery and subsequent experimental verification of new intrinsic magnetic TIs.[111]
5. **Argonne National Laboratory (ANL):** ANL has strong programs in topological materials and magnetism, with excellent characterization capabilities at the **APS** and **CNM**. Their work on topological semimetals and superconductors is highly synergistic with the search for intrinsic magnetic TIs.[138]

2.4.7 References

.[111]

Part III: The World of Frustration and Spin Liquids

3.1 The Definitive Experimental Signature of a Quantum Spin Liquid

3.1.1 Crisp Statement of the Open Problem

A quantum spin liquid (QSL) is an exotic, highly entangled state of matter where strong quantum fluctuations prevent the magnetic moments (spins) in a material from ordering or freezing, even at absolute zero temperature. While there are several promising candidate materials and a rich theoretical framework, there is no single, universally accepted "smoking gun" experimental signature that can unambiguously identify a material as a QSL. The central challenge is to establish a definitive set of experimental criteria to distinguish a true QSL from other disordered magnetic states and to directly detect its hallmark property: fractionalized excitations (spinons).[260]

3.1.2 Description of Current Work and Citations

The concept of a QSL was first proposed by P.W. Anderson in 1973 as a possible ground state for antiferromagnets on a triangular lattice.[261] Unlike conventional magnets that develop long-range order (e.g., ferromagnetism or antiferromagnetism) below a critical temperature, the spins in a QSL remain in a dynamic, fluctuating, liquid-like state down to $T=0$.[264] This is not a classical thermal disorder, but a coherent quantum state characterized by long-range entanglement.

Theoretical Hallmarks:

- **Absence of Magnetic Order:** The defining feature is the lack of any static, long-range magnetic order, meaning no spontaneous symmetry breaking.[261]
- **Fractionalized Excitations:** The elementary excitations of a QSL are not conventional spin waves (magnons). Instead, the spin of an electron (S=1) can "fractionalize" into exotic quasiparticles, such as two spin-1/2 "spinons." These fractionalized excitations are a key signature of the long-range entanglement in the QSL state.[262]
- **Emergent Gauge Fields:** The theoretical description of QSLs often involves emergent gauge fields, which mediate the interactions between the fractionalized quasiparticles. This can lead to novel phenomena like "emergent photons" in certain QSLs known as quantum spin ice.[261]

Candidate Materials:
The search for QSLs focuses on materials with strong geometric frustration, where the lattice geometry prevents all magnetic interactions from being simultaneously satisfied.

- **Kagome Lattice Antiferromagnets:** Materials with spins on a kagome lattice (a network of corner-sharing triangles) are prime candidates. The most studied example is **herbertsmithite**, ZnCu$_3$(OH)6Cl$_2$, which features a nearly perfect S=1/2 kagome lattice of Cu^{2+} ions. It shows no magnetic ordering down to 20 mK, despite strong antiferromagnetic interactions of ~190 K [[266]

Works cited

1. Iron-based high transition temperature superconductors | National Science Review, accessed June 29, 2025, https://academic.oup.com/nsr/article/1/3/371/2460181
2. Reviews of Modern Physics at 90: Progress in superconductivity - AIP Publishing, accessed June 29, 2025, https://pubs.aip.org/physicstoday/article-pdf/72/2/44/10122413/44_1_online.pdf
3. Full article: Two-dimensional functional materials: from properties to potential applications, accessed June 29, 2025, https://www.tandfonline.com/doi/full/10.1080/19475411.2020.1790055
4. Topological Insulators: A Review - ijsret, accessed June 29, 2025, https://ijsret.com/wp-content/uploads/2024/01/IJSRET_V10_issue1_199.pdf
5. large.stanford.edu, accessed June 29, 2025, http://large.stanford.edu/courses/2010/ph240/li1/#:~:text=Conclusion,crisis%20may%20be%20partially%20solved.
6. High-temperature Superconductors | Physics - Lumen Learning, accessed June 29, 2025, https://courses.lumenlearning.com/suny-physics/chapter/34-6-high-temperature-superconductors/
7. Superconductivity temperatures on the rise | CNRS News, accessed June 29, 2025, https://news.cnrs.fr/articles/superconductivity-temperatures-on-the-rise
8. Topological Quantum Materials for Realizing Majorana Quasiparticles - ACS Publications, accessed June 29, 2025, https://pubs.acs.org/doi/10.1021/acs.chemmater.8b04383
9. 2D materials: a wonderland for physical science - Oxford Academic, accessed June 29, 2025, https://academic.oup.com/nsr/article/9/5/nwab202/6442248
10. High-Temperature Superconductors (Cuprates and Iron-Based) | Superconducting Devices Class Notes | Fiveable, accessed June 29, 2025, https://library.fiveable.me/superconducting-devices/unit-3/high-temperature-superconductors-cuprates-iron-based/study-guide/997sQNtWI34d68t0
11. What are the latest theories in high temperature superconductivity? - Quora, accessed June 29, 2025, https://www.quora.com/What-are-the-latest-theories-in-high-temperature-superconductivity
12. Physics of iron-based high temperature superconductors, accessed June 29, 2025, https://boulderschool.yale.edu/sites/default/files/files/MatsudaNote.pdf
13. High-temperature superconductivity - Physics Stack Exchange, accessed June 29, 2025, https://physics.stackexchange.com/questions/406322/high-temperature-superconductivity
14. Progress and perspectives on electron-doped cuprates | Rev. Mod ..., accessed

June 29, 2025, https://link.aps.org/doi/10.1103/RevModPhys.82.2421
15. What are the competing theories for type II superconductivity? - Quora, accessed June 29, 2025, https://www.quora.com/What-are-the-competing-theories-for-type-II-superconductivity
16. My Title - Institut Laue-Langevin, accessed June 29, 2025, https://www.ill.eu/fileadmin/user_upload/ILL/1_About_ILL/List_of_PhD_thesis/These_Liu_M..pdf
17. Making High-Temperature Superconductivity Disappear to ..., accessed June 29, 2025, https://www.bnl.gov/newsroom/news.php?a=116992
18. Breaking Electron Waves Provide New Clues to High-Temperature Superconductivity | BNL Newsroom, accessed June 29, 2025, https://www.bnl.gov/newsroom/news.php?a=212619
19. Superconductivity | Argonne National Laboratory, accessed June 29, 2025, https://www.anl.gov/topic/superconductivity?page=1
20. In a first, researchers stabilize a promising new class of high-temperature superconductors at room pressure, accessed June 29, 2025, https://www6.slac.stanford.edu/news/2025-02-04-first-researchers-stabilize-promising-new-class-high-temperature-superconductors
21. Investigating High-Temperature Superconductors - Department of Energy, accessed June 29, 2025, https://www.energy.gov/science/articles/investigating-high-temperature-superconductors
22. Using magnetic fields to understand high-temperature ... - EurekAlert!, accessed June 29, 2025, https://www.eurekalert.org/news-releases/829979
23. Angle-resolved photoemission studies of quantum materials | Rev ..., accessed June 29, 2025, https://link.aps.org/doi/10.1103/RevModPhys.93.025006
24. ARPES on high-temperature superconductors: Simplicity vs. complexity (Review Article), accessed June 29, 2025, https://www.researchgate.net/publication/258071973_ARPES_on_high-temperature_superconductors_Simplicity_vs_complexity_Review_Article
25. Evidence for unconventional superconductivity in twisted bilayer ..., accessed June 29, 2025, https://yazdanilab.princeton.edu/highlights/evidence-unconventional-superconductivity-twisted-bilayer-graphene
26. Evidence for unconventional superconductivity in twisted bilayer graphene - OSTI.GOV, accessed June 29, 2025, https://www.osti.gov/pages/biblio/1842831
27. Closing in on high-temperature superconductivity | Penn State University, accessed June 29, 2025, https://www.psu.edu/news/research/story/closing-high-temperature-superconductivity
28. High-temperature superconductivity - Wikipedia, accessed June 29, 2025, https://en.wikipedia.org/wiki/High-temperature_superconductivity
29. arXiv:0905.1711v2 [cond-mat.supr-con] 20 May 2009, accessed June 29, 2025, https://arxiv.org/pdf/0905.1711

30. Dynamical mean-field theory of strongly correlated ... - Rutgers Physics, accessed June 29, 2025, https://www.physics.rutgers.edu/~udo/qmc/rmp68_13.pdf
31. Dynamical Mean-Field Theory of Strongly Correlated Electron Systems - JPS Journals, accessed June 29, 2025, https://journals.jps.jp/doi/pdf/10.7566/JPSCP.30.011001
32. Scientists Uncover the Origin of High-Temperature Superconductivity in Copper-Oxide Compound | BNL Newsroom - Brookhaven National Laboratory, accessed June 29, 2025, https://www.bnl.gov/newsroom/news.php?a=111864
33. Angle-resolved photoemission studies of the cuprate superconductors - Quantum Materials at UBC, accessed June 29, 2025, https://qmlab.ubc.ca/ARPES/PUBLICATIONS/Reviews/RMP_ARPES.pdf
34. Unlocking the secrets of high-temperature superconductors - EurekAlert!, accessed June 29, 2025, https://www.eurekalert.org/news-releases/806736
35. V. J. Emery's research works | Brookhaven National Laboratory and other places - ResearchGate, accessed June 29, 2025, https://www.researchgate.net/scientific-contributions/V-J-Emery-5669636
36. Scientists Enter Unexplored Territory in Superconductivity Search | BNL Newsroom, accessed June 29, 2025, https://www.bnl.gov/newsroom/news.php?a=113224
37. From Brookhaven National Lab: "Making High-Temperature Superconductivity Disappear to Understand Its Origin" - sciencesprings, accessed June 29, 2025, https://sciencesprings.wordpress.com/2020/02/07/from-brookhaven-national-lab-making-high-temperature-superconductivity-disappear-to-understand-its-origin/
38. New Grant to Aid Search for the Secrets of Superconductivity | BNL Newsroom, accessed June 29, 2025, https://www.bnl.gov/newsroom/news.php?a=25024
39. ORNL study advances quest for better superconducting materials, accessed June 29, 2025, https://www.ornl.gov/news/ornl-study-advances-quest-better-superconducting-materials
40. Superconductors - Oak Ridge Leadership Computing Facility, accessed June 29, 2025, https://www.olcf.ornl.gov/tag/superconductors/
41. Q&A: Jun-Sik Lee explains how new SSRL capabilities will probe ..., accessed June 29, 2025, https://www6.slac.stanford.edu/news/2025-06-09-qa-jun-sik-lee-explains-how-new-ssrl-capabilities-will-probe-mysteries
42. From The DOE's SLAC National Accelerator Laboratory: "In a first, researchers stabilize a promising new class of high-temperature superconductors at room pressure" - sciencesprings, accessed June 29, 2025, https://sciencesprings.wordpress.com/2025/02/07/from-the-does-slac-national-accelerator-laboratory-in-a-first-researchers-stabilize-a-promising-new-class-of-high-temperature-superconductors-at-room-pressure/
43. High-Temperature Superconductors Unveil New Phase of Matter - Innovations Report, accessed June 29, 2025,

https://www.innovations-report.com/science-tech/physics-and-astronomy/high-temperature-superconductor-spills-secret-a-172537/
44. A New Tool to Attack the Mysteries of High-Temperature Superconductivity | Lab Manager, accessed June 29, 2025, https://www.labmanager.com/a-new-tool-to-attack-the-mysteries-of-high-temperature-superconductivity-16881
45. Pseudogaps Are Not The Answer - Berkeley Lab News Center, accessed June 29, 2025, https://newscenter.lbl.gov/2006/01/30/pseudogaps-are-not-the-answer/
46. Superconducting Magnet Program – Accelerator Technology ..., accessed June 29, 2025, https://atap.lbl.gov/research/scientific-programs-and-centers/superconducting-magnet-program/
47. Physics Underlying High-Temperature Superconductivity - Lawrence Berkeley National Laboratory, accessed June 29, 2025, https://www2.lbl.gov/Science-Articles/Archive/super-mechanism.html
48. New Research Advances High-Temperature Superconductivity - Innovations Report, accessed June 29, 2025, https://www.innovations-report.com/science-tech/physics-and-astronomy/new-magnetism-research-brings-high-temp-superconductivity-applications-closer/
49. Superconductivity | Argonne National Laboratory, accessed June 29, 2025, https://www.anl.gov/topic/superconductivity
50. / ~ Los Alamos - OSTI, accessed June 29, 2025, https://www.osti.gov/servlets/purl/964943
51. Argonne superconductor technology licensed | C&EN Global Enterprise - ACS Publications, accessed June 29, 2025, https://pubs.acs.org/doi/10.1021/cen-v066n042.p005a
52. NEW HIGH-TEMPERATURE SUPERCONDUCTORS - Time, accessed June 29, 2025, https://time.com/archive/6924084/new-high-temperature-superconductors/
53. Laboratory Researchers Achieve High Temperature Superconductor Milestone, accessed June 29, 2025, https://www.sciencedaily.com/releases/2001/01/010102061737.htm
54. (PDF) Pseudogap phase of cuprate superconductors confined by ..., accessed June 29, 2025, https://www.researchgate.net/publication/386630781_Pseudogap_phase_of_cuprate_superconductors_confined_by_Fermi_surface_topology
55. Pseudogap temperature of cuprate superconductors from the Nernst effect | Phys. Rev. B, accessed June 29, 2025, https://link.aps.org/doi/10.1103/PhysRevB.97.064502
56. Vanishing nematic order beyond the pseudogap phase in overdoped cuprate superconductors | PNAS, accessed June 29, 2025, https://www.pnas.org/doi/10.1073/pnas.2106881118
57. The pseudogap in high-temperature superconductors: an experimental survey - SciSpace, accessed June 29, 2025, https://scispace.com/pdf/the-pseudogap-in-high-temperature-superconductors-an-22i3tjkdfn.pdf

58. What is pseudogap phase in high T_c cuprates? - Physics Stack Exchange, accessed June 29, 2025, https://physics.stackexchange.com/questions/756998/what-is-pseudogap-phase-in-high-t-c-cuprates
59. The pseudogap state in high-Tc superconductors: an infrared study, accessed June 29, 2025, http://infrared.ucsd.edu/basov_pubs/31-Puchkov-JPhys-96.pdf
60. Pseudogap and Superconducting Gap in High-Temperature Superconductors - Stanford University, accessed June 29, 2025, https://www-ssrl.slac.stanford.edu/research/highlights_archive/pseudogap.html
61. The pseudogap: friend or foe of high Tc? M. R. NORMAN*1, D. PINES2 and C. KALLIN3 1Materials Science Division, Argonne National - arXiv, accessed June 29, 2025, https://arxiv.org/pdf/cond-mat/0507031
62. DOE Pulse - Science and Technology Highlights from the DOE National Laboratories, accessed June 29, 2025, https://web.ornl.gov/info/news/pulse/archive_issues/pulse_v224_06.htm
63. Closing in on the Pseudogap - Berkeley Lab – Berkeley Lab News ..., accessed June 29, 2025, https://newscenter.lbl.gov/2011/03/24/pseudogap/
64. Spontaneous breaking of time-reversal symmetry in the pseudogap state of a high-T{sub c} superconductor. | Argonne National Laboratory, accessed June 29, 2025, https://www.anl.gov/argonne-scientific-publications/pub/42729
65. Dr Shuqiu Wang: High-temperature superconductivity - Physics - Oxford University, accessed June 29, 2025, https://www.physics.ox.ac.uk/our-people/shiquiwang/high-temperature-superconductivity
66. Key Advance in Understanding 'Pseudogap' Phase in High-Tc ..., accessed June 29, 2025, https://www.bnl.gov/newsroom/news.php?a=111155
67. Unraveling the Complex, Intertwined Electron Phases in a Superconductor | BNL Newsroom, accessed June 29, 2025, https://www.bnl.gov/newsroom/news.php?a=111783
68. Unraveling the origin of the pseudogap in a charge density wave ..., accessed June 29, 2025, https://www.anl.gov/article/unraveling-the-origin-of-the-pseudogap-in-a-charge-density-wave-compound
69. [1712.05113] Pseudogap phase of cuprate superconductors confined by Fermi surface topology - arXiv, accessed June 29, 2025, https://arxiv.org/abs/1712.05113
70. Signatures of superconductivity and pseudogap formation in nonequilibrium nodal quasiparticles revealed by ultrafast angle-resolved photoemission | Phys. Rev. B - Physical Review Link Manager, accessed June 29, 2025, https://link.aps.org/doi/10.1103/PhysRevB.88.245132
71. Scientists gain new insight into mysterious electronic phenomenon, accessed June 29, 2025, https://www.anl.gov/article/scientists-gain-new-insight-into-mysterious-electronic-phenomenon
72. First direct evidence that a mysterious phase of matter competes ..., accessed June 29, 2025, https://www.sciencedaily.com/releases/2014/12/141220104104.htm

73. Mysteries of the Bizarre 'Pseudogap' in Quantum Physics Finally Untangled, accessed June 29, 2025, https://www.simonsfoundation.org/2024/09/19/mysteries-of-the-bizarre-pseudogap-in-quantum-physics-finally-untangled/
74. Pseudogap and Superconducting Gap - Stanford University, accessed June 29, 2025, https://www-ssrl.slac.stanford.edu/research/pseudogap_summary.html
75. Direct Evidence of Pseudogap Competing with Superconductivity - Innovations Report, accessed June 29, 2025, https://www.innovations-report.com/engineering/materials-sciences/first-direct-evidence-that-a-mysterious-phase-of-matter-competes-with-high-temperature-superconductivity/
76. The pseudogap: friend or foe of high Tc? M. R. NORMAN*1, D. PINES2 and C. KALLIN3 1Materials Science Division, Argonne National - arXiv, accessed June 29, 2025, http://www.arxiv.org/pdf/cond-mat/0507031v1
77. Fermi Surface Transforms at the Onset of the Pseudogap State in a Cuprate Superconductor, accessed June 29, 2025, https://nationalmaglab.org/user-facilities/dc-field/research/science-highlights/fermi-surface-transforms-pseudogap-state/
78. Thermodynamics of the pseudogap in cuprates - Frontiers, accessed June 29, 2025, https://www.frontiersin.org/journals/physics/articles/10.3389/fphy.2022.1030616/full
79. Origin of the Pseudogap in High-Temperature Cuprate Superconductors | The Journal of Physical Chemistry Letters - ACS Publications, accessed June 29, 2025, https://pubs.acs.org/doi/abs/10.1021/jz200916t
80. Superconductor research is getting hot - Science! Astronomy & Space Exploration, and Others - Cloudy Nights, accessed June 29, 2025, https://www.cloudynights.com/topic/885055-superconductor-research-is-getting-hot/
81. Shattering Dreams of a Scientific Breakthrough: Nature Retracts Room-Temperature Superconductivity Study Amidst Allegations of Misconduct - The Debrief, accessed June 29, 2025, https://thedebrief.org/shattering-dreams-of-a-scientific-breakthrough-nature-retracts-room-temperature-superconductivity-study-amidst-allegations-of-misconduct/
82. Supposed room-temperature superconductors fail to convince critics, accessed June 29, 2025, https://revistapesquisa.fapesp.br/en/supposed-room-temperature-superconductors-fail-to-convince-critics/
83. Superconducting ternary hydrides: progress and challenges ..., accessed June 29, 2025, https://academic.oup.com/nsr/article/11/7/nwad307/7462326
84. Pressure-induced hydrogen-dominant high-temperature superconductors | National Science Review | Oxford Academic, accessed June 29, 2025, https://academic.oup.com/nsr/article/11/7/nwae004/7511108
85. Colloquium: Room temperature superconductivity: The roles of theory and

materials design | Rev. Mod. Phys. - Physical Review Link Manager, accessed June 29, 2025, https://link.aps.org/doi/10.1103/RevModPhys.95.021001
86. Data-driven search for high-temperature superconductors in ternary hydrides under pressure | Phys. Rev. B, accessed June 29, 2025, https://link.aps.org/doi/10.1103/PhysRevB.111.054505
87. Paper About Room Temperature Superconductivity Retracted from Nature | Chemistry And Physics - Labroots, accessed June 29, 2025, https://www.labroots.com/trending/chemistry-and-physics/23710/paper-temperature-superconductivity-retracted-nature-2
88. Room-Temperature Superconductor Discovery Meets With Resistance - Quanta Magazine, accessed June 29, 2025, https://www.quantamagazine.org/room-temperature-superconductor-discovery-meets-with-resistance-20230308/
89. Room Temperature Superconductor Discovery Retracted Over Controversy: Will We Ever Have Room Temperature Superconductors? - Quantum Zeitgeist, accessed June 29, 2025, https://quantumzeitgeist.com/room-temperature-superconductor-discovery-retracted/
90. Further Update in the Room-Temperature Superconductor Drama : r/Physics - Reddit, accessed June 29, 2025, https://www.reddit.com/r/Physics/comments/123ltg3/further_update_in_the_room_temperature/
91. Muted Response to New Claim of a Room-Temperature Superconductor - Physical Review Link Manager, accessed June 29, 2025, https://link.aps.org/doi/10.1103/Physics.16.39
92. A controversial room-temperature superconductor result has been retracted - Science News, accessed June 29, 2025, https://www.sciencenews.org/article/room-temperature-superconductor-retracted-ranga-dias
93. Room-Temperature Superconductivity Claim Falls Apart [Update ..., accessed June 29, 2025, https://www.quantamagazine.org/room-temperature-superconductivity-claim-falls-apart-update-20201014/
94. First ambient temperature and pressure superconductor announced - Science Media Centre España, accessed June 29, 2025, https://sciencemediacentre.es/en/reactions-study-still-pending-review-announces-first-superconductor-room-temperature-and-pressure
95. Bringing pressure-induced superconductivity back to ambient ..., accessed June 29, 2025, https://www.pnas.org/doi/10.1073/pnas.2501048122
96. Baby Steps Towards Ambient-Pressure High-Temperature Superconductors - Securities.io, accessed June 29, 2025, https://www.securities.io/baby-steps-towards-ambient-pressure-high-temperature-superconductors/
97. Superconductivity achieved at room temperature with new materials without the hassle of high-pressure equipment. This may lead to more practical ways to

achieve zero resistance in everything from power grids to experimental electronic devices. - Reddit, accessed June 29, 2025, https://www.reddit.com/r/OptimistsUnite/comments/1lmr04w/superconductivity_achieved_at_room_temperature/
98. Superconductivity achieved at room temperature with new materials - Earth.com, accessed June 29, 2025, https://www.earth.com/news/superconductivity-achieved-at-room-temperature-with-new-materials/
99. Feasible Route to High-Temperature Ambient-Pressure Hydride Superconductivity | Phys. Rev. Lett. - Physical Review Link Manager, accessed June 29, 2025, https://link.aps.org/doi/10.1103/PhysRevLett.132.166001
100. Machine Learning Assisted Material Discovery: A Small Data Approach - ACS Publications, accessed June 29, 2025, https://pubs.acs.org/doi/10.1021/accountsmr.1c00236
101. Light-Induced Superconductivity: New Advances Under Pressure - Innovations Report, accessed June 29, 2025, https://www.innovations-report.com/science-tech/physics-and-astronomy/light-induced-superconductivity-under-high-pressure/
102. Optical control of superconductivity - Andrea Cavalleri, accessed June 29, 2025, https://qcmd.mpsd.mpg.de/science/optical-control-of-superconductivity/
103. Room-temperature superconductors: New discovery brings science closer to the dream, accessed June 29, 2025, https://www.techexplorist.com/room-temperature-superconductors/97766/
104. High-Pressure Hydrogen Materials Synthesis and Testing - Hymarc, accessed June 29, 2025, https://www.hymarc.org/capabilities/high-pressure-hydrogen-materials-synthesis-and-testing
105. Self-driving lab transforms materials discovery - Argonne National Laboratory, accessed June 29, 2025, https://www.anl.gov/article/selfdriving-lab-transforms-materials-discovery
106. Materials Science Artificial Intelligence (AI) Project Supports Data Service Initiative - Globus, accessed June 29, 2025, https://www.globus.org/user-stories/materials-science-ai-project
107. Quantum and Condensed Matter Physics | Los Alamos National ..., accessed June 29, 2025, https://www.lanl.gov/engage/organizations/aldsct/theoretical/pcmcs
108. Metal Hydride Compressor for High-Pressure (875 bar) Hydrogen Delivery - Publications Search – Research, accessed June 29, 2025, https://www.sandia.gov/research/publications/search/?format=abstract&authors%5B0%5D=terry-johnson&per-page=200
109. Direct synthesis of catalyzed hydride compounds - Licensing and Technology Transfer, accessed June 29, 2025, https://ip.sandia.gov/patent/direct-synthesis-of-catalyzed-hydride-compounds/
110. Materials Project - About, accessed June 29, 2025, https://next-gen.materialsproject.org/about

111. Materials Project - Materials Sciences Division - Lawrence Berkeley National Laboratory, accessed June 29, 2025, https://materialssciences.lbl.gov/research/research-programs/materials-project/
112. Unlocking Materials Project Potential, accessed June 29, 2025, https://www.numberanalytics.com/blog/ultimate-guide-materials-project-computational-materials-science
113. High-pressure synthesis and neutron scattering study of tantalum hydride and a tantalum polymorph with A15-type structure | ORNL, accessed June 29, 2025, https://www.ornl.gov/publication/high-pressure-synthesis-and-neutron-scattering-study-tantalum-hydride-and-tantalum
114. Hydride superconductivity: here to stay, or to lead astray and soon go away? - arXiv, accessed June 29, 2025, https://arxiv.org/html/2501.01466v1
115. Why does room temperature superconducting need immense pressure? : r/QuantumPhysics, accessed June 29, 2025, https://www.reddit.com/r/QuantumPhysics/comments/1ec0yi4/why_does_room_temperature_superconducting_need/
116. (PDF) Machine Learning - Driven Materials Discovery: Unlocking Next-Generation Functional Materials - A minireview - ResearchGate, accessed June 29, 2025, https://www.researchgate.net/publication/390176388_Machine_Learning_-_Driven_Materials_Discovery_Unlocking_Next-Generation_Functional_Materials_-_A_minireview
117. Dynamical Mean-Field Theory of Strongly Correlated Fermion Systems and the Limit of Infinite Dimensions - ResearchGate, accessed June 29, 2025, https://www.researchgate.net/publication/215930256_Dynamical_Mean-Field_Theory_of_Strongly_Correlated_Fermion_Systems_and_the_Limit_of_Infinite_Dimensions
118. Model Hamiltonian for strongly correlated systems: Systematic, self ..., accessed June 29, 2025, https://link.aps.org/doi/10.1103/PhysRevB.99.125114
119. Electronic structure of strongly correlated systems: recent developments in multiconfiguration pair-density functional theory and multiconfiguration nonclassical-energy functional theory, accessed June 29, 2025, https://pmc.ncbi.nlm.nih.gov/articles/PMC9261488/
120. Methods of Modeling of Strongly Correlated Electron Systems - MDPI, accessed June 29, 2025, https://www.mdpi.com/2079-4991/13/2/238
121. 1 Dynamical Mean-Field Approach for Strongly Correlated Materials - cond-mat.de, accessed June 29, 2025, https://www.cond-mat.de/events/correl11/manuscripts/vollhardt.pdf
122. Correlated Electrons: From Models to Materials - cond-mat.de, accessed June 29, 2025, https://www.cond-mat.de/events/correl12/manuscripts/correl12.pdf
123. Mott transition and correlation effects on strictly localized states in an octagonal quasicrystal - arXiv, accessed June 29, 2025, https://arxiv.org/html/2505.15498v1
124. MACHINE LEARNING AND MONTE CARLO STUDIES OF STRONGLY CORRELATED SYSTEMS - Cornell eCommons, accessed June 29, 2025,

https://ecommons.cornell.edu/items/86209b3a-ae6a-4540-a439-8c86eed0f5b6
125. [1910.12650] Dynamical Mean-Field Theory of Strongly Correlated Electron Systems - arXiv, accessed June 29, 2025, https://arxiv.org/abs/1910.12650
126. Unravel Electronic Structure in Strongly Correlated Materials [Slides] - OSTI, accessed June 29, 2025, https://www.osti.gov/biblio/2282525
127. Quantum Monte Carlo Methods for Strongly Correlated ... - Physics, accessed June 29, 2025, http://physics.wm.edu/~shiwei/Preprint/Springer2003_Zhang_2.pdf
128. Difference between Monte Carlo and Quantum Monte Carlo methods? - Physics Stack Exchange, accessed June 29, 2025, https://physics.stackexchange.com/questions/56373/difference-between-monte-carlo-and-quantum-monte-carlo-methods
129. Quantum Materials – Accelerator Technology & Applied Physics ..., accessed June 29, 2025, https://atap.lbl.gov/research/scientific-programs-and-centers/quantum-materials/
130. Tensor Network Algorithms: A Route Map | Annual Reviews, accessed June 29, 2025, https://www.annualreviews.org/content/journals/10.1146/annurev-conmatphys-040721-022705
131. Review Articles & Learning Resources - Tensor Network, accessed June 29, 2025, https://tensornetwork.org/reviews_resources.html
132. Tensor Networks and Applications in Condenser Matter - mediaTUM, accessed June 29, 2025, https://mediatum.ub.tum.de/doc/1070963/1070963.pdf
133. Developments in the Tensor Network--from Statistical Mechanics to ..., accessed June 29, 2025, https://arxiv.org/abs/2111.12223
134. Theory of strongly correlated electron systems | Physics - Loughborough University, accessed June 29, 2025, https://www.lboro.ac.uk/departments/physics/research/research-themes/condensed-matter-and-materials-physics/theoryofstronglycorrelatedelectronsystems/
135. Quantum Materials - Institute for Advanced Materials & Manufacturing - UT Research, accessed June 29, 2025, https://research.utk.edu/iamm/research-areas/quantum-materials/
136. Toward a predictive theory of correlated materials (Journal Article) - OSTI.GOV, accessed June 29, 2025, https://www.osti.gov/pages/biblio/1462849
137. Materials Theory | ORNL, accessed June 29, 2025, https://www.ornl.gov/group/materials-theory
138. Research Groups | Argonne National Laboratory, accessed June 29, 2025, https://www.anl.gov/msd/research-groups
139. IMS Conferences and Workshops | Los Alamos National Laboratory, accessed June 29, 2025, https://www.lanl.gov/engage/collaboration/nsec/institute-for-materials-science/conferences-and-workshops
140. Condensed Matter Physics & Materials Science | HOME - Brookhaven National Laboratory, accessed June 29, 2025, https://www.bnl.gov/cmpmsd/
141. Condensed Matter Theory Group | Home - Brookhaven National Laboratory, accessed June 29, 2025, https://www.bnl.gov/cmpmsd/cmth/

142. Topological quantum computing with Majorana Fermions - YouTube, accessed June 29, 2025, https://m.youtube.com/watch?v=Xyfsr-coriQ
143. What are the challenges in making and controlling qubits for quantum computers? - Quora, accessed June 29, 2025, https://www.quora.com/What-are-the-challenges-in-making-and-controlling-qubits-for-quantum-computers
144. What Is a Topological Qubit? Ultimate Guide for 2025 | SpinQ, accessed June 29, 2025, https://www.spinquanta.com/news-detail/what-is-a-topological-qubit
145. Why is it helpful to use Majorana particle in topological quantum computing (they are just Fermions?!), accessed June 29, 2025, https://quantumcomputing.stackexchange.com/questions/41320/why-is-it-helpful-to-use-majorana-particle-in-topological-quantum-computing-the
146. Topological quantum computing: Majorana fermions and where to find them, accessed June 29, 2025, https://www.qutube.nl/quantum-computer-12/topological-quantum-computing-majorana-fermions-and-where-to-find-them
147. Majorana nanowires for topological quantum ... - AIP Publishing, accessed June 29, 2025, https://pubs.aip.org/aip/jap/article-pdf/doi/10.1063/5.0102999/19874157/231101_1_5.0102999.pdf
148. Topological quantum computation based on chiral Majorana ... - PNAS, accessed June 29, 2025, https://www.pnas.org/doi/10.1073/pnas.1810003115
149. Q&A: Will Microsoft's quantum 'breakthrough' revolutionize computing? - Penn State, accessed June 29, 2025, https://www.psu.edu/news/research/story/qa-will-microsofts-quantum-breakthrough-revolutionize-computing
150. Experimental review on Majorana zero-modes in hybrid nanowires - arXiv, accessed June 29, 2025, https://arxiv.org/html/2009.10985v2
151. Experimental review on Majorana zero-modes in hybrid nanowires - ResearchGate, accessed June 29, 2025, https://www.researchgate.net/publication/354409919_Experimental_review_on_Majorana_zero-modes_in_hybrid_nanowires
152. Disordered Majorana nanowires: Studying disorder without any disorder | Phys. Rev. B, accessed June 29, 2025, https://link.aps.org/doi/10.1103/PhysRevB.110.075401
153. Shadows That Compute: The Rise of Microsoft's Majorana 1 in Next-Generation Quantum Technologies | by Adnan Masood, PhD. | Medium, accessed June 29, 2025, https://medium.com/@adnanmasood/shadows-that-compute-the-rise-of-microsofts-majorana-1-in-next-generation-quantum-technologies-903a908bb071
154. Microsoft's claim of a working "topological qubit" sparks skepticism among physicists : r/Physics - Reddit, accessed June 29, 2025, https://www.reddit.com/r/Physics/comments/1jm9a5p/microsofts_claim_of_a_working_topological_qubit/
155. Microsoft Story Labs: Station Q, accessed June 29, 2025,

https://news.microsoft.com/stories/stationq/
156. Topological Quantum Processor: a Breakthrough in Computing | College of Engineering, accessed June 29, 2025, https://engineering.ucsb.edu/news/topological-quantum-processor-breakthrough-computing
157. Microsoft unveils Majorana 1, the world's first quantum processor ..., accessed June 29, 2025, https://azure.microsoft.com/en-us/blog/quantum/2025/02/19/microsoft-unveils-majorana-1-the-worlds-first-quantum-processor-powered-by-topological-qubits/
158. Microsoft Majorana 1 Path to Million Qubit Quantum Computers, Classical Encryption has ZERO SAFETY - QNu Labs, accessed June 29, 2025, https://www.qnulabs.com/blog/microsoft-majorana-1-path-to-million-qubit-quantum-computers-classical-encryption-has-zero-safety
159. Majorana 1: Microsoft's Quantum Computing Breakthrough! - YouTube, accessed June 29, 2025, https://www.youtube.com/shorts/9kxcGmHJnCI
160. Physicists are mostly unconvinced by Microsoft's new topological quantum chip, accessed June 29, 2025, https://www.sciencenews.org/article/microsoft-topological-quantum-majorana
161. Machine Learning the Disorder Landscape of Majorana Nanowires | Phys. Rev. Lett., accessed June 29, 2025, https://link.aps.org/doi/10.1103/PhysRevLett.132.206602
162. DOE National QIS Research Centers - Q-NEXT, accessed June 29, 2025, https://q-next.org/doe-national-qis-research-centers/
163. National QIS Research Centers | U.S. DOE Office of Science(SC), accessed June 29, 2025, https://science.osti.gov/Initiatives/QIS/QIS-Centers
164. Quantum Computing | Argonne National Laboratory, accessed June 29, 2025, https://www.anl.gov/mcs/quantum-computing
165. Materials Science | Argonne National Laboratory, accessed June 29, 2025, https://www.anl.gov/msd
166. DOE National Quantum Information Science Research Centers, accessed June 29, 2025, https://nqisrc.org/
167. Quantum Science Center: Home, accessed June 29, 2025, https://www.qscience.org/
168. C2QA | National Quantum Information Science Centers, accessed June 29, 2025, https://www.bnl.gov/quantumcenter/QIS-centers.php
169. Three-pronged approach discerns qualities of quantum spin liquids | ORNL, accessed June 29, 2025, https://www.ornl.gov/news/three-pronged-approach-discerns-qualities-quantum-spin-liquids
170. Quantum Computing Group | Home - Brookhaven National Laboratory, accessed June 29, 2025, https://www.bnl.gov/compsci/quantum/
171. Mapping the Electronic States in an Exotic Superconductor | BNL Newsroom, accessed June 29, 2025, https://www.bnl.gov/newsroom/news.php?a=118841
172. Condensed Matter Physics & Materials Science | Chiral ... - BNL, accessed June 29, 2025, https://www.bnl.gov/cmpmsd/aem/

173. Microsoft's Majorana Topological Chip -- An Advance 17 Years in The Making, accessed June 29, 2025, https://thequantuminsider.com/2025/02/19/microsofts-majorana-topological-chip-an-advance-17-years-in-the-making/
174. High spin axion insulator - PMC, accessed June 29, 2025, https://pmc.ncbi.nlm.nih.gov/articles/PMC11102527/
175. Mapping the unconventional orbital texture in topological crystalline ..., accessed June 29, 2025, https://www.osti.gov/pages/biblio/1557723
176. Topological Crystalline Insulators | Phys. Rev. Lett. - Physical Review Link Manager, accessed June 29, 2025, https://link.aps.org/doi/10.1103/PhysRevLett.106.106802
177. [2311.17018] Generation of higher-order topological insulators using periodic driving - arXiv, accessed June 29, 2025, https://arxiv.org/abs/2311.17018
178. Crystalline Topological Insulators: A TQFT Guide - Number Analytics, accessed June 29, 2025, https://www.numberanalytics.com/blog/crystalline-topological-insulators-tqft-guide
179. Experimental Realization of a Topological Crystalline Insulator in SnTe - KEK, accessed June 29, 2025, http://pfwww.kek.jp/acr2012pdf/part_a/12ah2_2.pdf
180. Experimental realization of a topological crystalline insulator in SnTe - ResearchGate, accessed June 29, 2025, https://www.researchgate.net/publication/228059259_Experimental_realization_of_a_topological_crystalline_insulator_in_SnTe
181. Surfaces of axion insulators | Phys. Rev. B - Physical Review Link Manager, accessed June 29, 2025, https://link.aps.org/doi/10.1103/PhysRevB.98.245117
182. Realization of the Axion Insulator State in Quantum Anomalous Hall Sandwich Heterostructures | Phys. Rev. Lett. - Physical Review Link Manager, accessed June 29, 2025, https://link.aps.org/doi/10.1103/PhysRevLett.120.056801
183. Visualization of an axion insulating state at the transition between 2 chiral quantum anomalous Hall states | PNAS, accessed June 29, 2025, https://www.pnas.org/doi/10.1073/pnas.1818255116
184. [1710.00471] Realization of the Axion Insulator State in Quantum Anomalous Hall Sandwich Heterostructures - arXiv, accessed June 29, 2025, https://arxiv.org/abs/1710.00471
185. Experimental Realization of an Intrinsic Magnetic Topological Insulator - Chin. Phys. Lett., accessed June 29, 2025, https://cpl.iphy.ac.cn/en/article/pdf/preview/10.1088/0256-307X/36/7/076801.pdf
186. (PDF) Progress on antiferromagnetic topological insulator MnBi2Te4 - ResearchGate, accessed June 29, 2025, https://www.researchgate.net/publication/367582615_Progress_on_antiferromagnetic_topological_insulator_MnBi2Te4
187. Generation of higher-order topological insulators using periodic driving - Institute of Physics, Bhubaneswar, accessed June 29, 2025, https://samkhya.iopb.res.in/Generation_higher-order_topo_insulators_periodic_driving_Arnob.pdf

188. Higher-order topological insulators (Journal Article) | OSTI.GOV, accessed June 29, 2025, https://www.osti.gov/pages/biblio/1499926
189. Realization of the Square-Root Higher-Order Topological Insulator in Electric Circuits | Nano Letters - ACS Publications, accessed June 29, 2025, https://pubs.acs.org/doi/10.1021/acs.nanolett.0c03049
190. Observation of a Higher-Order End Topological Insulator in a Real Projective Lattice, accessed June 29, 2025, https://pubmed.ncbi.nlm.nih.gov/38214384/
191. Experimental Observation of Higher-Order Topological Anderson Insulators | Phys. Rev. Lett. - Physical Review Link Manager, accessed June 29, 2025, https://link.aps.org/doi/10.1103/PhysRevLett.126.146802
192. One-dimensional -classified topological crystalline insulator under space-time inversion symmetry - Physical Review Link Manager, accessed June 29, 2025, https://link.aps.org/doi/10.1103/jxhg-xtzm
193. Higher-order topological insulators in three dimensions without crystalline counterparts | Phys. Rev. B - Physical Review Link Manager, accessed June 29, 2025, https://link.aps.org/doi/10.1103/PhysRevB.109.134205
194. Floquet engineering of topological phase transitions in a quantum spin Hall α – T 3 system, accessed June 29, 2025, https://link.aps.org/doi/10.1103/PhysRevB.111.045406
195. 2D Materials - Molecular Foundry - Lawrence Berkeley National Laboratory, accessed June 29, 2025, https://foundry.lbl.gov/tag/2d-materials/
196. Quantum Materials - Berkeley Physics, accessed June 29, 2025, https://physics.berkeley.edu/research-faculty/lanzara-group/projects/quantum-materials
197. Topological Materials | Argonne National Laboratory, accessed June 29, 2025, https://www.anl.gov/msd/topological-materials
198. Scientists make a surprising discovery about magnetic defects in topological insulators, accessed June 29, 2025, https://www.ameslab.gov/news/scientists-make-a-surprising-discovery-about-magnetic-defects-in-topological-insulators
199. [Literature Review] Boundary Witten effect in multi-axion insulators, accessed June 29, 2025, https://www.themoonlight.io/en/review/boundary-witten-effect-in-multi-axion-insulators
200. Axion Insulator State in a Ferromagnet/Topological Insulator/Antiferromagnet Heterostructure | Nano Letters - ACS Publications, accessed June 29, 2025, https://pubs.acs.org/doi/abs/10.1021/acs.nanolett.9b00047
201. Experimental realization of a reconfigurable electroacoustic topological insulator - PNAS, accessed June 29, 2025, https://www.pnas.org/doi/10.1073/pnas.1920549117
202. Unified characterization for higher-order topological phase transitions | Phys. Rev. Research, accessed June 29, 2025, https://link.aps.org/doi/10.1103/PhysRevResearch.5.L022032
203. Lawrence Berkeley National Laboratory - eScholarship, accessed June 29, 2025, https://escholarship.org/content/qt01m864fh/qt01m864fh.pdf

204. Enhancement of temperature of the quantum anomalous Hall effect ..., accessed June 29, 2025, https://link.aps.org/doi/10.1103/PhysRevB.111.184422
205. Enhanced Quantum Anomalous Hall Effect with an Active Capping Layer - PubMed, accessed June 29, 2025, https://pubmed.ncbi.nlm.nih.gov/37278509/
206. [2306.04552] High temperature, gate-free quantum anomalous Hall effect with an active capping layer - arXiv, accessed June 29, 2025, https://arxiv.org/abs/2306.04552
207. Room-Temperature Quantum Anomalous Hall Effect in Terbium monohalide - arXiv, accessed June 29, 2025, https://arxiv.org/html/2501.09970v1
208. Quantum anomalous Hall effect | National Science Review - Oxford Academic, accessed June 29, 2025, https://academic.oup.com/nsr/article/1/1/38/1505089
209. High-precision realization of robust quantum anomalous Hall state in a hard ferromagnetic topological insulator - CIQM, accessed June 29, 2025, http://ciqm.harvard.edu/uploads/2/3/3/4/23349210/chang_1412.3758v2.pdf
210. Pursuing the high-temperature quantum anomalous Hall effect in heterostructures | Phys. Rev. B - Physical Review Link Manager, accessed June 29, 2025, https://link.aps.org/doi/10.1103/PhysRevB.101.014423
211. High-temperature Quantum Anomalous Hall Effect Research Articles - R Discovery, accessed June 29, 2025, https://discovery.researcher.life/topic/high-temperature-quantum-anomalous-hall-effect/22285367?page=1&topic_name=High-Temperature%20Quantum%20Anomalous%20Hall%20Effect
212. High-Temperature Quantum Anomalous Hall Insulators in Lithium-Decorated Iron-Based Superconductor Materials - PubMed, accessed June 29, 2025, https://pubmed.ncbi.nlm.nih.gov/32909795/
213. High-Temperature Quantum Anomalous Hall Insulators in Lithium-Decorated Iron-Based Superconductor Materials | Phys. Rev. Lett., accessed June 29, 2025, https://link.aps.org/doi/10.1103/PhysRevLett.125.086401
214. Exchange-Biased Quantum Anomalous Hall Effect - PubMed, accessed June 29, 2025, https://pubmed.ncbi.nlm.nih.gov/37207689/
215. The Quantum Anomalous Hall Effect: Magnetism Uncovered - Number Analytics, accessed June 29, 2025, https://www.numberanalytics.com/blog/quantum-anomalous-hall-effect-magnetism
216. Unlocking Quantum Anomalous Hall Effect - Number Analytics, accessed June 29, 2025, https://www.numberanalytics.com/blog/quantum-anomalous-hall-effect-inorganic-compounds
217. The Road to High-Temperature Quantum Anomalous Hall Effect in Magnetic Topological Insulators | Request PDF - ResearchGate, accessed June 29, 2025, https://www.researchgate.net/publication/345354358_The_Road_to_High-Temperature_Quantum_Anomalous_Hall_Effect_in_Magnetic_Topological_Insulators
218. Toward robust quantum anomalous Hall effect - University of Science and Technology of China, accessed June 29, 2025, https://en.ustc.edu.cn/info/1015/2618.htm

219. Materials for raising the temperature of the quantized anomalous Hall and magnetoelectric effects - Mapping Ignorance, accessed June 29, 2025, https://mappingignorance.org/2017/07/13/materials-raising-temperature-quantized-anomalous-hall-magnetoelectric-effects/
220. Layer-dependent quantum anomalous Hall effect in rhombohedral graphene | Phys. Rev. B, accessed June 29, 2025, https://link.aps.org/doi/10.1103/PhysRevB.111.L081111
221. Quantum anomalous Hall effect in perfectly compensated collinear antiferromagnetic thin films | Phys. Rev. B, accessed June 29, 2025, https://link.aps.org/doi/10.1103/PhysRevB.106.195433
222. Semiconductor demonstrates elusive quantum physics model | Cornell Chronicle, accessed June 29, 2025, https://news.cornell.edu/stories/2022/01/semiconductor-demonstrates-elusive-quantum-physics-model
223. During search for elusive quantum material, researchers accidentally uncover new magnetic phenomenon - JHU Hub, accessed June 29, 2025, https://hub.jhu.edu/2020/08/04/tyrel-mcqueen-quantum-anomalous-anomalous-hall-effect/
224. Developing Graphene-Based Moiré Heterostructures for Twistronics ..., accessed June 29, 2025, https://pmc.ncbi.nlm.nih.gov/articles/PMC8728823/
225. Twistronics and moiré excitonic physics in van der Waals heterostructures - HEP Journals, accessed June 29, 2025, https://journal.hep.com.cn/fop/EN/10.1007/s11467-023-1355-6
226. Exotic Quantum Phenomena in Twisted Bilayer Graphene - arXiv, accessed June 29, 2025, https://arxiv.org/html/2411.00854v1
227. Correlations in moiré heterostructures - Stanford Digital Repository, accessed June 29, 2025, https://purl.stanford.edu/cs071hw8313
228. New Research on Superconductivity in Twisted Bilayer Graphene ..., accessed June 29, 2025, https://nationalmaglab.org/news-events/news/superconductivity-in-twisted-bilayer-graphene/
229. Twistronics lights up with moiré exciton experiments - Physics World, accessed June 29, 2025, https://physicsworld.com/a/twistronics-lights-up-with-moire-exciton-experiments/
230. Measurements of Correlated Insulator Gaps in a Transition-Metal Dichalcogenide Moiré Superlattice | Nano Letters - ACS Publications, accessed June 29, 2025, https://pubs.acs.org/doi/10.1021/acs.nanolett.5c00795
231. Correlated topological mixed-valence insulators in moir\'e heterobilayers | Phys. Rev. B, accessed June 29, 2025, https://link.aps.org/doi/10.1103/PhysRevB.110.L201105
232. Recent progress on 2D ferroelectric and multiferroic materials, challenges, and opportunity, accessed June 29, 2025, https://par.nsf.gov/servlets/purl/10268266
233. Unconventional superconductivity with preformed pairs in twisted bilayer

graphene | Phys. Rev. B - Physical Review Link Manager, accessed June 29, 2025, https://link.aps.org/doi/10.1103/PhysRevB.107.L060503
234. Unconventional superconductivity with preformed pairs in twisted bilayer graphene - aalto.fi)., accessed June 29, 2025, https://acris.aalto.fi/ws/portalfiles/portal/104921990/Unconventional_superconductivity_with_preformed_pairs_in_twisted_bilayer_graphene.pdf
235. Correlations and Topology in Moiré Materials: Moiré 2025, accessed June 29, 2025, https://moire25.ch/
236. Moiré Materials - Yale Scientific Magazine, accessed June 29, 2025, https://www.yalescientific.org/2024/01/moire-materials/
237. Correlated electronic states in multilayer moire superlattice of ..., accessed June 29, 2025, https://www.spiedigitallibrary.org/conference-proceedings-of-spie/PC13368/PC1336807/Correlated-electronic-states-in-multilayer-moire-superlattice-of-transition-metal/10.1117/12.3048019.full
238. Seeing moiré: Convolutional network learning applied to twistronics - Physical Review Link Manager, accessed June 29, 2025, https://link.aps.org/pdf/10.1103/PhysRevResearch.4.043224
239. Moiré than Meets the Eye - Berkeley Lab – Berkeley Lab News Center, accessed June 29, 2025, https://newscenter.lbl.gov/2025/03/24/moire-than-meets-the-eye/
240. New quasiparticle discovered in moiré patterns - Physics - University of California, Berkeley, accessed June 29, 2025, https://physics.berkeley.edu/news/new-quasiparticle-discovered-moir%C3%A9-patterns
241. For Layered 2D Materials, Robotics Produces Cleaner Interfaces Between Stacked Sheets, accessed June 29, 2025, https://www.energy.gov/science/bes/articles/layered-2d-materials-robotics-produces-cleaner-interfaces-between-stacked
242. Atom Identification in Bilayer Moiré Materials with Gomb-Net | ORNL, accessed June 29, 2025, https://www.ornl.gov/publication/atom-identification-bilayer-moire-materials-gomb-net
243. Moiré Patterns Open Up More Possibilities for Quantum Information | NIST, accessed June 29, 2025, https://www.nist.gov/quantum-information-science/moire-patterns-open-more-possibilities-quantum-information
244. (PDF) Intrinsic magnetic topological insulators - ResearchGate, accessed June 29, 2025, https://www.researchgate.net/publication/350321614_Intrinsic_magnetic_topological_insulators
245. Intrinsic Magnetic Topological Insulators - The Innovation, accessed June 29, 2025, https://www.the-innovation.org/article/id/648ae16ccf340000a100291f
246. Intrinsic magnetic topological materials - HEP Journals, accessed June 29, 2025, https://journal.hep.com.cn/fop/EN/10.1007/s11467-022-1250-6

247. Progress on the antiferromagnetic topological insulator MnBi 2 Te 4 - Oxford Academic, accessed June 29, 2025, https://academic.oup.com/nsr/article/11/2/nwac296/6967909
248. Tuning Fermi Levels in Intrinsic Antiferromagnetic Topological Insulators MnBi2Te4 and MnBi4Te7 by Defect Engineering and Chemic - OSTI, accessed June 29, 2025, https://www.osti.gov/servlets/purl/1766416
249. Experimental Realization of an Intrinsic Magnetic Topological Insulator * | Request PDF, accessed June 29, 2025, https://www.researchgate.net/publication/333753173_Experimental_Realization_of_an_Intrinsic_Magnetic_Topological_Insulator
250. Direct visualization of edge state in even-layer MnBi2Te4 at zero magnetic field - PMC, accessed June 29, 2025, https://pmc.ncbi.nlm.nih.gov/articles/PMC9747779/
251. Exploring Intrinsic Magnetic Topological Insulators: The Case of EuIn 2 As 2 - arXiv, accessed June 29, 2025, https://arxiv.org/html/2401.11386v3
252. [2408.16851] New magnetic topological materials from high-throughput search - arXiv, accessed June 29, 2025, http://arxiv.org/abs/2408.16851
253. Native defects in antiferromagnetic topological insulator MnBi2Te4 | ORNL, accessed June 29, 2025, https://www.ornl.gov/publication/native-defects-antiferromagnetic-topological-insulator-mnbi2te4
254. On the topological surface states of the intrinsic magnetic topological insulator Mn-Bi-Te family - Oxford Academic, accessed June 29, 2025, https://academic.oup.com/nsr/article/11/2/nwad066/7074582
255. Experimental realization of an intrinsic magnetic topological insulator - ResearchGate, accessed June 29, 2025, https://www.researchgate.net/publication/327835670_Experimental_realization_of_an_intrinsic_magnetic_topological_insulator
256. An Intrinsically Magnetic Topological Insulator - PHYSICS - APS.org, accessed June 29, 2025, https://physics.aps.org/articles/pdf/10.1103/Physics.13.s119
257. [2505.01252] Intrinsic magnetic topological insulators of the MnBi${}_2$Te${}_4$ family - arXiv, accessed June 29, 2025, https://arxiv.org/abs/2505.01252
258. Experimental Realization of an Intrinsic Magnetic Topological Insulator - Chin. Phys. Lett., accessed June 29, 2025, https://cpl.iphy.ac.cn/article/10.1088/0256-307X/36/7/076801
259. [1809.07926] Experimental realization of an intrinsic magnetic topological insulator - arXiv, accessed June 29, 2025, https://arxiv.org/abs/1809.07926
260. Quantum spin liquid signatures in monolayer 1T-NbSe2 - PMC - PubMed Central, accessed June 29, 2025, https://pmc.ncbi.nlm.nih.gov/articles/PMC10940636/
261. Quantum spin liquids: A review | Request PDF - ResearchGate, accessed June 29, 2025, https://www.researchgate.net/publication/309799265_Quantum_spin_liquids_A_review

262. (PDF) Experimental identification of quantum spin liquids - ResearchGate, accessed June 29, 2025, https://www.researchgate.net/publication/332226396_Experimental_identification_of_quantum_spin_liquids
263. Strong quantum fluctuations in a quantum spin liquid candidate with a Co-based triangular lattice | PNAS, accessed June 29, 2025, https://www.pnas.org/doi/10.1073/pnas.1906483116
264. The Frustrated Matter of Quantum Spin Liquids | NIST, accessed June 29, 2025, https://www.nist.gov/blogs/taking-measure/frustrated-matter-quantum-spin-liquids
265. Evidence of Long-Sought "Quantum Spin Liquid" Discovered | TU Wien, accessed June 29, 2025, https://www.tuwien.at/en/all-news/news/hinweise-auf-lange-gesuchte-quanten-spin-fluessigkeit-entdeckt
266. Colloquium: Herbertsmithite and the search for the quantum spin liquid | Rev. Mod. Phys., accessed June 29, 2025, https://link.aps.org/doi/10.1103/RevModPhys.88.041002