

UNIVERSITAS ISLAM INDONESIA

Jl. Kaliurang Km 14.5, Sleman Yogyakarta
LABORATORIUM TERPADU
Quantachrome TouchWin v1.22



Report date: Mon Jan 8 2024 Operator: Yusuf
Filename: 16731223_2.qcuPhysIso

Analysis Information

Sample

ID 1673_2 Weight 0.0855g
Description CFA-CTAB-5

Analysis

Data ID {31f7ffaa-a53f-4a2c-9c5c-4615c1d14882}
Operator Yusuf Date 2024.01.08 Duration 145.9min
Instrument St 3 on NOVA touch 4LX [s/n:170170510001] Firmware 1.07
Comments description of sample
Ambient Temp. 20.38°C Void Volume Mode NOVA mode Cell ID 43
Cell Type 9mm with rod Thermal Delay 300sec Po Mode Continuous

Adsorbate

Name Nitrogen Molecular Weight 28.013g/mol Cross Section Area 16.2Å²/mol
Non-ideality 6.580000e-05 1/torr Bath Temperature 77.35K

Degas information

Time 1.0 hours Temp 90.000000°C

Data Reduction Parameters

Thermal Transpiration yes Eff. Cell Diameter 0mm Eff. Molec. Diameter 0Å

Adsorbate Model

Name Nitrogen Molecular Weight 28.0134g Cross Section Area 16.2Å²/molec
Bath Temperature 77.35K

BET Multi-point BET results

Isotherm Branch Adsorption
Slope 66.0165
Intercept 0.492626
Correlation coeff., r 0.999772
C constant 135.009
Surface area 52.361 m²/g

Graph - BET Multi-point BET

+ BET (all) ○ BET — BF

