

UNIVERSITAS ISLAM INDONESIA

Jl. Kaliurang Km 14.5, Sleman Yogyakarta
LABORATORIUM TERPADU
Quantachrome TouchWin v1.22



Report date: Mon Jan 8 2024 Operator: Yusuf
Filename: 16731223_2.qcuPhysIso

Analysis Information

Sample

ID 1673_2 Weight 0.0855g
Description CFA-CTAB-5

Analysis

Data ID {31f7ffaa-a53f-4a2c-9c5c-4615c1d14882}
Operator Yusuf Date 2024.01.08 Duration 145.9 min
Instrument St 3 on NOVA touch 4LX [s/n:170170510001] Firmware 1.07
Comments description of sample
Ambient Temp. 20.38°C Void Volume Mode NOVA mode Cell ID 43
Cell Type 9mm with rod Thermal Delay 300 sec Po Mode Continuous

Adsorbate

Name Nitrogen Molecular Weight 28.013 g/mol Cross Section Area 16.2 Å²/mol
Non-ideality 6.580000e-05 1/torr Bath Temperature 77.35 K

Degas information

Time 1.0 hours Temp 90.000000°C

Data Reduction Parameters

Thermal Transpiration yes Eff. Molec. Diameter 0 Å
Eff. Cell Diameter 0 mm
Temp. Comp no
Thickness Method deBoer

Adsorbate Model

Name Nitrogen Molecular Weight 28.0134 g Cross Section Area 16.2 Å²/molec
Bath Temperature 77.35 K

Total Pore Volume results

Total Pore Volume 1.3865e-01 cc/g
for pores smaller than 18.90 nm (radius)
at relative pressure 0.94635