

P-102 Inspection Report — 2025

Document ID: APEL-INS-P102-2025 | Owner: Inspection & Integrity | Revision: 2.1

This dated record evaluates P-102 crude-transfer service.

Identity

Field	Value
Asset	P-102
Unit	CDU-4
Date	2025-06-21
Criticality	HIGH
WO	WO-5012

2025 measurements

The recorded measurements support later trend analysis.

Measured values

Parameter	Value	Unit
Pressure	37.0	bar
Corrosion	2.4	mm
Vibration	5.3	mm/s
Seal temperature	79	°C

2025 condition findings

The inspector records condition without extending the evidence.

Findings

- Localized casing corrosion and elevated vibration.
- External observation does not establish internal structural condition.
- Record is linked to the work order.

2025 historical context

Pressure change +3.0 bar; corrosion change +1.2 mm; vibration change +1.2 mm/s.

Series

- Pressure: 34 → 37 → 42 bar.
- Corrosion: 1.2 → 2.4 → 3.8 mm.
- Vibration: 4.1 → 5.3 → 7.2 mm/s.

2025 recommendation

The recommendation states the next action supported at that date.

Disposition

- Increase inspection frequency and investigate emerging vibration/corrosion trend.
- This report is not a final fitness-for-service decision.
- Owner: Inspection & Integrity.