

Part of the ROCKWOOL Group

INVOICE

Ordered by: 40062 Brake Parts India PVT. Ltd. IEC Nr. 0507083229 Village - Rewli PO Murthal GST 06AAGCA5049Q1Z8 131027 SONEPAT, HARYANA INDIA

Invoice address: 40062 Brake Parts India PVT. Ltd. IEC Nr. 0507083229 Village - Rewli PO Murthal GST 06AAGCA5049Q1Z8 131027 SONEPAT, HARYANA **INDIA**

Invoice no. / date:

163652069 / 22.09.2020

Page 1 / 1

Order no. / date:

7621832 / 28.08.2020

Your reference: Contactperson:

Material

60220042078

Corina Hendriks

PO Box 160 Roermond

Italii	IMOTOTIO	Number	Quantity	Price	Amount
	Material description	Unit	Unit	Unit	
10	Promaxon-D				
	bag 15 kg pallet 210 kg				
	Synthetic hydrated calcium silicate				
	136919	2.100,00	2.100,00	4.431,00	9.305,10
		KG	KG	1.000 KG	
	Stat. No.: 28399000				
	Delivery No/Date: 31707345 / 22.09.2020				
	Container Number: 46-bkl-1				
	Country of origin: BE				

Amount excl. VAT 9.305,10 **Output Tax** 0,00 0,00

Export supply 0% VAT # art. 146 (1) VAT Directive 2006/112/EC

EUR

9.305,10

Delivery date: Terms of delivery

22.09.2020 -FCA Roermond

Payment term:

60 days end of month on 28th

Gross/Nett weight: Transp. volume:

2.373 / 2.100 KG 23,100 M3

Delivery address: 40062 Brake Parts India PVT, Ltd. IEC Nr. 0507083229

PO Murthal GST 06AAGCA5049Q1Z8

Sonepat Haryana 131027

India

Rockwool B.V. | Industrieweg 15, 6045 JG Roermond, The Netherlands | Postbus 1160, 6040 KD Roermond, The Netherlands T: +31 (0) 475 35 35 35 | E: cs@lapinus.com | www.lapinus.com | KvK Nederland 13014428 | VAT NL0016.96,592.B01 Bank: ING BANK N.V. | NL87 INGB 0674 2921 11 | BIC/SWIFT INGBNL2A | Beneficiary: ROCKWOOL B.V.

The general terms and conditions of ROCKWOOL BV, as filed with the Chamber of Commerce The Netherlands, are applicable to all our offers and agreements and the execution thereof, more specifically they apply to this order and the execution thereof. You have received a copy of the general terms and conditions of ROCKWOOL BV with the quotation. On your first request we will send you a new copy. Transport cost may be subject to change, actual cost will be invoiced.

Industrieweg 15 Rockwool B.V.

6045 JG Roermond / The Netherlands

Our ordernr : 7621832

Delivery nr : 31707345

Your ordernr: 60220042078

Container nr: 46-bkl-1

Shipment nr.: 0005791430

PO Murthal GST 06AAGCA5049Q128 Brake Parts India PVT. Ltd. IEC Nr. 0507083229 . .

131027 Sonepat, Haryana India

M Lapinus

DETAILED PACKING LIST

Dimensions in m per package	1150,00 1150,00 1150,0			
Total gross weight per item kgs	2373,000			:
Total net weight per item kgs	2100,000			
Total quantity per item in m¹/m²/kg	2100,00			
Contents per package in m¹/m²/kg	n 1,00			
Type and number of packages	pallet 210 kg 2100 Kilogram			
Product and dimensions	Promaxon-D, bag 15 kg pallet 210 kg 15,0			

Date: 22-09-2020

Kgs

2373,000

2100,000 Kgs

140 BAGS ON 10 PALLETS



Part of the ROCKWOOL Group

For attn of

Mr./ Mrs.

Date |

23-09-2020

Please find attached Test Report of compliance with the order (EN 10204: 2004 / 2.2)

Client

Brake Parts India PVT. Ltd.

Client-orderno

60220042078

Lapinus orderno

7621832

Product:

Promaxon-D

bag 15 kg pallet 210 kg

Synthetic hydrated calcium silicate

Total order Qty:

2.100 kg

Batch no. Batch Qty:

2018083 - 630 kg

Batch no. Batch Qty:

2018109 - 630 kg

Batch no. Batch Qty:

2019223 - 210 kg

Batch no. Batch Qty:

2019223 - 210 kg

Batch no. Batch Qty:

2019112 - 420 kg

Kind regards

Customer Services

Lapinus ROCKWOOL B.V. Industrieweg 15 6045 JG Roermond PO Box 1160 6040 KD Roermond The Netherlands

cs@lapinus.com www.lapinus.com



Promat

Bormstraat 24 B-2830 Tisselt Belgium

Belgium T +32 (0)15 71 21 86 F +32 (0)15 71 26 90 www.promal com/industry

To: ROCKWOOL BV - Lapinus Fibres

For Customer: Rockwool BV

Gate B Energieweg 3 6045 JE Roermond

Nederland

PO 4503362353 article n° 136919 Loading date 15/07/2020

ANALYSIS PROMAXON D Synthetic hydrated calcium silicate VISUAL APPEARANCE: WHITE POWDER

BATCH NR.		₹.	PRODUCTION DATE	BULK DENSITY g/I	PARTICLE SIZE d(50) (µm)	COARSE PART (%) > 254 µ	MOISTURE %	WEIGHT (kg)
20 17	456	1	27-apr-2020	112,48	57,80	0,00	1,93	210
20 17	456	2	27-apr-2020	112,48	57,80	0,00	1,93	210
20 17	456	3	27-apr-2020	112,48	57,80	0.00	1,93	210
20 17	456	4	27-apr-2020	112,48	57,80	0,00	1,93	210
20 17	456	5	27-apr-2020	112,48	57,80	0.00	1,93	210
20 17	456	6	27-apr-2020	112,48	57,80	0,00	1,93	210
20 17	456	7	27-apr-2020	112,48	57,80	0.00	1,93	210
20 17	456	8	27-apr-2020	112,48	57,80	0,00	1,93	210
20 18	051	1	28-apr-2020	104.48	56,10	0,71	1,75	210
20 18	051	2	28-apr-2020	104,48	56,10	0,71	1,75	210
20 18	051	3	28-apr-2020	104,48	56,10	0,71	1,75	210
20 18	051	4	28-apr-2020	104,48	56,10	0,71	1,75	210
20 18	051	5	28-apr-2020	104,48	56,10	0,71	1,75	210
20 18	051	6	28-apr-2020	104,48	56,10	0,71	1,75	210
20 18	114	1	29-apr-2020	100,60	60,60	0,00	2,11	210
20 18	114	2	29-apr-2020	100,60	60,60	0,00	2,11	210
20 18	114	3	29-apr-2020	100,60	60,60	0,00	2,11	210
20 18	114	4	29-apr-2020	100,60	60,60	0,00	2,11	210
20 18	114	5	29-apr-2020	100,60	60,60	0,00	2,11	210
20 18	114	6	29-apr-2020	100,60	60,60	0.00	2,11	210
20 18	114	7	29-apr-2020	100,60	60.60	0,00	2.11	210
20 18	114	8	29-apr-2020	100,60	60,60	0.00	2,11	210
20 19	223	1	07-mei-2020	112,84	49,00	0,00	2,89	210
20 19	223	2	07-mei-2020	112,84	49,00	0,00	2,89	210
20 19	435	1	11-mei-2020	102,56	51,50	0,00	2,16	210
20 19	435	2	11-mei-2020	102,56	51,50	0.00	2,16	210





Bormstraat 24 B-2830 Tissett

Belgium T +32 (0)15 71 21 86 F +32 (0)15 71 26 90 www.promat.com/industry

To: **ROCKWOOL BV - Lapinus Fibres**

For Customer: Rockwool BV

Gate B

Energieweg 3 6045 JE Roermond

Nederland

PO 4503362353 article nº 136919 Loading date 15/07/2020

ANALYSIS	PROMAXON D Synthetic hydrated calcium silicate
	VISUAL APPEARANCE: WHITE POWDER
	The state of the s

BA	BATCH NR.		PRODUCTION DATE	BULK DENSITY g/I	PARTICLE SIZE d(50) (µm)	COARSE PART (%) > 254 µ	MOISTURE %	WEIGHT (kg)
	_							-
20 19		3	11-mei-2020	102,56	51,50	0,00	2,16	210
20 19	435	_4	11-mei-2020	102,56	51,50	0,00	2,16	210
20 19		5	11-mei-2020	102,56	51,50	0,00	2,16	210
20 19	435	6_	11-mei-2020	102,56	51,50	0,00	2,16	210
20 18	410	1	04-mei-2020	99,08	55,00	0,05	1,51	210
20 18		2	04-mei-2020	99,08	55,00	0,05	1,51	210
20 18	410	3	04-mel-2020	99,08	55,00	0,05	1,51	210
20 18	410	4	04-mei-2020	99,06	55,00	0,05	1,51	210
20 18	410	_5_	04-mei-2020	99,08	55,00	0,05	1,51	210
20 18	410	6	04-mei-2020	99,08	55,00	0,05	1,51	210
20 19	074	1	05-mei-2020	107,20	57,90	0,25	2,49	210
20 19	074	2	05-mei-2020	107,20	57,90	0,25	2,49	210
20 19	074	3	05-mei-2020	107.20	57,90	0,25	2,49	210
20 19	074	4	05-mei-2020	107,20	57,90	0,25	2,49	210
20 19	074	5	05-mei-2020	107,20	57,90	0.25	2,49	210
20 19	074	6	05-mei-2020	107,20	57,90	0,25	2,49	210
20 19	085	1	05-mei-2020	103,20	58,20	0,00	1,62	210
20 19	085	2	05-mei-2020	103,20	58,20	0.00	1,62	
20 19	085	3	05-mei-2020	103,20	58,20	0,00		210
20 19	085	4	05-mei-2020	103,20	58,20	0.00	1,62	210
20 19	085	5	05-mei-2020	103,20	58,20		1,62	210
20 19	085	6	05-mei-2020	103,20	58,20	0,00	1,62	210

10 080



Bormstraat 24 B-2830 Tisselt Belgium T +32 (0)15 71 21 86 F +32 (0)15 71 26 90 www.promat.com/industry

294

To: ROCKWOOL BV - Lapinus Fibres

For Customer: Rockwool BV

Gate B

Energieweg 3

6045 JE Roermond

Nederland

PO 4503405505 article n° 136919 Loading date 31/08/2020

ANALYSIS PROMAXON D Synthetic hydrated calcium silicate VISUAL APPEARANCE: WHITE POWDER										
BATCH NR.	PRODUCTION DATE	BULK DENSITY g/l	PARTICLE SIZE d(50) (µm)	COARSE PART (%) > 254 µ	MOISTURE %	WEIGHT (kg)				
20 19 112	3 06-mei-2020	107,40	60,00	0,00	.1,11	210				
20 19 112	4 06-mei-2020	107,40	60,00	0,00	1,11	210				
20 19 112	5 06-mei-2020	107,40	60,00	0,00	. 1,11	210				
20 19 112	6 06-mei-2020	107,40	60,00	0,00	1,11	210				
20 19 105	5 05-mei-2020	107,80	57,20	0,21	2,06	210				
20 19 105	6 05-mei-2020	107,80	57,20	21,00	2,06	210				
20 19 209	1 07-mei-2020	102,80	56,60	0,00	2,48	210				
20 19 209	2 07-mei-2020	102,80	56,60	0,00	2,48	210				
20 19 209	3 07-mei-2020	102,80	56,60	0,00	2,48	210				
20 19 209	4 07-mei-2020	102,80	56,60	0,00	2,48	210				
20 19 209	5 07-mei-2020	102,80	56,60	0,00	2,48	210				
20 19 209	6 07-mei-2020	102,80	56,60	0,00	2,48	210				
20 17 274	3 24-apr-2020	107,84	56,20	0,00	1,28	210				
20 17 274	4 24-apr-2020	107,84	56,20	0,00	1,28	210				
20 17 274	5 24-apr-2020	107,84	56,20	0,00	1,28	210				
20 17 274	6 24-apr-2020	107,84	56,20	0,00	1,28	210				
20 18 200	1 30-apr-2020	107,96	51,10	0,33	2,71	210				
20 18 200	2 30-apr-2020	107,96	51,10	0,33	2,71	210				
20 18 200	3 30-apr-2020	107,96	51,10	0,33	2,71	210				
20 18 200	4 30-apr-2020	107,96	51,10	0,33	2,71	210				
20 18 200	5 30-apr-2020	107,96	51,10	0,33	2,71	210				
20 18 200	6 30-apr-2020	107,96	51,10	0,33	2,71	210				
20 18 200	7 30-apr-2020	107,96	51,10	0,33	2,71	210				
20 18 200	8 30-apr-2020	107,96	51,10	0,33	2,71	210				



Bormstraat 24 B-2830 Tisselt Belgium

T +32 (0)15 71 21 86 F +32 (0)15 71 26 90 www.promat.com/industry 294

To: ROCKWOOL BV - Lapinus Fibres

For Customer: Rockwool BV

Gate B


Energieweg 3

6045 JE Roermond

Nederland

PO 4503405505 article n° 136919 Loading date 31/08/2020

	AUVA	100	ais peoma Visual		ANCE: W	mydrated HITE POV	calgium sind VDER	ate
BAT	CH NF	۹.	PRODUCTION DATE	BULK DENSITY g/l	PARTICLE SIZE d(50) (µm)	COARSE PART (%) > 254 μ	MOISTURE %	WEIGH' (kg)
20 19	162	3	06-mei-2020	107,56	52,60	0,00	2,78	210
20 19	162	4	06-mei-2020	107,56	52,60	0,00	2,78	210
20 19	162	5	06-mei-2020	107,56	52,60	0,00	2,78	210
20 19	162	6	06-mei-2020	107,56	52,60	0,00	2,78	210
20 18	024	1	27-apr-2020	102,36	61,00	0,40	1,00	210
20 18	024	2	27-apr-2020	102,36	61,00	0,40	1,00	210
20 18	024	3	27-apr-2020	102,36	61,00	0,40	1,00	210
20 18	024	4	27-apr-2020	102,36	61,00	0,40	1,00	210
20 18	024	5	27-арг-2020	102,36	61,00	0,40	1,00	210
20 18	024	6	27-apr-2020	102,36	61,00	0,40	1,00	210
20 18	034	1	28-apr-2020	110,72	62,40	0,00	1,91	210
20 18	034	2	28-арг-2020	110,72	62,40	0,00	1,91	210
20 18	034	3	28-apr-2020	110,72	62,40	0,00	1,91	210
20 18	034	4	28-арг-2020	110,72	62,40	0,00	1,91	210
20 18	034	5	28-apr-2020	110,72	62,40	0,00	1,91	210
20 18	034	6	28-apr-2020	110,72	62,40	0,00	1,91	210
20 19	234	1	08-mei-2020	103,28	50,20	0,00	2,51	210
20 19	234	2	08-mei-2020	103,28	50,20	0,00	2,51	210
20 19	234	3	08-mei-2020	103,28	50,20	0,00	2,51	210
20 19	234	4	08-mei-2020	103,28	50,20	0,00	2,51	210
20 19	234	5	08-mei-2020	103,28	50,20	0,00	2,51	210
20 19	234	6	08-mei-2020	103,28	50,20	0,00	2,51	210
20 19	234	7	08-mei-2020	103,28	50,20	0,00	2,51	210
20 19	234	8	08-mei-2020	103,28	50,20	0,00	2,51	210



Etex Building Performance NV Bormstraat 24 B-2830 Tissell Belgium T +32 (0)15 71 21 86 F +32 (0)15 71 26 90

www.promal.com/industry

0

For Customer:

Rocemond

PO 4503319283 Article nº 136919

Loading date: 03/09/2020

		: white powde		PARTICLE	COARSE		
	BATCH NR.	PRODUCTION DATE	BULK DENSITY g/l	SIZE d(50) (µm)	PART (%) > 254 u	MOISTURE %	WEIGHT (kg)
20 19	112 1	06/05/2020	107,40	60,00	0,00	1,11	210
20 19	112 2	06/05/2020	107,40	60,00	0,00	1,11	210
20 19	123 1	06/05/2020	101,60	59,10	0,00	2,28	210
20 19	123 2	08/05/2020	101,60	59,10	0,00	2,28	210
20 19	123 3	06/05/2020	101,60	59,10	0,00	2,28	210
20 19	123 4	06/05/2020	101,60	59,10	0,00	2,28	210
20 19	123 5	06/05/2020	101,60	59,10	0,19	2,28	210
20 19	123 6	08/05/2020	101,60	59,10	0,19	2,28	210
20 19	059 1	05/05/2020	51,00	51,00	0,19	2,27	210
20 19	059 2	05/05/2020	51,00	51,00	0,19	2,27	210
20 19	059 3	05/05/2020	51,00	51,00	0,19	2,27	210
20 19	059 4	05/05/2020	51,00	51,00	0,19	2,27	210
20 19	059 5	05/05/2020	51,00	51,00	0,14	2,27	210
20 19	059 6	05/05/2020	51,00	51,00	0,14	2,27	210
20 19	059 7	05/05/2020	51,00	51,00	0,14	2,27	210
20 19	059 8	05/05/2020	51,00	51,00	0,14	2,27	210
20 19	154 1	06/05/2020	106,80	54,70	0,14	2,87	210
20 19	154 2	06/05/2020	106,80	54,70	0,14	2,87	210
20 19	154 3	06/05/2020	106,80	54,70	0,00	2,87	210
20 19	154 4	06/05/2020	106,80	54,70	0,60	2,87	210
20 19	154 5	06/05/2020	106,80	54,70	0,00	2,87	210
20 19	154 6	06/05/2020	106,80	54,70	0,00	2,87	210



Bex Building Performance NV
Bormstraat 24
B-2630 Tisselt
Belglum
T +32 (0)15 71 21 86
F +32 (0)15 71 26 90
www.promal.com/industry

To:

ROCKWOOL BV - Lapinus Fibres

For Customer:

Shandong Double Link Brake

Material Co., Ltd. No 8, Haicheng Street 264500 Rushan City Shandong Province

PO 4503319283 Article n° 136919

Loading date: 03/09/2020

	BATCH NR.	PRODUCTION DATE	BULK DENSITY g/I	PARTICLE SIZE d(50) (µm)	COARSE PART (%) > 254 µ	MOISTURE %	WEIGHT (kg)
20 19	148 1	06/05/2020	106,98	58,00	0,00	2,20	210
20 19	148 2	06/05/2020	106,98	58,00	0,00	2,20	210
20 19	148 3	06/05/2020	106,96	58,00	0,00	2,20	210
20 19	148 4	06/05/2020	106,96	58,00	0,00	2,20	210
20 19	148 5	06/05/2020	106,96	58,00	0,00	2,20	210
20 19	148 6 : :	06/05/2020	106,96	58,00	0,00	2,20	210
20 19	148 7	06/05/2020	106,96	58,00	0,00	2,20	210
20 19	148 8	06/05/2020	106,96	58,00	0,00	2,20	210
							6300



Bormstraat 24 B-2830 Tisselt Belgium

T +32 (0)15 71 81 00 F +32 (0)15 71 81 09 E info@promat.be

To:

ROCKWOOL BV - Lapinus Fibres

For Customer: Rockwool BV

Industrienummer 7500 Laura Staal

Industrieweg 15 6045 JG Roermond

Nederland

PO 4503433106 Article nº 136919

Loading date: 14/09/2020

BATCH NR.	PRODUCTION DATE	BULK DENSITY g/I	PARTICLE SIZE d(50) (µm)	COARSE PART (%) > 254 µ	MOISTURE	WEIGHT (kg)
20 19 112 1	6/05/2020	107,40	60,00	0,00	1,11	210
20 19 112 2	6/05/2020	107,40	60,00	0,00	1,11	210
20 18 083 1	28/04/2020	98,60	56,40	0,00	1,60	210
20 18 083 2	28/04/2020	98,60	56,40	0,00	1,60	210
20 18 083 3	28/04/2020	98,60	56,40	0,00	1,60	210
20 18 083 4	28/04/2020	98,60	56,40	0,00	1,60	210
20 18 109 1	29/04/2020	97,84	57,10	0,24	1,06	210
20 18 109 2	29/04/2020	97,84	57,10	0,24	1,06	210
20 18 109 3	29/04/2020	97,84	57,10	0,24	1,06	210
20 18 109 4	29/04/2020	97,84	57,10	0,24	1,06	210
20 18 109 5	29/04/2020	97,84	57,10	0,24	1,06	210
20 18 109 6	29/04/2020	97,84	57,10	0,24	1,06	210
20 19 036 1	4/05/2020	102,16	58,40	0,05	1,54	210
20 19 036 2	4/05/2020	102,16	58,40	0,05	1,54	210
20 19 036 3	4/05/2020	102,16	58,40	0,05	1,54	210
20 19 036 4	4/05/2020	102,16	58,40	0,05	1,54	210
20 19 036 5	4/05/2020	102,16	58,40	0,05	1,54	210
20 19 036 6	4/05/2020	102,16	58,40	0,05	1,54	210
20 19 173 1	7/05/2020	104,92	58,50	0,00	2,13	210
20 19 173 2	7/05/2020	104,92	58,50	00,0	2,13	210
20 19 173 3	7/05/2020	104,92	58,50	0,00	2,13	210
20 19 173 4	7/05/2020	104,92	58,50	0,00	2,13	210
20 19 173 5	7/05/2020	104,92	58,50	0,00	2,13	210
20 19 173 6	7/05/2020	104,92	58,50	0,00	2,13	210



Bormstraat 24 B-2830 Tisselt Belgium

T +32 (0)15 71 81 00 F +32 (0)15 71 81 09 E info@promat.be

To:

ROCKWOOL BV - Lapinus Fibres

For Customer: Rockwool BV

Industrienummer 7500 Laura Staal

Industrieweg 15 6045 JG Roermond

Nederland

PO 4503433106 Article nº 136919

Loading date: 14/09/2020

(A)13	oual a	hhe	arailice: Willi	e bowde				
BATCH NR.		IR.	T PRODUCTION I		PARTICLE SIZE d(50) (µm)	COARSE PART (%) > 254 µ	MOISTURE %	WEIGHT (kg)
20	19 105	1	5/05/2020	107,80	57,20	0,21	2,06	210
20	19 105	2	5/05/2020	107,80	57,20	0,21	2,06	210
20	19 105	3	5/05/2020	107,80	57,20	0,21	2,06	210
20	19 105	4 .	5/05/2020	107,80	57,20	0,21	2,06	210
20	19 223	3	7/05/2020	112,84	49,00	0,00	2,89	210
								6090