

INVOICE

Invoice address: 40062
 Brake Parts India PVT. Ltd.
 IEC Nr. 0507083229
 Village - Rewli
 PO Murthal GST 06AAGCA5049Q1Z8
 131027 SONEPAT, HARYANA
 INDIA

Ordered by: 40062
 Brake Parts India PVT. Ltd.
 IEC Nr. 0507083229
 Village - Rewli
 PO Murthal GST 06AAGCA5049Q1Z8
 131027 SONEPAT, HARYANA
 INDIA

Invoice no. / date: 163753952 / 21.09.2021 Page 1 / 2
 Order no. / date: 8456384 / 20.08.2021
 Your reference: 60220048356
 Contactperson: Corina Hendriks



Item	Material Material description	Number Unit	Quantity Unit	Price Unit	Amount
10	Lapinus® RB210 bag 20 kg - pallet 500 kg 71797 Customer material number: 057005 Stat. No.: 68061000 Delivery No/Date: 32590528 / 13.09.2021 Container Number: FFAU4000064/BS532383 Country of origin: NL	10.000,00 KG	10.000,00 KG	4.095,00 1.000 KG	40.950,00
20	Promaxon-D bag 15 kg pallet 210 kg Synthetic hydrated calcium silicate 136919 Stat. No.: 28399000 Delivery No/Date: 32590528 / 13.09.2021 Container Number: FFAU4000064/BS532383 Country of origin: BE	4.200,00 KG	4.200,00 KG	4.500,00 1.000 KG	18.900,00
Amount excl. VAT					59.850,00
Output Tax				0,00 %	0,00

Delivery date: 13.09.2021 -
 Terms of delivery: FCA Roermond
 Payment term: 60 days end of month on28th
 Gross/Nett weight: 15.366 / 14.200 KG
 Transp. volume: 86,200 M3

Delivery address: 40062
 Brake Parts India PVT. Ltd.
 IEC Nr. 0507083229
 PO Murthal GST 06AAGCA5049Q1Z8
 Sonapat Haryana 131027
 India

Rockwool B.V. | Industrieweg 15, 6045 JG Roermond, The Netherlands | Postbus 1160, 6040 KD Roermond, The Netherlands
 T: +31 (0) 475 35 35 35 | E: cs@lapinus.com | www.lapinus.com | KvK Nederland 13014428 | VAT NL0016.96.592.B01 | EORI NL001696592
 Bank: ING BANK N.V. | NL87 INGB 0674 2921 11 | BIC/SWIFT INGBNL2A | Beneficiary: ROCKWOOL B.V.

The general terms and conditions of ROCKWOOL BV, as filed with the Chamber of Commerce The Netherlands, are applicable to all our offers and agreements and the execution thereof, more specifically they apply to this order and the execution thereof. You have received a copy of the general terms and conditions of ROCKWOOL BV with the quotation. On your first request we will send you a new copy. Transport cost may be subject to change, actual cost will be invoiced.

INVOICE

Invoice address: 40062

Brake Parts India PVT. Ltd.

IEC Nr. 0507083229

Village - Rewli

PO Murthal GST 06AAGCA5049Q1Z8


131027 SONEPAT, HARYANA

INDIA

Invoice no. / date:

163753952 / 21.09.2021

Page 2 / 2



Item	Material	Number	Quantity	Price	Amount
	Material description	Unit	Unit	Unit	
	Export supply 0% VAT # art. 146 (1) VAT Directive 2006/112/EC				

EUR 59.850,00

Rockwool B.V.
Industrieweg 15
6045 JG Roermond / The Netherlands

Our order nr : 8456384
Delivery nr : 32590528
Your order nr : 60220048356
Container nr : FFAU40000064

For: Brake Parts India PVT. Ltd.
IEC Nr. 0507083229
PO Murthal GST 06AAGCA5049Q1Z8
131027 Sonapat, Haryana
India



Shipment nr.: 0006417736

DETAILED PACKING LIST

Product and dimensions	Type and number of packages	Contents per package in m ³ / m ² / kg	Total quantity per item in m ³ / m ² / kg	Total net weight per item kgs	Total gross weight per item kgs	Dimensions in m per package
Lapinus® RB210, bag 20 kg	kg -pallet 500 kg					
2,0	0,1 10000 Kilogram	1,00	10000,00	10000,000	10620,000	1200,00 1200,00 1250,00
Promaxon-D, bag 15 kg	pallet 210 kg					
15,0	4200 Kilogram	1,00	4200,00	4200,000	4746,000	1150,00 1150,00 1150,00
TOTAL:				14200,000 Kgs	15366,000 Kgs	

BS532383

Date: 21-09-2021

780 BAGS PACKED ON 40 PALLETS

For attn of Mr./ Mrs.
Date 24-09-2021

Please find attached Test Report of compliance with the order (EN 10204: 2004 / 2.2)

Client Brake Parts India PVT. Ltd.
Client-orderno 60220048356
Lapinus orderno 8456384

Product: **Promaxon-D**
bag 15 kg pallet 210 kg
Synthetic hydrated calcium silicate

Total order Qty: 4.200 kg
Batch no. Batch Qty: 2131045 - 420 kg
Batch no. Batch Qty: 2131038 - 210 kg
Batch no. Batch Qty: 2131030 - 210 kg
Batch no. Batch Qty: 2124048 - 210 kg
Batch no. Batch Qty: 2124065 - 210 kg
Batch no. Batch Qty: 2124081 - 420 kg
Batch no. Batch Qty: 2131034 - 420 kg
Batch no. Batch Qty: 2126282 - 420 kg
Batch no. Batch Qty: 2126169 - 420 kg
Batch no. Batch Qty: 2126252 - 840 kg
Batch no. Batch Qty: 2131014 - 420 kg

Product: **Lapinus® RB210**
bag 20 kg - pallet 500 kg

Customer Code: **057005**
Total order Qty: 10.000 kg
Batch no. Batch Qty: 4503720217 - 3.000 kg
Batch no. Batch Qty: 4503663189 - 1.000 kg
Batch no. Batch Qty: 4503720214 - 6.000 kg



Part of the ROCKWOOL Group

Kind regards

Customer Services

Lapinus
ROCKWOOL B.V.
Industrieweg 15
6045 JG Roermond
PO Box 1160
6040 KD Roermond
The Netherlands

cs@lapinus.com
www.lapinus.com

This document is automatically generated and therefore contains no signature.
LF007/F03 / June 1994

341



Bormstraat 24
B-2830 Tiselt
Belgium
T +32 (0)15 71 21 86
F +32 (0)15 71 26 90
www.promat.com/industry

To : **ROCKWOOL BV - Lapinus Fibres**

For Customer: Rockwool BV
Gate B
Energieweg 3
6045 JE Roermond
Nederland

PO 4503719424

article n° 136919

Loading date 12/07/2021

ANALYSIS PROMAXON D Synthetic hydrated calcium silicate
VISUAL APPEARANCE: WHITE POWDER

BATCH NR.	PRODUCTION DATE	BULK DENSITY g/l	PARTICLE SIZE d(50) (µm)	COARSE PART (%) > 254 µ	MOISTURE %	WEIGHT (kg)
21 23 219 1	10-jun-2021	110,80	56,10	0,96	1,44	210
21 23 219 2	10-jun-2021	110,80	56,10	0,96	1,44	210
21 23 219 3	10-jun-2021	110,80	56,10	0,96	1,44	210
21 23 219 4	10-jun-2021	110,80	56,10	0,96	1,44	210
21 23 219 5	10-jun-2021	110,80	56,10	0,96	1,44	210
21 23 219 6	10-jun-2021	110,80	56,10	0,96	1,44	210
21 23 228 1	10-jun-2021	109,20	53,60	0,73	1,87	210
21 23 228 2	10-jun-2021	109,20	53,60	0,73	1,87	210
21 23 228 3	10-jun-2021	109,20	53,60	0,73	1,87	210
21 23 228 4	10-jun-2021	109,20	53,60	0,73	1,87	210
21 23 228 5	10-jun-2021	109,20	53,60	0,73	1,87	210
21 23 228 6	10-jun-2021	109,20	53,60	0,73	1,87	210
21 23 228 7	10-jun-2021	109,20	53,60	0,73	1,87	210
21 23 228 8	10-jun-2021	109,20	53,60	0,73	1,87	210
21 23 236 1	11-jun-2021	100,96	51,30	0,00	1,85	210
21 23 236 2	11-jun-2021	100,96	51,30	0,00	1,85	210
21 23 236 3	11-jun-2021	100,96	51,30	0,00	1,85	210
21 23 236 4	11-jun-2021	100,96	51,30	0,00	1,85	210
21 23 236 5	11-jun-2021	100,96	51,30	0,00	1,85	210
21 23 236 6	11-jun-2021	100,96	51,30	0,00	1,85	210
21 23 236 7	11-jun-2021	100,96	51,30	0,00	1,85	210
21 23 236 8	11-jun-2021	100,96	51,30	0,00	1,85	210
21 23 452 1	14-jun-2021	111,20	55,90	0,00	1,83	210
21 23 452 2	14-jun-2021	111,20	55,90	0,00	1,83	210
21 23 452 5	14-jun-2021	111,20	55,90	0,00	1,83	210



Bornstraat 24
B-2830 Tiselt
Belgium
T +32 (0)15 71 21 86
F +32 (0)15 71 26 90
www.promat.com/industry

To : **ROCKWOOL BV - Lapinus Fibres**

For Customer: Rockwool BV
Gate B
Energieweg 3
6045 JE Roermond
Nederland

PQ 4503719424

article n° 136919

Loading date 12/07/2021

ANALYSIS PROMAXON D Synthetic hydrated calcium silicate
VISUAL APPEARANCE: WHITE POWDER

BATCH NR.	PRODUCTION DATE	BULK DENSITY g/l	PARTICLE SIZE d(50) (µm)	COARSE PART (%) > 254 µ	MOISTURE %	WEIGHT (kg)
21 23 452 6	14-jun-2021	111,20	55,90	0,00	1,83	210
21 24 002 1	14-jun-2021	109,64	57,50	0,52	1,05	210
21 24 002 2	14-jun-2021	109,64	57,50	0,52	1,05	210
21 24 002 3	14-jun-2021	109,64	57,50	0,52	1,05	210
21 24 002 4	14-jun-2021	109,64	57,50	0,52	1,05	210
21 24 002 5	14-jun-2021	109,64	57,50	0,52	1,05	210
21 24 002 6	14-jun-2021	109,64	57,50	0,52	1,05	210
21 24 002 7	14-jun-2021	109,64	57,50	0,52	1,05	210
21 24 002 8	14-jun-2021	109,64	57,50	0,52	1,05	210
21 24 021 1	14-jun-2021	109,80	52,30	0,62	1,80	210
21 24 021 2	14-jun-2021	109,80	52,30	0,62	1,80	210
21 24 021 3	14-jun-2021	109,80	52,30	0,62	1,80	210
21 24 021 4	14-jun-2021	109,80	52,30	0,62	1,80	210
21 24 021 5	14-jun-2021	109,80	52,30	0,62	1,80	210
21 24 021 6	14-jun-2021	109,80	52,30	0,62	1,80	210
21 24 040 1	14-jun-2021	111,60	55,40	0,31	2,24	210
21 24 040 2	14-jun-2021	111,60	55,40	0,31	2,24	210
21 24 040 3	14-jun-2021	111,60	55,40	0,31	2,24	210
21 24 040 4	14-jun-2021	111,60	55,40	0,31	2,24	210
21 24 040 5	14-jun-2021	111,60	55,40	0,31	2,24	210
21 24 040 6	14-jun-2021	111,60	55,40	0,31	2,24	210
21 24 048 5	15-jun-2021	110,40	54,70	0,06	1,74	210
21 24 048 6	15-jun-2021	110,40	54,70	0,06	1,74	210
						10.080

342



Bormstraat 24
B-2830 Tiselt
Belgium
T +32 (0)15 71 21 86
F +32 (0)15 71 26 90
www.promat.com/industry

To : **ROCKWOOL BV - Lapinus Fibres**

For Customer: Rockwool BV
Gate B
Energieweg 3
6045 JE Roermond
Nederland

PO 4503725619

article n° 136919

Loading date 14/07/2021

ANALYSIS PROMAXON D Synthetic hydrated calcium silicate
VISUAL APPEARANCE: WHITE POWDER

BATCH NR.	PRODUCTION DATE	BULK DENSITY g/l	PARTICLE SIZE d(50) (µm)	COARSE PART (%) > 254 µ	MOISTURE %	WEIGHT (kg)
21 24 048 3	15-jun-2021	110,40	54,70	0,06	1,74	210
21 24 048 4	15-jun-2021	110,40	54,70	0,06	1,74	210
21 24 065 1	15-jun-2021	108,00	53,70	0,00	1,68	210
21 24 065 2	15-jun-2021	108,00	53,70	0,00	1,68	210
21 24 065 3	15-jun-2021	108,00	53,70	0,00	1,68	210
21 24 065 4	15-jun-2021	108,00	53,70	0,00	1,68	210
21 24 065 5	15-jun-2021	108,00	53,70	0,00	1,68	210
21 24 065 6	15-jun-2021	108,00	53,70	0,00	1,68	210
21 24 081 1	15-jun-2021	109,20	54,10	0,65	2,42	210
21 24 081 2	15-jun-2021	109,20	54,10	0,65	2,42	210
21 24 081 3	15-jun-2021	109,20	54,10	0,65	2,42	210
21 24 081 4	15-jun-2021	109,20	54,10	0,65	2,42	210
21 24 081 5	15-jun-2021	109,20	54,10	0,65	2,42	210
21 24 081 6	15-jun-2021	109,20	54,10	0,65	2,42	210
21 24 081 7	15-jun-2021	109,20	54,10	0,65	2,42	210
21 24 081 8	15-jun-2021	109,20	54,10	0,65	2,42	210
21 24 088 1	15-jun-2021	112,96	56,30	0,81	1,28	210
21 24 088 2	15-jun-2021	112,96	56,30	0,81	1,28	210
21 24 088 3	15-jun-2021	112,96	56,30	0,81	1,28	210
21 24 088 4	15-jun-2021	112,96	56,30	0,81	1,28	210
21 24 088 5	15-jun-2021	112,96	56,30	0,81	1,28	210
21 24 088 6	15-jun-2021	112,96	56,30	0,81	1,28	210
21 24 088 7	15-jun-2021	112,96	56,30	0,81	1,28	210
21 24 088 8	15-jun-2021	112,96	56,30	0,81	1,28	210
21 24 090 1	15-jun-2021	111,60	55,00	0,54	2,31	210



Bormstraat 24
B-2830 Tiselt
Belgium
T +32 (0)15 71 21 86
F +32 (0)15 71 26 90
www.promat.com/industry

To : **ROCKWOOL BV - Lapinus Fibres**

For Customer: Rockwool BV
Gate B
Energieweg 3
6045 JE Roermond
Nederland

PO 4503725619

article n° 136919

Loading date 14/07/2021

ANALYSIS PROMAXON D Synthetic hydrated calcium silicate
VISUAL APPEARANCE: WHITE POWDER

BATCH NR.	PRODUCTION DATE	BULK DENSITY g/l	PARTICLE SIZE d(50) (µm)	COARSE PART (%) > 254 µ	MOISTURE %	WEIGHT (kg)
21 24 090 2	15-jun-2021	111,60	55,00	0,54	2,31	210
21 24 090 3	15-jun-2021	111,60	55,00	0,54	2,31	210
21 24 090 4	15-jun-2021	111,60	55,00	0,54	2,31	210
21 24 090 5	15-jun-2021	111,60	55,00	0,54	2,31	210
21 24 090 6	15-jun-2021	111,60	55,00	0,54	2,31	210
21 24 113 1	16-jun-2021	106,80	49,00	0,00	2,12	210
21 24 113 2	16-jun-2021	106,80	49,00	0,00	2,12	210
21 24 113 3	16-jun-2021	106,80	49,00	0,00	2,12	210
21 24 113 4	16-jun-2021	106,80	49,00	0,00	2,12	210
21 24 113 5	16-jun-2021	106,80	49,00	0,00	2,12	210
21 24 113 6	16-jun-2021	106,80	49,00	0,00	2,12	210
21 24 152 1	16-jun-2021	110,00	53,00	0,00	2,55	210
21 24 152 2	16-jun-2021	110,00	53,00	0,00	2,55	210
21 24 152 3	16-jun-2021	110,00	53,00	0,00	2,55	210
21 24 152 4	16-jun-2021	110,00	53,00	0,00	2,55	210
21 24 152 5	16-jun-2021	110,00	53,00	0,00	2,55	210
21 24 152 6	16-jun-2021	110,00	53,00	0,00	2,55	210
21 24 206 1	17-jun-2021	114,80	53,40	0,00	1,86	210
21 24 206 2	17-jun-2021	114,80	53,40	0,00	1,86	210
21 24 206 3	17-jun-2021	114,80	53,40	0,00	1,86	210
21 24 206 4	17-jun-2021	114,80	53,40	0,00	1,86	210
21 24 206 5	17-jun-2021	114,80	53,40	0,00	1,86	210
21 24 206 6	17-jun-2021	114,80	53,40	0,00	1,86	210
						10.080



Bormstraat 24
B-2830 Tiselt
Belgium
T +32 (0)15 71 21 86
F +32 (0)15 71 26 90
www.promat.com/industry

344

To : ROCKWOOL BV - Lapinus Fibres

For Customer: Rockwool BV
Gate B
Energieweg 3
6045 JE Roermond
Nederland

PO 4503719428
article n° 136919
Loading date 04/08/2021

ANALYSIS PROMAXON D Synthetic hydrated calcium silicate
VISUAL APPEARANCE: WHITE POWDER

BATCH NR.	PRODUCTION DATE	BULK DENSITY g/l	PARTICLE SIZE d(50) (µm)	COARSE PART (%) > 254 µ	MOISTURE %	WEIGHT (kg)
21 24 048 1	15-jun-2021	110,40	54,70	0,06	1,74	210
21 24 048 2	15-jun-2021	110,40	54,70	0,06	1,74	210
21 25 111 1	23-jun-2021	110,40	53,90	0,05	1,63	210
21 25 111 2	23-jun-2021	110,40	53,90	0,05	1,63	210
21 25 111 3	23-jun-2021	110,40	53,90	0,05	1,63	210
21 25 111 4	23-jun-2021	110,40	53,90	0,05	1,63	210
21 25 111 5	23-jun-2021	110,40	53,90	0,05	1,63	210
21 25 111 6	23-jun-2021	110,40	53,90	0,05	1,63	210
21 25 011 5	21-jun-2021	109,24	51,90	0,00	2,28	210
21 25 011 6	21-jun-2021	109,24	51,90	0,00	2,28	210
21 25 011 7	21-jun-2021	109,24	51,90	0,00	2,28	210
21 25 011 8	21-jun-2021	109,24	51,90	0,00	2,28	210
21 25 129 1	23-jun-2021	114,80	54,30	0,00	1,87	210
21 25 129 2	23-jun-2021	114,80	54,30	0,00	1,87	210
21 25 129 3	23-jun-2021	114,80	54,30	0,00	1,87	210
21 25 129 4	23-jun-2021	114,80	54,30	0,00	1,87	210
21 25 129 5	23-jun-2021	114,80	54,30	0,00	1,87	210
21 25 129 6	23-jun-2021	114,80	54,30	0,00	1,87	210
21 25 129 7	23-jun-2021	114,80	54,30	0,00	1,87	210
21 25 129 8	23-jun-2021	114,80	54,30	0,00	1,87	210
21 25 068 1	22-jun-2021	110,40	45,70	0,00	1,61	210
21 25 068 2	22-jun-2021	110,40	45,70	0,00	1,61	210



Bormstraat 24
B-2830 Tiselt
Belgium
T +32 (0)15 71 21 86
F +32 (0)15 71 26 90
www.promat.com/industry

To : **ROCKWOOL BV - Lapinus Fibres**

For Customer: Rockwool BV
Gate B
Energieweg 3
6045 JE Roermond
Nederland

PO 4503719428
article n° 136919
Loading date 04/08/2021

ANALYSIS PROMAXON D Synthetic hydrated calcium silicate
VISUAL APPEARANCE: WHITE POWDER

BATCH NR.	PRODUCTION DATE	BULK DENSITY g/l	PARTICLE SIZE d(50) (µm)	COARSE PART (%) > 254 µ	MOISTURE %	WEIGHT (kg)
21 25 082 1	22-jun-2021	107,60	54,20	0,72	2,68	210
21 25 082 2	22-jun-2021	107,60	54,20	0,72	2,68	210
21 25 082 3	22-jun-2021	107,60	54,20	0,72	2,68	210
21 25 082 4	22-jun-2021	107,60	54,20	0,72	2,68	210
21 25 082 5	22-jun-2021	107,60	54,20	0,72	2,68	210
21 25 082 6	22-jun-2021	107,60	54,20	0,72	2,68	210
21 25 106 1	22-jun-2021	113,68	57,10	0,40	2,42	210
21 25 106 2	22-jun-2021	113,68	57,10	0,40	2,42	210
21 25 106 3	22-jun-2021	113,68	57,10	0,40	2,42	210
21 25 106 4	22-jun-2021	113,68	57,10	0,40	2,42	210
21 25 106 5	22-jun-2021	113,68	57,10	0,40	2,42	210
21 25 106 6	22-jun-2021	113,68	57,10	0,40	2,42	210
21 25 135 1	23-jun-2021	109,44	49,00	0,00	2,26	210
21 25 135 2	23-jun-2021	109,44	49,00	0,00	2,26	210
21 25 135 3	23-jun-2021	109,44	49,00	0,00	2,26	210
21 25 135 4	23-jun-2021	109,44	49,00	0,00	2,26	210
21 25 135 5	23-jun-2021	109,44	49,00	0,00	2,26	210
21 25 135 6	23-jun-2021	109,44	49,00	0,00	2,26	210
21 25 135 7	23-jun-2021	109,44	49,00	0,00	2,26	210
21 25 135 8	23-jun-2021	109,44	49,00	0,00	2,26	210

8.820



Bormstraat 24
B-2830 Tiselt
Belgium
T +32 (0)15 71 21 86
F +32 (0)15 71 26 90
www.promat.com/industry

345


To : **ROCKWOOL BV - Lapinus Fibres**

For Customer: Rockwool BV
Gate B
Energieweg 3
6045 JE Roermond
Nederland

PO 4503772923
article n° 136919
Loading date 25/08/2021

ANALYSIS PROMAXON D Synthetic hydrated calcium silicate
VISUAL APPEARANCE: WHITE POWDER

BATCH NR.	PRODUCTION DATE	BULK DENSITY g/l	PARTICLE SIZE d(50) (µm)	COARSE PART (%) > 254 µ	MOISTURE %	WEIGHT (kg)
21 27 091 1	06-jul-2021	111,20	53,70	0,27	1,71	210
21 27 091 2	06-jul-2021	111,20	53,70	0,27	1,71	210
21 27 091 3	06-jul-2021	111,20	53,70	0,27	1,71	210
21 27 091 4	06-jul-2021	111,20	53,70	0,27	1,71	210
21 27 091 5	06-jul-2021	111,20	53,70	0,27	1,71	210
21 27 091 6	06-jul-2021	111,20	53,70	0,27	1,71	210
21 27 091 7	06-jul-2021	111,20	53,70	0,27	1,71	210
21 27 091 8	06-jul-2021	111,20	53,70	0,27	1,71	210
21 26 443 3	05-jul-2021	112,00	53,30	0,00	2,00	210
21 26 443 4	05-jul-2021	112,00	53,30	0,00	2,00	210
21 26 443 5	05-jul-2021	112,00	53,30	0,00	2,00	210
21 26 443 6	05-jul-2021	112,00	53,30	0,00	2,00	210
21 27 014 1	05-jul-2021	112,00	51,90	0,00	2,05	210
21 27 014 2	05-jul-2021	112,00	51,90	0,00	2,05	210
21 27 014 3	05-jul-2021	112,00	51,90	0,00	2,05	210
21 27 014 4	05-jul-2021	112,00	51,90	0,00	2,05	210
21 27 014 5	05-jul-2021	112,00	51,90	0,00	2,05	210
21 27 014 6	05-jul-2021	112,00	51,90	0,00	2,05	210
21 27 014 7	05-jul-2021	112,00	51,90	0,00	2,05	210
21 27 014 8	05-jul-2021	112,00	51,90	0,00	2,05	210
21 26 276 1	02-jul-2021	110,40	55,10	0,35	1,65	210
21 26 276 2	02-jul-2021	110,40	55,10	0,35	1,65	210
21 26 276 3	02-jul-2021	110,40	55,10	0,35	1,65	210
21 26 276 4	02-jul-2021	110,40	55,10	0,35	1,65	210
21 26 276 5	02-jul-2021	110,40	55,10	0,35	1,65	210
21 26 276 6	02-jul-2021	110,40	55,10	0,35	1,65	210



Bormstraat 24
B-2830 Tiselt
Belgium
T +32 (0)15 71 21 86
F +32 (0)15 71 26 90
www.promat.com/industry

345

To : **ROCKWOOL BV - Lapinus Fibres**

For Customer: Rockwool BV
Gate B
Energieweg 3
6045 JE Roermond
Nederland

PO 4503772923
article n° 136919
Loading date 25/08/2021

ANALYSIS PROMAXON D Synthetic hydrated calcium silicate
VISUAL APPEARANCE: WHITE POWDER

BATCH NR.	PRODUCTION DATE	BULK DENSITY g/l	PARTICLE SIZE d(50) (µm)	COARSE PART (%) > 254 µ	MOISTURE %	WEIGHT (kg)
21 26 276 7	02-jul-2021	110,40	55,10	0,35	1,65	210
21 26 276 8	02-jul-2021	110,40	55,10	0,35	1,65	210
21 26 282 1	02-jul-2021	114,00	53,70	0,28	2,06	210
21 26 282 2	02-jul-2021	114,00	53,70	0,28	2,06	210
21 26 282 3	02-jul-2021	114,00	53,70	0,28	2,06	210
21 26 282 4	02-jul-2021	114,00	53,70	0,28	2,06	210
21 26 282 5	02-jul-2021	114,00	53,70	0,28	2,06	210
21 26 282 6	02-jul-2021	114,00	53,70	0,28	2,06	210
21 26 436 1	05-jul-2021	113,12	55,50	0,22	1,81	210
21 26 436 2	05-jul-2021	113,12	55,50	0,22	1,81	210
21 26 436 3	05-jul-2021	113,12	55,50	0,22	1,81	210
21 26 436 4	05-jul-2021	113,12	55,50	0,22	1,81	210
21 26 251 3	02-jul-2021	108,00	50,50	0,20	1,19	210
21 26 251 4	02-jul-2021	108,00	50,50	0,20	1,19	210
21 26 251 5	02-jul-2021	108,00	50,50	0,20	1,19	210
21 26 251 6	02-jul-2021	108,00	50,50	0,20	1,19	210
21 26 252 1	02-jul-2021	112,80	49,10	0,00	1,86	210
21 26 252 2	02-jul-2021	112,80	49,10	0,00	1,86	210
21 26 252 3	02-jul-2021	112,80	49,10	0,00	1,86	210
21 26 252 4	02-jul-2021	112,80	49,10	0,00	1,86	210
21 26 252 5	02-jul-2021	112,80	49,10	0,00	1,86	210
21 26 252 6	02-jul-2021	112,80	49,10	0,00	1,86	210
						10.080



Bornstraat 24
B-2630 Tessel
Belgium
T +32 (0)15 71 21 66
F +32 (0)15 71 26 00
www.promat.com/industry

346

To : ROCKWOOL BV - Lapinus Fibres

For Customer: Rockwool BV
Gate B
Energieweg 3
6045 JE Roermond
Nederland

PO 4503792579
article n° 136919
Loading date 10/09/2021

ANALYSIS PROMAXON D Synthetic hydrated calcium silicate
VISUAL APPEARANCE: WHITE POWDER

BATCH NR.	PRODUCTION DATE	BULK DENSITY g/l	PARTICLE SIZE d(50) (µm)	COARSE PART (%) > 254 µ	MOISTURE %	WEIGHT (kg)
21 31 038 1	03-aug-2021	108,00	51,90	0,00	1,95	210
21 31 038 2	03-aug-2021	108,00	51,90	0,00	1,95	210
21 31 038 3	03-aug-2021	108,00	51,90	0,00	1,95	210
21 31 038 4	03-aug-2021	108,00	51,90	0,00	1,95	210
21 31 038 5	03-aug-2021	108,00	51,90	0,00	1,95	210
21 31 038 6	03-aug-2021	108,00	51,90	0,00	1,95	210
21 31 038 7	03-aug-2021	108,00	51,90	0,00	1,95	210
21 31 038 8	03-aug-2021	108,00	51,90	0,00	1,95	210
21 31 030 1	03-aug-2021	103,60	50,40	0,00	2,08	210
21 31 030 2	03-aug-2021	103,60	50,40	0,00	2,08	210
21 31 030 3	03-aug-2021	103,60	50,40	0,00	2,08	210
21 31 030 4	03-aug-2021	103,60	50,40	0,00	2,08	210
21 31 030 5	03-aug-2021	103,60	50,40	0,00	2,08	210
21 31 030 6	03-aug-2021	103,60	50,40	0,00	2,08	210
21 31 034 1	03-aug-2021	108,00	50,80	0,00	2,00	210
21 31 034 2	03-aug-2021	108,00	50,80	0,00	2,00	210
21 31 034 3	03-aug-2021	108,00	50,80	0,00	2,00	210
21 31 034 4	03-aug-2021	108,00	50,80	0,00	2,00	210
21 31 034 5	03-aug-2021	108,00	50,80	0,00	2,00	210
21 31 034 6	03-aug-2021	108,00	50,80	0,00	2,00	210
21 31 034 7	03-aug-2021	108,00	50,80	0,00	2,00	210
21 31 034 8	03-aug-2021	108,00	50,80	0,00	2,00	210
21 31 045 1	03-aug-2021	108,80	51,40	0,00	1,78	210
21 31 045 2	03-aug-2021	108,80	51,40	0,00	1,78	210
21 31 045 3	03-aug-2021	108,80	51,40	0,00	1,78	210
21 31 045 4	03-aug-2021	108,80	51,40	0,00	1,78	210
21 31 045 5	03-aug-2021	108,80	51,40	0,00	1,78	210
21 31 045 6	03-aug-2021	108,80	51,40	0,00	1,78	210



Bornstraat 24
B-2830 Tessel
Belgium
T +32 (0)15 71 21 86
F +32 (0)15 71 28 80
www.promat.com/industry

To : ROCKWOOL BV - Lapinus Fibres

For Customer: Rockwool BV
Gate B
Energieweg 3
6045 JE Roermond
Nederland

PO 4503792579

article n° 136919

Loading date 10/09/2021

ANALYSIS PROMAXON D Synthetic hydrated calcium silicate
VISUAL APPEARANCE: WHITE POWDER

BATCH NR.	PRODUCTION DATE	BULK DENSITY g/l	PARTICLE SIZE d(50) (µm)	COARSE PART (%) > 254 µ	MOISTURE %	WEIGHT (kg)
21 31 014 1	02-aug-2021	111,60	49,60	0,00	2,21	210
21 31 014 2	02-aug-2021	111,60	49,60	0,00	2,21	210
21 31 014 3	02-aug-2021	111,60	49,60	0,00	2,21	210
21 31 014 4	02-aug-2021	111,60	49,60	0,00	2,21	210
21 31 014 5	02-aug-2021	111,60	49,60	0,00	2,21	210
21 31 014 6	02-aug-2021	111,60	49,60	0,00	2,21	210
21 28 169 7	30-jun-2021	110,32	50,40	0,35	0,79	210
21 28 169 8	30-jun-2021	110,32	50,40	0,35	0,79	210
21 30 076 1	02-aug-2021	110,00	49,80	0,00	1,89	210
21 30 076 2	02-aug-2021	110,00	49,80	0,00	1,89	210
21 30 076 3	02-aug-2021	110,00	49,80	0,00	1,89	210
21 30 076 4	02-aug-2021	110,00	49,80	0,00	1,89	210
21 30 076 5	02-aug-2021	110,00	49,80	0,00	1,89	210
21 30 076 6	02-aug-2021	110,00	49,80	0,00	1,89	210
21 30 073 1	02-aug-2021	110,60	49,10	0,00	2,16	210
21 30 073 2	02-aug-2021	110,60	49,10	0,00	2,16	210
21 30 073 3	02-aug-2021	110,60	49,10	0,00	2,16	210
21 30 073 4	02-aug-2021	110,60	49,10	0,00	2,16	210
21 30 073 5	02-aug-2021	110,60	49,10	0,00	2,16	210
21 30 073 6	02-aug-2021	110,60	49,10	0,00	2,16	210

10080

Test report Date : 22-7-2021

TEST REPORT of compliance with the order (EN 10204: 2004 / 2.2)

1.

Prod. Date : 9-7-2021

Product : Lapinus® RB210
bag 20 kg - pallet 500 kg

2. Testresults

Batch no.	Fibre length	Results ()		Limits ()	
		Min.	Max.	Min.	Max.
4503720214		140,00	140,00	125	175

Batch no.	Shotcontent	Results ()		Limits ()	
		Min.	Max.	Max.	
4503720214	Shot > 125 µm	0,02	0,10	0,2	

3. Herewith we declare the above mentioned test results being representative for the batch and in compliance with the product information sheet.
4. Our material is REACH registered and does not contain SVHC substances under REACH >0.1%.

Site	Telephone number	Contact	Fax number
Roermond	+31 475 353354	Customer Service	+31 475 353677

This document is automatically generated and therefore contains no signature.

LF007/F03 / June 1994

The information contained herein is based upon data considered to be accurate. However, no warranty is expressed or implied regarding the accuracy of these data, the results to be obtained from their use thereof, or any such use will not infringe upon any patent. This information is furnished only as a guide and upon the condition that the person receiving it shall make tests to determine its accuracy and suitability for his or her own purpose.

Test report Date : 3-8-2021

TEST REPORT of compliance with the order (EN 10204: 2004 / 2.2)

1.

Prod. Date : 12-7-221

Product : Lapinus® RB210
bag 20 kg - pallet 500 kg

2. Testresults

Batch no.	Fibre length	Results ()		Limits ()	
		Min.	Max.	Min.	Max.
4503720217		135,00	135,00	125	175

Batch no.	Shotcontent	Results ()		Limits ()	
		Min.	Max.	Max.	
4503720217	Shot > 125 µm	0,01	0,08	0,2	

3. Herewith we declare the above mentioned test results being representative for the batch and in compliance with the product information sheet.
4. Our material is REACH registered and does not contain SVHC substances under REACH >0.1%.

Site	Telephone number	Contact	Fax number
Roermond	+31 475 353354	Customer Service	+31 475 353677

This document is automatically generated and therefore contains no signature.

LF007/F03 / June 1994

The information contained herein is based upon data considered to be accurate. However, no warranty is expressed or implied regarding the accuracy of these data, the results to be obtained from their use thereof, or any such use will not infringe upon any patent. This information is furnished only as a guide and upon the condition that the person receiving it shall make tests to determine its accuracy and suitability for his or her own purpose.

Test report Date : 15-6-2021

TEST REPORT of compliance with the order (EN 10204: 2004 / 2.2)

1.

Prod. Date : 3-6-2021

Product : Lapinus® RB210
bag 20 kg - pallet 500 kg

2. Testresults

Batch no.	Fibre length	Results ()		Limits ()	
		Min.	Max.	Min.	Max.
4503663189		146,00	146,00	125	175

Batch no.	Shotcontent	Results ()		Limits ()	
		Min.	Max.	Max.	
4503663189	Shot > 125 µm	0,02	0,15	0,2	

- Herewith we declare the above mentioned test results being representative for the batch and in compliance with the product information sheet.
- Our material is REACH registered and does not contain SVHC substances under REACH >0.1%.

Site	Telephone number	Contact	Fax number
Roermond	+31 475 353354	Customer Service	+31 475 353677

This document is automatically generated and therefore contains no signature.

LF007/F03 / June 1994

The information contained herein is based upon data considered to be accurate. However, no warranty is expressed or implied regarding the accuracy of these data, the results to be obtained from their use thereof, or any such use will not infringe upon any patent. This information is furnished only as a guide and upon the condition that the person receiving it shall make tests to determine its accuracy and suitability for his or her own purpose.