MEENAKSHI POLYMERS PVT.LTD. HARIDWAR

DOC NO. MPPL/F/QAD/35/PL
REV.DATE-02-01-2018
ORG.01/08/2016
REV NO-02

DAILY MIS REPORT-A+B+C & C SHIFT 20-09-26

Date-: 19-09-26

MONTH-SEP-26

SR.NO	DEFECT	REASON	CR AAEL	CR AAD	ENGINE GUARD	PEDAL BRAKE	PGC	HANDLE	TOTAL	RENICKEL	RECHROME	BUFFF	OK	B GRADE	SCRAP	TOTAL
1	PEEL OFF	PLATING SHOP	0	0	0	0	0	3	3	0	0	0	0	0	3	3
2	TOUCHING	PLATING SHOP	0	0	0	0	0	0	0	0	0	0	0	0	0	0
3	DULL PLATING	PLATING SHOP	28	18	7	11	5	0	69	69	0	0	0	0	0	69
4	CLAENING FAULT	PLATING SHOP	38	21	18	0	0	3	80	77	0	0	0	3	0	80
5	PLATING PITTING	PLATING SHOP	0	0	0	0	0	0	0	0	0	0	0	0	0	0
6	YELLOW	PLATING SHOP	92	94	2	101	39	2	330	0	330	0	0	0	0	330
7	ROUGHNESS	PLATING SHOP	0	12	36	0	0	0	48	0	0	0	48	0	0	48
8	PASSIVE BUFF	PLATING SHOP	0	0	0	0	0	0	0	0	0	0	0	0	0	0
9	CHROME BUFF	PLATING SHOP	35	54	11	172	0	0	272	0	0	272	0	0	0	272
10	HANDLE OD OVER SIZE	PLATING SHOP	0	0	0	0	0	43	43	0	0	0	43	0	0	43
TOTAL PLATING DEFECT			193	199	74	284	44	51	845	146	330	272	91	3	3	845
TOTAL PLATING DEFECT %			11.6	5.6	2.0	6.5	0.7	1.7	3.7							
11	CLEANING FAULT	WELD SHOP	28	14	0	0	0	0	42	42	0	0	0	0	0	42
12	SPATTER	WELD SHOP	3	4	1	0	0	0	8	0	0	0	8	0	0	8
13	MIG WIRE	WELD SHOP	5	3	4	0	0	0	12	0	0	0	12	0	0	12
14	PEDAL CUT	WELD SHOP	0	0	0	0	0	0	0	0	0	0	0	0	0	0
15	TRACIBILITY MISS	WELD SHOP	0	0	0	2	0	0	2	0	0	0	2	0	0	2
16	WELDING PUNCTURE	WELD SHOP	23	32	9	7	0	0	71	0	0	0	71	0	0	71
17	WELDING PIN HOLE	WELD SHOP	0	0	0	0	0	0	0	0	0	0	0	0	0	0
18	ID UNDER SIZE	BOP.	0	0	0	2	0	0	2	0	0	0	2	0	0	2
19	WIRE SHORT	WELD SHOP	0	4	0	0	0	0	4	0	0	0	0	4	0	4
20	WELDING MISS	WELD SHOP	1	0	0	0	0	0	1	0	0	0	1	0	0	1
21	WELDING SHIFT	WELD SHOP	0	0	0	0	0	0	0	0	0	0	0	0	0	0
22	SPATTER SOUND	WELD SHOP	0	0	0	0	0	0	0	0	0	0	0	0	0	0
23	WELDING IN COMPLETE	WELD SHOP	0	1	0	0	0	0	1	0	0	0	1	0	0	1
24	EXCESS WELDING	WELD SHOP	0	1	1	0	0	0	2	0	0	0	2	0	0	2
25	GRINDING MARK	WELD SHOP	4	4	1	0	0	17	26	6	0	0	0	20	0	26
TOTAL WELDING DEFECT			64	63	16	11	0	17	171	48	0	0	99	24	0	171
TOTAL WELDING DEFECT %			3.8	1.8	0.4	0.3	0.0	0.6	0.7							
25	RUSTY MARK	BOP.	0	2	0	0	0	0	2	0	0	0	0	2	0	2
26	GRAIN OPENING	BOP.	0	0	0	0	0	3	3	0	0	0	0	3	0	3
27	PGC THREAD MISS	BOP.	0	0	0	0	0	0	0	0	0	0	0	0	0	0
28	MATERIAL FAULT	BOP.	16	15	15	6	0	18	70	48	0	0	0	22	0	70
29	MATERIAL PITTING	BOP.	0	0	0	0	0	19	19	0	0	0	0	19	0	19
30	PGC THREAD OPPOSITE	BOP.	0	0	0	0	0	0	0	0	0	0	0	0	0	0
31	LINE MARK	BOP.	1	0	0	0	2	2	5	0	0	0	0	5	0	5
32	CD BEND/STAY	WELD SHOP	0	0	3	0	0	0	3	0	0	0	3	0	0	3
33	BAR LINE	PRESS SHOP	0	0	0	0	0	0	0	0	0	0	0	0	0	0
34	WRINKLE	MACHINE SHOP	0	0	0	0	0	0	0	0	0	0	0	0	0	0
35	DIE MARK ON PIPE	PRESS SHOP	0	0	0	0	0	0	0	0	0	0	0	0	0	0
TOTAL BOP DEFECT			17	17	18	6	2	42	102	48	0	0	3	51	0	102
TOTAL BOP DEFECT%			1.0	0.5	0.5	0.1	0.0	1.4	0.4							
36	DENT & SCRATCH	HANGLING	41	16	95	1	0	38	191	146	0	0	0	45	0	191
37	BUFFING NG	BUFFING SHOP	0	0	0	0	0	0	0	0	0	0	0	0	0	0
38	WRONG STAMP	FEBRACTION	0	0	0	0	0	0	0	0	0	0	0	0	0	0
39	HANDLE PUNCH MISS	FEBRACTION	0	0	0	0	0	0	0	0	0	0	0	0	0	0
40	HANDLE STAMP MISS	FEBRACTION	0	0	0	0	0	0	0	0	0	0	0	0	0	0
TOTAL OTHER PLATING DEFECT			41	16	95	1	0	38	191	146	0	0	0	45	0	191
OTHER DEFECT %			2.5	0.4	2.6	0.0	0.0	1.3	0.8							
41	CENTERLESS MARK	center less shop	0	0	0	0	0	8	8	0	0	0	0	8	0	8
TOTAL CENTER LESS DEFECT			0	0	0	0	0	8	8	0	0	0	0	8	0	8
CENTER LESS DEFECT %			0.0	0.0	0.0	0.0	0.0	0.3	0.0							
OVER ALL TOTAL DEFECT			315	295	203	302	46	156	1317	388	330	272	193	131	3	1317
TOTAL DEFECT %			18.9	8.2	5.5	6.9	0.7	5.3	5.8							
TOTAL STRAIGHT PASS			81.1	91.8	94.5	93.1	99.3	94.7	94.2							
PRODUCTION			1664	3584	3688	4356	6635	2960	22887							
REWORK PLANT PRODUCTION																
REWORK PLANT DEFECT QTY.																
CUSTOMER RETURN DEFECT QTY.																
TOTAL DEFECT QTY																

B-GRADE - CARRIER AADL = NOS. ENGINE GUARD = NOS , PEDAL BRAKE = NOS. , HANDLE = NOS. PGC = NOS.

PREPARED BY- 21/09/26

REVIEWED BY-

APPROVED BY-

note