



रत सल

STEEL AUTHORITY OF INDIA LIMITED  
BOKARO STEEL PLANT  
BOKARO STEEL CITY - 827001, JHARKHAND, INDIA

Test Certificate  
HOT ROLLED MEDIUM AND HIGH  
TENSILE STRUCTURAL STEEL

16

MATERIAL DESCRIPTION : HR PLATE IS 2062 E250BR SLAK  
TEST CERTIFICATE NO. : 1074722  
SHIPPING ADVISE NO. : 81360264  
WAGON NO. : ECOR11005

MILL : HRCP  
DATE : 15.08.2025  
DATE : 14.08.2025

TO  
BM BSO KANPUR  
WHM PANKI  
PANKI , PO GANGAGANJ 208020  
KANPUR

We certify that the material described below fully confirms to 2062:2011. Chemical composition and Mechanical / Physical properties of the product as tested in accordance with the scheme of testing and inspection contained in BIS Certification Marks License No: CM/L-0484856 are as indicated against each Coil / Cast No or Order No. The Material supplied conforms to the standard rolling / dimensional and weight tolerances.

(Please refer to 2062:2011 for details of specification requirements)

| Chemical Analysis, Mechanical Properties, Specifications & Other Information |          |           |                                         |        |                   |                    |                    |                    |                     |                     |                    |                     |                      |                  |              |                        |             |                         |
|------------------------------------------------------------------------------|----------|-----------|-----------------------------------------|--------|-------------------|--------------------|--------------------|--------------------|---------------------|---------------------|--------------------|---------------------|----------------------|------------------|--------------|------------------------|-------------|-------------------------|
| ITEM NO.                                                                     | CAST NO. | BATCH NO. | SALES ORDER & SIZE<br>(MM)<br>T X W X L | TON    | C %<br>(0.22 MAX) | Mn %<br>(1.50 MAX) | P %<br>(0.045 MAX) | S %<br>(0.045 MAX) | Si %<br>(0.03-0.40) | Al %<br>(0.01-0.10) | CE %<br>(0.41 MAX) | YS MPa<br>(250 MIN) | UTS MPa<br>(410 MIN) | El %<br>(23 MIN) | BEND<br>(2T) | Impav J<br>(27MIN @RT) | EDGE<br>( ) | GRADE                   |
| 1                                                                            | 2557407  | 1240029B  | 1201015275<br>8.000X1,800X8,000         | 12.760 | 0.15              | 0.75               | 0.013              | 0.010              | 0.148               | 0.034               | 0.278              | 347.0<br>330.0      | 470.0<br>457.0       | 30.0<br>33.0     | OK           | 130                    | UnTrim      | IS 2062 E250BR<br>SLAIR |
| 2                                                                            | 2557407  | 1240029A  | 1201015275<br>8.000X1,800X8,000         | 18.240 | 0.15              | 0.75               | 0.013              | 0.010              | 0.148               | 0.034               | 0.278              | 347.0<br>330.0      | 470.0<br>457.0       | 30.0<br>33.0     | OK           | 130                    | UnTrim      | IS 2062 E250BR<br>SLAIR |
| 3                                                                            | 2557404  | 1240027A  | 1201015275<br>8.000X1,800X8,000         | 18.230 | 0.16              | 0.75               | 0.015              | 0.010              | 0.148               | 0.038               | 0.287              | 339.0<br>347.0      | 463.0<br>470.0       | 30.0<br>30.0     | OK           | 128                    | UnTrim      | IS 2062 E250BR<br>SLAIR |
| 4                                                                            | 2557404  | 1240027B  | 1201015275<br>8.000X1,800X8,000         | 11.810 | 0.16              | 0.75               | 0.015              | 0.010              | 0.148               | 0.038               | 0.287              | 339.0<br>347.0      | 463.0<br>470.0       | 30.0<br>30.0     | OK           | 128                    | UnTrim      | IS 2062 E250BR<br>SLAIR |
| TOTAL TONNAGE :                                                              |          |           |                                         | 61.04  |                   |                    |                    |                    |                     |                     |                    |                     |                      |                  |              |                        |             |                         |

Issued Against Billing  
No. 4004720097  
MT 11.8.10 Date 30.05.18

Auth Signature

Remarks: MTC is issued according to EN 10204 TYPE 3.1. Second set of mechanical properties pertains to the same heat  
This is to certify that the above mentioned product do not contain any radioactive element higher than the natural level. The product or packing material does not contain any hazardous substance as per RoHS norms.

| LEGEND (where applicable) :     |                                                                       |                                |                                | THIRD PARTY / DDQA |  |  |  | AUTHORISED SIGNATORY |  |  |  |
|---------------------------------|-----------------------------------------------------------------------|--------------------------------|--------------------------------|--------------------|--|--|--|----------------------|--|--|--|
| One Mpa=1 Nsq.mm=0.102 kg/sq.mm | MAE = Micro Alloying Elements                                         | Hard = Hardness                | IMP = Impact Value (full size) |                    |  |  |  |                      |  |  |  |
| EL = Elongation                 | GC = Galvanised Corrugated                                            |                                |                                |                    |  |  |  |                      |  |  |  |
| YS = Yield Stress               | GPD = Galvanised Plain Deep Drawing ST-RL=Stretched & Roller Levelled |                                |                                |                    |  |  |  |                      |  |  |  |
| UTS = Ultimate Tensile Strength | TXWX L = ThicknessXWidthXLength                                       | COR-OD=Corrugated Ordinary     |                                |                    |  |  |  |                      |  |  |  |
| CE = Carbon Equivalent          | D. DRW = Deep Drawing                                                 |                                |                                |                    |  |  |  |                      |  |  |  |
|                                 | CUP = Cupping Value                                                   | Process Route : BOF-LF-CCS-HSM |                                |                    |  |  |  |                      |  |  |  |

FOR SENIOR MANAGER (MTL)  
RESEARCH & CONTROL LABORATORY