



RESEARCH & CONTROL LABORATORY



STEEL AUTHORITY OF INDIA LIMITED
BOKARO STEEL PLANT
BOKARO STEEL CITY - 827001, JHARKHAND, INDIA

Test Certificate

STRUCTURAL STEEL PART 1

HOT ROLLED MEDIUM AND HIGH TENSILE STEEL

MATERIAL DESCRIPTION : HR PLATE IS 2062 E250BR SIALK

TEST CERTIFICATE NO. : 1124811

SHIPPING ADVICE NO. : 81437384

WAGON NO. : SEC99265

MILL : HRCF

DATE : 12.03.2026

DATE : 12.03.2026

TO

BM BSO JAIPUR

RAJASTHAN ISPAT UDYOG (DISTRIBUTOR)

E-341, ROAD NO. 16, VISHWAKARMA 302013

JAIPUR

We certify that the material described below fully confirms to 2062(PART 1):2025. Chemical composition and Mechanical / Physical properties of the product as tested in accordance with the scheme of testing and inspection contained in BIS Certification Marks License No: **CM/L-0484856** are as indicated against each Coil / Cast No or Order No. The Material supplied conforms to the standard rolling / dimensional and weight tolerances.

(Please refer to 2062(PART 1):2025 for details of specification requirements)

Chemical Analysis, Mechanical Properties, Specifications & Other Information																	
ITEM NO.	CAST NO.	BATCH NO.	SALES ORDER & SIZE (MM)	TON	C%	Mn%	P%	S %	Si%	Al%	CE%	YS MPa	UTS MPa	El %	BEND (2T)	EDGE ()	GRADE
			T X W X L		(0.22 MAX)	(1.50 MAX)	(0.045 MAX)	(0.045 MAX)	(0.03-0.40)	(0.01-0.10)	(0.41 MAX)	(250 MIN)	(410 MIN)	(23 MIN)			
6	2652111	1349271B	1201069504	8.150	0.14	0.86	0.040	0.006	0.147	0.035	0.283	333.0	464.0	29.0	OK	UnTrim	IS 2062 E250BR
TOTAL TONNAGE :				62.61													
SIAIK																	

Remarks: MTC is issued according to EN 10204 TYPE 3.1. Second set of mechanical properties pertains to the same heat This is to certify that the above mentioned product do not contain any radioactive element higher than the natural level. The product or packing material does not contain any hazardous substance as per RoHS norms.

LEGEND (where applicable):				THIRD PARTY / DDQA		AUTHORISED SIGNATORY
One Mpa=1 Nsq.mm=0.102 kg/sq.mm	MAE = Micro Alloying Elements	Hard = Hardness				
EL = Elongation	GC = Galvanised Corrugated	IMP = Impact Value (full size)				
YS = Yield Stress	GPD = Galvanised Plain Deep Drawing	ST-RL=Stretched & Roller Levelled				
UTS = Ultimate Tensile Strength	TXWX L = ThicknessXwidthXLength	COR-OD=Corrugated Ordinary				
CE = Carbon Equivalent	D.DRW = Deep Drawing					
	CUP = Cupping Value	Process Route : BOF-LF-CCS-HSM			FOR SENIOR MANAGER (MTL.)	
					RESEARCH & CONTROL LABORATORY	