



संज्ञा

STEEL AUTHORITY OF INDIA LIMITED
BOKARO STEEL PLANT
BOKARO STEEL CITY - 827001, JHARKHAND, INDIA
Test Certificate
HOT ROLLED STEEL SHEET, PLATE AND STRIP FOR FORMING AND FLANGING PURPOSES

9



MATERIAL DESCRIPTION : HR COIL IS5986 ISH30S SLAK
TEST CERTIFICATE NO. : 1124801
SHIPPING ADVISE NO. : 81437387
WAGON NO. : SEC23762

MILL : HSM
DATE : 12.03.2026
DATE : 12.03.2026

TO
BM BSO JAIPUR
RAJASTHAN ISPAT UDYOG (DISTRIBUTOR)
E-341, ROAD NO. 16, VISHWAKARMA 302013
JAIPUR

We certify that the material described below fully confirms to IS 5986 : 2017. Chemical composition and Mechanical / Physical properties of the product as tested in accordance with the scheme of testing and inspection contained in BIS Certification Marks License No: CM/L # 0563246 are as indicated against each Coil / Cast No or Order No. The Material supplied conforms to the standard rolling / dimensional and weight tolerances.

(Please refer to IS 5986 : 2017 for details of specification requirements)

ITEM NO.	CAST NO.	BATCH NO.	SALES ORDER & SIZE (MM)	TON	Chemical Analysis, Mechanical Properties, Specifications & Other Information										GRADE
					C%	Mn%	P%	S %	Si%	Al%	YS MPA	UTS MPA	El %	BEND	
1	2652406	1354938	1201070445 T X W X L 4.000X1.500	28.330	(0.15 MAX)	(0.80 MAX)	(0.040 MAX)	(0.040 MAX)	(0.500 MAX)	(0.010 MIN)	(205 MIN)	(330-440)	(20/28 MIN)	(T/2T)	IS5986 ISH30S SLAK
2	2558880	1354927	1201069318 8.000X1.500	28.450	(0.09 MAX)	(0.35 MAX)	(0.016 MAX)	(0.005 MAX)	(0.175 MAX)	(0.022 MIN)	(312.0 MIN)	(415.0)	(38.0)	OK	IS5986 ISH30S SLAK
TOTAL TONNAGE :				56.78	0.08	0.46	0.017	0.007	0.137	0.038	329.0	439.0	36.0	OK	IS5986 ISH30S SLAK

Remarks: MTC is issued according to EN 10204 TYPE 3.1

This is to certify that the above mentioned product do not contain any radioactive element higher than the natural level. The product or packing material does not contain any hazardous substance as per RoHS norms.

LEGEND (where applicable):		MAE = Micro Alloying Elements	Hard = Hardness	THIRD PARTY / DDQA	AUTHORISED SIGNATORY
One Mpa=1 Nsq.mm=0.102 kg/sq.mm	GC = Galvanised Corrugated	IMP = Impact Value (full size)			
EL = Elongation	GPD = Galvanised Plain Deep Drawing ST-RL=Stretched & Roller Levelled				
YS = Yield Stress	TXWX L = ThicknessXWidthXLength	COR-OD=Corrugated Ordinary			
UTS = Ultimate Tensile Strength	D.DRW = Deep Drawing				
CE = Carbon Equivalent	CUP = Cupping Value	Process Route : BOP-LF-CCS-HSM			

FOR SENIOR MANAGER (MTL)
RESEARCH & CONTROL LABORATORY