Sheet Metal Gauge Chart

Thickness by gauge and material · millimetres and inches

GAUGE 3–36
4 material systems
1 page

GAUGE MSG	OZ / FT² NOMINAL	CARBON STEEL MM	CARBON STEEL INCH	GALVANIZED MM	STAINLESS MM	AL · BRASS · CU MM · B&S
3	160	6.073	0.2391	6.170	6.350	5.827
4	150	5.695	0.2242	5.789	5.954	5.189
5	140	5.314	0.2092	5.410	5.555	4.620
6	130	4.935	0.1943	5.029	5.159	4.115
7	120	4.554	0.1793	4.651	4.763	3.665
8	110	4.176	0.1644	4.270	4.366	3.264
9	100	3.797	0.1495	3.891	3.967	2.906
10	90	3.416	0.1345	3.510	3.571	2.588
11	80	3.038	0.1196	3.132	3.175	2.304
12	70	2.657	0.1046	2.753	2.779	2.052
13	60	2.278	0.0897	2.372	2.380	1.829
14	50	1.897	0.0747	1.994	1.984	1.628
15	45	1.709	0.0673	1.803	1.786	1.450
16	40	1.519	0.0598	1.613	1.588	1.290
17	36	1.367	0.0538	1.461	1.427	1.151
18	32	1.214	0.0478	1.311	1.270	1.024
19	28	1.062	0.0418	1.158	1.110	0.912
20	24	0.912	0.0359	1.006	0.953	0.813
21	22	0.836	0.0329	0.930	0.874	0.724
22	20	0.759	0.0299	0.853	0.792	0.643
23	18	0.683	0.0269	0.777	0.714	0.574
24	16	0.607	0.0239	0.701	0.635	0.511
25	14	0.531	0.0209	0.627	0.556	0.455
26	12	0.455	0.0179	0.551	0.475	0.404
27	11	0.417	0.0164	0.513	0.437	0.361
28	10	0.378	0.0149	0.475	0.396	0.320
29	9	0.343	0.0135	0.437	0.358	0.287
30	8	0.305	0.0120	0.399	0.318	0.254
31	7	0.267	0.0105	0.361	0.277	–
32	6.5	0.246	0.0097	0.343	–	–
33	6	0.229	0.0090	0.323	–	–
34	5.5	0.208	0.0082	0.305	–	–
35	5	0.191	0.0075	0.284	–	–
36	4.5	0.170	0.0067	0.267	–	–

16 GAUGE IS NOT ONE THICKNESS

The number alone does not determine thickness — the material does. At 16 ga the four systems give:

carbon **1.519 mm** · galvanized **1.613 mm** · stainless **1.588 mm** · aluminium **1.290 mm**

That is a **25.0% spread** across four answers that are all correct. Always state the material, not just the gauge.

HOW THESE NUMBERS ARE DEFINED

Carbon (MSG) — nominal weight in oz/ft² divided by 41.82 lb/ft²/in.

Galvanized — MSG weight plus 2.5 oz/ft² of zinc coating.

Stainless — US Standard Gauge, n/64 in steps.

Al / brass / Cu — B&S (AWG) geometric law, $d = 0.127 \times 92^{(36-n)/39}$ mm.

Rounding — inch to 4 dp from the defined value, mm derived from that inch × 25.4. Shaded rows 8–24 are the common fabrication range.