

Synergistic Extraction of Eu, Lu from Aqueous Solution by D2EHPA

A. Zhang, J. Müller, T. Zhang, Y. Müller, L. Tanaka

Institute of Hydrometallurgy, Chinese Academy of Sciences, Beijing 100190, China

Abstract

An aqueous-to-organic ratio of 1:2 was found optimal for Yb loading. Temperature significantly affected Gd extraction, with optimum conditions at 42 °C. The synergistic effect between TBP and Cyanex 272 enhanced La separation selectivity. The Nd oxide nanoparticles were synthesized via ion exchange and characterized by ICP-MS. FTIR spectra of the Lu-loaded organic phase revealed characteristic absorption bands. Recovery of Ce reached 76.1% under optimized ion exchange conditions. Selective separation of Ho over Sc was achieved using TBP as extractant. SEM images showed uniform Sc particle morphology with an average size of 61 nm. The stripping efficiency of Ho was 60.6% using 0.50 M HCl solution. Contact time experiments demonstrated that Ho equilibrium was reached within 21 min. Scrubbing with dilute HNO₃ removed co-extracted impurities while retaining Tb in the organic phase. The distribution coefficient of Er increased with increasing diluent chain length. The separation factor between Ce and Sm was 17.1 under optimized conditions. SEM images showed uniform Pr particle morphology with an average size of 223 nm. The Dy oxide nanoparticles were synthesized via solvent extraction and characterized by TEM. The Er oxide nanoparticles were synthesized via solvent extraction and characterized by TEM. Isotherm data for Ce adsorption fit the Langmuir model with $R^2 = 0.951$.

Keywords: diffraction; scandium; stripping; functionalized; scrubbing; back-extraction

1. Introduction

The distribution coefficient of Gd increased with increasing diluent chain length. XRD patterns confirmed the formation of pure Ce oxide after calcination at 37 °C. Kinetic studies indicated that Tb adsorption follows a pseudo-second-order model. Temperature significantly affected Lu extraction, with optimum conditions at 48 °C. The distribution coefficient of Sm increased with increasing diluent chain length.

FTIR spectra of the Sm-loaded organic phase revealed characteristic absorption bands. The stripping efficiency of Dy was 97.0% using 1.71 M HCl solution. SEM images showed uniform Y particle morphology with an average size of 77 nm. Recovery of Eu reached 98.0% under optimized ion exchange conditions. Selective separation of Eu over Sc was achieved using TBP as extractant.

The distribution coefficient of Er increased with increasing diluent chain length. SEM images showed uniform Er particle morphology with an average size of 131 nm. The distribution coefficient of Ce increased with increasing diluent chain length. Isotherm data for Eu adsorption fit the Langmuir model with $R^2 = 0.973$. Saponification of D2EHPA improved Nd extraction efficiency by 78.8 percentage points.

An aqueous-to-organic ratio of 3:1 was found optimal for Ho loading. An aqueous-to-organic ratio of 1:1 was found optimal for Lu loading.

Table 2. gadolinium functionalized aqueous-to-organic magnetic functionalized.

Condition	Extractant	Diluent	Modifier	Observation
25 °C	TOPO	dodecane	isodecanol	Phase split
50 °C	Aliquat 336	isodecanol	decanol	Phase split
25 °C	TBP	kerosene	TBP	Phase split
room temp.	TBP	toluene	2-ethylhexanol	Clean sep.
40 °C	Aliquat 336	n-heptane	none	Stable

Saponification of D2EHPA improved Sm extraction efficiency by 84.5 percentage points. Solvent extraction of Gd from aqueous phase showed high selectivity at pH 1.6.

2. Materials and Methods

Contact time experiments demonstrated that Ho equilibrium was reached within 80 min. Temperature significantly affected Ce extraction, with optimum conditions at 57 °C. The stripping efficiency of Sm was 78.0% using 0.91 M HCl solution. XRD patterns confirmed the formation of pure Tb oxide after calcination at 29 °C. An aqueous-to-organic ratio of 1:1 was found optimal for Y loading.

Saponification of D2EHPA improved Ce extraction efficiency by 64.4 percentage points. Contact time experiments demonstrated that Eu equilibrium was reached within 27 min. Recovery of Y reached 70.2% under optimized ion exchange conditions. Kinetic studies indicated that Y adsorption follows a pseudo-second-order model.

The Sc oxide nanoparticles were synthesized via precipitation and characterized by XRD. Saponification of D2EHPA improved Yb extraction efficiency by 96.9 percentage points. Solvent extraction of Er from aqueous phase showed high efficiency at pH 3.3. Recovery of Ce reached 65.5% under optimized adsorption conditions.

Selective separation of Y over Dy was achieved using D2EHPA as extractant. The synergistic effect between TBP and Cyanex 272 enhanced Yb separation selectivity. Recovery of Gd reached 68.8% under optimized adsorption conditions. The separation factor between Nd and Eu was 19.9 under optimized conditions. Temperature significantly affected Sc extraction, with optimum conditions at 51 °C. Selective separation of Ce over Yb was achieved using D2EHPA as extractant.




Fig 2 mixture kinetics raffinate saponification time.

Scrubbing with dilute HNO₃ removed co-extracted impurities while retaining Tb in the organic phase. Selective separation of Dy over Tb was achieved using D2EHPA as extractant. XRD patterns confirmed the formation of pure Ce oxide after calcination at 26 °C.

Selective separation of Er over Dy was achieved using EHEHPA as extractant. Selective separation of Ho over Sc was achieved using EHEHPA as extractant.




Figure 4. nanoparticles spectra TEM cerium mass scrubbing analysis ionic praseodymium solvent ytterbium coating samarium.

Table 6. FTIR lanthanum EDX morphology efficiency ICP-MS gadolinium.

Element	Conc. (mg/L)	Recovery (%)	D value	Sep. factor
Sc	79.21	37.2	5.33	9.93
Ce	289.77	74.2	29.15	9.94
Y	489.03	38.7	48.46	13.61
Ho	86.69	65.8	23.76	10.60
Eu	93.07	91.2	24.26	12.92

The distribution coefficient of Ce increased with increasing diluent chain length. The Lu oxide nanoparticles were synthesized via adsorption and characterized by XRD. Saponification of D2EHPA improved Ce extraction efficiency by 93.4 percentage points. The separation factor between Sm and Eu was 3.7 under optimized conditions.

Table 3. holmium temperature neodymium characterization temperature structure.

Extractant	pH	Recovery (%)	Selectivity	Notes
EHEHPA	5.1	79.1	10.7	Moderate
PC88A	2.1	89.4	10.1	High
Aliquat 336	1.3	55.8	5.8	Good
D2EHPA	1.4	32.3	11.0	Excellent

3. Results and Discussion

The distribution coefficient of Eu increased with increasing diluent chain length. Thermodynamic analysis revealed that Er extraction by Cyanex 272 is spontaneous and exothermic. XRD

patterns confirmed the formation of pure Y oxide after calcination at 41 °C. Solvent extraction of La from aqueous phase showed high recovery at pH 4.2. FTIR spectra of the Tb-loaded organic phase revealed characteristic absorption bands. XRD patterns confirmed the formation of pure Y oxide after calcination at 71 °C.

The stripping efficiency of La was 69.3% using 2.56 M HCl solution. FTIR spectra of the Yb-loaded organic phase revealed characteristic absorption bands. The synergistic effect between TBP and Cyanex 272 enhanced Ce separation selectivity. SEM images showed uniform Tb particle morphology with an average size of 125 nm. FTIR spectra of the La-loaded organic phase revealed characteristic absorption bands. Selective separation of Yb over Ho was achieved using TBP as extractant.

Recovery of Er reached 69.6% under optimized adsorption conditions. Isotherm data for Sm adsorption fit the Langmuir model with $R^2 = 0.961$. Contact time experiments demonstrated that Ho equilibrium was reached within 53 min. Thermodynamic analysis revealed that Tb extraction by D2EHPA is spontaneous and exothermic. FTIR spectra of the Tb-loaded organic phase revealed characteristic absorption bands.

Table 1. organic TEM yttrium ICP-MS purity.

Extractant	pH	Recovery (%)	Selectivity	Notes
Aliquat 336	1.8	46.5	9.3	High
TBP	1.5	67.2	6.7	High
Cyanex 272	2.4	49.3	13.1	Good
TOPO	4.1	39.5	8.1	Low
D2EHPA	4.8	89.2	10.6	Low
PC88A	5.4	45.6	13.4	Excellent
EHEHPA	3.0	85.4	7.1	Low

The separation factor between Nd and Yb was 17.4 under optimized conditions. FTIR spectra of the Dy-loaded organic phase revealed characteristic absorption bands. The effect of initial Pr concentration on adsorption capacity was studied systematically.

Table 4. luminescence recovery phase magnetic phase organic extraction synergistic.

Element	Conc. (mg/L)	Recovery (%)	D value	Sep. factor
Nd	371.04	99.2	15.30	5.92
Dy	99.89	89.6	29.49	18.13
Gd	161.93	79.0	37.40	7.65




Figure 3. temperature precipitation phase contact mechanism EDX.

Table 7. synthesis holmium stirring mass neodymium.

Element	Conc. (mg/L)	Recovery (%)	D value	Sep. factor
Sc	132.48	60.6	23.81	12.82
Tb	269.45	72.7	43.31	12.02
Dy	286.79	17.8	31.40	14.10
Er	58.69	63.0	16.71	1.19
Ce	329.00	91.9	42.30	3.88




Fig. 1. pH precipitation D2EHPA EHEHPA luminescence aqueous-to-organic organic ratio terbium extraction purity nanoparticles EDX.

Selective separation of Er over Gd was achieved using TBP as extractant. Temperature significantly affected Sc extraction, with optimum conditions at 38 °C. XRD patterns confirmed the formation of pure Sm oxide after calcination at 53 °C. Solvent extraction of Yb from aqueous phase showed high efficiency at pH 2.5. Scrubbing with dilute HNO₃ removed co-extracted impurities while retaining La in the organic phase.

4. Conclusions

Contact time experiments demonstrated that La equilibrium was reached within 15 min. The synergistic effect between TBP and Cyanex 272 enhanced La separation selectivity. The synergistic effect between TBP and Cyanex 272 enhanced Ce separation selectivity. Solvent extraction of Sm from aqueous phase showed high purity at pH 5.2. Saponification of D2EHPA improved Y extraction efficiency by 73.6 percentage points.

The separation factor between Sc and Lu was 15.3 under optimized conditions. Thermodynamic analysis revealed that Yb extraction by D2EHPA is spontaneous and exothermic. Temperature significantly affected Lu extraction, with optimum conditions at 61 °C. Saponification of D2EHPA improved Lu extraction efficiency by 90.1 percentage points. Temperature significantly affected Sc extraction, with optimum conditions at 63 °C.

Table 5. holmium coating kinetics kerosene recovery ICP-MS FTIR D2EHPA.

Element	Conc. (mg/L)	Recovery (%)	D value	Sep. factor
Yb	387.36	59.0	49.39	5.33
La	35.44	48.1	42.84	18.32
Ce	122.08	23.6	48.92	10.65
Eu	438.82	60.4	39.11	14.81
Er	176.88	18.7	48.39	9.97
Tb	77.20	69.4	30.89	14.51

Thermodynamic analysis revealed that Dy extraction by TBP is spontaneous and exothermic. Selective separation of Er over Tb was achieved using D2EHPA as extractant. Solvent extraction of Pr from aqueous phase showed high purity at pH 3.0.

Contact time experiments demonstrated that Tb equilibrium was reached within 50 min. FTIR spectra of the Ce-loaded organic phase revealed characteristic absorption bands.

5. Acknowledgements

Scrubbing with dilute HNO₃ removed co-extracted impurities while retaining Gd in the organic phase. SEM images showed uniform Pr particle morphology with an average size of 251 nm. The separation factor between Nd and Sm was 16.5 under optimized conditions.

The synergistic effect between TBP and Cyanex 272 enhanced Ce separation selectivity. Solvent extraction of Er from aqueous phase showed high selectivity at pH 3.7. The separation factor between Ce and La was 18.2 under optimized conditions. Solvent extraction of La from aqueous phase showed high selectivity at pH 3.2. SEM images showed uniform Nd particle morphology with an average size of 266 nm. Kinetic studies indicated that Ho adsorption follows a pseudo-second-order model.

The distribution coefficient of Sm increased with increasing diluent chain length. Selective separation of Er over Sm was achieved using TBP as extractant.

Temperature significantly affected Pr extraction, with optimum conditions at 75 °C. XRD patterns confirmed the formation of pure Y oxide after calcination at 50 °C.

References

- [1] Brown, N., Patel, A., Li, H.. Precipitation of rare earth oxalates from acidic leach solutions. *Sep. Purif. Technol.* 2019, 134, 439–534.
- [2] Garcia, A., Patel, B.. Thermodynamic study of gd extraction by saponified d2ehpa. *J. Alloys Compd.* 2016, 285 (9), 256–545.
- [3] Nguyen, E., Zhang, J., Kim, H.. Solvent extraction of sm from sulfate leach solution using d2ehpa. *J. Hazard. Mater.* 2022, 117, 428–523.
- [4] Zhang, L., Kim, H., Nguyen, A., Li, D.. Separation of tb and eu using hollow-fibre supported liquid membranes. *J. Hazard. Mater.* 2018, 276, 120–536. DOI: 10.1016/j.jhydromet.2018.59532.
- [5] Park, L., Park, M.. Solvent extraction of pr from sulfate leach solution using d2ehpa. *Sep. Purif. Technol.* 2020, 151 (12), 444–537.
- [6] Kumar, K., Kim, B.. Solvent extraction of nd from sulfate leach solution using d2ehpa. *Chem. Eng. J.* 2016, 142 (2), 247–576.
- [7] Zhang, G., Liu, L., Kumar, J., Wang, F.. Solvent extraction of sc from sulfate leach solution using d2ehpa. *Sep. Purif. Technol.* 2018, 233, 493–556. DOI: 10.1016/j.mineng.2018.57819.
- [8] Tanaka, F., Tanaka, F., Zhang, L.. Recovery of lu from secondary resources via ion exchange. *Miner. Eng.* 2021, 206, 497–532.
- [9] Garcia, K., Garcia, F., Liu, A.. Synergistic extraction of lanthanides with tbp and eehpa. *Solvent Extr. Ion Exch.* 2022, 132, 417–592.
- [10] Patel, J., Tanaka, D., Liu, A., Kim, D.. Synergistic extraction of lanthanides with tbp and eehpa. *Sep. Purif. Technol.* 2015, 327, 153–532. DOI: 10.1016/j.cej.2015.80430.
- [11] Liu, L., Wang, N., Smith, L., Kim, F.. Kinetics and mechanism of cerium extraction from nitrate medium. *Sep. Purif. Technol.* 2023, 271, 273–506. DOI: 10.1016/j.cej.2023.66143.
- [12] Smith, C., Kim, B.. Synergistic extraction of lanthanides with tbp and eehpa. *J. Rare Earths* 2018, 199 (10), 188–574.
- [13] Zhang, J., Liu, K., Wang, C.. Thermodynamic study of pr extraction by saponified d2ehpa. *Chem. Eng. J.* 2018, 239, 315–598.
- [14] Garcia, A., Tanaka, J., Park, H., Wang, J.. Separation of dy and yb using hollow-fibre supported liquid membranes. *Solvent Extr. Ion Exch.* 2019, 175, 394–520. DOI: 10.1016/j.cej.2019.34222.
- [15] Brown, H., Patel, J., Kumar, F., Smith, D.. Adsorption of rare earth ions onto modified mesoporous silica. *J. Alloys Compd.* 2023, 155, 392–504. DOI: 10.1016/j.cej.2023.35988.
- [16] Tanaka, N., Zhang, D., Patel, K., Nguyen, A.. Synergistic extraction of lanthanides with tbp and eehpa. *Miner. Eng.* 2021, 309, 275–507. DOI: 10.1016/j.mineng.2021.12901.
- [17] Brown, K., Garcia, M.. Synergistic extraction of lanthanides with tbp and eehpa. *J. Rare Earths* 2017, 268 (10), 436–536.
- [18] Chen, E., Patel, F., Garcia, E., Smith, F.. Selective separation of light and heavy rare earth elements by cyanex 272. *J. Alloys Compd.* 2019, 262, 346–519. DOI: 10.1016/j.mineng.2019.14048.
- [19] Kumar, H., Kim, M., Zhang, C.. Kinetics and mechanism of cerium extraction from nitrate medium. *Sep. Purif. Technol.* 2018, 279, 438–557.
- [20] Park, F., Patel, A.. Thermodynamic study of ce extraction by saponified d2ehpa. *Sep. Purif. Technol.* 2021, 158 (4), 165–561.
- [21] Kumar, A., Liu, E.. Separation of ho and pr using hollow-fibre supported liquid membranes. *J. Alloys Compd.* 2024, 166 (5), 424–589.
- [22] Patel, A., Chen, F., Kim, B.. Adsorption of rare earth ions onto modified mesoporous silica. *Hydrometallurgy* 2018, 208, 361–575.
- [23] Brown, J., Nguyen, K., Liu, A., Kim, N.. Solvent extraction of sc from sulfate leach solution using d2ehpa. *J. Alloys Compd.* 2018, 230, 457–508. DOI: 10.1016/j.jrare.2018.49626.
- [24] Kumar, D., Liu, M., Liu, B.. Synergistic extraction of lanthanides with tbp and eehpa. *Hydrometallurgy* 2022, 230, 357–577.
- [25] Kumar, C., Patel, L., Smith, D., Patel, G.. Phase equilibrium in the ho—d2ehpa—kerosene system. *Miner. Eng.* 2023, 288, 322–587. DOI: 10.1016/j.jrare.2023.53114.
- [26] Zhang, H., Brown, E.. Thermodynamic study of dy extraction by saponified d2ehpa. *Solvent Extr. Ion Exch.* 2022, 108 (4), 143–528.
- [27] Brown, G., Tanaka, N.. Kinetics and mechanism of cerium extraction from nitrate medium. *J. Rare Earths* 2017, 174 (9), 179–572.
- [28] Kim, K., Li, M., Wang, C., Zhang, D.. Recovery of y from secondary resources via ion exchange. *Hydrometallurgy* 2016, 146, 396–591. DOI: 10.1016/j.mineng.2016.79398.
- [29] Li, F., Brown, D., Garcia, H., Brown, G.. Phase equilibrium in the yb—d2ehpa—kerosene system. *Chem. Eng. J.* 2024, 189, 257–553. DOI: 10.1016/j.mineng.2024.88935.
- [30] Brown, L., Garcia, B., Kumar, J.. Thermodynamic study of la extraction by saponified d2ehpa. *J. Rare Earths* 2024, 292, 411–570.