

Cold rolling of the Ni-Cr-Mo demo alloy (NiCrMo-D).

Tensile strength grew from 760 MPa to 905 MPa (ISO 6892).

Corrosion rate was NOT measured for this alloy.

Conclusion dated 2025-02-14.